BS ISO 8371:2015



### **BSI Standards Publication**

# Iron ores for blast furnace feedstocks — Determination of the decrepitation index



BS ISO 8371:2015 BRITISH STANDARD

#### National foreword

This British Standard is the UK implementation of ISO 8371:2015. It supersedes BS ISO 8371:2007 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/58, Iron ores.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 79286 1

ICS 73.060.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2015.

Amendments issued since publication

Date Text affected

# INTERNATIONAL STANDARD

BS ISO 8371:2015 ISO 8371

Third edition 2015-08-01

# Iron ores for blast furnace feedstocks — Determination of the decrepitation index

Minerais de fer pour charges de hauts fourneaux — Détermination de l'indice de décrépitation



BS ISO 8371:2015 ISO 8371:2015(E)



#### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Coı	ntents	Page
Fore	eword	iv
Intro	oduction	v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	1
5	Sampling, sample preparation and preparation of test portions	
6	Apparatus	2
7	Procedure 7.1 Number of determinations for the test 7.2 Heating 7.3 Sieving	2
8	Expression of results	3
9	Test report	3
10	Verification	4
Bibli	liography	5

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 102, Iron ore and direct reduced iron, Subcommittee SC 3, Physical testing.

This third edition cancels and replaces the second edition (ISO 8371:2007) which has been technically revised to address the care needed during hand sieving, to introduce the mechanical sieving and to exclude the reference to ISO 4701.

#### Introduction

This International Standard concerns one of a number of physical test methods that have been developed to measure various physical parameters and characteristics and to evaluate the behaviour of iron ores, including reducibility, disintegration, crushing strength, apparent density, etc. This method was developed to provide a uniform procedure, validated by collaborative testing, to facilitate comparisons of tests made in different laboratories.

The results of this test have to be considered in conjunction with other tests used to evaluate the quality of iron ores as feedstocks for blast furnace processes.

This International Standard can be used to provide test results as part of a production quality control system, as a basis of a contract, or as part of a research project.

# Iron ores for blast furnace feedstocks — Determination of the decrepitation index

CAUTION — This International Standard may involve hazardous operations and equipment. This International Standard does not purport to address all of the safety issues associated with its use. It is the responsibility of the user of this International Standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to its use.

#### 1 Scope

This International Standard specifies a method to provide a relative measure for evaluating the degree of size degradation caused by rapid heating of iron ores. It specifies the determination of the decrepitation index.

This International Standard is applicable to lump ores for blast furnace feedstocks.

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3082, Iron ores — Sampling and sample preparation procedures

ISO 3310-1, Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth

ISO 3310-2, Test sieves — Technical requirements and testing — Part 2: Test sieves of perforated metal plate

ISO 11323, Iron ore and direct reduced iron — Vocabulary

#### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 11323 apply.

#### 4 Principle

The test portion is rapidly heated from room temperature to  $700\,^{\circ}$ C, maintained at this temperature for 30 min and then cooled in air down to room temperature. It is sieved with a test sieve having square openings of 6,3 mm. The decrepitation index is calculated as the mass percentage of material of size -6,3 mm.

#### 5 Sampling, sample preparation and preparation of test portions

#### 5.1 Sampling and sample preparation

Sampling of a lot and preparation of a test sample shall be in accordance with ISO 3082.

The size range for lump ores shall be -25,0 mm +20,0 mm.

A test sample of at least 5,0 kg, on a dry basis, of the sized lump ores shall be obtained.

## BS ISO 8371:2015 **ISO 8371:2015(E)**

Oven-dry the test sample to constant mass at  $105\,^{\circ}\text{C} \pm 5\,^{\circ}\text{C}$  and cool it to room temperature. Screen the sized sample again on a 20,0 mm sieve to remove any adhering fines, and keep the test material in a desiccator until testing.

NOTE Constant mass is achieved when the difference in mass between two subsequent measurements becomes less than 0,05 % of the initial mass of the test sample.

#### 5.2 Preparation of test portions

Only particles taken at random shall be used to constitute a test portion.

At least 10 test portions, each of approximately 500 g (±the mass of 1 particle) shall be prepared from the test sample.

Weigh the test portions to the nearest 1 g and register the mass of each test portion on its recipient label.

#### 6 Apparatus

#### 6.1 General

The test apparatus shall comprise:

- a) ordinary laboratory equipment, such as an oven, hand tools, time-control device and safety equipment;
- b) a furnace;
- c) a test-portion holder;
- d) test sieves;
- e) a weighing device.
- **6.2 Furnace**, having a heating capacity and temperature control able to heat the test portion from room temperature to 700 °C in 30 min.
- **6.3 Test portion holder**, made of non-scaling, heat-resistant metal to withstand temperatures higher than 700 °C, equipped with a thermocouple to measure the temperature of the sample. The cover shall be of the loose fitting type and shall not provide a gas-tight seal.
- **6.4** Test sieves, conforming to ISO 3310-1 or ISO 3310-2 and having square apertures of the following nominal sizes: 6.30 mm; 3.15 mm and 500  $\mu$ m.
- **6.5 Weighing device,** capable of weighing the test sample and test portions to an accuracy of 1 g.

#### 7 Procedure

#### 7.1 Number of determinations for the test

Owing to the heterogeneity of lump ores, carry out the test 10 times on each test sample.

#### 7.2 Heating

WARNING — This test involves handling of hot apparatus. In addition, for some iron ores, spitting may occur when loading the sample into the hot container. Suitable hand and eye protection shall be used by the operator.

Turn on the furnace and begin heating. When its temperature reaches 700 °C, keep it constant for a further 20 min. Place the test portion in the sample holder, cover and put the set in the furnace. After 30 min, remove the holder and the test portion from the furnace and allow the test portion to cool to below 50 °C.

#### 7.3 Sieving

Discharge the test portion carefully from the sample holder, determine and record its mass ( $m_1$ ). Hand sieve with care on the 6,30 mm, 3,15 mm and 500  $\mu$ m sieves (6.4). Determine and record the mass passing 6,30 mm ( $m_2$ ), 3,15 mm and 500  $\mu$ m to one decimal place.

NOTE 1 Equivalent mechanical sieving can be used provided that preliminary test programme is carried out according to ISO 3086, the hand sieving being the reference method.

NOTE 2 Sieving results are influenced by the sieve shaker characteristics. Therefore in cases where two or more laboratories need to compare their results for commercial or research purposes, the sieving conditions are to be adjusted until identical results are obtained for the same test sample.

#### 8 Expression of results

The decrepitation index, DI<sub>-6,3</sub>, expressed as a percentage by mass, is calculated from the following equation:

$$DI_{-6,3} = 100 \times \frac{m_2}{m_1}$$

where

 $m_1$  is the mass, in grams, of the test portion after thermal treatment;

 $m_2$  is the mass, in grams, of the undersize fraction passing the 6,30 mm sieve.

Express the result to one decimal place.

#### 9 Test report

The test report shall include the following information:

- a) a reference to this International Standard, i.e. ISO 8371;
- b) all details necessary for the identification of the sample;
- c) the name and address of the test laboratory;
- d) the date of the test;
- e) the date of the test report;
- f) the signature of the person responsible for the test;
- g) the details of any operation and any test conditions not specified in this International Standard or regarded as optional, as well as any incident which may have had an influence on the results;
- h) the decrepitation index, DI<sub>-6.3</sub> and the individual results of the 10 tests;
- i) the mean values of the decrepitation index for the whole 10 tests;
- j) the type of sieve used.

#### 10 Verification

Regular checking of apparatus is essential to ensure test-result reliability. The frequency of checking is a matter for each laboratory to determine.

The conditions of the following items shall be checked:

- sieves;
- weighing device;
- temperature control and measurement device;
- time control device.

It is recommended that internal reference material be prepared and used periodically to check test repeatability.

Appropriate records of verification activities shall be maintained.

### **Bibliography**

[1] ISO 3086, Iron ores — Experimental methods for checking the bias of sampling



# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

#### About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

#### Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

#### **Buying standards**

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

#### **Subscriptions**

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

#### **BSI Group Headquarters**

389 Chiswick High Road London W4 4AL UK

#### **Revisions**

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

#### Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

#### **Useful Contacts:**

#### **Customer Services**

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

#### Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

#### Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

#### **Copyright & Licensing**

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

