

**BS ISO 8575:2016**



**BSI Standards Publication**

# **Aerospace — Fluid systems — Hydraulic system tubing**

**bsi.**

**National foreword**

This British Standard is the UK implementation of ISO 8575:2016.

The UK participation in its preparation was entrusted to Technical Committee ACE/69, Aerospace hydraulic systems, fluids and components.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.

Published by BSI Standards Limited 2016

ISBN 978 0 580 86676 0

ICS 49.080

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2016.

**Amendments/corrigenda issued since publication**

| Date | Text affected |
|------|---------------|
|------|---------------|

---

INTERNATIONAL  
STANDARD

BS ISO 8575:2016

**ISO**  
**8575**

Second edition  
2016-11-15

---

---

**Aerospace — Fluid systems —  
Hydraulic system tubing**

*Série aérospatiale — Systèmes de fluides — Tubes pour systèmes  
hydrauliques*



Reference number  
ISO 8575:2016(E)

© ISO 2016



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

Page

|   |           |
|---|-----------|
| <b>Foreword</b> .....   | <b>iv</b> |
| <b>Introduction</b> .....   | <b>v</b>  |
| <b>1 Scope</b> .....  | <b>1</b>  |
| <b>2 Normative references</b> .....                                     | <b>1</b>  |
| <b>3 Terms and definitions</b> .....                                    | <b>1</b>  |
| <b>4 Requirements</b> .....   | <b>1</b>  |
| 4.1 General.....  | 1         |
| 4.2 Pressure lines.....   | 2         |
| 4.2.1 Tubing material.....  | 2         |
| 4.2.2 Tube sizes.....   | 2         |
| 4.2.3 Qualification.....  | 2         |
| 4.3 Suction and return lines.....                                       | 2         |
| 4.3.1 Tubing Material.....  | 2         |
| 4.3.2 Tube sizes.....   | 2         |
| <b>Annex A (informative) Aerospace hydraulic tubing materials</b> ..... | <b>8</b>  |
| <b>Bibliography</b> .....   | <b>9</b>  |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/TC 20, *Aircraft and space vehicles*, Subcommittee SC 10, *Aerospace fluid systems and components*.

This second edition cancels and replaces the first edition (ISO 8575:1990), which has been technically revised.

## Introduction

The purpose of this document is to provide information relating to the sizes and materials of tubing for use in aerospace hydraulic pressure and return and suction lines.

International Standards use the International System of units (SI); however, large segments of the aerospace industry make use of other measurement systems as a matter of common working practice. Although tube sizes were originally defined (and are frequently cited) using non-SI units, all dimensions used in this document are given in SI units, with inch units also indicated for the convenience of the user.

The decimal sign used in International Standards is the comma (","); however, the comma is not used in common working practice for inch dimensions. Therefore, in common with many other aerospace standards, the decimal point is used in this document when providing dimensions in inches.

**NOTE** The use of non-SI units and the decimal point in this document does not constitute general acceptance of measurement systems other than SI within International Standards.





# Aerospace — Fluid systems — Hydraulic system tubing

## 1 Scope

This document provides information relating to the sizes and materials of tubing for use in aerospace hydraulic pressure and return and suction lines. For pressure lines, the requirements apply to the pressure and temperature ranges covered by pressure class D, E and J and temperature type 13 and type 20 as specified in ISO 6771.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 8574, *Aerospace — Hydraulic system tubing — Qualification tests for bent tubes*

ISO 6771, *Aerospace — Fluid systems and components — Pressure and temperature classifications*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp/>

### 3.1

#### **inch — tubing**

tubing diameters and wall thickness in fractional inch increments and based on industry standards

### 3.2

#### **metric tubing**

tubing diameters and wall thickness in SI-metric units

Note 1 to entry: Metric tubing is in compliance with ISO 2964.

## 4 Requirements

### 4.1 General

The pipe dimensions quoted are in common use for the stated materials in the different pressure and temperature classes. Inclusion of a dimension under a pressure and temperature class in this document does not constitute a guarantee of fitness for purpose in all circumstance. Aircraft Systems designers should verify each tube assembly application with the appropriate stress authority.

## 4.2 Pressure lines

### 4.2.1 Tubing material

Material for tubing used in hydraulic system pressure line shall be in accordance with [Table 1](#) and shall conform to the appropriate physical properties specified in [Table 1](#).

### 4.2.2 Tube sizes

The outside diameters, wall thicknesses and materials of tubing used in the manufacture of tube assemblies shall conform, where applicable, to the relevant requirements given in [Table 2](#) or [Table 3](#) for inch tubing and [Table 4](#) or [Table 5](#) for metric tubing.

Where no wall thickness is shown in the tables for a particular combination of tube outside diameter and material and it is desired to use that combination, a suitable wall thickness shall be selected and verified by testing in accordance with ISO 8574.

### 4.2.3 Qualification

Tubing having outside diameters, wall thicknesses and materials as specified in [Table 2](#) and [Table 3](#) shall have been verified by testing in accordance with the requirements of ISO 8574.

## 4.3 Suction and return lines

### 4.3.1 Tubing Material

Materials for tubing used in hydraulic system suction and return lines may be as given in [Table 1](#) and verified in accordance with ISO 8574 or at the discretion of the aircraft designer.

### 4.3.2 Tube sizes

Unless otherwise specified, the outside diameters for inch tubing used in suction and return lines shall be selected from those specified in [Table 2](#) or [Table 3](#) for inch tubing, and from [Table 4](#) or [Table 5](#) for metric tubing.

The corresponding wall thicknesses shall be selected and verified in accordance with [Table 2](#) to [Table 5](#) or at the discretion of the aircraft designer.

**Table 1 — Tubing materials**

| Material |   | Ultimate tensile strength |               | Yield strength         |               | Percent elongation<br>$A_{\min.}$ |
|----------|---|---------------------------|---------------|------------------------|---------------|-----------------------------------|
| Code no. | Description   | $R_m$ min.<br>MPa         | min.<br>(psi) | $R_{p0,2}$ min.<br>MPa | min.<br>(psi) | %                                 |
| 1        | Cold worked corrosion resistant steel 304-1/8H                      | 725                       | (105 000)     | 515                    | (75 000)      | 20                                |
| 2        | High strength corrosion resistant steel 21-6-9                      | 980                       | (142 000)     | 825                    | (120 000)     | 20                                |
| 3        | Re-annealed corrosion resistant steel UNS S32100                    | 500                       | (72 500)      | 210                    | (30 500)      | 40                                |
| 4        | Cold-worked and stress relieved titanium Ti-3AL-2.5V                | 860                       | (125 000)     | 720                    | (105 000)     | 10                                |
| 5        |   | 690                       | (100 000)     | 655                    | (95 000)      | 14                                |
| 6        | Unalloyed titanium TiCP   | 350                       | (50 000)      | 250                    | (35 000)      | 28                                |
| 7        | Aluminium alloy (6061), Solution treated and artificially aged (T6) | 290                       | (42 000)      | 240                    | (34 000)      | 10                                |

NOTE While waiting for the publication of International Standards for the materials described in [Table 1](#), national standards accepted by the corresponding country conforming to the requirements specified in this table are given in [Annex A](#) for information.

Table 2 — Outside diameters, wall thicknesses and materials for hydraulic tubing, pressure lines — Inch tubing

| Temperature <sup>a</sup>                                       |        | Type 13<br>-65 °F to 275 °F (-55 °C to 135 °C) |      |        |      |             |                                      |             |      |             |      |        |
|--|--------|--|------|--------|------|-------------|--------------------------------------|-------------|------|-------------|------|--------|
| Pressure class <sup>a</sup><br>Design-Operating-Pressure (DOP) |        | Class D<br>21 000 kPa<br>(3 000 psi)           |      |        |      |             | Class J<br>35 000 kPa<br>(5 000 psi) |             |      |             |      |        |
| Material code no.  |        | 1  |      | 2      |      | 4 or 5      |                                      | 4 or 5      |      | 4 or 5      |      |        |
| Material designation   |        | 304-1/8H                                       |      | 21-6-9 |      | Ti-3AL-2.5V |                                      | Ti-3AL-2.5V |      | Ti-3AL-2.5V |      |        |
| Tube outside diameter  |        | Tube wall thickness                            |      |        |      |             |                                      |             |      |             |      |        |
|  |        | Type A   |      |        |      |             | Type B                               |             |      |             |      |        |
| Dash size  | mm     | (inch)   | mm   | (inch) | mm   | (inch)      | mm                                   | (inch)      | mm   | (inch)      | mm   | (inch) |
| 4  | 6,35   | (.250)   | 0,51 | .020   | 0,41 | (.016)      | 0,41                                 | (.016)      | 0,64 | (.025)      | 0,55 | (.022) |
| 6  | 9,525  | (.375)   | 0,71 | .028   | 0,51 | (.020)      | 0,48                                 | (.019)      | 0,76 | (.030)      | 0,81 | (.032) |
| 8  | 12,70  | (.500)   | 0,89 | .035   | 0,66 | (.026)      | 0,66                                 | (.026)      | 1,02 | (.040)      | 1,09 | (.043) |
| 10   | 15,875 | (.625)   | 1,24 | .049   | 0,84 | (.033)      | 0,81                                 | (.032)      | 1,27 | (.050)      | 1,37 | (.054) |
| 12   | 19,05  | (.750)   | 1,47 | .058   | 0,99 | (.039)      | 0,99                                 | (.039)      | 1,50 | (.059)      | 1,65 | (.065) |
| 16   | 25,4   | (1.000)  | 1,65 | .065   | 1,32 | (.052)      | 1,32                                 | (.051)      | 2,01 | (.079)      | 2,23 | (.088) |
| 20   | 31,75  | (1.250)  |      |        | 1,78 | (.070)      | 1,78                                 | (.070)      | 2,49 | (.098)      | 2,67 | (.105) |
| 24   | 38,1   | (1.500)  |      |        |      |             |                                      |             |      |             | 3,18 | (.125) |
| 32   | 50,8   | (2.000)  |      |        |      |             |                                      |             |      |             |      |        |

<sup>a</sup> Temperature and pressure classes according to ISO 6771.

Table 3 — Outside diameters, wall thicknesses and materials for hydraulic tubing, suction and return lines — Inch tubing

| Temperature <sup>a</sup>  |  | Type 13<br>-65 °F to 275 °F (-55 °C to 135 °C)   |                                   |  |   |                   |    |                      |         |                     |        |                     |        |        |        |
|---|--|--|-----------------------------------|--|---|-------------------|----|----------------------|---------|---------------------|--------|---------------------|--------|--------|--------|
| Pressure class <sup>a</sup><br>Design-Operating-Pressure<br>(DOP) | Class N/A <sup>b</sup><br>1 500 kPa<br>(220 psi) | Class N/A <sup>b</sup><br>1 500 kPa<br>(220 psi) | Class A<br>4 200 kPa<br>(600 psi) | Class N/A or B <sup>b</sup><br>7 000 or 10 500 kPa <sup>c</sup><br>(1 000 or 1 500 psi) <sup>c</sup> | Class A or N/A <sup>b</sup><br>4 200 or 7 000 kPa <sup>c</sup><br>(600 or 1 000 psi) <sup>c</sup> | Material code no. |    | Material designation |         | Tube wall thickness |        | Tube wall thickness |        |        |        |
|   |  |  |                                   |  |   | 3                 | 7  | UNS S32100           | 6061-T6 | mm                  | (inch) | mm                  | (inch) | mm     | (inch) |
| Dash size   | mm   | (inch)   | mm                                | (inch)   | mm  | (inch)            | mm | (inch)               | mm      | (inch)              | mm     | (inch)              | mm     | (inch) |        |
| 4   | 6,35   | (.250)   |                                   |  |   |                   |    |                      |         |                     | 0,89   | (.035)              |        |        |        |
| 6   | 9,525  | (.375)   |                                   |  |   |                   |    |                      |         |                     | 0,89   | (.035)              |        |        |        |
| 8   | 12,70  | (.500)   |                                   |  |   |                   |    |                      |         |                     | 0,89   | (.035)              |        |        |        |
| 10  | 15,875   | (.625)   |                                   |  |   |                   |    |                      |         |                     | 0,89   | (.035)              |        |        |        |
| 12  | 19,05  | (.750)   |                                   |  |   |                   |    |                      |         |                     | 0,89   | (.035)              |        |        |        |
| 16  | 25,4   | (1.000)  |                                   |  |   |                   |    |                      |         |                     | 1,22   | (.048)              |        |        |        |
| 20  | 31,75  | (1.250)  |                                   |  |   |                   |    |                      |         | 0,89                | (.035) | 1,24                | (.049) | 0,61   | (.024) |
| 24  | 38,1   | (1.500)  |                                   |  |   |                   |    |                      |         | 0,89                | (.035) | 1,24                | (.049) | 0,61   | (.024) |
| 32  | 50,8   | (2,000)  |                                   |  |   |                   |    |                      |         | 0,71                | (.028) |                     |        |        |        |

<sup>a</sup> Temperature and pressure classes according to ISO 6771.

<sup>b</sup> No pressure class definition in ISO 6771 at the time of the preparation of this document, N/A: Not applicable.

<sup>c</sup> Used for different DOPs.

Table 4 — Outside diameter, wall thicknesses, and materials for hydraulic tubing pressure and return lines — Metric tubing

| Temperature <sup>a</sup> |            | Type 13 <sup>b</sup><br>-55 °C to 135 °C (- 65 °F to 275 °F) |           |           |                  |                                   |               |               |               |                                   |               |               |               |               |                                     |               |           |           |           |
|--------------------------|------------|--|-----------|-----------|------------------|-----------------------------------|---------------|---------------|---------------|-----------------------------------|---------------|---------------|---------------|---------------|-------------------------------------|---------------|-----------|-----------|-----------|
| Pressure <sup>a</sup>    |            | Class H<br>14 000 kPa (2 000 psi)                            |           |           |                  | Class D<br>21 000 kPa (3 000 psi) |               |               |               | Class E<br>28 000 kPa (4 000 psi) |               |               |               |               |                                     |               |           |           |           |
| Material code no.        |            | 1  |           | 2         |                  | 4                                 |               | 1             |               | 2                                 |               | 4             |               | 2             |                                     | 4             |           | 6         |           |
| Material designation     |            | 304-1/8H   |           | 21-6-9    |                  | Ti-3AL-2.5V                       |               | 304-1/8H      |               | 21-6-9                            |               | Ti-3AL-2.5V   |               | 21-6-9        |                                     | Ti-3AL-2.5V   |           | TiCP      |           |
| Tube outside diameter    |            | Tube wall thickness  |           |           |                  |                                   |               |               |               |                                   |               |               |               |               |                                     |               |           |           |           |
| DN Size                  | mm (inch)  | mm (inch)  | mm (inch) | mm (inch) | mm (inch)        | mm (inch)                         | mm (inch)     | mm (inch)     | mm (inch)     | mm (inch)                         | mm (inch)     | mm (inch)     | mm (inch)     | mm (inch)     | mm (inch)                           | mm (inch)     | mm (inch) | mm (inch) | mm (inch) |
| DN05                     | 5 (.196)   | —  | —         | —         | (.015)<br>(.019) | (0,4) <sup>c</sup><br>0,5         | 0,4<br>(.015) | 0,4<br>(.015) | 0,4<br>(.015) | 0,4<br>(.015)                     | 0,4<br>(.015) | 0,4<br>(.015) | 0,4<br>(.015) | 0,6<br>(.023) | (0,4) <sup>c</sup><br>0,5<br>(.019) | —             | —         | —         | —         |
| DN06                     | 6 (.236)   | —  | —         | —         | (.015)<br>(.019) | (0,4) <sup>c</sup><br>0,5         | 0,4<br>(.015) | 0,4<br>(.015) | 0,4<br>(.015) | 0,4<br>(.015)                     | 0,4<br>(.015) | 0,4<br>(.015) | 0,4<br>(.015) | 0,6<br>(.023) | 0,5<br>(.019)                       | 0,8<br>(.031) | —         | —         | —         |
| DN08                     | 8 (.314)   | —  | —         | —         | (.015)<br>(.019) | (0,4) <sup>c</sup><br>0,5         | 0,4<br>(.015) | 0,4<br>(.015) | 0,4<br>(.015) | 0,4<br>(.015)                     | 0,4<br>(.015) | 0,4<br>(.015) | 0,4<br>(.015) | 0,6<br>(.023) | 0,6<br>(.023)                       | 0,9<br>(.035) | —         | —         | —         |
| DN10                     | 10 (.393)  | —  | —         | —         | (.019)           | 0,5                               | 0,5<br>(.019) | 0,5<br>(.019) | 0,5<br>(.019) | 0,5<br>(.019)                     | 0,5<br>(.019) | 0,5<br>(.019) | 0,5<br>(.019) | 0,8<br>(.031) | 0,8<br>(.031)                       | 1,2<br>(.047) | —         | —         | —         |
| DN12                     | 12 (.472)  | —  | —         | —         | (.019)           | 0,5                               | 0,5<br>(.019) | 0,5<br>(.019) | 0,5<br>(.019) | 0,5<br>(.019)                     | 0,5<br>(.019) | 0,5<br>(.019) | 0,5<br>(.019) | 0,9<br>(.035) | 0,9<br>(.035)                       | 1,4<br>(.055) | —         | —         | —         |
| DN14                     | 14 (.551)  | —  | —         | —         | (.019)           | 0,5                               | 0,5<br>(.019) | 0,5<br>(.019) | 0,5<br>(.019) | 0,5<br>(.019)                     | 0,5<br>(.019) | 0,5<br>(.019) | 0,5<br>(.019) | —             | 1,0<br>(.039)                       | 1,6<br>(.063) | —         | —         | —         |
| DN16                     | 16 (.660)  | —  | —         | —         | (.023)           | 0,6                               | 0,6<br>(.023) | 0,6<br>(.023) | 0,6<br>(.023) | 0,6<br>(.023)                     | 0,6<br>(.023) | 0,6<br>(.023) | 0,6<br>(.023) | 1,2<br>(.047) | 1,2<br>(.047)                       | 1,8<br>(.071) | —         | —         | —         |
| DN18                     | 18 (.709)  | —  | —         | —         | (.028)           | 0,7                               | 0,7<br>(.028) | 0,7<br>(.028) | 0,7<br>(.028) | 0,7<br>(.028)                     | 0,7<br>(.028) | 0,7<br>(.028) | 0,7<br>(.028) | —             | 1,3<br>(.051)                       | —             | —         | —         | —         |
| DN20                     | 20 (.787)  | —  | —         | —         | (.028)           | 0,7                               | 0,7<br>(.028) | 0,7<br>(.028) | 0,7<br>(.028) | 0,7<br>(.028)                     | 0,7<br>(.028) | 0,7<br>(.028) | 0,7<br>(.028) | 1,5<br>(.059) | 1,5<br>(.059)                       | —             | —         | —         | —         |
| DN22                     | 22 (.866)  | —  | —         | —         | (.031)           | 0,8                               | 0,8<br>(.031) | 0,8<br>(.031) | 0,8<br>(.031) | 0,8<br>(.031)                     | 0,8<br>(.031) | 0,8<br>(.031) | 0,8<br>(.031) | —             | 1,6<br>(.063)                       | —             | —         | —         | —         |
| DN25                     | 25 (.984)  | —  | —         | —         | (.035)           | 0,9                               | 0,9<br>(.035) | 0,9<br>(.035) | 0,9<br>(.035) | 0,9<br>(.035)                     | 0,9<br>(.035) | 0,9<br>(.035) | 0,9<br>(.035) | 1,9<br>(.075) | 1,8<br>(.071)                       | —             | —         | —         | —         |
| DN28                     | 28 (1.102) | —  | —         | —         | (.031)           | 1,0                               | 1,0<br>(.031) | 1,0<br>(.031) | 1,0<br>(.031) | 1,0<br>(.031)                     | 1,0<br>(.031) | 1,0<br>(.031) | 1,0<br>(.031) | —             | 2,0<br>(.078)                       | —             | —         | —         | —         |
| DN32                     | 32 (1.260) | —  | —         | —         | (.039)           | 1,2                               | 1,2<br>(.039) | 1,2<br>(.039) | 1,2<br>(.039) | 1,2<br>(.039)                     | 1,2<br>(.039) | 1,2<br>(.039) | 1,2<br>(.039) | 2,2<br>(.087) | 2,2<br>(.087)                       | —             | —         | —         | —         |

<sup>a</sup> Temperature and pressure classes according to ISO 6771.

<sup>b</sup> For higher temperature (Type 20), refer to Table 5.

<sup>c</sup> Values in ( ) are based on calculation only. Values below 0,5 mm wall thickness are critical due to manufacturing reason.

**Table 5 — Outside diameter, wall thicknesses, and materials for hydraulic tubing pressure lines — Metric tubing**

| Temperature <sup>a</sup> |    |         | Type 20<br>- 55 °C to 200 °C<br>(- 65 °F to 400 °F) |        |                                      |        |
|--------------------------|----|---------|---|--------|--------------------------------------|--------|
| Pressure <sup>a</sup>    |    |         | Class D<br>21 000 kPa<br>(3 000 psi)                |        | Class D<br>21 000 kPa<br>(3 000 psi) |        |
| Material code no.        |    |         | 4   |        |                                      |        |
| Material designation     |    |         | Ti-3AL-2.5V   |        |                                      |        |
| Tube outside diameter    |    |         | Tube wall thickness                                 |        |                                      |        |
| DN size                  | mm | (inch)  | mm  | (inch) | mm                                   | (inch) |
| DN05                     | 5  | (.196)  | —   | —      | —                                    | —      |
| DN06                     | 6  | (.236)  | 0,4   | (.015) | 0,7                                  | (.028) |
| DN08                     | 8  | (.314)  | —   | —      | —                                    | —      |
| DN10                     | 10 | (.393)  | 0,6   | (.023) | 0,9                                  | (.035) |
| DN12                     | 12 | (.472)  | 0,7   | (.028) | 1,0                                  | (.039) |
| DN14                     | 14 | (.551)  | —   | —      | —                                    | —      |
| DN16                     | 16 | (.660)  | 0,9   | (.035) | 1,3                                  | (.051) |
| DN18                     | 18 | (.709)  | —   | —      | —                                    | —      |
| DN20                     | 20 | (.787)  | 1,1   | (.043) | 1,8                                  | (.063) |
| DN22                     | 22 | (.866)  | —   | —      | —                                    | —      |
| DN25                     | 25 | (.984)  | 1,4   | (.055) | 2,2                                  | (.087) |
| DN28                     | 28 | (1.102) | —   | —      | —                                    | —      |
| DN32                     | 32 | (1.260) | 1,6   | (.063) | 2,5                                  | (.098) |

<sup>a</sup> Temperature and pressure classes according to ISO 6771.

## Annex A (informative)

### Aerospace hydraulic tubing materials

National standards for tubing material accepted by the corresponding countries conforming to the requirements specified in [Table 1](#) are given in [Table A.1](#). The reference number for the corresponding future International Standards are also given for information.

**Table A.1 — Corresponding national standards for tubing materials**

| Code no | Alloy       | ISO <sup>a</sup>       | Standards from other international bodies |   | National standards |          |                  |            | Industry standards     |
|---------|-------------|------------------------|---|---|--------------------|----------|------------------|------------|------------------------|
|         |             |                        | EN Standard                               | SAE Standard                                | China              | France   | UK               | USA        |                        |
| 1       | 304-1/8H    |                        |   | AMS-T-6845<br>AMS 5566                      | YB678 <sup>b</sup> |          |                  |            |                        |
| 2       | 21-6-9      |                        |   | AMS 5561                                    |                    |          |                  |            | ASNA 3288<br>BMS 7-185 |
| 3       | 321/347     |                        |   | AMS 5557<br>AMS 5570<br>AMS 5571            |                    |          | BS T66<br>BS T72 |            | NSA 3512<br>NSA 3507   |
| 4/5     | Ti-3AL-2.5V | ISO 18487 <sup>c</sup> | EN 3120                                   | AMS 4944<br>AMS 4945<br>AMS 4946<br>AS 5620 |                    |          |                  |            | ABS 5004<br>ABS 5141   |
| 6       | Ti CP       |                        |   |   |                    |          |                  | ASTM B 338 |                        |
| 7       | 6061-T6     |                        | EN 2070                                   | AMS-T-7081<br>AMS 4083                      |                    | AIR 9302 |                  |            | ASNA 3410              |

<sup>a</sup> The International Standards (ISO 9522, ISO 9540, ISO 9630, ISO 9620) mentioned in the previous edition of this document are non-current.

<sup>b</sup> TBC.

<sup>c</sup> In preparation at publication of this document.



## Bibliography

- [1] ISO 2964, *Aerospace — Tubing — Outside diameters and thicknesses — Metric dimensions*





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

## Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

## Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com).

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Useful Contacts

### Customer Services

**Tel:** +44 345 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 345 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

### BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK