

BS ISO 9022-17:2015



BSI Standards Publication

# Optics and photonics — Environmental test methods

Part 17: Combined contamination, solar  
radiation

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 9022-17:2015. It supersedes BS ISO 9022-17:1994 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee CPW/172, Optics and Photonics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.  
Published by BSI Standards Limited 2015

ISBN 978 0 580 88212 8

ICS 37.020

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2015.

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------

---

---

---

**Optics and photonics —  
Environmental test methods —**

**Part 17:  
Combined contamination, solar  
radiation**

*Optique et photonique — Méthodes d'essais d'environnement —  
Partie 17: Essai combiné contamination-rayonnement solaire*





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 General information and test conditions</b> .....	<b>1</b>
3.1 General.....	1
3.2 Specimens .....	2
<b>4 Conditioning</b> .....	<b>2</b>
4.1 Conditioning method 90: Basic cosmetic substances and artificial hand sweat, combined with solar radiation .....	2
4.2 Conditioning method 91: Fuels and other resources for aircraft, naval vessels, and land vehicles, combined with solar radiation.....	2
<b>5 Procedure</b> .....	<b>2</b>
5.1 General.....	2
5.2 Preconditioning, recovery, evaluation, and general level for acceptance.....	2
<b>6 Environmental test code</b> .....	<b>4</b>
<b>7 Specification</b> .....	<b>5</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 172, *Optics and photonics*, Subcommittee SC 1, *Fundamental standards*.

This second edition cancels and replaces the first edition (ISO 9022-17:1994), of which it constitutes a minor revision.

ISO 9022 consists of the following parts, under the general title *Optics and photonics — Environmental test methods*:

- *Part 1: Definitions, extent of testing*
- *Part 2: Cold, heat and humidity*
- *Part 3: Mechanical stress*
- *Part 4: Salt mist*
- *Part 6: Dust*
- *Part 7: Resistance to drip or rain*
- *Part 8: High internal pressure, low internal pressure, immersion*
- *Part 9: Solar radiation and weathering*
- *Part 11: Mould growth*
- *Part 12: Contamination*
- *Part 14: Dew, hoarfrost, ice*
- *Part 17: Combined contamination, solar radiation*
- *Part 20: Humid atmosphere containing sulfur dioxide or hydrogen sulfide*

- *Part 22: Combined cold, dry heat or temperature change with bump or random vibration*
- *Part 23: Low pressure combined with cold, ambient temperature and dry and damp heat*

## Introduction

Optical instruments are affected during their use by a number of different environmental parameters which they are required to resist without significant reduction in performance and to remain within defined specifications.

The type and severity of these parameters depend on the conditions of use of the instrument (for example, in the laboratory or workshop) and on its geographical location. The environmental effects on optical instrument performance in the tropics and subtropics are totally different from those found when they are used in arctic regions. Individual parameters cause a variety of different and overlapping effects on instrument performance.

The manufacturer attempts to ensure, and the user naturally expects, that instruments will resist the likely rigours of their environment throughout their life. This expectation can be assessed by exposure of the instrument to a range of simulated environmental parameters under controlled laboratory conditions. The severity of these conditions is often increased to obtain meaningful results in a relatively short period of time.

In order to allow assessment and comparison of the response of optical instruments to appropriate environmental conditions, ISO 9022 contains details of a number of laboratory tests which reliably simulate a variety of different environments. The tests are based largely on IEC standards, modified where necessary to take into account features special to optical instruments.

As a result of continuous progress in all fields, optical instruments are no longer only precision-engineered optical products, but, depending on their range of application, also contain additional assemblies from other fields. For this reason, the principal function of the instrument is to be assessed to determine which International Standard should be used for testing. If the optical function is of primary importance, then ISO 9022 is applicable, but if other functions take precedence then the appropriate International Standard in the field concerned should be applied. Cases can arise where application of both ISO 9022 and other appropriate International Standards will be necessary.



# Optics and photonics — Environmental test methods —

## Part 17:

### Combined contamination, solar radiation

#### 1 Scope

This part of ISO 9022 specifies the methods relating to the environmental tests of optical instruments and including additional assemblies from other fields (e.g. mechanical, chemical, and electronic devices) under equivalent conditions, for their ability to resist the influence of combined contamination and solar radiation. “Contamination”, as used in this part of ISO 9022, means the contact of optical instruments with corrosive chemical substances (hereafter called test agents).

Complete instruments or assemblies are, however, not be tested to this part of ISO 9022 except for special reasons (refer to ISO 9022-12). As a rule, representative substrates are used as specimens.

The tests described in this part of ISO 9022 are designed for the selection of materials and components for instruments likely to be subjected to combined contamination and solar radiation during service life, rather than for regular production control.

The purpose of testing is to investigate the resistance of an instrument, and in particular, of instrument surfaces, coatings, or synthetic materials, to a short-time exposure to the test agents combined with solar radiation.

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9022-1, *Optics and photonics — Environmental test methods — Part 1: Definitions, extent of testing*

ISO 9022-9, *Optics and photonics — Environmental test methods — Part 9: Solar radiation and weathering*

ISO 9022-12, *Optics and photonics — Environmental test methods — Part 12: Contamination*

#### 3 General information and test conditions

##### 3.1 General

Exposure of the specimen to the combined stress conditions renders the test much more severe than separate exposure to any of the conditions cited.

The test shall be conducted in ambient atmospheric conditions in accordance with ISO 9022-1.

The test agents listed in [Tables 1](#) and 2 were selected from ISO 9022-12, conditioning methods 86 and 89.

The test shall be conducted in accordance with the requirements of ISO 9022-9 and ISO 9022-12.

The surface of the specimens shall be orientated so that the test agents do not flow away during testing. If liquid test agents are used, enough drops shall be deposited in one place on the surface to form a circular spot of approximately 10 mm diameter. During the test, the test agents may not flow into each other. In the case of spreading liquids, several specimens should be used if necessary. Viscous or paste

liquids shall be spread evenly and thinly in the form of the spot described above (thickness approximately 0,1 mm). It should be noted that heating of the test agents can cause them to spread during the test. Test agents which evaporate during the test shall not be replaced.

The relevant specification might require testing of a complete instrument or assembly if such instrument or assembly would be likely to encounter, during its service life, complete flooding rather than partial contamination only. After having preconditioned such specimens as described in ISO 9022-12, the surface shall be completely and copiously sprayed, by means of an atomizer, with a test agent specified in the relevant specification. Any test agent evaporating during exposure shall not be replaced.

### **3.2 Specimens**

For specimens, see ISO 9022-12.

## **4 Conditioning**

[Tables 1](#) and [2](#) show combinations of degrees of severity from ISO 9022-9 and test agents from ISO 9022-12, conditioning methods 86 and 89.

### **4.1 Conditioning method 90: Basic cosmetic substances and artificial hand sweat, combined with solar radiation**

See [Table 1](#).

### **4.2 Conditioning method 91: Fuels and other resources for aircraft, naval vessels, and land vehicles, combined with solar radiation**

See [Table 2](#).

## **5 Procedure**

### **5.1 General**

The test shall be conducted in accordance with the requirements of the relevant specifications and the reference documents.

### **5.2 Preconditioning, recovery, evaluation, and general level for acceptance**

For preconditioning, recovery, evaluation, and general level for acceptance, see ISO 9022-12.

**Table 1 — Degrees of severity for conditioning method 90: Basic cosmetic substances and artificial hand sweat, combined with solar radiation**

Degree of severity		01	02	03 <sup>a</sup>	04 <sup>a</sup>
Temperature limits within test chamber	°C $\frac{t_2}{t_1}$	55 ± 2	55 ± 2	40 ± 2	55 ± 2
		25 ± 2			
Relative humidity	%	<40			
Recirculating air speed	m/s	1,5 to 3			
Irradiance	kW/m <sup>2</sup>	1 ± 0,1	0 to 1,0 <sup>b</sup>	1 ± 0,1	1 ± 0,1
Total exposure time <sup>c</sup>	days	3	5	4	10
Irradiation <sup>c</sup>	kWh/m <sup>2</sup>	24	45	96	240
Test sequence <sup>c</sup>		Figure 1	Figure 2	Figure 3	Figure 3
Number of cycles		5	5	1	
Test agents		Paraffin oil, high purity Glycerine, high purity Vaseline, white Lanoline (unguentum molle) Cold cream (unguentum leniens) Artificial hand sweat <sup>d</sup>			
State of operation		1			
<p><sup>a</sup> For testing representative specimens only.</p> <p><sup>b</sup> Tolerance for intermediate irradiance levels and upper limit ±0,1 kW.</p> <p><sup>c</sup> Refer to ISO 9022-9, Figures 1 to 3.</p> <p><sup>d</sup> High purity composition: 4,0 g sodium chloride 1,0 g urea 3,5 g ammonium chloride 3,0 ml lactic acid 0,5 ml acetic acid 0,5 ml pyruvic acid 1,0 ml butyric acid</p> <p>Add sufficient distilled water to make 1 000 ml of solution.</p>					

**Table 2 — Degrees of severity for conditioning method 91: Fuels and other resources for aircraft, naval vessels, and land vehicles, combined with solar radiation**

Degree of severity		01 <sup>a</sup>	02 <sup>a</sup>
Temperatures limits within test chamber	°C $\frac{t_2}{t_1}$	40 ± 2	55 ± 2
		25 ± 2	
Relative humidity	%	<40	
Recirculating air speed	m/s	1,5 to 3	
Irradiance	kW/m <sup>2</sup>	1 ± 0,1	1 ± 0,1
Total exposure time <sup>b</sup>	days	4	10
Irradiation <sup>b</sup>	kWh/m <sup>2</sup>	96	240
Test sequence <sup>b</sup>		Figure 3	Figure 3

**Table 2** (continued)

Degree of severity	01 <sup>a</sup>	02 <sup>a</sup>
Number of cycles	1	
Test agents <sup>c</sup>	Petrol, super-grade Fuel oil (diesel oil) Turbine fuel for aircraft Turbine lubricating oil, synthetic Combustion engine lubricating oil Lubricating grease for aircraft and instruments Hydraulic oil, mineral-base Hydraulic fluid, phosphoric-ester-base Damping fluid, silicone-oil-base Brake fluid for motor vehicles De-icing and defrosting fluids Antifreeze agent Fire-extinguishing agent (bromochlorodifluoromethane) General purpose detergent Potassium hydroxide (KOH) (alkaline battery electrolyte), mass quota $w(\text{KOH}) = 0,35$ Sulfuric acid ( $\text{H}_2\text{SO}_4$ ) (acid battery electrolyte), mass quota $w(\text{H}_2\text{SO}_4) = 0,34$ Diester mixture <sup>d</sup>	
State of operation	1	
<sup>a</sup>	For testing representative specimens only.	
<sup>b</sup>	Refer to ISO 9022-9, Figure 3.	
<sup>c</sup>	The relevant specification specifies the commercial type, if not indicated in this Table.	
<sup>d</sup>	Composition: fluid paraffin, mass fraction $w_1 = 65 \%$ ; dioctylophthalate, mass fraction $w_2 = 20 \%$ ; tricresilophosphate, mass fraction $w_3 = 15 \%$ .	

## 6 Environmental test code

The environmental test code shall be as defined in ISO 9022-1, giving a reference to ISO 9022 and the codes for the conditioning method chosen, the degree of severity and the state of operation.

**EXAMPLE** The environmental test of optical instruments for resistance to combined basic cosmetic substances and artificial hand sweat, solar radiation, conditioning method 90, degree of severity 02, state of operation 1, is identified as:

**Environmental test ISO 9022-90-02-1**

## 7 Specification

The relevant specification shall contain the following details:

- a) environmental test code;
- b) type and number of specimens;
- c) test agents not to be used and/or test agents to be used in addition;
- d) test agents to be used for testing complete instruments or assemblies; identification of the commercial type of the test agents specified for ISO 9022-12, conditioning method 89;
- e) type and scope of initial test;
- f) preconditioning if other than described in ISO 9022-12;
- g) recovery if other than described in ISO 9022-12;
- h) type and scope of final test;
- i) criteria for evaluation taking account of ISO 9022-12;
- j) type and scope of test report.





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™