

Cylindrical cork stoppers — Physical tests —

Part 7: Determination of dust content

ICS 55.100; 79.100



National foreword

This British Standard was published by BSI. It is the UK implementation of ISO 9727-7:2007.

The UK participation in its preparation was entrusted to Technical Committee PRI/81, Cork.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 29 June 2007

© BSI 2007

Amendments issued since publication

Amd. No.	Date	Comments

ISBN 978 0 580 52940 5

**This document is now
PUBLIC**

INTERNATIONAL
STANDARD

ISO
9727-7

First edition
2007-05-15

**Cylindrical cork stoppers — Physical
tests —**

**Part 7:
Determination of dust content**

*Bouchons cylindriques en liège — Essais physiques —
Partie 7: Détermination de la quantité de poussières*



Reference number
ISO 9727-7:2007(E)

This document is now
POOBLIC

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9727-7 was prepared by Technical Committee ISO/TC 87, *Cork*.

This first edition of ISO 9727-7, together with the other parts of ISO 9727:2007, cancels and replaces ISO 9727:1991, which has been technically revised.

ISO 9727 consists of the following parts, under the general title *Cylindrical cork stoppers — Physical tests*:

- *Part 1: Determination of dimensions*
- *Part 2: Determination of mass and apparent density for agglomerated cork stoppers*
- *Part 3: Determination of humidity content*
- *Part 4: Determination of dimensional recovery after compression*
- *Part 5: Determination of extraction force*
- *Part 6: Determination of liquid tightness*
- *Part 7: Determination of dust content*



**This document is now
PUBLIC**

blank

Cylindrical cork stoppers — Physical tests —

Part 7: Determination of dust content

1 Scope

This part of ISO 9727 specifies a test method for determining the dust content of a cylindrical cork stopper.

It is applicable to all types of cylindrical cork stoppers ready for use, intended to be completely inserted in the bottle neck (straight cork stoppers).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 633, *Cork — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 633 and the following apply.

3.1

straight cork stopper

«*ras de bague*»

stopper which is completely introduced in the bottle neck, its superior end reaching the top border of the bottle

4 Materials

4.1 Ethanolic solution (10 %), prepared with demineralised water and previously filtered through a membrane of 1,2 µm porosity.

5 Apparatus

5.1 Conical flask, of 500 ml capacity, with a bottom diameter of at least 100 mm.

5.2 Orbital stirrer, allowing to reach a rotational frequency between 140 r/min and 160 r/min.

5.3 Glass or stainless-steel filter, fixed to a vacuum device.

5.4 Membranes and oven, to dry them.

This document is not
POOBLIC

5.4.1 First possibility

5.4.1.1 **Membrane**, of cellulose acetate or polycarbonate with 1,2 μm porosity.

5.4.1.2 **Oven**, regulated at $30\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$.

5.4.2 Second possibility

5.4.2.1 **Membrane**, of glass microfibre with 1,2 μm porosity.

5.4.2.2 **Oven**, regulated at $103\text{ }^{\circ}\text{C} \pm 4\text{ }^{\circ}\text{C}$.

5.5 **Balance**, with a resolution inferior or equal to 0,000 1 g.

5.6 **Desiccator**, with hygroscopic salt and saturation indicator.

6 Test conditions

6.1 Environment

The test shall be carried out in an environment with the following characteristics:

— temperature $21\text{ }^{\circ}\text{C} \pm 4\text{ }^{\circ}\text{C}$;

— relative humidity of air $60\% \pm 20\%$.

6.2 Cork stoppers

6.2.1 Temperature

At the beginning of the test, confirm that the stoppers of the test sample are at a temperature of $21\text{ }^{\circ}\text{C} \pm 4\text{ }^{\circ}\text{C}$.

6.2.2 Humidity

At the beginning of the test, confirm that the stoppers of the test sample are at a humidity of $6\% \pm 2\%$.

If humidity is not between 4 % and 8 %, the result of the humidity obtained shall be referred to in the test report.

7 Sampling

From each lot, take the quantity of stoppers that correspond to the sampling plan previously agreed between the interested parties. The test piece is composed of 4 cork stoppers.

8 Procedure

8.1 Place 4 cork stoppers in a 500 ml conical flask (5.1) and add 250 ml of the filtered ethanolic solution (4.1).

8.2 Place the conical flask for 10 min on the stirring plate (5.2) at a rotational frequency between 140 r/min and 160 r/min.

8.3 Filter the ethanolic solution obtained through a membrane of 1,2 μm previously dried and weighted to 0,1 mg. Register the initial mass, m_1 , expressed in milligrams.

- 8.3.1 First possibility (5.4.1):** filter on a membrane of cellulose acetate or polycarbonate (5.4.1.1).
- 8.3.2 Second possibility (5.4.2):** filter on a membrane of glass microfibre (5.4.2.1).
- 8.4** Rinse the stoppers and conical flask with 50 ml of filtered ethanolic solution (4.1) and filter (8.3).
- 8.5** Rinse the membrane funnel with 50 ml of filtered ethanolic solution (4.1) and filter (8.3).
- 8.6** Transport the membrane to the oven and let it dry according to one of the following possibilities.
- 8.6.1 First possibility (5.4.1):** use the oven at $30\text{ °C} \pm 2\text{ °C}$ (5.4.1.2) and let the membrane dry for 24 h.
- 8.6.2 Second possibility (5.4.2):** use the oven at $103\text{ °C} \pm 4\text{ °C}$ (5.4.2.2) and let the membrane dry for 1 h.
- 8.7** Let it cool in the desiccator for 30 min.
- 8.8** Weigh the membrane at ambient temperature to 0,1 mg and register the result, m_2 , expressed in milligrams (final mass).

9 Results

The dust quantity per cork stopper, expressed in milligrams, rounded off to the nearest 0,1 mg, is given by the equation:

$$(m_2 - m_1) / 4$$

where

m_1 is the initial mass of the dried and weighted membrane (8.3);

m_2 is the final mass (8.8).

10 Test report

The test report shall include the following information:

- a) a reference to this part of ISO 9727;
- b) complete identification of the sample, including its type and origin;
- c) sampling report;
- d) results obtained;
- e) any deviation from this part of ISO 9727 that may have affected the results.



BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.

BSI

389 Chiswick High Road
London
W4 4AL

This document is now
PUBLIC