



BSI Standards Publication

Plain bearings — Testing of bearing metals — Resistance to corrosion by lubricants under static conditions

National foreword

This British Standard is the UK implementation of ISO 10129:2017. It supersedes BS ISO 10129:2006, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee MCE/12, Plain bearings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

ISBN 978 0 580 92854 3

ICS 21.100.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2017.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
10129

Second edition
2017-03

**Plain bearings — Testing of bearing
metals — Resistance to corrosion by
lubricants under static conditions**

*Paliers lisses — Essai des matériaux antifriction — Résistance à la
corrosion par des lubrifiants dans des conditions statiques*



Reference number
ISO 10129:2017(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Health and safety	1
5 General principles	1
6 Lubricants	2
7 Apparatus	2
8 Preparation of test samples	2
9 Test procedure	3
10 Expression of results	3
10.1 Mass change	3
10.2 Changes in dimensions	3
10.3 Surface changes.....	3
10.4 Microstructural changes.....	4
10.5 Type and nature of the corrosion products	4
10.6 Change of lubricant.....	4
11 Test report	4
Bibliography	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 2, *Materials and lubricants, their properties, characteristics, test methods and testing conditions*.

This second edition cancels and replaces the first edition (ISO 10129:2006), which has been technically revised.

Introduction

It is essential that certain properties of bearing materials combined within the tribological system remain unchanged or change only within a permissible range over a long period of time. It is on account of these properties that the materials are regarded as being especially suitable for the tribological system. As to the tribological system “plain bearing”, the compatibility between the bearing materials and lubricant is of special interest and is dependent on chemical and mechanical actions.

The test established in this document determines the behaviour of plain bearing materials with respect to corrosion by lubricants (lubricating oils) under static conditions, i.e. without any mechanical action taking place simultaneously.

In order for such corrosion tests to be evaluated and compared, it is necessary that they be carried out in accordance with the conditions laid down in this document. Other conditions are to be indicated in detail.

Plain bearings — Testing of bearing metals — Resistance to corrosion by lubricants under static conditions

1 Scope

This document establishes a test of the corrosion-resistance of bearing materials to lubricants. It also specifies the most important general principles for carrying out such corrosion testing.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

corrosion

reaction of a bearing material to its environment, causing a measurable change in the material and which can result in corrosion damage

Note 1 to entry: In most cases, this reaction is of a chemical nature. It can, however, also involve chemical or mechanical processes. Material changes solely caused by or found only in combination with mechanical influences are not dealt with in this document. For a detailed explanation of the various causes of damage to plain bearings, see ISO 7146-1.

4 Health and safety

Resources, test pieces, test materials, test equipment and test procedures shall comply with the current health and safety regulations/laws of the country in which the test is carried out. Where equipment, materials and/or reagents that may be hazardous to health are specified, appropriate precautions in conformity with local regulations/laws shall be taken.

5 General principles

5.1 In general, corrosion tests are carried out as comparison tests, i.e. several materials and lubricants are compared with one another. However, it is also possible to include already known behaviour in the test reference materials or reference lubricants.

5.2 The duration of the test shall be chosen, and, if necessary, extended, so that at the end of the test, definite information on the corrosion behaviour of the material tested and, possibly, of the reference material can be obtained under the specified test conditions.

5.3 A value for a single material test is less informative, owing to a greater dispersion of the results, which often occurs when determining an increase or decrease in mass.

Therefore, each result shall be given as a mean value from at least three tests.

6 Lubricants

The quantity of lubricant used shall be at least 10 ml/cm² of bearing material surface.

Specifications indicating the type and performance level of the oils are used to characterize the lubricants used for the tests.

However, in order to be able to draw conclusions concerning, for example, the additives used and their effect, it is recommended that the precise chemical and physical data be given, as follows:

- density at 15 °C, in grams per millilitre;
- flash point, in degree Celsius;
- neutralization value;
- saponification value;
- base number;
- kinematic viscosity at 40 °C, in square millimetres per second;
- kinematic viscosity at 100 °C, in square millimetres per second;
- sulfate ash yield, as a percentage by mass;
- zinc content, as a percentage by mass;
- phosphorus content, as a percentage by mass;
- barium content, as a percentage by mass;
- calcium content, as a percentage by mass;
- content of sulfur in corrosive forms, as a percentage by mass.

7 Apparatus

7.1 Beaker(s), of sufficient capacity to allow each test sample to be fully immersed.

7.2 Heating bath, preferably an oil bath, capable of maintaining the required temperature to within ± 2 °C.

The heating bath shall be large enough to allow the beaker to be immersed up to three quarters of its height to prevent overspill of heating bath fluid into the test beaker.

8 Preparation of test samples

8.1 The preferred test sample shall be a complete bearing. Where this is not possible, a test sample of bearing material shall be cut out from parts sufficiently large that any influences of strong mechanical cold-working and of high temperature rise at the edges of the cut are eliminated. Burrs shall be removed.

8.2 The surface of the bearing material shall not be less than 25 cm² in order to eliminate as far as possible the influence of irregularities. If one bearing surface area is less than 25 cm², consider using more than one in the test vessel and combine the result.

8.3 The surface condition of test samples during the tests shall agree as far as possible with the surface condition of the bearing material in practice. The test sample shall be thoroughly cleaned and degreased. Suitable organic solvents (e.g. white spirit or methanol) should be used.

8.4 Test samples shall be clearly identified or could be marked. Marking methods which harm the mechanical strength of the bearing (e.g. electromechanical methods) shall be avoided.

9 Test procedure

Perform the following test procedure before testing.

- a) Record the mass, dimensions and roughness of the test samples.
- b) Place the bearing material test samples in the beakers (7.1) in such a way that they are completely covered by the lubricant in order to avoid the influence at the phase limit air/lubricant. Protect the beakers against dirt by means of a cover.
- c) In principle, test only samples of the same bearing material in one beaker in order to avoid any interaction. The atmosphere should be free from any substance which could interfere with the test.
- d) During the test, maintain the beakers at the specified test temperature to within ± 2 °C. Recommended test temperatures are 80 °C, 100 °C, 120 °C, 150 °C and 180 °C.

The duration of the test shall be 20 days at least; it may be extended if necessary (see 5.2). Intermediate assessments shall be made after one week and after two weeks. Test temperatures and test times should be chosen to reflect operating conditions in the intended bearing application.

- e) For the purpose of the intermediate and final assessments, clean the test samples by spraying using an appropriate solvent as one of the means. Dry them in a hot-air cabinet until a constant mass is attained. Record the mass, dimensions and roughness.

10 Expression of results

10.1 Mass change

Data concerning the mass changes of the samples are only really informative when the surface of the test samples is uniformly attacked.

The mass change of the samples (mass loss or increase in mass) shall be given as the mean value from at least three samples.

10.2 Changes in dimensions

Data concerning the dimensional changes of the samples are only really informative when the surface of the test samples is uniformly attacked.

The dimensional change of the samples (decrease or increase in dimensions) shall be given as the mean value from at least three samples.

10.3 Surface changes

During the intermediate and final assessments, check the surfaces of the test samples with regard to the frequency, extension and distribution of single corrosion points, as well as discolouration.

Record the macro and micro surface condition by means of photographs. Optical and electron microscopy methods may be used to characterize the surface changes. Depth measurements may be taken by using a scanning electron microscope or surface finish scans.

10.4 Microstructural changes

Metallographical structure tests are necessary if, for example, a constituent or the grain boundary is especially attacked during the corrosion process. Use an appropriate drawing or a photograph to record the positions of the sections and, if necessary, the places from where the test samples were taken.

10.5 Type and nature of the corrosion products

Indicate the colour and nature of the corrosion products in the test report. For basic tests, it can be useful to determine the chemical composition and structure of the corrosion products, for example, by X-ray photoelectron spectroscopy or Auger electron spectroscopy analysis techniques.

10.6 Change of lubricant

The chemical composition or the physical properties of the lubricant can change on reaction with the bearing material. The recording of this change can help considerably when evaluating the compatibility test. The list given in [Clause 6](#) may serve as a basis for the data to be determined.

11 Test report

As well as the presentation of results, the test report shall contain at least the following information:

- a) a reference to this document, i.e. ISO 10129:2017;
- b) chemical composition of the bearing material samples, and their designation if necessary;
- c) condition of the material, e.g. cast, hot-rolled, cold-rolled or method of heat treatment;
- d) type of sample, e.g. test sample cut out of solid or multilayer material (e.g. steel/AlSn6Cu) or prefabricated part (bearing liner or bush);
- e) method of sampling, e.g. longitudinal direction or at right angles to this;
- f) dimensions of the test sample before and after testing;
- g) surface roughness of the test sample before and after testing;
- h) method of cleaning;
- i) microsection before and after testing, to determine the structure, e.g. grain size, distribution of lead or tin in the case of heterogeneous alloys;
- j) test duration and test temperature;
- k) type and nature of the corrosion products;
- l) date and place of testing and name of tester;
- m) photographs, sample micro and macro appearance before and after testing.

Bibliography

- [1] ISO 7146-1, *Plain bearings — Appearance and characterization of damage to metallic hydrodynamic bearings — Part 1: General*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK