BS ISO 10575:2012



BSI Standards Publication

Resilient floor coverings — Specification for rubber sheet floor coverings with backing



BS ISO 10575:2012 BRITISH STANDARD

National foreword

This British Standard is the UK implementation of ISO 10575:2012.

The UK participation in its preparation was entrusted to Technical Committee PRI/3/60, Textile & Resilient Floor Coverings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 61742 3

ICS 97.150

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2012.

Amendments issued since publication

Date Text affected

INTERNATIONAL STANDARD

ISO 10575:2012 ISO 10575

First edition 2012-08-01

Resilient floor coverings — Specification for rubber sheet floor coverings with backing

Revêtements de sol résilients — Spécifications pour les revêtements de sol en caoutchouc avec dossier



BS ISO 10575:2012 ISO 10575:2012(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10575 was prepared by Technical Committee ISO/TC 219, Floor coverings.

Resilient floor coverings — Specification for rubber sheet floor coverings with backing

1 Scope

This International Standard specifies the characteristics of rubber sheet floor coverings with backing.

This International Standard includes a classification system based on intensity of use, which shows where resilient floor coverings should provide satisfactory service.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-B02, Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test

ISO 4649:2010, Rubber, vulcanized or thermoplastic — Determination of abrasion resistance using a rotating cylindrical drum device

ISO 4918, Resilient, textile and laminate floor coverings — Castor chair test

ISO 7619-1, Rubber, vulcanized or thermoplastic — Determination of indentation hardness — Part 1: Durometer method (Shore hardness)

ISO 23999, Resilient floor coverings — Determination of dimensional stability and curling after exposure to heat

ISO 24340, Resilient floor coverings — Determination of thickness of layers

ISO 24341, Resilient and textile floor coverings — Determination of length, width and straightness of sheet

ISO 24343-1, Resilient and laminate floor coverings — Determination of indentation and residual indentation — Part 1: Residual indentation

ISO 24344, Resilient floor coverings — Determination of flexibility and deflection

ISO 24346, Resilient floor coverings — Determination of overall thickness

ASTM D883, Standard Terminology Relating to Plastics

ASTM D1566, Standard Terminology Relating to Rubber

ASTM D3389, Standard Test Method for Coated Fabrics Abrasion Resistance (Rotary Platform Abrader)

ASTM F1515, Standard Test Method for Measuring Light Stability of Resilient Flooring by Colour Change

EN 431, Resilient floor coverings — Determination of peel resistance

EN 663, Resilient floor coverings — Determination of conventional pattern depths

3 Terms and definitions

3 1

rubber material

polymeric binder in the rubber sheet floor covering with backing satisfying the definition of rubber in ASTM D1566, and having been vulcanized such that it became thermoset as defined in ASTM D883

3.2

reliefed

having a permanent multi-level surface produced by mechanical means, with a minimal differential in height of 0,25 mm

4 Categories of rubber sheet floor coverings with backing

Rubber sheet floor coverings covered by this International Standard shall be categorized as:

- Category A: Homogeneous rubber sheet floor covering with backing Floor covering based on natural and/or synthetic rubber with one or more layers of the same composition and colour, patterned throughout its thickness with either fibrous or foamed backing.
- Category B: Heterogeneous rubber sheet floor covering with backing Floor covering based on natural and/or synthetic rubber consisting of a wear layer and other compact layers which differ in composition and/or design and can contain a reinforcement with either fibrous, foamed or other backing.
- Category C: Rubber sheet floor covering with backing with a decorative layer Floor covering based on natural and/or synthetic rubber consisting of a decorative layer and other compact layer which differ in composition and/or design and can contain a reinforcement with either fibrous, foamed or other backing.

The thickness of the decorative layer shall at least reach the values given in Table 2. These values are based on the relationship of the appearance retaining after removing a specified thickness and the abrasion value measured.

The floor covering may have smooth, embossed or reliefed pattern wearing surfaces.

5 Requirements

All rubber floor sheet with backing shall conform to the appropriate general requirements specified in Table 1, when tested in accordance with the test methods given therein.

Table 1 — General minimum requirements

| Charac | teristic | Require | ements | Test method |
|---------------------------------------|-------------------------------|----------------------------------|----------------------------|--|
| Overall thickness; Tolerance on nomin | al total gauge mm | average | Individual results | |
| | reliefed | Nominal value ± 0,20 mm | Nominal value ± 0,25 mm | ISO 24346 |
| | smooth or embossed | Nominal value ± 0,20 mm | Nominal value ± 0,25 mm | |
| Width | | not less than spec | ified | ISO 24341 |
| Length | | not less than spec | ified | ISO 24341 |
| Thickness of wear la | ayer | not less than spec | ified | ISO 24340 |
| Dimensional stability | y | tolerance allowed | 0,4 % | ISO 23999 |
| Flexibility: diameter | of mandrel 20 mm | no cracking | | ISO 24344 Method A |
| Residual indentation | 1 | ≤ 0,25 mm | | ISO 24343-1 |
| Abrasion resistance | of wear layer | ≤ 250 mm ³ | | ISO 4649:2010, Method A, vertical load (5 ± 0,1) N |
| | or | < 1 g | | ASTM D3389 H18/500 g |
| Peel resistance | | Mean value ≥ 50 N in the foam | 1/50 mm or rupture | EN 431 |
| Calaur factores to a | whiting all limbs a | 6 minimum on blue | e wool scale | ICO 405 DO2 Mathad 2 |
| Colour fastness to a | i tiliciai light ^a | ≥ 3 on grey scale | | ISO 105-B02 Method 3 |
| | | ΔE not greater than | n 8,0 | A O.T.N. 54545 |
| | or | after 300 h exposu | ıre | ASTM F1515 |

^a Expose a full size test specimen. Store a further test specimen in the dark, which will constitute the reference standard for assessment of colour change.

6 Classification

The classification scheme for resilient floor coverings is described in ISO 10874. The requirements for rubber sheet floor coverings with backing in accordance with this scheme are specified in Table 2.

Table 2 — Classification minimum requirements

| | | | Overall thick va | Overall thickness nominal value | Minimum | Relation | Resistance to castor | Hardness of |
|---------|-----|---------------------------|---------------------|---------------------------------|---------------|-------------|--|-------------|
| lodmyS | | ا إم امره ا | m) | (mm) | thickness of | PDa/TLb | chair for smooth or | wear layer |
| Sylling | | | Categor | Category A, B, C | wear layer | Category C | embossed pattern | ISO 7619-1 |
| | | | Reliefed pattern | Smooth or embossed | Category B, C | EN 663 | ISO 4918 | Shore A |
| Y S | | domestic moderate | 2,5 | 2,5 | | | | |
| | ŏ | domestic general/medium | | | | G C | | G G |
| | | domestic heavy | 3,2 | | | o o o | | Oo N |
| | ŏ | commercial moderate | | | 1,0 | | | |
| | J | commercial general | | u c | | | | |
| | | commercial heavy | | o o | | | No disturbance to the surface other than slight | |
| | ŏ | commercial very heavy | | | | 8,00 | oriange in appearance and no delamination shall occur after 25 000 cycles | > 75 |
| |)ii | light industrial moderate | | | | | | |

Table 2 (continued)

| | 9 | 9 | Overall thick va | Overall thickness nominal value (mm) | Minimum thickness of | Relation PD ^a /TL ^b | Resistance to castor chair for smooth or | Hardness of wear layer |
|-------|---------|--------------------------|---------------------|--------------------------------------|-------------------------|--|--|---------------------------|
| C a s | oyilloo | asn IO laxa | Categor | Category A, B, C | wear layer | Category C | embossed pattern | ISO 7619-1 |
| | | | Reliefed pattern | Smooth or embossed | Category B, C | EN 663 | ISO 4918 | Shore A |
| 42 | | light industrial general | | и С | , | o C | No disturbance to the surface other than slight change in appearance | 7 |
| 43 | | light industrial heavy | | o S | 2 | o, O | and no delamination shall occur after 25 000 cycles | <u>8</u> |

a PD = Pattern depth in mm.

 $^{\rm b}$ TL $_{\rm =}$ Thickness loss in mm, calculated according to the formula below (EN 663).

BS ISO 10575:2012 ISO 10575:2012(E)

$$TL = \frac{m_L}{\rho \cdot A_a}$$

where:

TL is thickness loss in mm;

 m_{L} is weight loss in mg;

 ρ is density in mg/mm³ (ISO 23996);

 A_a is abraded area in mm² ($A_a = 3~200~\text{mm}^2$, Taber-Test ASTM D3389).

7 Marking, labelling and packaging

Rubber sheet floor covering with backing and/or their packaging shall be marked as follows:

- a) number and date of this International Standard, i.e. ISO 10575:2012;
- b) manufacturer's or supplier's identification;
- c) product name;
- d) colour/pattern, and batch number if applicable;
- e) classes/symbols appropriate for the product.

Annex A (informative)

Optional properties

Where the following properties are required for specific applications, the floor covering should be tested in accordance with the appropriate methods:

- electrical resistance (see EN 1081 and ASTM F150);
- electrostatic propensity/static dissipation (see EN 1815);
- effect of stains/resistance to chemicals (see ISO 26987);
- cigarette resistance (see EN 1399): In general use, a rubber floor covering, depending on the colour and/or pattern, is expected to have the following rating when tested in accordance with EN 1399: Method A, stubbed cigarettes: rating 4 or higher; Method B, burning cigarettes: rating 3 or higher;
- reaction to fire; determination of the burning behaviour using a radiant heat source (see ISO 9239 and ASTM E648);
- reaction to fire; ignitability when subject to direct impingement of flame (ISO 11925-2);
- reaction to fire; specific optical density of smoke generated (ASTM E662).

Bibliography

- [1] ISO 9239, Reaction to fire tests for floorings Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2002).
- [2] ISO 10874, Resilient, textile and laminate floor coverings Classification
- [3] ISO 11925-2, Reaction to fire tests for building products Part 2: Ignitability when subject to direct impingement of flame
- [4] ISO 23996, Resilient floor coverings Determination of density
- [5] ISO 26987, Resilient floor coverings Determination of staining and resistance to chemicals
- [6] ASTM E648, Standard Test Method for Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source
- [7] ASTM E662, Standard Test Method for Specific Optical Density of Smoke Generated by Solid Materials
- [8] ASTM F150, Standard Test Method for Electrical Resistance of Conductive and Static Dissipative Resilient Flooring
- [9] EN 1815, Resilient and textile floor coverings Assessment of static electrical propensity
- [10] EN 1399, Resilient floor coverings Determination of resistance to stubbed and burning cigarettes
- [11] EN 1081, Resilient floor coverings Determination of the electrical resistance



ICS 97.150

Price based on 8 pages



British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

