

BS ISO 11494:2014



BSI Standards Publication

Jewellery — Determination of platinum in platinum jewellery alloys — ICP-OES method using yttrium as internal standard element

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 11494:2014. It supersedes BS ISO 11494:2008 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/53, Specifications and test methods for jewellery and horology.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 74803 5

ICS 39.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2014.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
11494

Second edition
2014-12-01

**Jewellery — Determination of
platinum in platinum jewellery alloys
— ICP-OES method using yttrium as
internal standard element**

*Joallerie, bijouterie — Dosage du platine dans les alliages de platine
pour la joallerie, bijouterie — Méthode par ICP-OES utilisant
l'yttrium comme étalon interne*



Reference number
ISO 11494:2014(E)

© ISO 2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
6 Equipment	2
7 Sampling	2
8 Procedure	2
8.1 Internal standard solution.....	2
8.2 Calibration solutions.....	3
8.3 Sample solution.....	3
8.4 Preparation of the platinum alloy solution containing ruthenium, iridium, or tungsten.....	3
8.5 Measurements.....	3
8.6 Calculation and expression of results.....	4
9 Repeatability	7
10 Test report	7
Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 174, *Jewellery*.

This second edition cancels and replaces the first edition (ISO 11494:2008), which has been technically revised with the following changes:

- a) change in the scope that this method is the referee method;
- b) addition of a warning in [Clause 8](#) that suitable health and safety procedures should be followed;
- c) addition of a standard solution in [8.1](#);
- d) addition of an alternative calibration solution in [8.2.2](#);
- e) addition of an alternative sample solution in [8.3.2](#);
- f) addition of an alternative route for calculation in [8.6.4](#);
- g) International Standard editorially revised.

Introduction

The following definitions apply in understanding how to implement an ISO International Standard and other normative ISO deliverables (TS, PAS, IWA):

- “shall” indicates a requirement;
- “should” indicates a recommendation;
- “may” is used to indicate that something is permitted;
- “can” is used to indicate that something is possible, for example, that an organization or individual is able to do something.

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.1 defines a requirement as an “expression in the content of a document conveying criteria to be fulfilled if compliance with the document is to be claimed and from which no deviation is permitted.”

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.2 defines a recommendation as an “expression in the content of a document conveying that among several possibilities one is recommended as particularly suitable, without mentioning or excluding others, or that a certain course of action is preferred but not necessarily required, or that (in the negative form) a certain possibility or course of action is deprecated but not prohibited.”

Jewellery — Determination of platinum in platinum jewellery alloys — ICP-OES method using yttrium as internal standard element

1 Scope

This International Standard describes a method for the determination of platinum in platinum jewellery alloys, preferably within the range of fineness specified in ISO 9202, by means of inductively coupled plasma optical emission spectrometry (ICP-OES).

This method applies to platinum jewellery alloys that might contain silver, indium, iridium, gallium, copper, cobalt, nickel, tin, and ruthenium. However, this list is not exhaustive and care is always to be taken to investigate potential interference effects.

This method is intended to be used as the recommended method for the determination of fineness in alloys covered by ISO 9202 up to 990 ‰.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11596, *Jewellery — Sampling of precious metal alloys for and in jewellery and associated products*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

bracketing

running of standards and samples in the following sequence: low standard – sample – high standard – sample – low standard – sample – high standard – sample – low standard – sample – high standard

4 Principle

At least two accurately weighed samples are dissolved in aqua regia and made up to an exactly weighed mass. Exactly weighed portions (aliquots) of these sample solutions are mixed with the internal standard and made up to the standard measuring volume.

Using ICP-OES, the platinum content of the sample solution is measured by comparison of the ratio intensities of the spectral emission of platinum (recommended lines are 265,95 nm, 214,42 nm, 299,80 nm, or 306,47 nm) and appropriate yttrium lines with the ratios for solutions containing known masses of platinum and yttrium using the bracketing method.

Minor modifications are required when the alloy contains ruthenium, rhodium, iridium, or tungsten.

5 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity. All reagents shall be platinum free.

5.1 Hydrochloric acid (HCl), approximately 30 % to 37 % HCl (mass fraction).

5.2 Nitric acid (HNO₃), approximately 65 % to 70 % HNO₃ (mass fraction).

5.3 Pure platinum (Pt).

The platinum content shall be at least 999,9 ‰. If a lower platinum content (999,5 ‰) is used, appropriate corrections should be applied.

5.4 Internal standard, an yttrium compound like yttrium chloride (YCl₃ · 6H₂O) or yttrium oxide (Y₂O₃) in analytical grade.

5.5 Pure copper.

Copper content shall be 999,9 ‰. and platinum free.

5.6 Orthophosphoric acid (H₃PO₄), 85 % (mass fraction).

5.7 Aqua regia.

Mix 3 volumes of hydrochloric acid ([5.1](#)) and 1 volume of nitric acid ([5.2](#)).

6 Equipment

6.1 Customary laboratory apparatus.

6.2 ICP-OES, capable of simultaneously measuring the platinum emission and the emission line of the internal standard yttrium, with a minimum optical resolution of 0,02 nm.

6.3 Analytical balance, with a reading accuracy of 0,01 mg.

7 Sampling

The sampling procedure shall be performed in accordance with ISO 11596.

8 Procedure

WARNING — Suitable health and safety procedures should be followed.

8.1 Internal standard solution

Dissolve approximately 680 mg YCl₃ · 6H₂O ([5.4](#)) in 200 ml water and make up to 1 000 ml with water. Alternatively, dissolve approximately 250 mg Y₂O₃ in a mixture of 25 ml water and 25 ml nitric acid and make up to 1 000 ml with water. Due to the sensitivity of the instrument, the concentration may be changed to achieve optimum performance.

This also applies to the calibration solutions (see [8.2](#)) and the sample solutions (see [8.3](#)).

8.2 Calibration solutions

8.2.1 Weigh approximately 100 mg of platinum accurately to 0,01 mg into a tared 100 ml volumetric flask and add 40 ml of aqua regia (5.7). Heat gently until dissolution of the sample is complete. Allow to cool. Make up with water to 100 ml and mix thoroughly. Weigh this platinum stock solution.

Weigh approximately 4,5 g, 5,5 g, 6,5 g, 7,5 g, 8,25 g, 8,5 g, 8,75 g, 9,25 g, 9,5 g, and 9,75 g of the platinum stock solution accurately to at least 0,001 g, each into a 100 ml volumetric flask. Add 10 g of the internal standard solution (8.1) accurately to at least 0,001 g. Add 10 ml of HCl (5.1) and make up to 100 ml with water. Mix thoroughly.

In the presence of certain other elements (e.g. silver), it can be necessary to increase the HCl concentration to a maximum of 50 ml. The acid concentration of calibration solutions and sample solutions shall be consistent.

8.2.2 Alternatively weigh 45 mg, 55 mg, 65 mg, 75 mg, 82,5 mg, 85 mg, 87,5 mg, 92,5 mg, 95 mg, and 97,5 mg platinum accurately to 0,01 mg each into a 1 000 ml flask and dissolve in a mixture of 100 ml HCl (5.1) and 30 ml HNO₃ (5.2). Add 100 g accurately to 0,01 g of the internal standard solution (8.1). Add 100 ml HCl (5.2) and make up to 1 000 ml with water. Mix thoroughly.

In the presence of certain other elements (e.g. silver), it can be necessary to increase the HCl concentration to a maximum of 500 ml. The acid concentration of calibration solutions and sample solutions shall be consistent.

NOTE Depending on the range of the platinum contents in the samples, not all standards are necessary.

8.3 Sample solution

8.3.1 Weigh approximately 100 mg of the sample to the nearest 0,01 mg, dissolve and treat the sample as described in 8.2.1. Weigh approximately 10 g of this sample stock solution accurately to 0,001 g into a 100 ml volumetric flask and add 10 g of the internal standard solution (8.1) accurately to 0,001 g. Add 10 ml of HCl (5.1) and make up to 100 ml with water. Mix thoroughly.

In the presence of certain other elements (e.g. silver), it can be necessary to increase the HCl concentration to a maximum of 50 ml. The acid concentration of calibration solutions and sample solutions shall be consistent.

8.3.2 Alternatively weigh 100 mg sample accurately to at least 0,01 mg into a 1 000 ml flask and dissolve and treat the sample as described in 8.2.2.

In the presence of certain other elements (e.g. silver), it can be necessary to increase the HCl concentration to a maximum of 500 ml. The acid concentration of calibration solutions and sample solutions shall be consistent.

NOTE Attention is drawn to the possibility that smaller samples will also be more affected by any variation on homogeneity in the material sampled.

8.4 Preparation of the platinum alloy solution containing ruthenium, iridium, or tungsten

Platinum alloys containing more than 5 % of the cited elements can require a pressure dissolution or involve a preliminary alloying stage with a quantity of 10 times of platinum-free copper (5.5).

In the presence of tungsten, 200 µl of orthophosphoric acid (5.6) shall be added.

Calibration solutions and sample solutions shall be matrix matched.

8.5 Measurements

The data processing unit of the ICP-OES is used to establish a measuring program in which the intensities of the platinum emission lines and of the internal standard element yttrium can be measured simultaneously. Set up the instrument in accordance with the manufacturer's instructions and choose appropriate background correction positions. A clean torch, spray chamber, and sample uptake tubes

shall be used and the plasma shall be stabilized before use, following the recommendations of the instruments manufacturer.

Each standard and sample solution shall have a minimum stabilization time of 30 s, followed by the integration times and the number of integrations required to obtain a maximum relative standard deviation (RSD) of 0,2 % [see 8.6.2, Formula (1)]. The accurate mass of platinum of the sample solution is derived from the measurement of the two calibration solutions bracketing the rough value of the sample solution [see 8.6.3, Formula (4) or 8.6.4, Formula (9), depending on the way of calibration and sample solution preparation].

The analytical results obtained with the four platinum emission lines shall be compared and only lines without interference effects shall be chosen for calculation.

NOTE The platinum emission at 265,95 nm can be interfered by ruthenium, rhodium, and chromium and the platinum emission at 299,80 nm and 306,47 nm can be interfered by iridium and chromium.

8.6 Calculation and expression of results

8.6.1 If the solution has been prepared in accordance with 8.2.1 and 8.3.1, use 8.6.3 or, if the solution is prepared according to the alternative route (8.2.2 and 8.3.2), use 8.6.4 for calculation.

8.6.2 The method of internal standardization is based on the linear relation between the intensity ratios (I_{Pt}/I_Y) and the concentration ratios (C_{Pt}/C_Y) or, better, mass ratios (m_{Pt}/m_Y). Using the same mass of yttrium (internal standard solution) to prepare all solutions, it is not necessary to have an exact volume of the measuring solutions. The accuracy of the 100 ml volumetric flask is satisfactory. The other important advantage of always referring to the same mass of the internal standard is that all calculations can be done with m_{Pt} instead of m_{Pt}/m_Y , nominal.

In general, the data processing unit provides the quotients from the simultaneously registered single measurements of the platinum and the yttrium intensities.

If the mean value, \bar{Q} , of the five intensity quotients (Q_1, Q_2, Q_3, Q_4, Q_5) belonging to each solution is calculated using Formula (1):

$$\bar{Q} = \frac{1}{5} \left(\sum_{n=1}^5 \frac{I_{Pt}}{I_Y} \right) \quad (1)$$

then this mean value shall have an RSD from Q not larger than 0,2 %.

8.6.3 In view of deviations from the nominal mass, m_{IS} , expressed in grams, of the internal standard solution ($m_{IS} = 10,000$ g), each intensity quotient belonging to a measuring solution shall be corrected by the corresponding real mass of internal standard solution, $W_{IS,n}$, expressed in grams, used to prepare this measuring solution. The corrected quotient, Q_C , is calculated using Formula (2):

$$Q_C = Q \cdot \frac{W_{IS,n}}{m_{IS}} \quad (2)$$

To determine the platinum content of the sample using the corrected intensity quotient, the exact masses of platinum in the calibration solutions $m_{Pt,Cs,n}$, expressed in milligrams, are required. These masses shall be calculated individually for each calibration solution or calibration point using Formula (3):

$$m_{Pt,Cs,n} = \frac{W_{Pt,SS}}{m_{SS,Pt}} \cdot W_{SS,Pt,n} \quad (3)$$

where

$W_{Pt,SS}$ is the mass of platinum used to prepare the platinum stock solution, in milligrams;

$m_{SS,Pt}$ is the mass of the prepared platinum stock solution, in grams;

$W_{SS,Pt,n}$ is the mass of platinum stock solution used to prepare the calibration solution, n , in grams.

The two calibration points nearest to the expected platinum sample content, corresponding to the low mass, a , and to the high mass, b , are used to determine the platinum mass in the sample solution using Formula (4):

$$m_{Pt} = a + \frac{(b-a) \cdot (Q_{Cs} - Q_{Ca})}{(Q_{Cb} - Q_{Ca})} \quad (4)$$

where

a is the mass of platinum in the calibration solution used as “low-standard”, according to Formula (3), expressed in milligrams;

b is the mass of platinum in the calibration solution used as “high-standard”, according to Formula (3), expressed in milligrams;

Q_{Ca} is the corrected intensity ratio I_{Pt}/I_Y of the “low-standard”;

Q_{Cb} is the corrected intensity ratio I_{Pt}/I_Y of the “high-standard”;

Q_{Cs} is the corrected intensity ratio I_{Pt}/I_Y of the sample measuring solution.

The final mass of platinum of the sample solution corresponds to the mean value of five measuring cycles and evaluations of this type, \bar{m}_{Pt} , and is calculated using Formula (5):

$$\bar{m}_{Pt,fin} = \frac{1}{5} \left(\sum_{n=1}^5 m_{Pt} \right) \quad (5)$$

The RSD of m_{Pt} shall not exceed 0,30 %.

Once \bar{m}_{Pt} has been determined from the five single determinations of the sample solution, the platinum content of the sample, X_{Pt} , in parts per thousand, is calculated using Formula (6):

$$X_{Pt} = \frac{\bar{m}_{Pt} \cdot m_{SS,Sa}}{W_{Sa} \cdot W_{SS,Sa}} \cdot 1000 \quad (6)$$

where

W_{Sa} is the mass of sample used to prepare the sample stock solution, in milligrams;

$m_{SS,Sa}$ is the mass of the prepared sample stock solution, in grams;

$W_{SS,Sa}$ is the mass of sample stock solution used to prepare the sample measuring solution, in grams.

CAUTION — In order to comply with this International Standard, other algorithms used shall be validated.

8.6.4 Alternatively, in view of deviations from the nominal mass, m_{IS} , expressed in grams, of the internal standard solution ($m_{IS} = 100,00$ g), each intensity quotient belonging to a measuring solution shall be corrected by the corresponding real mass of internal standard solution, $W_{IS,n}$, expressed in grams, used to prepare this measuring solution. The corrected quotient, Q_C , is calculated using Formula (7):

$$Q_C = Q \cdot \frac{W_{IS,n}}{m_{IS}} \quad (7)$$

To determine the platinum content of the sample using the corrected intensity quotient, the exact masses of platinum in the calibration solutions $m_{Pt,Cs,n}$, expressed in milligrams, are required, using Formula (8):

$$m_{Pt,Cs,n} = W_{Pt,Cs,n} \quad (8)$$

where

$W_{Pt,Cs,n}$ is the mass of platinum used to prepare the platinum calibration solution, in milligrams.

The two calibration points nearest to the expected platinum sample content, corresponding to the low mass, a , and to the high mass, b , are used to determine the platinum mass in the sample solution using Formula (9):

$$m_{Pt} = a + \frac{(b-a) \cdot (Q_{Cs} - Q_{Ca})}{(Q_{Cb} - Q_{Ca})} \quad (9)$$

where

a is the mass of platinum in the calibration solution used as “low-standard”, according to Formula (8), in milligrams;

b is the mass of platinum in the calibration solution used as “high-standard”, according to Formula (8), in milligrams;

Q_{Ca} is the corrected intensity ratio I_{Pt}/I_Y of the “low-standard”;

Q_{Cb} is the corrected intensity ratio I_{Pt}/I_Y of the “high-standard”;

Q_{Cs} is the corrected intensity ratio I_{Pt}/I_Y of the sample measuring solution.

The final mass of platinum of the sample solution corresponds to the mean value of five measuring cycles and evaluations of this type, \bar{m}_{Pt} , and is calculated using Formula (10):

$$\bar{m}_{Pt,fin} = \frac{1}{5} \left(\sum_{n=1}^5 m_{Pt} \right) \quad (10)$$

The RSD of m_{Pt} shall not exceed 0,30 %.

Once \bar{m}_{Pt} has been determined from the five single determinations of the sample solution, the platinum content of the sample, X_{Pt} , in parts per thousand, is calculated using Formula (11):

$$X_{Pt} = \frac{\bar{m}_{Pt}}{W_{Sa}} \cdot 1000 \quad (11)$$

where

W_{Sa} is the mass of sample used to prepare the sample solution, in milligrams.

CAUTION — In order to comply with this International Standard, other algorithms used shall be validated.

9 Repeatability

Duplicate determinations shall give results differing by less than 3 ‰ for platinum. If the difference is greater than this, the assay shall be repeated.

10 Test report

With reference to this method, the test report shall contain at least the following information:

- a) identification of the sample including source, date of receipt, form of sample;
- b) sampling procedure;
- c) method used by the reference to this International Standard, i.e. ISO 11494:2014;
- d) platinum content of the sample, in parts per thousand (‰) by mass, as single values and mean values;
- e) if relevant, any deviations from the method specified in this International Standard;
- f) platinum line and internal standard line used;
- g) any unusual features observed during the determination;
- h) date of test;
- i) identification of the laboratory carrying out the test;
- j) signature of the laboratory manager and operator.

Bibliography

- [1] ISO 9202, *Jewellery — Fineness of precious metal alloys*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™