

BS ISO 11852:2017



BSI Standards Publication

Rubber — Determination of magnesium content of field natural rubber latex by titration

National foreword

This British Standard is the UK implementation of ISO 11852:2017. It supersedes BS ISO 11852:2011 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Raw materials (including latex) for use in the rubber industry.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017.
Published by BSI Standards Limited 2017

ISBN 978 0 580 89058 1

ICS 83.040.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2017.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

**Rubber — Determination of
magnesium content of field natural
rubber latex by titration**

*Caoutchouc — Détermination par titrage de la teneur en magnésium
du latex de plantation de caoutchouc naturel*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	2
6 Reagents	2
7 Procedure	3
8 Expression of results	4
9 Precision	4
10 Test report	4
Annex A (informative) Precision	5
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This second edition cancels and replaces the first edition (ISO 11852:2011), which has been technically revised to be applicable only to field latex. Therefore, all references to concentrated natural rubber latex have been removed and the following changes have been made:

- the title of this document has been changed;
- an introduction has been added to explain the advantages of the method described in this document;
- the definition of natural rubber latex concentrate has been removed from [Clause 3](#);
- the determination of magnesium content of concentrated latex in [Clause 5](#) has been deleted;
- because borax is a substance of high concern and reprotoxic, the buffer solution ([6.4](#)) has been changed from borax buffer solution to ammonium chloride/ammonium hydroxide buffer solution;
- the precision data for concentrated latex in [Annex A](#) have been deleted.

Introduction

In this document, no additional chemical is required to mask the interference from other divalent ions. The end-point determination in this method is easily determined since most, if not all, of the interferences have been removed during the centrifugation process. Furthermore, the chemical used for masking the interference in the alternative method has an unpleasant odour.

Another advantage of this document is that the centrifuge machine used in the method is already available in laboratory for desludging purposes. Hence, no additional cost is incurred by the laboratory to carry out the test.

Rubber — Determination of magnesium content of field natural rubber latex by titration

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This document specifies a titration method for the determination of the magnesium content of field natural rubber latex.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385:2005, *Laboratory glassware — Burettes*

ISO 648:2008, *Laboratory glassware — Single-volume pipettes*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

magnesium content

amount of magnesium, and possibly also other alkaline-earth metals, present in a sample of natural rubber field latex

Note 1 to entry: When ammonia is added to field latex, the calcium and magnesium ions present in varying concentrations in the serum of the latex are, to a large extent, precipitated as ammonium phosphate complexes, which gradually settle out in the sludge. The results of the test method described in this document are expressed as the magnesium content on the assumption, which is not strictly true, that magnesium is the only divalent alkaline-earth ion remaining in the latex after the sludge has been removed. Calcium ions are also present, occasionally in appreciable amounts.

4 Principle

The latex is centrifuged at between 2 500 m/s² (250g) and 5 000 m/s² (500g), using a laboratory centrifuge, for 3 min. A known mass of the resultant latex, free of sludge, is diluted with water, and the residual magnesium content present in the latex is determined by titration with the disodium salt of

ethylenediaminetetraacetic acid (EDTA·Na₂) in the presence of a buffer, using Eriochrome Black T¹⁾ as indicator.

This method is applicable to field latex preserved with ammonia or with a combination of ammonia and formaldehyde, in which the ammonia content on titration is not less than 0,2 % of the latex. The method determines the total concentration of divalent alkaline-earth ions remaining in the latex after the removal of sludge, and this is taken as the magnesium content.

The magnesium content can be expressed either as a percentage of the mass of the latex or in milligrams per kilogram of latex.

5 Apparatus

5.1 Laboratory centrifuge, capable of producing an acceleration between 2 500 m/s² (250g) and 5 000 m/s² (500g).

5.2 Centrifuge tubes, each of at least 50 cm³ capacity.

5.3 pH-meter, equipped with a glass electrode and a saturated calomel electrode of the sleeve or sintered-disc type and capable of reading to 0,1 pH-units. Calibrate the pH-meter by using buffer solutions of pH 4,0, 7,0 and 10,0.

5.4 Burette, of capacity 10 cm³ or 50 cm³, complying with the requirements of ISO 385:2005, class A.

5.5 Balance, accurate to 0,1 mg.

5.6 Volumetric pipette, of capacity 10 cm³, complying with the requirements of ISO 648:2008, class A.

5.7 Beaker, of capacity 400 cm³.

6 Reagents

Use reagents of recognized analytical grade and deionized water or water of equivalent purity.

6.1 Magnesium sulfate solution, 0,005 M.

Dissolve 1,231 6 g of magnesium sulfate heptahydrate (MgSO₄·7H₂O) in water. Make up to 1 dm³ in a volumetric flask. 1 cm³ of this solution is equivalent to 1 cm³ of 0,005 mol/dm³ EDTA·Na₂.

6.2 EDTA·Na₂ solution, 0,005 M.

6.2.1 Preparation

Dissolve approximately 1,86 g of EDTA·Na₂ in water and make up to 1 dm³. Standardize by titrating against standard magnesium sulfate solution (6.1).

6.2.2 Standardization

Pipette 10 cm³ of the standard magnesium sulfate solution into a beaker (5.7). Add 200 cm³ of water and adjust the pH to 10,3 by adding buffer solution (6.4). Add about 0,1 g of Eriochrome Black T indicator (6.3) and titrate with the EDTA·Na₂ solution (6.2). The colour change is from red to permanent blue.

1) Eriochrome is a registered trademark of Huntsman Petrochemical, LLC. Eriochrome Black T is an example of suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named.

The concentration of the EDTA·Na₂ solution, $c(\text{EDTA}\cdot\text{Na}_2)$, is given, in mol/dm³, by [Formula \(1\)](#):

$$c(\text{EDTA}\cdot\text{Na}_2) = \frac{10 \times 0,005}{V} \quad (1)$$

where V is the volume of EDTA·Na₂ solution used, in cm³.

6.3 Eriochrome Black T indicator.

Grind together, in a small pestle and mortar, 0,3 g of Eriochrome Black T and 100 g of sodium or potassium chloride to give a homogeneous mixture.

6.4 Buffer solution.

Dissolve 67,5 g of ammonium chloride (NH₄Cl) in 250 cm³ of deionized water, mix with 570 cm³ of 25 % ammonium hydroxide (NH₄OH) and make up to 1 dm³ with deionized water. The solution should have a pH of about 10,5.

7 Procedure

Carry out the procedure in duplicate, using separate test portions obtained from the same homogenized sample. If the individual results differ from their mean by more than 0,05 percentage points when the results are expressed as a percentage or by more than 5 mg/kg when the results are expressed in mg/kg, repeat the determination.

Fill each of two centrifuge tubes to 90 % of its capacity with field latex and place in the centrifuge. Balance the two tubes and centrifuge the latex for 3 min at between 2 500 m/s² (250g) and 5 000 m/s² (500g).

Taking care not to disturb the sludge at the bottom of the tube, weigh approximately 2 g to 3 g of the supernatant latex into a beaker containing 100 cm³ of water. Mix well.

Check the pH of the latex solution and, if it is less than 10,3, add sufficient buffer solution ([6.4](#)) to raise the pH above this value. Note that, if the ammonia concentration is less than 0,35 % with respect to the latex or less than 0,50 % with respect to the water content for a latex of 30 % dry-rubber content, it is not in fact necessary to adjust the pH in this way.

Add about 0,1 g of Eriochrome Black T indicator ([6.3](#)) to the latex solution and stir. Then titrate with 0,005 mol/dm³ EDTA·Na₂ solution ([6.2](#)) until the colour of the solution becomes blue.

NOTE 1 The end-point is a little difficult to detect with latex and it can be useful to have an over-titrated solution at hand for comparison.

NOTE 2 This test method might not be applicable to field natural rubber latex containing preservatives other than ammonia, in particular, tetramethylthiuram disulfide (TMTD) or zinc oxide (ZnO).

8 Expression of results

Calculate the magnesium content expressed as a percentage of the latex, $w_{\text{Mg}(\%)}$, using [Formula \(2\)](#):

$$w_{\text{Mg}(\%)} = \frac{c(\text{EDTA} \cdot \text{Na}_2) \times V \times 24,31}{10 \times m} \quad (2)$$

Calculate the magnesium content expressed in mg/kg of latex, w_{Mg} , using [Formula \(3\)](#):

$$w_{\text{Mg}} = \frac{c(\text{EDTA} \cdot \text{Na}_2) \times V \times 24,31 \times 10^3}{m} \quad (3)$$

where

$c(\text{EDTA} \cdot \text{Na}_2)$ is the concentration of the standardized EDTA·Na₂ solution used, in mol/dm³;

V is the volume of EDTA·Na₂ solution used, in cm³;

m is the mass of field latex taken, in g.

Take as the test result the average of the two determinations:

- rounded to two decimal places when the magnesium content is expressed as a percentage;
- rounded to the nearest whole number when the content is expressed in milligrams per kilogram.

9 Precision

See [Annex A](#).

10 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 11852;
- b) all details necessary for the complete identification of the product tested;
- c) the method of sampling used;
- d) the type of instrument used;
- e) the results obtained and the units in which they have been expressed;
- f) any unusual features noted during the determination;
- g) any operations not included in this document or in the International Standards to which reference is made, as well as any incident which might have affected the result;
- h) the date of the test.

Annex A (informative)

Precision

A.1 The precision of the test method was determined in accordance with ISO/TR 9272. Refer to ISO/TR 9272 for terminology and other statistical details.

A.2 The precision data are given in [Table A.1](#). The precision parameters should not be used for acceptance or rejection of any group of materials without documentation that the parameters are applicable to those particular materials and the specific test protocols of the test method. The precision is expressed on the basis of a 95 % confidence level for the values established for repeatability, r , and reproducibility, R .

A.3 The results contained in [Table A.1](#) are average values and give an estimate of the precision of this test method as determined in an interlaboratory test programme carried out in 2010 in which six laboratories took part, performing duplicate analyses on two samples (A and B) which were prepared from field latex.

Before the bulk was sub-sampled into two bottles labelled A and B, it was filtered and homogenized by thorough stirring. Thus, essentially, samples A and B were the same and were treated as such in the statistical computations.

Each participating laboratory was required to carry out the test, using these two samples, on the dates given to them.

A.4 A type 1 precision was evaluated based on the method of sampling used for the interlaboratory test programme.

A.5 The repeatability, r (in measurement units), of the test method has been established as the appropriate value tabulated in [Table A.1](#). Two single test results, obtained in the same laboratory under normal test method procedures, that differ by more than the tabulated value of r (for any given level) are considered to come from different, or non-identical, sample populations.

A.6 The reproducibility, R (in measurement units), of the test method has been established as the appropriate value tabulated in [Table A.1](#). Two single test results, obtained in different laboratories under normal test method procedures, that differ by more than the tabulated value of R (for any given level) are considered to come from different, or non-identical, sample populations.

Table A.1 — Precision data for field latex

Average result mg/kg	Within-laboratory		Between laboratories	
	s_r	r	s_R	R
123	3,72	10,53	3,76	10,63
r is the repeatability (in measurement units); s_r is the within-laboratory standard deviation; R is the reproducibility (in measurement units); s_R is the between-laboratory standard deviation.				

A.7 In test method terminology, bias is the difference between an average test value and a reference (or true) test property value. Reference values do not exist for this test method since the value (of the

test property) is exclusively defined by the test method. Bias, therefore, cannot be determined for this particular method.

Bibliography

- [1] ISO/TR 9272, *Rubber and rubber products — Determination of precision for test method standards*
- [2] ISO 17403, *Rubber — Determination of magnesium content of field and concentrated natural rubber latices by titration (cyanide-free method)*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK