

BS ISO 11973:2015



BSI Standards Publication

Heat-resistant cast steels and alloys for general applications

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 11973:2015.

The UK participation in its preparation was entrusted to Technical Committee ISE/111, Steel Castings and Forgings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 76499 8

ICS 77.140.20; 77.140.80

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 11973:2015

ISO
11973

Second edition
2015-09-15

**Heat-resistant cast steels and alloys
for general applications**

*Aciers et alliages moulés réfractaires destinés à des applications
générales*



Reference number
ISO 11973:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 General conditions for delivery	1
4 Heat treatment	1
5 Chemical composition	1
6 Mechanical properties	1
7 Maximum use temperature	1
8 Supplementary requirements	1
Annex A (informative) UNS cast grades similar to ISO cast grades	5
Bibliography	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC17, *Steel*, Subcommittee SC11, *Steel castings*.

This second edition cancels and replaces the first edition (ISO 11973:1999), which has been technically revised with the following changes:

- [Clause 8](#) revised;
- [Table 1](#) composition limits modified — various grades;
- [Tables 1](#) and [2](#) — grade number added;
- [Annex A](#) added.

Heat-resistant cast steels and alloys for general applications

1 Scope

This International Standard specifies chemical composition and mechanical properties of cast steels and alloys for heat-resistant service.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4990, *Steel castings — General technical delivery requirements*

3 General conditions for delivery

Materials furnished in conformity with this International Standard shall conform to the applicable requirements of ISO 4990 including the supplementary requirements that are indicated on the enquiry and purchase order.

4 Heat treatment

GX40CrSi13, GX40CrSi17, GX30CrSi7, GX40CrSi24, GX40CrSi28, and GX130CrSi29 may be annealed at a temperature of 800 °C to 850 °C. If required, GX30CrSi7 may also be supplied in the as-cast condition. Other grades produced according to this International Standard do not require heat treatment. If heat treatment is required, the treatment should be established by agreement between the manufacturer and the purchaser, and should be specified in the purchase contract.

5 Chemical composition

The chemical composition of the alloys shall comply with the values given in [Table 1](#).

6 Mechanical properties

Mechanical testing at room temperature shall be performed when agreed upon between the manufacturer and purchaser in which case the material shall conform to the requirements listed in [Table 2](#).

7 Maximum use temperature

Limited information on maximum use temperatures are included in [Table 2](#). These values are intended to allow comparison of grades. The actual conditions of service must be considered when selecting a grade including the composition of the environment and service mechanical loading.

8 Supplementary requirements

A list of standardized supplementary requirements for use on the option of the purchaser is included in ISO 4990. Others, whether or not in ISO 4990, may be used with this specification upon agreement between the manufacturer and the purchaser.

Table 1 — Chemical composition, % (m/m)

Grade designation		C	Si	Mn	P	S	Cr	Mo	Ni	Others
Name	Number									
GX30CrSi7	1.4710	0,20 0,35	1,0 2,5	0,5 1,0	0,035	0,030	6,0 8,0	0,15	0,5	
GX40CrSi13	1.4729	0,30 0,50	1,0 2,5	1,0	0,040	0,030	12,0 14,0	0,15	0,5	
GX40CrSi17	1.4740	0,30 0,50	1,0 2,5	1,0	0,040	0,030	16,0 19,0	0,50	1,0	
GX40CrSi24	1.4745	0,30 0,50	1,0 2,5	1,0	0,040	0,030	23,0 26,0	0,50	1,0	
GX40CrSi28	1.4776	0,30 0,50	1,0 2,5	1,0	0,040	0,030	27,0 30,0	0,50	1,0	
GX130CrSi29	1.4777	1,20 1,40	1,0 2,5	0,5 1,0	0,035	0,030	27,0 30,0	0,50	1,0	
GX25CrNiSi18-9	1.4825	0,15 0,35	0,5 2,5	2,0	0,040	0,030	17,0 19,0	0,50	8,0 10,0	
GX25CrNiSi20-14	1.4832	0,15 0,35	0,5 2,5	2,0	0,040	0,030	19,0 21,0	0,50	13,0 15,0	
GX40CrNiSi22-10	1.4826	0,30 0,50	1,0 2,5	2,0	0,040	0,030	21,0 23,0	0,50	9,0 11,0	
GX40CrNiSiNb24-24	1.4855	0,30 0,50	1,0 2,5	2,0	0,040	0,030	23,0 25,0	0,50	23,0 25,0	Nb: 0,80-1,80
GX40CrNiSi25-12	1.4837	0,30 0,50	1,0 2,5	0,5 2,0	0,040	0,030	24,0 27,0	0,50	11,0 14,0	
GX40CrNiSi25-20	1.4848	0,30 0,50	1,0 2,5	2,0	0,040	0,030	24,0 27,0	0,50	19,0 22,0	
GX40CrNiSi27-4	1.4823	0,30 0,50	1,0 2,5	1,5	0,040	0,030	25,0 28,0	0,50	3,0 6,0	
GX50NiCrCo20-20-20	1.4874	0,35 0,65	1,0	2,0	0,040	0,030	19,0 22,0	2,50 3,00	18,0 22,0	Co: 18,5 -22,0 Nb: 0,75 - 1,25 W: 2,0- 3,0
GX10NiCrSiNb32-20	1.4859	0,05 0,15	0,5 1,5	2,0	0,040	0,030	19,0 21,0	0,50	31,0 33,0	Nb: 0,50 -1,50
GX40NiCrSi35-17	1.4806	0,30 0,50	1,0 2,5	2,0	0,040	0,030	16,0 18,0	0,50	34,0 36,0	
GX40NiCrSi35-26	1.4857	0,30 0,50	1,0 2,5	2,0	0,040	0,030	24,0 27,0	0,50	33,0 36,0	
GX40NiCrSiNb35-26	1.4852	0,30 0,50	1,0 2,5	2,0	0,040	0,030	24,0 27,0	0,50	33,0 36,0	Nb: 0,80-1,80
GX40NiCrSi38-19	1.4865	0,30 0,50	1,0 2,5	2,0	0,040	0,030	18,0 21,0	0,50	36,0 39,0	
GX40NiCrSiNb38-19	1.4849	0,30 0,50	1,0 2,5	2,0	0,040	0,030	18,0 21,0	0,50	36,0 39,0	Nb 1,20 -1,80
G-NiCr28W	2.4879	0,35 0,55	1,0 2,0	1,5	0,040	0,030	27,0 30,0	0,50	47,0 50,0	W: 4,0-6,0

NOTE A single value is the maximum limit.

^a Balance.

Table 1 (continued)

Grade designation		C	Si	Mn	P	S	Cr	Mo	Ni	Others
Name	Number									
G-NiCr50Nb	2.4680	0,10	1,0	1,0	0,020	0,020	48,0 52,0	0,50	a	Fe: 1,00 N: 0,16 Nb: 1,00 -1,80
G-NiCr19	2.4687	0,40 0,60	0,5 2,0	1,5	0,040	0,030	16,0 21,0	0,50	50,0 55,0	
G-NiCr15	2.4815	0,35 0,65	2,0	1,3	0,040	0,030	13,0 19,0	-	64,0 69,0	
GX50NiCr- CoW35-25-15-5	1.4869	0,45 0,55	1,0 2,0	1,0	0,040	0,030	24,0 26,0	-	33,0 37,0	W: 4,0-6,0 Co: 14,0-16,0
G-CoCr28	2.4778	0,05 0,25	0,5 1,5	1,5	0,040	0,030	27,0 30,0	0,50	4,0	Co: 48,0-52,0 Fe: balance

NOTE A single value is the maximum limit.

a Balance.

Table 2 — Mechanical properties at room temperature and maximum use temperature

Grade designation		$R_{p0,2}$	R_m	A		Maximum use temperature ^b °C
Name	Number	MPa ^a min.	MPa ^a min	% min.	HBW	
GX30CrSi7	1.4710					750
GX40CrSi13	1.4729				300 ^c	850
GX40CrSi17	1.4740				300 ^c	900
GX40CrSi24	1.4745				300 ^c	1 050
GX40CrSi28	1.4776				320 ^c	1 100
GX130CrSi29	1.4777				400 ^c	1 100
GX25CrNiSi18-9	1.4825	230	450	15		900
GX25CrNiSi20-14	1.4832	230	450	10		900
GX40CrNiSi22-10	1.4826	230	450	8		950
GX40CrNiSiNb24-24	1.4855	220	400	4		1 050
GX40CrNiSi25-12	1.4837	220	450	6		1 050
GX40CrNiSi25-20	1.4848	220	450	6		1 100
GX40CrNiSi27-4	1.4823	250	400	3	400 ^d	1 100
GX40NiCrCo20-20-20	1.4874	320	400	6		1 150
GX10NiCrNb32-20	1.4859	170	440	20		1 000
GX40NiCrSi35-17	1.4806	220	420	6		980
GX40NiCrSi35-26	1.4857	220	440	6		1 050
GX40NiCrSiNb35-26	1.4852	220	440	4		1 050
GX40NiCrSi38-19	1.4865	220	420	6		1 050
GX40NiCrSiNb38-19	1.4849	220	420	4		1 000
G-NiCr28W	2.4879	220	400	3		1 200
G-NiCr50Nb	2.4680	230	540	8		1 050
G-NiCr19	2.4687	220	440	5		1 100
G-NiCr15	2.4815	200	400	3		1 100
GX50NiCrCoW35-25-15-5	1.4869	270	480	5		1 200
G-CoCr28	2.4778	e	e	e		1 200

^a 1 MPa = 1 N/mm².

^b Maximum use temperature depends on the actual use conditions and these values are being given only to aid the user. These are given for oxidising environments. The actual composition will also affect performance.

^c Maximum HBW in annealed condition. Castings may also be supplied in the “as-cast” condition, in which case hardness limits will not apply.

^d Maximum HBW.

^e Properties as agreed.

Annex A (informative)

UNS cast grades similar¹⁾ to ISO cast grades

Table A.1 — UNS cast grades similar to ISO cast grades

Grade designation		UNS number (similar or identical)
Name	Number	
GX30CrSi7	1.4710	—
GX40CrSi13	1.4729	J91153
GX40CrSi17	1.4740	—
GX40CrSi24	1.4745	—
GX40CrSi28	1.4776	J92605
GX130CrSi29	1.4777	—
GX25CrNiSi18-9	1.4825	J92803
GX25CrNiSi20-14	1.4832	—
GX40CrNiSi22-10	1.4826	J92803
GX40CrNiSiNb24-24	1.4855	—
GX40CrNiSi25-12	1.4837	J93503
GX40CrNiSi25-20	1.4848	J94204
GX40CrNiSi27-4	1.4823	J93005
GX40NiCrCo20-20-20	1.4874	—
GX10NiCrNb32-20	1.4859	N08151
GX40NiCrSi35-17	1.4806	N08002
GX40NiCrSi35-26	1.4857	N08705
GX40NiCrSiNb35-26	1.4852	—
GX40NiCrSi38-19	1.4865	N08004
GX40NiCrSiNb38-19	1.4849	N08008
G-NiCr28W	2.4879	—
G-NiCr50Nb	2.4680	R20501
G-NiCr19	2.4687	—
G-NiCr15	2.4815	N06006
GX50NiCrCoW35-25-15-5	1.4869	—
G-CoCr28	2.4778	—

NOTE The grade designations including the names and the numbers follow the rules of EN 10027-1 and EN 10027-2.

1) The similar UNS (Unified Numbering System) grades may not be equivalent to the grades in this International Standard.

Bibliography

- [1] EN 10027-1, *Designation system for steels — Part 1: Steel names*
- [2] EN 10027-2, *Designation system for steels — Part 2: Steel numbers*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™