

BS ISO 12000:2014



BSI Standards Publication

Plastics/rubber — Polymer dispersions and rubber latices (natural and synthetic) — Definitions and review of test methods

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 12000:2014. It supersedes BS ISO 12000:2000 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/21, Testing of plastics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 74666 6

ICS 83.040.10; 83.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2014.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
12000

Third edition
2014-10-01

**Plastics/rubber — Polymer
dispersions and rubber latices
(natural and synthetic) — Definitions
and review of test methods**

*Plastiques/caoutchouc — Dispersions de polymères et latex de
caoutchouc (naturel et synthétique) — Définitions et revue des
méthodes d'essai*



Reference number
ISO 12000:2014(E)

© ISO 2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	3
4 Sampling	3
5 Conditioning	3
6 Test methods	3
7 Precision of the test methods used	5
8 Test report	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials* in collaboration with ISO/TC 45, *Rubber and rubber products*.

This third edition cancels and replaces the second edition (ISO 12000:2000), which has been technically revised to update the references to the test methods and change dated references to undated references.

Plastics/rubber — Polymer dispersions and rubber latices (natural and synthetic) — Definitions and review of test methods

1 Scope

This International Standard gives definitions relative to polymer dispersions and latices and identifies the test methods applicable for determining the properties of polymer dispersions, comprising products of synthetic or natural origin including synthetic and natural rubber latices. Some of the test methods apply only to polymer dispersions or latices of specific chemical composition or to those to be used for specific applications.

NOTE When they are not the subject of an existing International Standard, the test methods to be used for investigation of an individual polymer dispersion or latex are intended to be the subject of an agreement between the interested parties.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 35, *Natural rubber latex concentrate — Determination of mechanical stability*

ISO 123, *Rubber latex — Sampling*

ISO 124, *Latex, rubber — Determination of total solids content*

ISO 125, *Natural rubber latex concentrate — Determination of alkalinity*

ISO 126, *Natural rubber latex concentrate — Determination of dry rubber content*

ISO 127, *Rubber, natural latex concentrate — Determination of KOH number*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 472, *Plastics — Vocabulary*

ISO 506, *Rubber latex, natural, concentrate — Determination of volatile fatty acid number*

ISO 705, *Rubber latex — Determination of density between 5 °C and 40 °C*

ISO 706, *Rubber latex — Determination of coagulum content (sieve residue)*

ISO 976, *Rubber and plastics — Polymer dispersions and rubber latices — Determination of pH*

ISO 1147, *Plastics/rubber — Polymer dispersions and synthetic rubber latices — Freeze-thaw cycle stability test*

ISO 1409, *Plastics/rubber — Polymer dispersions and rubber latices (natural and synthetic) — Determination of surface tension by the ring method*

ISO 1652, *Rubber latex — Determination of apparent viscosity by the Brookfield test method*

ISO 1656, *Rubber, raw natural, and rubber latex, natural — Determination of nitrogen content*

ISO 1657, *Rubber, raw and rubber latex — Determination of iron content — 1,10-Phenanthroline photometric method*

ISO 1802, *Natural rubber latex concentrate — Determination of boric acid content*

ISO 2005, *Rubber latex, natural, concentrate — Determination of sludge content*

ISO 2006-1, *Rubber latex, synthetic — Determination of mechanical stability — Part 1: High-speed method*

ISO 2006-2, *Rubber latex, synthetic — Determination of mechanical stability — Part 2: Moderate-speed method under load*

ISO 2115, *Plastics — Polymer dispersions — Determination of white point temperature and minimum film-forming temperature*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

ISO 2555, *Plastics — Resins in the liquid state or as emulsions or dispersions — Determination of apparent viscosity by the Brookfield Test method*

ISO 2811-1, *Paints and varnishes — Determination of density — Part 1: Pyknometer method*

ISO 2811-3, *Paints and varnishes — Determination of density — Part 3: Oscillation method*

ISO 3136, *Rubber latex — Styrene-butadiene — Determination of bound styrene content*

ISO 3219, *Plastics — Polymers/resins in the liquid state or as emulsions or dispersions — Determination of viscosity using a rotational viscometer with defined shear rate*

ISO 3251, *Paints, varnishes and plastics — Determination of non-volatile-matter content*

ISO 3899, *Rubber — Nitrile latex — Determination of residual acrylonitrile content*

ISO 3900, *Rubber — Nitrile latex — Determination of bound acrylonitrile content*

ISO 4576, *Plastics — Polymer dispersions — Determination of sieve residue (gross particle and coagulum content)*

ISO 4655, *Rubber — Reinforced styrene-butadiene latex — Determination of total bound styrene content*

ISO 7143, *Binders for paints and varnishes — Methods of test for characterizing water-based binders*

ISO 7780, *Rubbers and rubber latices — Determination of manganese content — Sodium periodate photometric methods*

ISO 8053, *Rubber and latex — Determination of copper content — Photometric method*

ISO 9252, *Synthetic rubber latex — Microbiological examination*

ISO 13741-1, *Plastics/rubber — Polymer dispersions and rubber latices (natural and synthetic) — Determination of residual monomers and other organic components by capillary-column gas chromatography — Part 1: Direct liquid injection method*

ISO 13741-2, *Plastics/rubber — Polymer dispersions and rubber latices (natural and synthetic) — Determination of residual monomers and other organic components by capillary-column gas chromatography — Part 2: Headspace method*

ISO 13773, *Rubber — Polychloroprene latex — Determination of alkalinity*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

NOTE Where individual standards overlap, it is intended that they will be harmonized by the Technical Committees responsible for them, ISO/TC 45 and ISO/TC 61.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

dispersion

heterogeneous system in which a finely divided material is distributed in another material

[SOURCE: ISO 472]

3.2

polymer dispersion

liquid to semi-liquid material, usually milky-white, containing the polymeric material in a stable condition finely dispersed in a continuous liquid phase, normally water

3.3

latex

colloidal aqueous dispersion of a polymeric material

[SOURCE: ISO 472]

Note 1 to entry: Frequently, “latex” is also used as a synonym for polymer dispersions in general.

Note 2 to entry: Polymer dispersions and latices are often further explained by adding the designation of the base polymer by name or by abbreviation, for instance polyacrylate dispersion, SBR latex.

4 Sampling

Sampling shall be carried out in accordance with ISO 123 (rubber latex).

Representative samples of polymer dispersions and of latices are a prerequisite for reliable and reproducible results from the test methods. Therefore the material to be tested shall be uniform.

5 Conditioning

The conditioning and testing atmosphere shall comply with the specified test method or referring standard, as applicable. If there are no such requirements, then samples shall be conditioned and tests carried out in one of the standard atmospheres specified in either ISO 291 for polymer dispersions or ISO 23529 for latices, as appropriate.

6 Test methods

Test methods shall be selected from those given in [Table 1](#) for rubber latices, and those in [Table 2](#) for polymer dispersions, as appropriate.

Table 1 — Test methods developed by ISO/TC 45

Property	Units	Test method	Comments
Physical and physico-chemical properties			
Mechanical stability	s	ISO 35	Natural rubber latex only
Total solids content	% (m/m)	ISO 124	
Alkalinity	g/100 g of latex	ISO 125	Natural rubber latex only
Dry rubber content	% (m/m)	ISO 126	Natural rubber latex only
Density	Mg/m ³	ISO 705	Natural rubber latex only
Coagulum content (sieve residue)	% (m/m)	ISO 706 ^a	
pH	pH-units	ISO 976 ^a	
Surface tension	mN/m	ISO 1409	
Viscosity	mPa × s	ISO 1652	Apparent viscosity
Sludge content	% (m/m)	ISO 2005	Natural rubber latex only
High-speed mechanical stability	% (m/m)	ISO 2006	Synthetic rubber latex only
Microbiological examination	—	ISO 9252	
Chemical properties			
KOH number		ISO 127	Natural rubber latex only
Volatile fatty acid number		ISO 506	Natural rubber latex only
Nitrogen content	% (m/m)	ISO 1656	Natural rubber latex only
Iron content (1,10-phenanthroline photometric method)	ppm (m/m)	ISO 1657	
Boric acid content	% (m/m)	ISO 1802	Natural rubber latex only
Bound styrene content	% (m/m)	ISO 3136	Styrene-butadiene latex
Residual acrylonitrile content	% (m/m)	ISO 3899	Nitrile latex
Bound acrylonitrile content	% (m/m)	ISO 3900	Nitrile latex
Total bound styrene content	% (m/m)	ISO 4655	Reinforced styrene-butadiene latex
Manganese content (sodium periodate photometric method)	mg/kg	ISO 7780	
Copper content (photometric method)	mg/kg	ISO 8053	Synthetic rubber latex only
Alkalinity	mmol HCl per 100 g	ISO 13773	
General			
Sampling	—	ISO 123	
^a Test methods for polymer dispersions used as raw materials for paints are specified in ISO 7143.			

Table 2 — Test methods developed by ISO/TC 61

Property	Units	Test method	Comments
Physical and physico-chemical properties			
Non-volatile matter at specified temperatures	% (<i>m/m</i>)	ISO 3251 ^b	
Apparent viscosity by Brookfield Test method (general procedure)	Pa × s	ISO 2555	
Density	g/ml	ISO 2811-1 ^b ISO 2811-3 ^b	
Viscosity using rotational viscometer at defined shear rate	Pa × s	ISO 3219 ^a	
Gross particle content by sieve analysis	% (<i>m/m</i>)	ISO 4576 ^a	Residue on sieve(s) substantially larger than average particle size
Chemical properties			
Residual monomers and other organic constituents by capillary-column gas chromatography	mg/kg	ISO 13741-1 ^a ISO 13741-2 ^a	Direct liquid injection method Headspace method
General			
Freeze-thaw cycle stability	number of cycles	ISO 1147	Generally, applicable only to polymer dispersions
White point temperature and minimum film-forming temperature	°C	ISO 2115	
^a Test methods for polymer dispersions used as raw materials for paints are specified in ISO 7143.			
^b Developed by ISO/TC 35.			

7 Precision of the test methods used

Details of the precision of the test method used shall be given in a “Precision” clause. If the experimental data on which the stated precision is based are included in the standard, this may be placed in an informative annex. The precision shall be expressed as a percentage of the results in terms of the following:

- a) repeatability;
- b) reproducibility.

8 Test report

The results of the individual tests performed on a polymer dispersion/latex shall be recorded in a test report. This shall comply with the requirements of the particular International Standard in question, but shall include at least the following information:

- a) a reference to the International Standard used for the test;
- b) all details necessary to identify completely the product and sample tested;
- c) the results of the test and the conditions of testing;
- d) any deviations from the procedure specified;
- e) any unusual incident noted during the test;
- f) the date and place of the test.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™