

BS ISO 12103-1:2016



BSI Standards Publication

Road vehicles — Test contaminants for filter evaluation

Part 1: Arizona test dust

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 12103-1:2016. It supersedes BS ISO 12103-1:1997 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee MCE/21/2, Air filters for air supply to I.C. engines and compressors - Not on aircraft.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 83214 7

ICS 43.060.20; 43.060.40

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2016.

Amendments/corrigenda issued since publication

| Date | Text affected |
|------|---------------|
|------|---------------|

INTERNATIONAL
STANDARD

ISO
12103-1

Second edition
2016-03-01

**Road vehicles — Test contaminants for
filter evaluation —**

**Part 1:
Arizona test dust**

Véhicules routiers — Poussière pour l'essai des filtres —

Partie 1: Poussière d'essai d'Arizona



Reference number
ISO 12103-1:2016(E)

© ISO 2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

| | Page |
|---|-----------|
| Foreword | iv |
| Introduction | v |
| 1 Scope | 1 |
| 2 Test dust description | 1 |
| 3 Test dust designation | 1 |
| 4 Particle size distribution | 1 |
| 5 Chemical composition | 2 |
| 5.1 Typical chemical content of ISO specified Arizona test dusts..... | 2 |
| 5.2 Chemical analysis methodology — X-ray fluorescence analysis (XRF)..... | 2 |
| Annex A (normative) Analysis equipment and operating procedure | 3 |
| Annex B (informative) History of Arizona test dust | 7 |
| Annex C (informative) Handling and preparation | 9 |
| Bibliography | 14 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 22, *Road vehicles*, Subcommittee SC 34, *Propulsion, powertrain and powertrain fluids*.

This second edition cancels and replaces the first edition (ISO 12103-1:1997), which has been technically revised.

ISO 12103 consists of the following parts, under the general title *Road vehicles — Test contaminants for filter evaluation*:

- *Part 1: Arizona test dust*
- *Part 2: Aluminium oxide test dust*

The following parts are under preparation:

- *Part 3: Soot aerosol*

Introduction

This part of 12103 specifies four grades of test dusts made from Arizona desert sand composed of naturally occurring compounds which motor vehicles are commonly subjected to. These test dusts are used to determine performance of filtration systems. Due to the abrasive characteristics of these materials, they have also been used in wear studies involving bearings, internal combustion engines and fuel injection systems, seals, fan blades, windshield wipers, etc.

This part of ISO 12103 specifies particle size distribution of four grades of test dust by volume percent as opposed to number characterization.

Dusts complying with volume distribution specified in this part of ISO 12103 are not appropriate for calibration of particle counters. For this purpose, refer to ISO 11171.

This is an Arizona Test Dust standard, not other region document. Other dusts and documents can be brought forward to the committee to be developed into a standard.

Road vehicles — Test contaminants for filter evaluation —

Part 1: Arizona test dust

1 Scope

This part of ISO 12103 defines particle size distribution and chemical content limits involving four grades of test dust made from Arizona desert sand.

2 Test dust description

ISO test dusts according to this part of ISO 12103 are manufactured from Arizona desert sand. Arizona desert sand is a naturally occurring contaminant consisting primarily of silicon dioxide with smaller amounts of other compounds. It is collected from the Salt River area of Arizona desert and sized to specific particle size.

Arizona desert sand has also been referred to as Arizona road dust, Arizona test dust, Arizona silica, AC fine or coarse test dust, and SAE fine or coarse test dust.

Bulk density of ISO test dusts made from Arizona sand varies with particle size (see [Table 1](#)).

Table 1 — Bulk density

| Category | Approximate bulk density, kg/m ³ |
|---------------|---|
| ISO ultrafine | 500 |
| ISO fine | 900 |
| ISO medium | 1 025 |
| ISO coarse | 1 200 |

3 Test dust designation

Arizona test dusts are available in four standard grades designated as follows:

- ISO 12103-1, A.1 ultrafine test dust;
- ISO 12103-1, A.2 fine test dust;
- ISO 12103-1, A.3 medium test dust;
- ISO 12103-1, A.4 coarse test dust.

4 Particle size distribution

Particle size distribution is determined using a light scattering particle size analyser, as referenced in ISO 13320.

[Table 2](#) specifies cumulative volume particle size limits for ISO test dusts made from Arizona desert sand, when determined using a Microtrac S3500™¹⁾ particle size analyser.

When the different type analyser is employed by a test laboratory, the laboratory should generate suitable correlation data between the analyser by which these powders are supplied to conform [Microtrac¹⁾ analyser] and by the analyser adopted by the test laboratory.

Table 2 — Particle size distributions (volume % less than)

| Size, µm | A1 ultrafine | A2 fine | A3 medium | A4 coarse |
|----------|--------------|--------------|--------------|--------------|
| 352,00 | — | — | — | 100,0 |
| 248,90 | — | — | 100,0 | 99,0 – 100,0 |
| 176,00 | — | 100,0 | 99,0 – 100,0 | 97,2 – 98,2 |
| 124,50 | — | 99,0 – 100,0 | 97,2 – 98,6 | 93,0 – 94,0 |
| 88,00 | — | 97,9 – 98,9 | 94,7 – 96,0 | 85,0 – 86,5 |
| 44,00 | — | 89,5 – 91,5 | 82,0 – 83,5 | 58,0 – 60,0 |
| 22,00 | 100,0 | 73,5 – 76,0 | 62,5 – 64,5 | 36,0 – 38,5 |
| 11,00 | 95,5 – 97,5 | 57,0 – 59,5 | 42,3 – 43,6 | 21,0 – 23,0 |
| 5,50 | 65,0 – 69,0 | 39,5 – 42,5 | 22,1 – 23,2 | 11,5 – 12,5 |
| 2,75 | 23,0 – 27,0 | 21,3 – 23,3 | 10,3 – 11,1 | 5,5 – 6,3 |
| 1,38 | 7,0 – 10,0 | 8,0 – 9,5 | 3,8 – 4,4 | 1,8 – 2,1 |
| 0,97 | 3,0 – 5,0 | 4,5 – 5,5 | 2,0 – 2,4 | 0,74 – 0,83 |

NOTE Data shown per [Table 2](#) was determined using the particle size analysis instrument indicated in normative [Annex A](#). Use of any other particle size analysis equipment will obtain different results.

5 Chemical composition

5.1 Typical chemical content of ISO specified Arizona test dusts

See [Table 3](#).

Table 3 — Chemical content

| Element | Percentage of mass |
|-----------|--------------------|
| Silicon | 69,0 – 77,0 |
| Aluminium | 8,0 – 14,0 |
| Iron | 4,0 – 7,0 |
| Potassium | 2,0 – 5,0 |
| Calcium | 2,5 – 5,5 |
| Sodium | 1,0 – 4,0 |
| Magnesium | 1,0 – 2,0 |
| Titanium | 0,0 – 1,0 |

5.2 Chemical analysis methodology — X-ray fluorescence analysis (XRF)

Chemical analysis is performed using an X-ray fluorescence analyser per ASTM C114-15.

1) Microtrac and Microtrac S3500 are trademarks. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named.

Annex A (normative)

Analysis equipment and operating procedure

A.1 Particle size analyser

A.1.1 General

Particle size data of ISO specified Arizona test dusts as shown in [Table 2](#), were determined using a Microtrac Model S3500™ light scattering type analyser. Use of any other particle size analysis equipment will obtain different results. Other particle size analysis instruments may be acceptable for analysis of test dust products specified in ISO 12103-1, if suitability and correlation is determined between the Microtrac S3500™ and the other analyser. Use of particle size analysis instruments other than the Microtrac S3500™ will require a modified particle size analysis procedure.

The Microtrac Model S3500™ employs use of three light scattering lasers that are combined to produce the resulting particle size distribution data. A tri-laser system uses precise angular measurement of scattered light through a full 180° angular range with three lasers and two detector arrays. Analysis of scattered light to determine particle size employs a Mie based unified angular scattering theory with a dynamic range of 0,02 microns to 2 800 microns (see [Table A.1](#)).

Normally, it is not acceptable to publish a manufacturer's name or equipment identification. However, due to the close tolerance of the specified particle size limits and variation between instruments by multiple manufacturers, one particle size analysis instrument was defined for this specification.

Particle size distribution specified limits shown in [Table 2](#) were derived from sample analysis of PTI manufactured test dust produced prior to May 1994 using three separate Microtrac Model S3500™ light scattering analysers.

Table A.1 — Microtrac Model S3500™ specifications

| Item | Specification |
|-----------------|--|
| Measuring range | 0,02 micron to 2 800 micron |
| Basic range | Wet 0,7 micron to 1 000 micron |
| High range | Wet 2,75 micron to 2 800 micron |
| Standard range | Wet 0,24 micron to 1 400 micron |
| Special range | Wet 0,086 micron to 1 400 micron |
| Extended range | Wet 0,021 micron to 2 000 micron |
| Enhanced range | Wet 0,021 micron to 2 800 micron |
| Precision | Spherical Glass Beads D50 = 642 micron, Precision as CV = 0,7 % Spherical Glass Beads D50 = 56 micron, Precision as CV = 1,0 % Spherical Latex Beads D50 = 0,4 micron, Precision as CV = 0,6 % |
| Lasers | Wavelength 780 nm |

Table A.1 (continued)

| | |
|------------------|---|
| Power | 3 mW nominal |
| Detection system | Two fixed photo-electric detectors with logarithmically spaced segments placed at correct angles for optimal scattered light detection. 0,02° to 163 ° using 151 detector segments. |
| Data handling | Volume, Number and Area distributions as well as percentile and other summary data. Data are stored in ODBC format in encrypted Microsoft Access Databases to ensure compatibility with external statistical software applications. Data integrity may be ensured using FDA 21 CFR Part 11 compliant security features including password protection, electronic signatures and assignable permissions. |

A.1.2 Microtrac S3500™ particle size analysis procedure

A.1.2.1 Sample preparation

Typical sample preparation is as follows.

- a) It is important to ensure the sample taken is representative of the lot of test dust to be tested and mixed well before placing into a clean 20 ml to 50 ml sample vial.
- b) Obtain a clean vial and add the required representative sample quantity based on [Table A.2](#).

Table A.2 — Microtrac S3500™ Sample Weights

| ISO grade | Sample amount in mg |
|---------------|---------------------|
| ISO ultrafine | 14-16 |
| ISO fine | 29-31 |
| ISO medium | 39-41 |
| ISO coarse | 54-56 |

- c) Add one drop of dispersant to the vial. It is very important that dispersant used does not create bubbles.
- d) Add approximately 10 ml distilled water to the vial and mix by gently moving the vial in a circular motion. Avoid creating bubbles.
- e) Place sample vial and contents in an external low power ultrasonic bath, having a water depth of 2 cm, for 30 s. The ultrasonic bath should be in the range of 50 W to 100 W, 50 kHz to 80 kHz. Do not use the Microtrac internal ultrasonic as it may cause bubbles.

A.1.2.2 Analyser software sample set-up

Analyser software sample set-up is done as follows.

- a) Open the Microtrac FLEX software program.
- b) Click “Measure” on the main program window and select S3500/S3000.
- c) Click “File” and select “Open Measurement Database”, select appropriate database for the material being analysed.
- d) Click “SOP” (Standard Operating Procedure) icon on the measure toolbar. Click Options button to setup appropriate measurement setup parameters. Set measurement parameters per the followings:
 - 1) Timing tab is set as follows:
 - Set Zero time = 30 s;

- Run time = 30 s;
 - Number of runs = 3.
- 2) Identifier tab is used to enter general information if desired.
- 3) Analysis tab is set using the following tabs:
- i) Particle information tab:
 - I) Select Refractive Index of 1,51 and save with the appropriate particle name.
 - II) Particle characteristics box:
 - Set transparency; Transparent;
 - Set Shape; Irregular.
 - ii) Fluid information tab:
 - Select fluid; water;
 - Select refractive index; 1,333.
 - iii) Analysis options tab:
 - Select S3000 from Analysis Mode drop down list;
 - Select Enabled Standard from Filter drop down list.
 - iv) Sample loading tab is used to enter user defined loading index limits for each grade per [Table A.2](#).

Table A.3 — Microtrac S3500™ loading index limits

| ISO grade | Loading index limits |
|---------------|----------------------|
| ISO ultrafine | 0,89 - 0,90 |
| ISO fine | 0,86 - 0,87 |
| ISO medium | 0,86 - 0,87 |
| ISO coarse | 0,87 - 0,88 |

- v) Perspective tab is set as follows:
 - Select Geom 4 Root from Progression drop down list;
 - Select Volume from the Distribution drop down list.
- vi) SDC tab is set as follows:
 - I) SDC options; Set the following parameters:
 - Number of Rinses = 3;
 - Number of Deaerate Cycles = 3;
 - Flow = 55.
 - II) Click OK button when all parameters have been entered.

III) Enter appropriate name in the SOP Name to Save or Delete box on the Measurement SOP dialogue box and then click the save button.

- e) Open the identifiers (ID) tab. Set the identifiers per the following:
 - 1) Enter material description in the title section, i.e. ISO 12103-1, A.2 fine test dust.
 - 2) Enter ID in first line of Sample ID section.
- f) Click “Flow” icon on SDC/ASVR toolbar on the right side of the measurement window to start the recirculator.
- g) Click “S/Z” (set zero) icon on the measure toolbar. After the set zero is successfully completed, the time will appear on the upper left portion of the screen highlighted in green.
- h) Click the “Load Sample” (LD) icon on the measure toolbar.

A.1.2.3 Sample loading and analysis

Obtain a clean pipette and load prepared sample into recirculator making sure the entire sample is loaded without creating bubbles. The indicator bar shall be within the transmission range (green zone) when the entire sample has been loaded. If excess sample has been loaded abort the procedure, rinse recirculator and start over.

Operate icons per the following.

- Click “Run” icon on the measurement bar.
- Click the print icon when sample run is completed.

A.2 Instrument calibration

The Microtrac S3500™ analyser cannot be calibrated by the user, but National Institute of Standards and Technology traceable glass powder sold by the manufacturer can be used to verify the analyser is working correctly. Analysis of NIST traceable glass beads should be performed at least every six months.

A secondary calibration material shall be used to verify the analyser is operating correctly. Analysis of the secondary calibration material shall immediately follow analysis of the batch of test dust analysed. Secondary calibration material used shall be from a prior batch of the same grade of test dust being analysed.

Annex B (informative)

History of Arizona test dust

During the 1930s, air intake cleaning devices became widely used by engine manufacturers for use in reducing particulates ingested by internal combustion engines. By 1940, the SAE Journal indicated a need for a standardized test contaminant to evaluate performance of air cleaner systems. The 1943 edition of the SAE Handbook recommends collecting test dust by placing canvas cloth on the ground behind tractors or implements in the Salt River Valley, Arizona, USA.

During following years, a more controlled method of producing large volumes of test dust was required. As a result, the AC Spark Plug Company, division of General Motors Corporation, devised a method of manufacturing test dust by ball milling Arizona desert sand. Two grades of test dust were produced to the following particle size specification given in [Table B.1](#), as published in former SAE J726 Air Cleaner Test Standard, and analysed for particle size using a Roller^{TM2)} analyser.

Table B.1 — Particle size distribution by mass %

| Size, μm | Fine grade | Coarse grade |
|---------------------|------------|--------------|
| 0 – 5 | 39 \pm 2 | 12 \pm 2 |
| 5 – 10 | 18 \pm 3 | 12 \pm 3 |
| 10 – 20 | 16 \pm 3 | 14 \pm 3 |
| 20 – 40 | 18 \pm 3 | 23 \pm 3 |
| 40 – 80 | 9 \pm 3 | 30 \pm 3 |
| 80 – 200 | — | 9 \pm 3 |

In 1979, AC Spark Plug began using a Leeds and Northrup MicrotracTM laser diffraction particle size analyser, in place of the RollerTM analyser, to determine particle size distributions of AC Fine and Coarse Test Dusts. AC indicated that considerable correlation testing between the L and N MicrotracTM and RollerTM analysers was performed and in 1982 requested that SAE subcommittees revise fine and coarse test dust particle size specifications per [Table B.2](#).

Table B.2 — Particle size distribution by volume % (as measured with an L and N MicrotracTM analyser)

| Size, μm | Fine grade | Coarse grade |
|---------------------|------------|--------------|
| 5,5 | 38 \pm 3 | 13 \pm 3 |
| 11 | 54 \pm 3 | 24 \pm 3 |
| 22 | 71 \pm 3 | 37 \pm 3 |
| 44 | 89 \pm 3 | 56 \pm 3 |
| 88 | 97 \pm 3 | 84 \pm 3 |
| 176 | 100 | 100 |

2) Roller is a trademark. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named.

AC Rochester (formerly AC Spark Plug Company) ceased production of AC fine and coarse test dusts in August 1992. ACTM fine³⁾ and ACTM coarse⁴⁾ were also referred to as air cleaner fine (ACFTD) and air cleaner coarse (ACCTD). These dusts were ball mill processed and are no longer available.

During 1981, Powder Technology, Inc. (PTI) began formulating test contaminants for the filtration and aerospace industries. PTI used a Coulter Counter TAITM ⁵⁾ analyser to determine particle size of test dusts. The published specification during 1982 for standardized fine and coarse Arizona test dusts was the RollerTM table shown previously as [Table B.1](#).

PTI originally produced SAE fine and coarse test dusts according to the distributions listed per [Table B.1](#) using the Coulter Counter TAITM analyser as a means of size measurement.

The Coulter Counter TAITM instrument originally used by Powder Technology, Inc. became obsolete and was replaced with a Coulter Multisizer IIeTM ⁶⁾ analyser May 1994. Particle size designation of ISO test dusts described in ISO 12103-1:1997 reflect Coulter Multisizer IIeTM correlation data derived from analysis of samples of PTI manufactured test dusts produced prior to May 1994. ISO 12103-1:1997 provided cumulative volume particle size limits in [Table B.3](#).

Table B.3 — Particle size distribution as measured by Coulter Multisizer IIeTM

| Size, µm | ISO 12103-1:2016, A.1 ultrafine (% less than) | ISO 12103-1:2016, A.2 fine (% less than) | ISO 12103-1:2016, A.3 medium (% less than) | ISO 12103-1:2016, A.4 coarse (% less than) |
|----------|---|--|--|--|
| 1 | 1,0 – 3,0 | 2,5 – 3,5 | 1,0 – 3,0 | 0,6 – 1,0 |
| 2 | 9,0 – 13,0 | 10,5 – 12,5 | 4,0 – 5,5 | 2,2 – 3,7 |
| 3 | 21,0 – 27,0 | 18,5 – 22,0 | 7,5 – 9,5 | 4,2 – 6,0 |
| 4 | 36,0 – 44,0 | 25,5 – 29,5 | 10,5 – 13,0 | 6,2 – 8,2 |
| 5 | 56,0 – 64,0 | 31,0 – 36,0 | 15,0 – 19,0 | 8,0 – 10,5 |
| 7 | 83,0 – 88,0 | 41,0 – 46,0 | 28,0 – 33,0 | 12,0 – 14,5 |
| 10 | 97,0 – 100 | 50,0 – 54,0 | 40,0 – 45,0 | 17,0 – 22,0 |
| 20 | 100 | 70,0 – 74,0 | 65,0 – 69,0 | 32,0 – 36,0 |
| 40 | — | 88,0 – 91,0 | 84,0 – 88,0 | 57,0 – 61,0 |
| 80 | — | 99,5 – 100 | 99,0 – 100 | 87,5 – 89,5 |
| 120 | — | 100 | 100 | 97,0 – 98,0 |
| 180 | — | — | — | 99,5 – 100 |
| 200 | — | — | — | 100 |

ISO test dusts according to this part of ISO 12103 are produced by a dry jet milling process. Particle size distributions are not identical to former dusts produced by AC Rochester Corporation, a division of GM. Therefore, efficiency and dust capacity of filters tested with this part of ISO 12103 test dusts may deviate from results obtained with former dusts.

Revision of the first edition of this part of ISO 12103 proposed by PTI in 2010 was approved by ISO committee members because the Coulter Multisizer IIeTM became obsolete and its replacement with a Microtrac S3500TM was judged to be rational. The proposed particle size limits in [Table 2](#) were determined by multiple analyses of historical samples used to determine the particle size limits specified in ISO 12103-1:1997.

- 3) AC fine is a trademark. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named.
- 4) AC coarse is a trademark. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named.
- 5) Coulter Counter TAI is a trademark. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named.
- 6) Coulter Multisizer IIe is a trademark. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named.

Annex C (informative)

Handling and preparation

C.1 Preparation prior to use

Care should be taken in preparation of test dusts because stratification or agglomeration of particles may occur during shipping and handling. Stratification of particles involves formation of layers of particles of differing sizes within a vessel containing test dust. Stratification is caused by natural migration of particles propelled by vibration during handling or storage. Although no documented scientific studies have been conducted relative to stratification of Arizona test dust particles, it is possible that coarse particles migrate to the top and fine particles concentrate near the bottom of storage containers. Therefore, it is recommended that test dusts be mixed or rebled immediately preceding use.

Test dusts may retain or absorb moisture during the manufacturing process or in storage. Moisture content of test dusts is not considered significant relative to many types of testing involving these materials. However, sensitive or closely controlled test programs may require that test dust be dried in an oven prior to use.

C.2 Health hazards in handling test dusts

Health hazards are identified by the following causes and effects:

- a) **Eye contact.** (Acute/chronic) exposure to airborne dust may cause immediate or delayed irritation or inflammation of the cornea.
- b) **Inhalation.** (Chronic) Inhalation exposure to free silica may cause delayed lung injury, including silicosis, a disabling and potentially fatal lung disease, and/or cause or aggravate other lung diseases or conditions.
- c) **Skin contact.** This material contains sodium oxide and calcium oxide, which may be harmful or irritating to skin.
- d) **Ingestion.** No adverse effects.
- e) **Carcinogenic potential.** This material contains respirable crystalline silica (quartz). Crystalline silica (quartz) inhaled from occupational sources is classified as carcinogenic to humans.

NOTE Potential health effects might vary depending upon the duration and degree of exposure.

C.3 First aid measures

First aid measures should be taken per the following:

- a) **Eyes.** Immediately flush eye thoroughly with water. Get medical attention if irritation persists.
- b) **Skin.** Wash with soap and water. Seek medical attention if irritation persists.
- c) **Inhalation.** Remove person to fresh air. If breathing is difficult, administer oxygen. If not breathing, give artificial respiration. Seek medical help if coughing and other symptoms do not subside.
- d) **Ingestion.** Do not induce vomiting. If conscious, have the victim drink plenty of water and call a physician if discomfort is experienced.

C.4 Fire fighting measures

Fire fighting measures are not necessary because of the following descriptions:

- a) **Flash point.** N/A.
- b) **Auto ignition temperature.** Not combustible.
- c) **Flammable limits.** N/A.
- d) **Lower explosive limit.** None.
- e) **Upper explosive limit.** None.
- f) **Special fire fighting procedures.** None.
- g) **Extinguishing media.** Not combustible.
- h) **Unusual fire and explosion hazards.** None.
- i) **Hazardous combustion products.** None.

C.5 Accidental release measures

Accidental release measures should be taken per the following:

- a) **Respiratory protection.** Use local exhaust or general dilution ventilation to control dust levels below applicable exposure limits. Minimize dispersal of dust into the air. Use appropriate approved respiratory protection for respirable crystalline silica.
- b) **Eye protection.** Wear safety glasses with side shields or goggles to avoid contact with the eyes. In extremely dusty environments and unpredictable environments, wear tight-fitting unvented or indirectly vented goggles to avoid eye irritation or injury.
- c) **Methods for cleanup.** Use a vacuum or other appropriate cleaning device that does not generate airborne dust.

C.6 Handling and storage

Handling and storage should be done per the following:

- a) **Handling.** Use adequate ventilation and dust collection.
- b) **Storage.** Store in a manner so that airborne dust does not exceed applicable exposure limits. Store material in a closed container.

C.7 Exposure controls/personal protection

Exposure controls and personal protection should be done per the following:

- a) **Local exhaust ventilation.** Use sufficient local exhaust ventilation to reduce the level of airborne respirable crystalline silica.
- b) **Respiratory protection.** Use appropriate, approved respiratory protection for respirable crystalline silica.
- c) **Hand protection.** Hand protection is not needed, as the material does not pose a health risk to skin.
- d) **Eye protection.** Wear safety glasses with side shields or goggles to avoid contact with the eyes. In extremely dusty environments and unpredictable environments, wear tight-fitting unvented or indirectly vented goggles to avoid eye irritation or injury.

- e) **Skin protection.** Skin protection is not needed, as the material does not pose a health risk to skin.

C.8 Physical and chemical properties

Physical and chemical properties are as follows:

- a) **Appearance.** Tan, brown, light brown, reddish brown.
- b) **Odor.** No odor.
- c) **Physical state.** Solid.
- d) **Boiling point.** 2 212 °C.
- e) **Flash point.** Non-flammable.
- f) **Flammability.** Non-flammable.
- g) **Explosive properties.** Not explosive.
- h) **Oxidizing properties.** N/A.
- i) **Vapor pressure.** N/A.
- j) **Specific gravity (H₂O = 1,0).** 2,65.
- k) **Solubility in water.** Insoluble.
- l) **Vapor density.** Not applicable.
- m) **Fat solubility.** Insoluble.
- n) **Melting point.** 1 615 (±75) °C.

C.9 Stability and reactivity

Stability and reactivity are characterized as follows:

- a) **Stability.** Product is stable.
- b) **Incompatibility** (materials to avoid). Strong acids.
- c) **Hazardous decomposition.** Will not occur.
- d) **Hazardous polymerization.** Will not occur.
- e) **Conditions to avoid.** None.

C.10 Toxicology information

C.10.1 Potential health effects

Potential health effects may vary depending upon the duration and degree of exposure. To reduce or eliminate health hazards associated with this product, use exposure controls or personal protection methods as described in [C.7](#).

C.10.2 Eye contact

(Acute/chronic) Exposure to airborne dust may cause immediate or delayed irritation or inflammation of the cornea.

C.10.3 Inhalation

The following are concerns regarding inhalation.

- a) The major concern is silicosis, caused by the inhalation and retention of respirable crystalline silica dust. Silicosis can exist in several forms, chronic (or ordinary), accelerated, or acute. Chronic or ordinary silicosis (often referred to as simple silicosis) is the most common form of silicosis, and can occur after many years of exposure to relatively low levels of airborne respirable crystalline silica dust. It is further defined as either simple or complicated silicosis. Simple silicosis is characterized by lung lesions (shown as radiographic opacities) less than 1 cm in diameter, primarily in the upper lung zones. Often, simple silicosis is not associated with symptoms, detectable changes in lung function or disability.
- b) Simple silicosis may be progressive and may develop into complicated silicosis or progressive massive fibrosis (PMF). Complicated silicosis or PMF is characterized by lung lesions (shown as radiographic opacities) greater than 1 cm in diameter. Although there may be no symptoms associated with complicated silicosis or PMF, the symptoms, if present, are shortness of breath, wheezing, cough and sputum production. Complicated silicosis or PMF may be associated with decreased lung function and may be disabling.
- c) Advanced complicated silicosis or PMF may lead to death. Advanced complicated silicosis or PMF can result in heart disease secondary to the lung disease (corpumonale). Accelerated Silicosis can occur with exposure to high concentrations of respirable crystalline silica over a relatively short period; the lung lesions can appear within five (5) years of initial exposure. Progression can be rapid. Accelerated silicosis is similar to chronic or ordinary silicosis, except that lung lesions appear earlier and progression is more rapid.
- d) Acute silicosis can occur with exposures to very high concentrations of respirable crystalline silica over a very short time period, sometimes as short as a few months. The symptoms of acute silicosis include progressive shortness of breath, fever, cough and weight loss. Acute silicosis is fatal.

C.10.4 Carcinogenic potential

The International Agency for Research on Cancer ("IARC") concluded that there was "*sufficient evidence* in humans for the carcinogenicity of crystalline silica in the forms of quartz or cristobalite from occupational sources", and that there is "*sufficient evidence* in experimental animals for the carcinogenicity of quartz and cristobalite."

NOTE 1 The overall IARC evaluation was that "crystalline silica inhaled in the form of quartz or cristobalite from occupational sources is *carcinogenic to humans* (Group 1)."

NOTE 2 The IARC evaluation noted, "Carcinogenicity was not detected in all industrial circumstances studies. Carcinogenicity may be dependent on inherent characteristics of the crystalline silica or on external factors affecting its biological activity or distribution of its polymorphs." For further information on the IARC evaluation, see IARC Monographs on the Evaluation of Carcinogenic Risks to Humans, Volume 68, and "Silica, Some Silicates..." (1997).

C.11 Ecological information

No ecological concerns have been identified.

C.12 Disposal considerations

All disposal methods shall be in accordance with all local laws and regulations. Regulations may vary in different locations. Waste characterization and compliance with applicable laws are the responsibility solely of the waste generator.

The packaging and material may be land filled; however, material should be covered to minimize generation of airborne dust.

C.13 Transportation information

Arizona test dusts are treated in transportation as follows:

- UN number not assigned;
- Not classified as dangerous goods under ADR (road), RID (train) or IMDG (ship).

Bibliography

- [1] ISO 11171, *Hydraulic fluid power — Calibration of automatic particle counters for liquids*
- [2] ISO 13319, *Determination of particle size distributions — Electrical sensing zone method*
- [3] ISO 13320, *Particle size analysis — Laser diffraction methods*
- [4] SAE J726, *Specification — Air Cleaner Test Code (June 1993 Revision)*
- [5] BS 3406-51983, *Determination of particle size of powders*
- [6] ASTM C114-15,⁷⁾ *Standard Test Methods for Chemical Analysis of Hydraulic Cement*
- [7] AIR CLEANER TEST CODE SAE 1943 Edition
- [8] SAE Air Cleaner Test Code Subcommittee Minutes 24 February 1992
- [9] Microtrac S3500TM operation manual

7) Replaced ASTM C114-13.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

