

BS ISO 12418-2:2012



BSI Standards Publication

# Plastics — Post-consumer poly(ethylene terephthalate) (PET) bottle recyclates

Part 2: Preparation of test specimens  
and determination of properties

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 12418-2:2012.

The UK participation in its preparation was entrusted to Technical Committee PRI/82, Thermoplastic materials.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012  
Published by BSI Standards Limited 2012

ISBN 978 0 580 66137 2

ICS 83.080.20

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2012.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

---

---

**Plastics — Post-consumer poly(ethylene terephthalate) (PET) bottle recyclates —**

**Part 2:**

**Preparation of test specimens and  
determination of properties**

*Plastiques — Recyclats de bouteilles en poly(téréphtalate d'éthylène)  
(PET) post-consommation —*

*Partie 2: Préparation des éprouvettes et détermination des propriétés*





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

<b>Contents</b>		Page
<b>Foreword</b> .....		iv
<b>1 Scope</b> .....		1
<b>2 Normative references</b> .....		1
<b>3 Terms and definitions</b> .....		1
<b>4 Characterization of PET recyclates</b> .....		1
<b>4.1 Classification of characteristics</b> .....		1
<b>4.2 Test methods</b> .....		1
<b>Annex A (normative) Method for the determination of impurities in PET flakes</b> .....		3
<b>Annex B (normative) Method for the determination of the bulk density of PET flakes</b> .....		5
<b>Annex C (informative) Method for the determination of the melt volume-flow rate (MVR) of PET recyclates</b> .....		7
<b>Annex D (informative) Potentiometric method for the determination of the residual alkalinity of PET recyclates</b> .....		9
<b>Bibliography</b> .....		11

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12418-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

ISO 12418 consists of the following parts, under the general title *Plastics — Post-consumer poly(ethylene terephthalate) (PET) bottle recyclates*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*

# Plastics — Post-consumer poly(ethylene terephthalate) (PET) bottle recyclates —

## Part 2: Preparation of test specimens and determination of properties

### 1 Scope

This part of ISO 12418 specifies the test methods to be used in determining the properties of post-consumer poly(ethylene terephthalate) (PET) bottle recyclates.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 1628-1, *Plastics — Determination of the viscosity of polymers in dilute solution using capillary viscometers — Part 1: General principles*

ISO 1628-5, *Plastics — Determination of the viscosity of polymers in dilute solution using capillary viscometers — Part 5: Thermoplastic polyester (TP) homopolymers and copolymers*

ISO 15270, *Plastics — Guidelines for the recovery and recycling of plastics waste*

ISO 15512:2008, *Plastics — Determination of water content*

EN 15348:2007, *Plastics — Recycled plastics — Characterization of poly(ethylene terephthalate) (PET) recyclates*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472 and ISO 15270 apply.

### 4 Characterization of PET recyclates

#### 4.1 Classification of characteristics

The characteristics of PET recyclates are classified into two types, given in Table 1, as follows:

- those which are required for all recyclates (i.e. mandatory characteristics);
- customer specifications (these are optional).

#### 4.2 Test methods

The characteristics shall be determined using the test methods given in Table 1. A certificate of analysis, including the test results for each batch of recyclate, the sampling method and the number of replicates, shall be provided by the supplier to the purchaser on request.

**NOTE** The sampling method and the number of replicates are important in determining the quality of the material. Quality levels can vary within the batch and from batch to batch, depending on the source of the recyclate.

Table 1 — Characterization of PET recyclates

Characteristics	Unit	Test method	Notes
<b>Mandatory items</b>			
Form		Visual examination	Flakes, pellets or powder
Colour		Visual examination	Natural or coloured
Maximum flake size	mm		Determined by the size of the screen in the grinder
Maximum pellet size	mm		Determined by the die opening of the pelletizer and measured by ruler or callipers
Intrinsic viscosity (IV)	dl/g	ISO 1628-5 in combination with ISO 1628-1 (including its Amendment ISO 1628-1:2009/Amd 1)	Solvent shall be a mixture of phenol and 1,1,2,2-tetrachloroethane (6:4)
Contamination due to labels and other visible contaminants	mg/kg	Annex A	Only for flakes
Contamination due to poly(vinyl chloride)	mg/kg	Annex A	Only for flakes
Contamination due to poly-olefins, and including adhesive	mg/kg	Annex A	Only for flakes
Water content	%	ISO 15512:2008, method B	
Bulk density	kg/m <sup>3</sup>	Annex B	
<b>Optional items</b>			
Melt volume-flow rate (MVR)	cm <sup>3</sup> /10 min	Annex C	-
Alkalinity	pH	Annex D	Only for flakes
Filterability	10 MPa/h/cm <sup>2</sup>	EN 15348:2007, Annex F	

Other tests may be carried out by agreement between the purchaser and the supplier. If they are, the results of such tests shall be reported.



## Annex A (normative)

### Method for the determination of impurities in PET flakes

#### A.1 General

This annex specifies a method for the determination of the content of the following impurities in flakes of PET recyclates:

- pieces of label and other visible contaminants;
- poly (vinyl chloride) (PVC);
- polyolefins (POs), and including adhesive.

#### A.2 Principle

A weighed test portion of the recyclate is spread evenly over the bottom of a shallow tray.

The pieces of label and other visible contaminants are picked out using tweezers and weighed. The test portion, still in the tray, is then placed in a forced air circulation oven at 220 °C for 1 h.

During this heat treatment, the PVC in the test portion becomes discoloured and can be detected visually. The polyolefins in the test portion melt and turn yellow. The adhesive is also yellowed and might be indistinguishable from the polyolefins.

#### A.3 Apparatus

**A.3.1 Oven**, with forced air circulation, capable of being maintained at 220 °C.

**A.3.2 Technical balance**, capable of weighing to the nearest 0,1 g.

**A.3.3 Analytical balance**, capable of weighing to the nearest 0,000 1 g.

**A.3.4 Spatula**, made of wood or metal.

**A.3.5 Tweezers**.

**A.3.6 Tray**, made of aluminium or enamelled ironware, with a bottom of surface area not less than 0,05 m<sup>2</sup>.

#### A.4 Procedure

Weigh out, to the nearest 0,1 g, approximately 100 g of flakes and record the mass ( $m_0$ ). Spread the flakes evenly over the bottom of the metal tray.

Stir the flakes slowly in the tray with a spatula and pick out the pieces of label and other visible contaminants using tweezers. Continue this procedure for not less than 30 min. Weigh the pieces of label and other visible contaminants picked out ( $m_1$ ), using an analytical balance.

Put the tray containing the remaining material into an oven, preheated to 220 °C, and leave it at that temperature for 1 h. Remove the tray, allow to cool and inspect the material for not less than 30 min, as follows:

- a) Pick out the black carbonized particles (PVC). Weigh the particles picked out ( $m_2$ ), using an analytical balance.
- b) Pick out the yellowish particles (POs and adhesive). If they are stuck to PET flakes, separate them. Weigh the particles picked out ( $m_3$ ), using an analytical balance.

## A.5 Expression of results

**A.5.1** The content of label and other visible contaminants, expressed in mg/kg, is given by the following formula:

$$\text{Content of label and other visible contaminants} = \frac{m_1 \times 10^6}{m_0} \quad (\text{A.1})$$

where

$m_1$  is the mass of label and other visible contaminants, in g;

$m_0$  is the initial mass of the test portion, in g.

**A.5.2** The PVC content, expressed in mg/kg, is given by the following formula:

$$\text{PVC content} = \frac{m_2 \times 10^6}{m_0} \quad (\text{A.2})$$

where

$m_2$  is the mass of the discoloured (black) particles, in g;

$m_0$  is the initial mass of the test portion, in g.

**A.5.3** The PO content (which will include any adhesive present), expressed in mg/kg, is given by the following formula:

$$\text{PO content} = \frac{m_3 \times 10^6}{m_0} \quad (\text{A.3})$$

where

$m_3$  is the mass of the yellowish particles, in g;

$m_0$  is the initial mass of the test portion, in g.

## A.6 Test report

The test report shall include the following information:

- a) a reference to this part of ISO 12418 (ISO 12418-2);
- b) all details necessary for identification of the sample tested;
- c) the results of the test;
- d) details of any additional operations carried out or changes made in the procedure;
- e) the date of the test.

## Annex B (normative)

### Method for the determination of the bulk density of PET flakes

#### B.1 Principle

A container of known volume is weighed and then filled with PET flakes up to the brim and reweighed. The bulk density is calculated from the container volume and the mass of the PET flakes.

#### B.2 Apparatus

**B.2.1 Container**, approximately 120 mm in diameter and approximately 150 mm in depth, with a smooth brim.

**B.2.1 Ruler**, to remove sample material protruding above the brim of the container.

**B.2.1 Balance**, capable of weighing to the nearest 0,1 g.

#### B.3 Procedure

Take a sufficient amount of sample to allow three determinations to be carried out.

Weigh the container ( $m_{c1}$ ) to the nearest 0,1 g.

Using a suitable scoop, fill the container until it overflows. Tap the brim of the container three times and level the contents across the brim of the container using a ruler. Weigh the filled container ( $m_{c2}$ ) to the nearest 0,1 g.

Repeat the above procedure twice to give three results.

#### B.4 Calculation

Calculate the bulk density from the following formula:

$$\rho_b = \frac{m_{c2} - m_{c1}}{V} \times 10^3$$

where

$\rho_b$  is the bulk density, in kg/m<sup>3</sup>;

$m_{c1}$  is the mass of the container, in g;

$m_{c2}$  is the mass of the test portion and container, in g;

$V$  is the volume of the container, in cm<sup>3</sup>.

#### B.5 Test report

The test report shall include the following information:

- a) a reference to this part of ISO 12418 (ISO 12418-2);
- b) all details necessary for identification of the sample tested;

- c) the results of the test (the three individual results plus their mean);
- d) details of any additional operations carried out or changes made in the procedure;
- e) the date of the test.

## Annex C (informative)

### Method for the determination of the melt volume-flow rate (MVR) of PET recyclates

#### C.1 General

This annex specifies a method for the determination of the melt volume-flow rate (MVR) of PET recyclates in accordance with ISO 1133-1 and ISO 1133-2.

#### C.2 Drying conditions

Dry a test sample of PET recyclate at 160 °C for  $4^{+2}_0$  h in a circulating-air oven, prior to performing a compacted charge by compression.

NOTE Because PET is hygroscopic, its viscosity decreases rapidly due to hydrolysis if the material is allowed to absorb moisture. The test sample is therefore dried prior to testing in order to improve the comparability of test results.

#### C.3 Preforming for flakes

When flakes of PET recyclate are used, prepare a preformed compacted charge in accordance with Annex C of ISO 1133-1:2011, using the following conditions:

- a) cylinder temperature: 240 °C to 242 °C;
- b) mass of sample placed in cylinder: 6 g to 8 g;
- c) load on piston: 1,5 kN;
- d) loading time: 2 min under vacuum.

#### C.4 Size of die

A half size die of length 4,000 mm  $\pm$  0,025 mm and bore diameter 1,050 mm  $\pm$  0,005 mm (see ISO 1133-1 and ISO 1133-2) shall normally be used. If testing materials using this die gives a melt volume-flow rate of less than 5 cm<sup>3</sup>/10 min, the standard die 8,000 mm  $\pm$  0,025 mm in length and having a bore of nominal diameter 2,095 mm should preferably be used.

#### C.5 Test temperature

A test temperature of 280 °C shall be used.

#### C.6 Size of test sample

A test sample of mass 6 g to 10 g shall be used.

#### C.7 Nominal load on piston

The nominal load on the piston shall be 5 kg.

## C.8 Charging the cylinder

Introduce the dried test sample into the cylinder immediately after it has been taken out of the oven in order to avoid moisture regain. During the charging, compress the material with the packing rod using hand pressure. Ensure the charge is as free from air as possible. Complete the charging process in less than 30 s.

If the sample is in flake form, introduce the preformed compacted charge immediately after the preforming process, and complete the charging process in less than 30 s.

## C.9 Preheating time

A preheating time of 5 min shall be used.

It is recommended that a die plug be inserted in the die exit so that it effectively prevents molten low-viscosity material from coming out through the die exit during the pre-heating period.

## C.10 Measurements

Measure the time taken by the reference mark on the piston to cover a specified distance or measure the distance moved by the piston during a predetermined time.

The time between the end of charging the cylinder and the end of measurement should preferably not exceed 10 min to avoid degradation of the material during the test.

## C.11 Cleaning the apparatus

The apparatus, including the cylinder, the piston and the die, shall be cleaned thoroughly after each determination. The presence of contaminants or their thermolysis products is a major problem as these might accelerate hydrolytic degradation of a hygroscopic material like PET.

## C.12 Equation for converting MVR to IV

A very good correlation has been found between  $\log(\text{MVR})$  and IV. In the case of homopolymers, the following equation has been established on the basis of data from four laboratories:

$$\log(\text{MVR}) = -2,400 \text{ IV} + 2,735$$

Since such a conversion equation might depend on the type of comonomer, it is recommended that a specific equation be established for each type of PET. In the case of PET recyclate, it is necessary to establish a new conversion equation each time the source of the recyclate changes.

## C.13 Test report

The test report shall include the following information:

- a) a reference to this part of ISO 12418 (ISO 12418-2);
- b) all details necessary for identification of the sample tested;
- c) the result of the test;
- d) details of any additional operations carried out or changes made in the procedure;
- e) the date of the test.

## **Annex D** (informative)

### **Potentiometric method for the determination of the residual alkalinity of PET recyclates**

#### **D.1 General**

This annex specifies a method for the determination of the residual alkalinity in PET recyclates.

NOTE It has been prepared on the basis of the procedure described in EN 15348:2007, Annex E.

#### **D.2 Principle**

A given quantity of sample is mixed, by stirring, with a measured volume of distilled water. The residual alkali present on the surface of the pieces or particles of the PET recyclate contributes to an increase in the pH of the water, which can be measured using a combined glass electrode pH-meter.

#### **D.3 Apparatus**

**D.3.1 Magnetic stirrer or mechanical stirring device.**

**D.3.2 Balance**, capable of weighing to the nearest 0,1 g;

**D.3.3 Beaker**, capacity 1 000 ml;

**D.3.4 Graduated cylinder**, capacity 500 ml;

**D.3.5 pH-meter**, with combined glass electrode.

#### **D.4 Materials**

**D.4.1 Distilled water**, with a pH between 6 and 8.

#### **D.5 Procedure**

Calibrate the pH-meter with buffer solutions of known pH. Weigh exactly 100 g of the sample into a 1 000 ml beaker and add 500 ml of distilled water. Stir for 10 min, ensuring that all the PET recyclate is completely immersed in the water during this time.

After stirring, decant off the solution, immerse the pH probe in it and record the pH when it has stabilized.

#### **D.6 Expression of results**

Report the result of the analysis as the pH of the solution, together with the initial pH of the distilled water for comparison.

## **D.7 Test report**

The test report shall include the following information;

- a) a reference to this part of ISO 12418 (ISO 12418-2);
- b) all details necessary for identification of the sample tested;
- c) the result of the test;
- d) details of any additional operations carried out or changes made in the procedure;
- e) the date of the test.



## Bibliography

- [1] FDA (US Food and Drug Administration) publication: *Points to consider for the use of recycled plastics in food packaging: chemistry considerations*, August 2006, revision of the first (1992) edition
- [2] FDA (US Food and Drug Administration) publication 21 CFR 170.39, *Threshold of regulation for substances used in food-contact articles*, Federal Register 60, No. 136, 36595, July 17, 1995
- [3] BAYER, F.L.: The threshold of regulation and its application to indirect food additive contaminants in recycled plastics, *Food Additives and Contaminants*, **14**, No. 6-7, 661-670 (1997)
- [4] FRANZ, R., HUBER, M., and WELLE, F.: Recycling of post-consumer poly(ethylene terephthalate) for direct food contact application — a feasibility study using a simplified challenge test, *Deutsche Lebensmittel-Rundschau*, **94**, 303-308 (1998)
- [5] FRANZ, R., and WELLE, F.: Analytical screening and evaluation of market grade post-consumer poly(ethylene terephthalate) (PET) flakes for re-use in food packaging, *Deutsche Lebensmittel-Rundschau*, **95**, 94-100 (1999)
- [6] FRANZ, R.: Programme on the recyclability of food-packaging materials with respect to food safety considerations: polyethylene terephthalate (PET), paper and board, and plastics covered by functional barriers, *Food Additives and Contaminants*, **19**, 93-110 (2002)
- [7] OHKADO, Y., KAWAMURA, Y., MUTSUGA, M., TAMURA, H., and TANAMOTO, K.: Analysis of Residual Volatiles in Recycled Polyethylene Terephthalate, *Shokuhin Eiseigaku Zasshi* (Journal of the Food Hygienics Society of Japan), **46**, 13-20 (2005)
- [8] SATA, N., WATANABE, K., KAYAMA, S., KONISHI, T., and UTSUMI, M.: Analysis of residual volatiles in commercial poly ethylene terephthalate (PET) flakes recycled by physical process from post-consumer PET bottles, *Japanese Journal of Food Chemistry and Safety (JJFCS)*, **17(2)**, 116-122 (2010)
- [9] European Commission Regulation (EC) No. 2023/2006 of 22 December 2006 on good manufacturing practice for materials and articles intended to come into contact with food, *Official Journal of the European Union*, OJ L 384/75-78 (29.12.2006)
- [10] European Commission Regulation (EC) No. 282/2008 of 27 March 2008 on recycled plastic materials and articles intended to come into contact with foods and amending Regulation (EC) No. 2023/2006, *Official Journal of the European Union*, OJ L 86/9-18 (28.3.2008)
- [11] Opinion of the Scientific Panel on food additives, flavourings, processing aids and materials in contact with food (AFC) on guidelines on submission of dossier for safety evaluation by the EFSA of a recycling process to produce recycled plastics intended to be used for manufacture of materials and articles in contact with food (EFSA-Q-2004-168); After public consultation and discussion in panel 21 May 2008), the EFSA Journal (2008) 717, 1-12
- [12] ISO 1133-1:2011, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*
- [13] ISO 1133-2, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 2: Method for materials sensitive to time-temperature history and/or moisture*





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™