

BS ISO 13007-1:2010



BSI Standards Publication

Ceramic tiles — Grouts and adhesives

Part 1: Terms, definitions and specifications for adhesives

bsi.

...making excellence a habit.™

Version correct as of 03/01/2015. (c) The British Standards Institution 2013 Licensed copy: Lee Shau Kee Library, HKUST. Version correct as of 03/01/2015. (c) The British Standards Institution 2013 Licensed copy: Lee Shau Kee Library, HKUST.

National foreword

This British Standard is the UK implementation of ISO 13007-1:2010.

The UK participation in its preparation was entrusted to Technical Committee B/539, Ceramic tiles and other rigid tiling.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2010

ISBN 978 0 580 68615 3

ICS 83.180; 91.100.23

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2010.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

ISO
13007-1

Second edition
2010-09-15

Ceramic tiles — Grouts and adhesives —

Part 1: Terms, definitions and specifications for adhesives

Carreaux céramiques — Mortiers de joints et colles —

Partie 1: Termes, définitions et spécifications relatives aux colles



Reference number
ISO 13007-1:2010(E)

© ISO 2010

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification and designation	3
5 Requirements	4
5.1 Substrates	4
5.2 Specifications for cementitious adhesives — C	5
5.3 Specifications for dispersion adhesives — D	6
5.4 Specifications for reaction resin adhesives — R	7
6 Marking, labelling and packaging	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13007-1 was prepared by Technical Committee ISO/TC 189, *Ceramic tiles*.

This second edition cancels and replaces the first edition (ISO 13007-1:2004), which has been technically revised. It also incorporates the Technical Corrigendum ISO 13007-1:2004/Cor.1:2006.

ISO 13007 consists of the following parts, under the general title *Ceramic tiles — Grouts and adhesives*:

- *Part 1: Terms, definitions and specifications for adhesives*
- *Part 2: Test methods for adhesives*
- *Part 3: Terms, definitions and specifications for grouts*
- *Part 4: Test methods for grouts*

Ceramic tiles — Grouts and adhesives —

Part 1: Terms, definitions and specifications for adhesives

1 Scope

This part of ISO 13007 defines terms concerning the products, working methods and application properties for ceramic tile adhesives. It specifies values of performance requirements for all ceramic tile adhesives [cementitious (C), dispersion (D) and reaction resin (R) adhesives].

This part of ISO 13007 is applicable to ceramic tile adhesives for internal and external tile installations on walls and floors.

It is not applicable to criteria or recommendations for the design and installation of ceramic tiles.

NOTE Ceramic tile adhesives can also be used for other types of tiles (natural and agglomerated stones, etc.), where these do not adversely affect the materials.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 13006, *Ceramic tiles — Definitions, classification, characteristics and marking*

ISO 13007-2:2010, *Ceramic tiles — Grouts and adhesives — Part 2: Test methods for adhesives*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13006 and the following apply.

3.1

substrate

fixing surface

surface on which the tile is installed or fixed

3.2

wall and floor tiles

tiles made out of ceramic tile or natural and agglomerated stones

3.3

cementitious adhesive

C

mixture of hydraulic binding agents, aggregates and organic additives, mixed with water or liquid admix immediately prior to use

3.4
dispersion adhesive

D
ready-for-use mixture of organic binding agent(s) that is in the form of an aqueous polymer dispersion, organic additives and mineral fillers

3.5
reaction resin adhesive

R
single or multi-component mixture of synthetic resin, mineral fillers and organic additives in which curing occurs by chemical reaction

3.6
notched trowel

toothed tool, which makes it possible to apply the adhesive as a series of ribs of a uniform thickness on to the fixing surface and the reverse face of the tile

3.7
application to one surface only

adhesive applied only to the fixing surface with a trowel to obtain a uniform layer and then combed with a notched trowel

3.8
application to both surfaces

adhesive applied to the fixing surface and to the reverse surface of the tiles

3.9
shelf life

time of storage under stated conditions during which an adhesive can be expected to maintain its working properties

3.10
maturing time

interval between the time when the cementitious adhesive is mixed and the time when it is ready for use

3.11
pot life

time interval during which the adhesive can be used after mixing

3.12
open time

maximum time interval after application at which tiles can be embedded in the applied adhesive and meet the specified tensile adhesion strength requirement

3.13
slip

downward movement of a tile applied to a combed adhesive layer on a vertical surface

3.14
adjustability

maximum time interval after which the tile's position in the adhesive layer can be adjusted without significant loss of adhesion strength

3.15
adhesion strength

maximum strength per unit surface area which can be measured by shear or tensile testing

3.16

deformability

capacity of a hardened adhesive to be deformed by stresses between the tile and the fixing surface without damage to the installed surface

3.17

transverse deformation

deflection recorded at the centre when a beam of hardened adhesive is subjected to three point loading

3.18

fundamental characteristic

characteristic that is absolutely required of an adhesive

3.19

additional characteristic

characteristic of an adhesive for specific service conditions where enhanced levels of performance are required

3.20

special characteristic

characteristic of an adhesive which provides further information about its general performance

4 Classification and designation

4.1 Tile adhesives are classified into three types (see 3.3, 3.4 and 3.5, and ISO 13006):

- C cementitious adhesive
- D dispersion adhesive
- R reaction resin adhesive

For each type, there are different possible classes, related to combinations of the different additional and special characteristics, in accordance with Tables 1, 2 and 3. These classes are designated with the following numbers and letters:

- 1 normal adhesive
- 2 improved adhesive
- F fast-setting cementitious adhesive
- A accelerated drying dispersion adhesive
- T slip-resistant adhesive
- E adhesive with extended open time
- S special deformable characteristic for cementitious adhesives only
- P adhesive with adhesion to exterior glue plywood

4.2 The designation of the adhesive is generated with the symbol of the type (C, D or R), followed by the abbreviation of the class or classes to which it belongs. Table 1 describes the designation of tile adhesives.

Table 1 — Examples of designation and classification

Symbol type	Number	Class	Description
C	1		Normal cementitious adhesive
C	1	F	Fast-setting cementitious adhesive
C	1	T	Normal cementitious adhesive with slip resistance
C	1	FT	Fast-setting cementitious adhesive with slip resistance
C	2		Cementitious adhesive with improved characteristics
C	2	E	Cementitious adhesive with improved characteristics and extended open time
C	2	F	Fast-setting cementitious adhesive with improved characteristics
C	2	T	Cementitious adhesive with improved characteristics and slip resistance
C	2	TE	Cementitious adhesive with improved characteristics, slip resistance and extended open time
C	2	FT	Fast-setting cementitious adhesive with improved characteristics and slip resistance
D	1		Normal dispersion adhesive
D	1	T	Normal dispersion adhesive with slip resistance
D	2		Dispersion adhesive with improved characteristics
D	2	A	Accelerated drying dispersion adhesive with improved characteristics
D	2	T	Dispersion adhesive with improved characteristics with slip resistance
D	2	TE	Dispersion adhesive with improved characteristics, slip resistance and extended open time
R	1		Normal reaction resin adhesive
R	1	T	Normal reaction resin adhesive with slip resistance
R	2		Reaction resin adhesive with improved characteristics
R	2	T	Reaction resin adhesive with improved characteristics and slip resistance

NOTE Additional designations can be inserted according to the combination of the different symbols of the characteristics.

EXAMPLE Deformable, improved cementitious adhesive with extended open time and normal adhesion to exterior glue plywood: C2ES1P1.

5 Requirements

5.1 Substrates

The standard concrete substrate is mandatory. Other substrates may be used upon agreement, if the substrate is recommended for the ceramic tile application by the adhesive manufacturer. To demonstrate compatibility with other optional substrates, the adhesive shall be applied to the selected substrate in accordance with the tensile adhesion strength method given in ISO 13007-2:2010, 4.4.4.2. When the result of $\geq 0,5 \text{ N/mm}^2$ is achieved or cohesive failure occurs in the substrate, the requirement shall be considered satisfied.

5.2 Specifications for cementitious adhesives — C

Cementitious adhesives shall comply with all of the C1 fundamental characteristics reported in Table 2. The amount of water or liquid admix required for preparing the cementitious adhesive shall be the same for all tests. The additional characteristics for C2 (improved performance) products are also contained in Table 2. Table 3 gives the special characteristics that can be reported for cementitious adhesives.

Table 2 — Specifications for cementitious adhesives — C

Classification	Property	Requirement	Test method in ISO 13007-2:2010
C1 – Normal cementitious adhesives (fundamental characteristics)	Tensile adhesion strength	$\geq 0,5 \text{ N/mm}^2$	4.4.4.2
	Tensile adhesion strength after water immersion	$\geq 0,5 \text{ N/mm}^2$	4.4.4.3
	Tensile adhesion strength after heat ageing	$\geq 0,5 \text{ N/mm}^2$	4.4.4.4
	Tensile adhesion strength after freeze-thaw cycle	$\geq 0,5 \text{ N/mm}^2$	4.4.4.5
	Open time: tensile adhesion strength	$\geq 0,5 \text{ N/mm}^2$ After not less than 20 min	4.1
C2 – Improved cementitious adhesives (additional characteristics)	Tensile adhesion strength	$\geq 1,0 \text{ N/mm}^2$	4.4.4.2
	Tensile adhesion strength after water immersion	$\geq 1,0 \text{ N/mm}^2$	4.4.4.3
	Tensile adhesion strength after heat ageing	$\geq 1,0 \text{ N/mm}^2$	4.4.4.4
	Tensile adhesion strength after freeze-thaw cycle	$\geq 1,0 \text{ N/mm}^2$	4.4.4.5

Table 3 — Specifications for cementitious adhesives (C) — Special characteristics

Special characteristic	Property	Requirement	Test method in ISO 13007-2:2010
T – Slip resistance	Slip	$\leq 0,5$ mm	4.2
F – Fast-setting adhesives	Tensile adhesion strength	$\geq 0,5$ N/mm ² after no more than 6 h	4.4.4.2
	Open time: tensile adhesion strength	$\geq 0,5$ N/mm ² after not less than 10 min	4.1
	All other requirements at least equal to or better than those listed for C1 adhesives as in Table 2	See Table 2 under C1 adhesives	See Table 2 under C1 adhesives
S – Transverse deformation	Deformable adhesive (S1)	$\geq 2,5$ mm, < 5 mm	4.5
	Highly deformable adhesives (S2)	≥ 5 mm	4.5
E – Extended open time	Extended open time: tensile adhesion strength	$\geq 0,5$ N/mm ² after not less than 30 min	4.1
P – Exterior glue plywood adhesion (optional substrates)	Normal exterior glue plywood adhesion (P1)	$\geq 0,5$ N/mm ²	4.4.4.2
	Improved exterior glue plywood adhesion (P2)	≥ 1 N/mm ²	4.4.4.2

5.3 Specifications for dispersion adhesives — D

All dispersion adhesives shall comply with the D1 fundamental characteristics reported in Table 4. The additional characteristics for D2 (improved performance) products are also contained in Table 4. Table 5 gives the special characteristics that can be reported for dispersion adhesives.

Table 4 — Specifications for dispersion adhesives — D

Classification	Property	Requirement	Test method in ISO 13007-2:2010
D1 – Normal adhesive (fundamental characteristics)	Shear adhesion strength	≥ 1 N/mm ²	4.3.4
	Shear adhesion strength after heat ageing	≥ 1 N/mm ²	4.3.6
	Open time: tensile adhesion strength	$\geq 0,5$ N/mm ² after not less than 20 min	4.1
D2 – Improved adhesive (additional characteristics)	Shear adhesion strength after 21 days' air cure, 7 days' water immersion	$\geq 0,5$ N/mm ²	4.3.5
	Shear adhesion strength at elevated temperature	≥ 1 N/mm ²	4.3.7

Table 5 — Specifications for dispersion adhesives (D) — Special characteristics

Special characteristic	Property	Requirement	Test method in ISO 13007-2:2010
T – Slip resistance	Vertical slip resistance	$\leq 0,5$ mm	4.2
A – Accelerated drying	Shear adhesion strength after 7 days' air cure, 7 days' water immersion	$\geq 0,5$ N/mm ²	4.3.5
	Shear adhesion strength at elevated temperature	≥ 1 N/mm ²	4.3.7
E – Extended open time	Extended open time: tensile adhesion strength	$\geq 0,5$ N/mm ² after not less than 30 min	4.1

5.4 Specifications for reaction resin adhesives — R

All reaction resin adhesives shall comply with the R1 fundamental characteristics reported in Table 6. The additional characteristics for R2 (improved performance) products are also contained in Table 6. Table 7 gives the special characteristics that can be reported for reaction resin adhesives.

Regarding the characteristic of chemical resistance, there is no indication of limit value or chemical agent. When specific chemical resistance data are required for a project, testing shall conform to ISO 13007-2:2010, 4.6 (determination of chemical resistance), with chemical concentrations and immersion temperatures chosen to simulate exposure conditions. The test media shall consist of media to which the chemical-resistant materials are exposed in service and the test conditions (temperature, etc.) shall simulate the anticipated service and exposure conditions as closely as possible.

Table 6 — Specifications for reaction resin adhesives — R

Classification	Property	Requirement	Test method in ISO 13007-2:2010
R1 – Normal adhesive (fundamental characteristics)	Shear adhesion strength	≥ 2 N/mm ²	4.3.4
	Shear adhesion strength after water immersion	≥ 2 N/mm ²	4.3.5
	Open time: tensile adhesion strength	$\geq 0,5$ N/mm ² after not less than 20 min	4.1
R2 – Improved adhesives (additional characteristics)	Shear adhesion strength after thermal shock	≥ 2 N/mm ²	4.3.8

Table 7 — Specification for reaction resin adhesives (R) — Special characteristics

Special characteristic	Property	Requirement	Test method in ISO 13007-2:2010
T – Slip resistance	Vertical slip resistance	$\leq 0,5$ mm	4.2

6 Marking, labelling and packaging

Products complying with the requirements of this part of ISO 13007 shall be clearly marked with the following information:

- a) reference to this part of ISO 13007, i.e. ISO 13007-1:2010;
- b) name of the product;
- c) manufacturer's mark and place of origin;
- d) date or code of production, shelf life and conditions of storage;
- e) type of adhesive in accordance with Clause 4 (using symbols given in Table 1);
- f) instructions for use:
 - 1) recommended areas for use;
 - 2) mix proportions, if applicable;
 - 3) maturing time, if applicable;
 - 4) pot life;
 - 5) mode of application;
 - 6) open time;
 - 7) delay for grouting and opening to traffic, if applicable.

NOTE In the designation of an adhesive, information about special properties can be included when the product is intended for use in specific applications.

This information shall be marked on the packaging or on the product's technical data sheet.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™