BS ISO 13543:2016



BSI Standards Publication

Copper, lead, zinc and nickel sulfide concentrates — Determination of mass of contained metal in a lot



BS ISO 13543:2016 BRITISH STANDARD

National foreword

This British Standard is the UK implementation of ISO 13543:2016.

The UK participation in its preparation was entrusted to Technical Committee NFE/36, Copper lead and zinc ores and concentrates.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016. Published by BSI Standards Limited 2016

ISBN 978 0 580 81812 7

ICS 73.060.99

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2016.

Amendments/corrigenda issued since publication

Date Text affected

INTERNATIONAL STANDARD

ISO 13543:2016 ISO 13543

Second edition 2016-06-01

Copper, lead, zinc and nickel sulfide concentrates — Determination of mass of contained metal in a lot

Concentrés sulfurés de cuivre, de plomb, de zinc et de nickel — Détermination de la masse de métal contenu dans un lot



BS ISO 13543:2016 **ISO 13543:2016(E)**



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Foreword			Page
			iv
1	Scop	oe	1
2	Norr	mative references	1
3	Tern	ns and definitions	1
4	Determination of mass of contained metal		2
	4.1	General	
	4.2	Wet mass of the lot	2
	4.3	Metal content of the lot	2
	4.4	Dry mass of the lot	2
	4.5	Mass of contained metal	
		4.5.1 Major elements	
		4.5.2 Precious metals	3
5	Dete	ermination of variance of mass of contained metal	3
6	Examples of calculation of contained metal and its variance		4
	6.1	Static scale	4
		6.1.1 General	
		6.1.2 Mass of contained copper	
		6.1.3 Mass of contained gold	5
	6.2	Draft survey	6
Rihl	iogrank	hv	Ω

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information.

The committee responsible for this document is ISO/TC 183, *Copper, lead, zinc and nickel ores and concentrates*.

This second edition cancels and replaces the first edition (ISO 13543:1996), which has been technically revised.

Copper, lead, zinc and nickel sulfide concentrates — Determination of mass of contained metal in a lot

WARNING — This International Standard may involve hazardous materials, operations and equipment. It is responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard specifies the method for determining the mass of contained metal in a lot, based on the wet mass, moisture content and dry basis metal content of the lot. The procedure for estimating the variance and confidence intervals for the mass of contained metal is also specified.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10251, Copper, lead, zinc and nickel concentrates — Determination of mass loss of bulk material on drying

ISO 12743, Copper, lead, zinc and nickel concentrates — Sampling procedures for determination of metal and moisture content

ISO 12744, Copper, lead, zinc and nickel concentrates — Experimental methods for checking the precision of sampling

ISO 12745, Copper, lead and zinc ores and concentrates — Precision and bias of mass measurement techniques

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

lot

quantity of concentrate to be sampled

3.2

wet mass of the lot

combined mass of concentrate and moisture of the lot at the time of weighing and sampling

3.3

moisture determination

quantitative measurement of the mass loss of the moisture test portion under the conditions of drying specified in ISO 10251

3.4

chemical analysis

quantitative determination of the required chemical constituents of the analysis test portion

3.5

precision

measure of the random variations within a set of measurements

3.6

dry mass of the lot

mass of concentrate in the lot after correcting for the mass of moisture in the lot

4 Determination of mass of contained metal

4.1 General

The mass of contained metal in a lot is determined from measurements of the wet mass, moisture content and dry basis metal content.

4.2 Wet mass of the lot

The wet mass of the lot shall be determined using static scales, belt scales or draft surveys. However, due to their superior precision, static scales are recommended.

4.3 Metal content of the lot

Samples for chemical analysis shall be collected in accordance with ISO 12743 and analysed in accordance with the relevant ISO chemical analysis standards.

4.4 Dry mass of the lot

Calculate the dry mass of the lot using Formula (1):

$$m_{\rm D} = m_{\rm W} \left(1 - \frac{M}{100} \right) \tag{1}$$

where

 $m_{\rm D}$ is the dry mass of the lot, in tonnes;

 $m_{\rm W}$ is the wet mass of the lot, in tonnes;

M is the moisture content of the lot, in percent of the wet mass (mass fraction).

4.5 Mass of contained metal

4.5.1 Major elements

For the major elements copper, lead, zinc, and nickel, the mass of contained metal in the lot is given by Formula (2):

$$m_{\rm M} = \frac{m_{\rm D} a_{\rm L}}{100} \tag{2}$$

where

 $m_{\rm M}$ is the mass of contained metal in the lot, in tonnes;

 $m_{\rm D}$ is the dry mass of the lot, in tonnes;

 $a_{\rm L}$ is the metal content of the lot on a dry basis, in percent (mass fraction).

Alternatively, Formula (2) may be rewritten as Formula (3):

$$m_{\rm M} = \frac{m_{\rm W} F a_{\rm L}}{100} \tag{3}$$

where *F* is the moisture factor given by Formula (4):

$$F = 1 - \frac{M}{100} \tag{4}$$

4.5.2 Precious metals

For the precious metals silver and gold, the mass of contained metal in the lot is given by Formula (5):

$$m_{\rm M} = \frac{m_{\rm W} F a_{\rm L}}{1000} \tag{5}$$

where

 $m_{\rm M}$ is the mass of contained metal in the lot, in kilograms;

 $m_{\rm W}$ is the wet mass of the lot, in tonnes;

F is the moisture factor;

 $a_{\rm L}$ is the precious metal content of the lot on a dry basis, in grams per tonne (mass fraction).

5 Determination of variance of mass of contained metal

The variance of the mass of contained metal in the lot may be determined from Formula (3) by taking the partial derivatives with respect to the wet mass, the moisture factor and the metal content of the lot as given in Formula (6):

$$s_{\rm M}^2 = \left(\frac{\partial m_{\rm M}}{\partial m_{\rm W}}\right)^2 s_{\rm W}^2 + \left(\frac{\partial m_{\rm M}}{\partial F}\right)^2 s_{\rm F}^2 + \left(\frac{\partial m_{\rm M}}{\partial a_{\rm L}}\right)^2 s_{\rm T}^2 \tag{6}$$

where

- $s_{\rm M}^{2}$ is the estimated variance of the mass of contained metal in the lot;
- $s_{\rm W}^2$ is the estimated variance of the wet mass of the lot;
- is the estimated total variance of the moisture factor = $(s_H/100)^2$ with s_H being the total precision (one standard deviation) of moisture determination;
- $s_{\rm T}^2$ is the estimated total variance of the metal content of the lot.

NOTE The estimated total variances of the moisture factor and the metal content include the contributions from primary sampling, sample processing and analysis.

Determining the partial derivatives and substituting them into Formula (6) gives Formula (7):

$$s_{\rm M}^2 = \left(\frac{Fa_{\rm L}}{100}\right)^2 s_{\rm W}^2 + \left(\frac{m_{\rm W} a_{\rm L}}{100}\right)^2 s_{\rm F}^2 + \left(\frac{m_{\rm W} F}{100}\right)^2 s_{\rm T}^2 \tag{7}$$

Formula (7) may be simplified as Formula (8):

$$s_{\rm M}^2 = m_{\rm M}^2 \left[\frac{s_{\rm W}^2}{m_{\rm W}^2} + \frac{s_{\rm F}^2}{F^2} + \frac{s_{\rm T}^2}{a_{\rm L}^2} \right] \tag{8}$$

Formula (8) is applicable to both the major elements and the precious metals.

The variance of the wet mass of the lot shall be determined in accordance with the procedures specified in ISO 12745 for estimating the precision of mass measurement techniques. The variances of the moisture factor and the metal content of the lot shall be determined according to the procedures specified in ISO 12744. The analyses shall be carried out according to the methods prescribed in relevant International Standards.

6 Examples of calculation of contained metal and its variance

6.1 Static scale

6.1.1 General

Assume a 500 t lot containing a mass fraction of 30 % copper, a mass fraction of 10 g of gold/t and a mass fraction of 8 % moisture is weighed using a static hopper scale with a capacity of 25 t, i.e. 20 hopper loads. The precision (one standard deviation) of the hopper scale is 0,1 % relative. The lot is divided into 10 sub-lots and a single moisture determination is carried out on each subsample. A single lot sample is constituted for chemical analysis. The total precisions of the copper, gold and moisture determinations (one standard deviation) are mass fractions of 0,05 % copper, 0,5 g of gold/t and 0,1 % moisture absolute, respectively.

6.1.2 Mass of contained copper

$$m_{\rm W} = 500 \, \rm t$$

$$s_{\rm W}^2 = \left(\frac{25 \times 0.1}{100}\right)^2 \times 20 = 0.0125$$

$$F = 1 - \frac{8}{100} = 0,92$$

$$s_{\rm F}^2 = \frac{\left(0, 1/100\right)^2}{10} = 0,000\,000\,1$$

$$a_{\rm L}$$
 = 30 % copper

$$s_{\rm T}^2 = (0.05)^2 = 0.0025$$

Formulae (3) and (8) give

$$m_{\rm M} = \left(\frac{500 \times 0.92 \times 30}{100}\right) = 138 \text{ t copper}$$

$$s_{\rm M}^2 = 138^2 \times \left(\frac{0.0125}{500^2} + \frac{0.0000001}{0.92^2} + \frac{0.0025}{30^2}\right)$$

$$= 138^2 \times \left(0.00000005 + 0.00000012 + 0.00000278\right)$$

$$= 0.00095 + 0.0023 + 0.0529$$

$$= 0.056$$

Calculation of the standard deviation $s_{\rm M}$ gives

$$s_{\rm M}$$
 = 0,24 t copper

Hence, at the 95 % confidence level (i.e. two standard deviations), the mass of contained copper metal is

$$m_{\rm M}$$
 = 138 ± 0,5 t copper (i.e. ±0,4 % relative)

The 95 % confidence range is 137,5 t of copper to 138,5 t of copper.

The precision of the measured copper content of the lot is the major contributor to the uncertainty in the mass of contained metal. The uncertainty can be reduced by carrying out additional analyses on the lot sample, or, in future, by analysing each sub-lot separately.

6.1.3 Mass of contained gold

$$m_{\rm W} = 500 \, {\rm t}$$

$$s_{\rm W}^2 = \left(\frac{25 \times 0.1}{100}\right)^2 \times 20 = 0.0125$$

$$F = 1 - \frac{8}{100} = 0,92$$

$$s_{\rm F}^2 = \frac{\left(0, 1/100\right)^2}{10} = 0,000\,000\,1$$

$$a_{\rm L}$$
 = 10 g of gold/t

$$s_{\rm T}^2 = (0,5)^2 = 0,25$$

Formulae (5) and (8) give

$$m_{\rm M} = \left(\frac{500 \times 0,92 \times 10}{1000}\right) = 4,6 \,\mathrm{kg}\,\mathrm{gold}$$

BS ISO 13543:2016 ISO 13543:2016(E)

$$s_{\rm M}^2 = 4.6^2 \times \left(\frac{0.0125}{500^2} + \frac{0.0000001}{0.92^2} + \frac{0.25}{10^2} \right)$$

$$= 4.6^2 \times \left(0.000000 \ 05 + 0.000000 \ 12 + 0.002 \ 5 \right)$$

$$= 0.0000011 + 0.00000025 + 0.0529$$

$$= 0.053$$

Calculation of the standard deviation $s_{\rm M}$ gives

$$s_{\rm M}$$
 = 0,23 kg gold

Hence, at the 95 % confidence level, the mass of contained gold is

$$m_{\rm M}$$
 = 4,6 ± 0,5 kg gold (i.e. ±11 % relative)

The 95 % confidence range is 4,1 kg of gold to 5,1 kg of gold.

The precision of the measured gold content of the lot is the major contributor to the uncertainty in the mass of contained metal. Once again, the uncertainty can be reduced by carrying out additional analyses on the lot sample, or, in future, by analysing each sub-lot separately.

6.2 Draft survey

Assume a lot containing a mass fraction of 30 % copper and 8 % moisture has a wet mass of 25 000 t. If the wet mass is determined by draft survey with a relative precision (one standard deviation) of 1 % and the copper and moisture content of the lot have been determined with total precisions (one standard deviation) of mass fractions of 0.05 % copper and 0.1 % moisture absolute respectively, then

$$m_{\rm W} = 25\,000\,{\rm t}$$

$$s_{\rm W}^2 = \left(\frac{25\ 000 \times 1}{100}\right)^2 = 62\ 500$$

$$F = 1 - \frac{8}{100} = 0,92$$

$$s_{\rm F}^2 = \left(\frac{0.1}{100}\right)^2 = 0.000001$$

$$a_{\rm L}$$
 = 30 % copper

$$s_{\rm T}^2 = (0,05)^2 = 0,0025$$

Hence, Formulae (3) and (8) give

$$m_{\rm M} = \left(\frac{25\,000 \times 0,92 \times 30}{100}\right) = 6\,900\,\text{t copper}$$

$$s_{\rm M}^2 = 6\,900^2 \times \left(\frac{62\,500}{25\,000^2} + \frac{0,000\,001}{0,92^2} + \frac{0,002\,5}{30^2} \right)$$
$$= 6\,900^2 \times \left(0,000\,1 + 0,000\,001\,2 + 0,000\,002\,8 \right)$$
$$= 4\,761 + 57 + 133$$
$$= 4\,951$$

Calculation of the standard deviation $s_{\rm M}$ gives

$$s_{\rm M}$$
 = 70 t copper

Hence, at the 95 % confidence level, the mass of contained copper metal is

$$m_{\rm M}$$
 = 6 900 ± 140 t copper (i.e. ±2,0 % relative)

The 95 % confidence range is 6 760 t of copper to 7 040 t of copper.

Clearly, the precision of mass determination is the major contributor to the uncertainty in the mass of contained metal. This situation is typical when the wet mass of the lot is determined by draft survey, which is much less precise than using weigh hoppers.

Bibliography

- [1] ISO 10258, Copper sulfide concentrates Determination of copper content Titrimetric methods
- [2] ISO 10378, Copper, lead and zinc sulfide concentrates Determination of gold and silver Fire assay gravimetric and flame atomic absorption spectrometric method
- [3] ISO 10469, Copper sulfide concentrates Determination of copper Electrogravimetric method
- [4] ISO 11441, Lead sulfide concentrates Determination of lead content Back titration of EDTA after precipitation of lead sulfate
- [5] ISO 12739, Zinc sulfide concentrates Determination of zinc Ion-exchange/EDTA titrimetric method
- [6] ISO 13291, Zinc sulfide concentrates Determination of zinc Solvent extraction and EDTA titrimetric method





British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible
 by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced in any format to create an additional copy.
 This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com **Email (enquiries):** cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

 $\textbf{Email:} \ knowledge centre @bsigroup.com$

Copyright & Licensing

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

