

BS ISO 13756:2015



BSI Standards Publication

Jewellery — Determination of silver in silver jewellery alloys — Volumetric (potentiometric) method using sodium chloride or potassium chloride

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 13756:2015. It supersedes BS ISO 13756:1997 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/53, Specifications and test methods for jewellery and horology.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 74805 9
ICS 39.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

**Jewellery — Determination of
silver in silver jewellery alloys —
Volumetric (potentiometric) method
using sodium chloride or potassium
chloride**

*Joallerie — Dosage de l'argent dans les alliages d'argent pour la
bijouterie-joaillerie — Méthode volumétrique (potentiométrique)
utilisant le chlorure de sodium ou le chlorure de potassium*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	1
5 Apparatus	2
6 Sampling	2
7 Procedure	2
7.1 Determination of sodium chloride or potassium chloride standard solution factor.....	2
7.1.1 Preparation of silver standards.....	2
7.1.2 Titration of standard silver solution.....	2
7.1.3 Calculation of sodium chloride or potassium chloride standard solution factor	3
7.2 Determination.....	3
7.2.1 Preparation of the sample solution.....	3
7.2.2 Elimination of palladium.....	3
7.2.3 Titration of the sample solution.....	3
8 Calculation and expression of results	3
8.1 Calculation.....	3
8.2 Repeatability.....	4
9 Test report	4
Bibliography	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 174, *Jewellery*.

This second edition cancels and replaces the first edition (ISO 13756:1997), which has been technically revised with the following changes:

- addition of an analytical balance in [Clause 5](#);
- change of requirement for sampling in [Clause 6](#);
- addition of a warning in [Clause 7](#) that suitable health and safety procedures should be followed;
- International Standard editorially revised.

Introduction

The following definitions apply in understanding how to implement an ISO International Standard and other normative ISO deliverables (TS, PAS, IWA):

- “shall” indicates a requirement;
- “should” indicates a recommendation;
- “may” is used to indicate that something is permitted;
- “can” is used to indicate that something is possible, for example, that an organization or individual is able to do something.

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.1 defines a requirement as an “expression in the content of a document conveying criteria to be fulfilled if compliance with the document is to be claimed and from which no deviation is permitted.”

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.2 defines a recommendation as an “expression in the content of a document conveying that among several possibilities one is recommended as particularly suitable, without mentioning or excluding others, or that a certain course of action is preferred but not necessarily required, or that (in the negative form) a certain possibility or course of action is deprecated but not prohibited.”

Jewellery — Determination of silver in silver jewellery alloys — Volumetric (potentiometric) method using sodium chloride or potassium chloride

1 Scope

This International Standard specifies a volumetric method for the determination of silver in silver jewellery alloys, preferably within the range of fineness stated in ISO 9202. These alloys may contain copper, zinc, cadmium, and palladium. Apart from palladium, which must be precipitated before commencing titration, these elements do not interfere with this method of determination.

NOTE This method is an alternative recommended method to ISO 11427.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11596, *Jewellery — Sampling of precious metal alloys for and in jewellery and associated products*

3 Principle

The sample is dissolved in dilute nitric acid. The silver content of the resulting solution is determined by titration with standard sodium chloride or potassium chloride solution using a potentiometric indication of the equivalence point.

4 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.1 Nitric acid (HNO_3), 33 % HNO_3 (mass fraction), with sufficiently low content of halides (check with silver nitrate test).

4.2 Sodium chloride solution, $c(\text{NaCl}) = 0,1 \text{ mol/l}$.

Dissolve 5,84 g of sodium chloride (dried at 105 °C) in water and dilute to 1 000 ml.

4.3 Potassium chloride solution, $c(\text{KCl}) = 0,1 \text{ mol/l}$.

Dissolve 7,44 g of potassium chloride (dried at 105 °C) in water and dilute to 1 000 ml.

4.4 Disodium dimethylglyoxime octahydrate solution.

Dissolve 10 g of disodium dimethylglyoxime octahydrate in 1 000 ml of water.

4.5 Silver, minimum purity 999,9 parts per thousand (‰) by mass.

5 Apparatus

5.1 Customary laboratory apparatus.

5.2 Motor-driven plunger or piston-type burette, linked to potentiometer or automatic titrator and capable of delivering increments of 0,05 ml at the equivalence point.

5.3 Titration apparatus, with combination silver electrode or silver chloride coated silver electrode and Hg/Hg₂SO₄ electrode or other suitable reference electrode.

A silver chloride coating can be obtained by electrolysis, branching a silver electrode as anode in a dilute hydrochloric acid solution $c(\text{HCl}) = 0,1 \text{ mol/l}$. After suitable surface preparation, apply an anodic current density of 1 mA/cm^2 for approximately one hour, until the silver surface is completely covered with silver chloride.

5.4 Analytical balance, with a reading accuracy of 0,01 mg.

6 Sampling

The sampling procedure for silver and silver alloys shall be performed in accordance with ISO 11596.

7 Procedure

WARNING — Suitable health and safety procedures should be followed

7.1 Determination of sodium chloride or potassium chloride standard solution factor

7.1.1 Preparation of silver standards

Weigh, to the nearest 0,01 mg, three samples, each of 300 mg to 500 mg of silver (4.5), and transfer them to glass beakers. Add 5 ml of nitric acid (4.1) to each, and warm gently to dissolve the silver. Keep the tops of the beakers covered with watch glasses. Heat until evolution of nitrogen oxides ceases. Allow to cool. Rinse the watch glasses into beakers. Transfer to the titration apparatus (5.3). Add the minimum volume of water, within the range of about 20 ml to 60 ml, to satisfy the requirements of the titration apparatus (5.3) with respect to measurement and stirring.

The mass of the standard silver samples should lie within 20 mg of the mass of silver in the sample portion.

7.1.2 Titration of standard silver solution

Add, via the plunger-burette (5.2) under continuous stirring, sufficient sodium chloride standard solution (4.2) or potassium chloride standard solution (4.3) to precipitate about 95 % of the silver in the solution. Titrate the remaining silver in such a manner that the equivalence point can be interpolated from 0,05 ml additions of the sodium chloride or potassium chloride standard solution.

NOTE This split titration approach can be effected automatically using an automatic titrator with so called dynamic volume dosing based on the measured potential difference across the electrodes in the titration apparatus (5.3).

7.1.3 Calculation of sodium chloride or potassium chloride standard solution factor

The sodium chloride or potassium chloride standard solution factor, F , is calculated using Formula (1)

$$F = \frac{m_{\text{AgF}}}{V_{\text{AgF}}} \quad (1)$$

where

m_{AgF} is the mass of silver, in milligrams;

V_{AgF} is the volume of sodium chloride or potassium chloride solution at equivalence point, in millilitres.

The factor determinations shall not differ from each other by more than 0,05 %, relative value. The mean value, \bar{F} , shall be used in subsequent calculations for maximum accuracy. The sodium chloride or potassium chloride standard solution factor shall be determined immediately before analysis of the sample portions.

7.2 Determination

7.2.1 Preparation of the sample solution

Weigh, to the nearest 0,01 mg, two sample portions, each containing between 300 mg and 500 mg of silver, and transfer them to glass beakers. Add 5 ml of nitric acid (4.1) to each and warm gently to dissolve the alloy. Keep the tops of the beakers covered with watch glasses. Heat until evolution of nitrogen oxides ceases. Allow to cool. Rinse the watch glasses into beakers. Transfer to the titration apparatus (5.3). Add water as per 7.1.1.

7.2.2 Elimination of palladium

Palladium, if present, shall be eliminated by adding an aqueous solution of disodium dimethylglyoxime octahydrate (4.4). For each 100 mg of palladium, add 50 ml of this solution before commencing titration.

7.2.3 Titration of the sample solution

Proceed exactly as per the standard solution. It may be necessary to carry out a pilot determination to obtain an approximate value of the silver content.

8 Calculation and expression of results

8.1 Calculation

The mass m_{Ag} in milligrams of silver in the sample portion is calculated using Formula (2):

$$m_{\text{Ags}} = \bar{F} \cdot V_{\text{Ags}} \quad (2)$$

where

\bar{F} is the sodium chloride or potassium chloride standard solution factor, in milligrams of silver for each millilitre of solution;

V_{Ags} is the volume of sodium chloride or potassium chloride at equivalence point, in millilitres.

The silver content of the sample W_{Ag} in parts by mass per thousand (‰) is calculated using Formula (3):

$$W_{\text{Ag}} = \frac{m_{\text{AgS}}}{m_{\text{s}}} \cdot 10^3 \quad (3)$$

where

m_{s} is the mass of the sample, in milligrams.

8.2 Repeatability

The results of duplicate determinations shall correspond to better than one part per thousand (‰) by mass of silver. If the variation is greater than this, the assay shall be repeated.

9 Test report

The test report shall include the following information:

- a) identification of the sample including source, date of receipt, form of sample;
- b) sampling procedure;
- c) the method used by reference to this International Standard, i.e. ISO 13756:2014;
- d) silver content of the sample, in parts by mass per thousand (‰), as single values and mean values;
- e) if relevant, any deviations from the method specified in this International Standard, i.e. ISO 13756:2014;
- f) any unusual features observed during the determination;
- g) date of test;
- h) identification of laboratory carrying out this analysis;
- i) signature of laboratory manager and operator.

Bibliography

- [1] ISO 9202, *Jewellery — Fineness of precious metal alloys*
- [2] ISO 11427, *Jewellery — Determination of silver in silver jewellery alloys — Volumetric (potentiometric) method using potassium bromide*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™