

BS ISO 14285:2014



BSI Standards Publication

Rubber and plastics gloves for food services — Limits for extractable substances

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 14285:2014.

The UK participation in its preparation was entrusted to Technical Committee CH/205/3, Medical gloves.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 69660 2

ICS 67.250; 83.140.99

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2014.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
14285

First edition
2014-02-15

**Rubber and plastics gloves for food
services — Limits for extractable
substances**

*Gants en caoutchouc et en plastique pour les services alimentaires —
Limites pour les substances extractibles*



Reference number
ISO 14285:2014(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Types	1
4 Requirements	2
4.1 Allowable limits of extractable substances from the gloves.....	2
4.2 Heavy metals.....	2
4.3 Phthalate content.....	2
5 Sample preparation	2
5.1 Determination of heavy metals.....	2
5.2 Determination of potassium permanganate consumption and the evaporation residue.....	3
5.3 Determination of the phthalate content.....	3
6 Provision for use	3
7 Labelling and marking	3
Annex A (normative) Determination of heavy metals	4
Annex B (normative) Determination of potassium permanganate consumption	8
Annex C (normative) Determination of evaporated residue	10
Annex D (normative) Determination of phthalate content	12
Annex E (informative) Precision	16
Bibliography	18

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 4, *Products (other than hoses)*.

Rubber and plastics gloves for food services — Limits for extractable substances

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies limits for extractable chemical substances for single-use gloves made from natural rubber, synthetic rubber, or plastic materials that are intended for use in food preparation, food handling, and related application in food service industry.

This International Standard does not cover the specification for extractable biological substances and physical requirements of the gloves. It is not applicable to gloves used under extreme conditions such as those having pH less than 4,5 and/or temperature above 40 °C. This International Standard does not cover gloves being exposed to fat and oil foods.

NOTE The physical requirements specified for gloves could be found in related International Standards, for example, ISO 11193-1 and ISO 11193-2.

This International Standard does not cover safe and proper application of the gloves with subsequent handling, packaging, and storage procedures.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 14372:2004, *Child use and care articles – Cutlery and feeding utensils – Safety requirements and tests*

3 Types

Gloves are classified into the following types:

- a) type 1: natural rubber latex;
- b) type 2: synthetic latex;
- c) type 3: polyvinyl chloride (PVC);
- d) type 4: polyethylene (PE);
- e) type 5: polypropylene (PP).

NOTE Gloves made from blend polymer are not covered in this International Standard.

4 Requirements

4.1 Allowable limits of extractable substances from the gloves

The allowable extractable substances for all types of glove shall not exceed the limits presented in [Table 1](#).

Determination of the extractable substances shall be carried out according to the test methods given in [Table 1](#).

Table 1 — Maximum limits for allowable extractable substances from food-contact gloves

Parameters	Maximum limit	Test methods
Heavy metals, µg/ml	See Table 2	Annex A
Potassium permanganate consumption, µg/ml	≤10	Annex B
Evaporation residue, µg/ml		
Distilled water	≤100	Annex C
10 % ethanol	≤100	

4.2 Heavy metals

The heavy metals shall not exceed the limits given in [Table 2](#) when tested in accordance with [Annex A](#).

Table 2 — Limits of heavy metals

Element	Maximum limit µg/ml
Arsenic, As	0,05
Cadmium, Cd	0,05
Chromium, Cr	0,5
Lead, Pb	0,5
Zinc, Zn	15,0

4.3 Phthalate content

The total content of phthalate for Type 3 glove shall not exceed 0,1 % (m/m). The determination of phthalate content shall be carried out as described in [Annex D](#), or in 6.3.2 of EN 14372.

5 Sample preparation

5.1 Determination of heavy metals

Cut one piece of 5 cm × 5 cm test sample to provide a surface area of 50 cm² taken from the palm or the back of a glove.

The extraction is done by immersing the test piece in a container of 100 ml of the recommended extraction medium. Use water bath to control the temperature, according to the condition given in [Table 3](#).

After extraction, remove the test piece from the container and keep the solution for the determination of heavy metals.

Table 3 — Conditions for sample preparation

Parameters	Extraction medium	Conditions
Heavy metals	4 % acetic acid	(40 ± 1) °C for (10 ± 1) min
Potassium permanganate consumption	Distilled water	(40 ± 1) °C for (10 ± 1) min
Evaporation residue	Distilled water 10 % ethanol	(40 ± 1) °C for (10 ± 1) min

5.2 Determination of potassium permanganate consumption and the evaporation residue

Cut two pieces of 5 cm × 5 cm from the palm or the back of gloves to provide a total surface area of 100 cm². Wash the test samples with distilled water to remove any lubricant or powder used to prevent the gloves from sticking together.

The extraction is done by immersing the test pieces in a container of 200 ml of the recommended extraction medium. Use water bath to control the temperature, according to the condition given in [Table 3](#).

After extraction, remove the test pieces from the container and keep the solution for the determination of potassium permanganate consumption and the evaporation residue.

5.3 Determination of the phthalate content

The extraction procedure is as described in [Annex D](#), or in EN 14372.

6 Provision for use

6.1 The manufacturer shall provide information on the provision of the gloves for application in wet or dry conditions.

6.2 The glove should remain intact after exposure to wet surfaces throughout the food preparation or handling processes as recommended by the manufacturer.

6.3 The glove shall be used only once.

7 Labelling and marking

7.1 The language used for labelling and marking shall be as agreed upon between the interested parties.

7.2 Information provided shall be at the box or packaging container.

7.3 Appropriate labelling for food service gloves shall include instructions for use that identify materials or conditions with which contact should be avoided.

7.4 Gloves made of natural rubber latex shall be provided with the following label: “Natural rubber latex, which may cause an allergic reaction has been used in the manufacturing of this product”, or words to that effect.

Annex A (normative)

Determination of heavy metals

A.1 Principle

This test procedure describes the method for the determination of an individual heavy metal element extracted from gloves using inductively coupled plasma optical emission spectroscopy (ICP-OES). The basis of the method is the measurement of emission of light by an optical spectroscopic technique. The sample solutions are nebulized and the aerosol that is produced is transported to the plasma torch where the excitation occurs. Characteristic emission spectra are produced by radio frequency inductively coupled plasma (ICP). The spectra are dispersed by a grating spectrometer and the intensities of the lines are monitored by a detector. The signals from the detector(s) are processed and controlled by a computer system. A suitable background correction technique is used to compensate for variable background contributions to the determination of trace elements.

A.2 Apparatus

Use usual laboratory apparatus and, in particular, the following.

A.2.1 ICP-OES, equipment consisting of sample holder, plasma torch, spray chamber, nebulizer, optical unit, detector, system control, and data output device.

NOTE Detailed operating instructions is not provided due to the differences between various makers and models.

A.2.2 Analytical balance, capable of measuring accurately up to 0,0001 g.

A.2.3 Containers, for storage of standard solution and calibrant.

NOTE All containers shall be cleaned with 10 % (v/v) nitric acid before use.

A.2.4 Glassware, all glassware shall be soaked with 10 % (v/v) nitric acid at least 24 h before use.

A.2.4.1 Glass beakers, of suitable capacity.

A.2.4.2 Volumetric flasks, of suitable size.

A.2.4.3 Erlenmeyer flask.

A.2.4.4 Pipette.

A.2.4.5 Funnel.

A.2.5 Micropipettes.

A.3 Reagents

A.3.1 Argon gas, gas with purity of over 99,99 % (v/v).

A.3.2 Nitrogen gas, gas with purity of over 99,99 % (v/v).

A.3.3 Nitric acid, $\rho(\text{HNO}_3) = 1,4 \text{ g/ml}$ [$w(\text{HNO}_3) = 650 \text{ g/kg}$].

A.3.4 Deionised water.

A.3.5 Nitric acid solution 5 % (v/v), prepare by adding 50 ml of nitric acid ([A.3.3](#)) to deionised water ([A.3.4](#)) and bring the volume to 1 000 ml of volumetric flask ([A.2.4.2](#)).

A.3.6 Standard stock solutions, 100 mg/l of arsenic (As), cadmium (Cd), chromium (Cr), lead (Pb), and zinc (Zn).

NOTE Standard stock solutions of other concentrations can be used. The standard stock solutions can be purchased or prepared from high purity grade chemicals or metals. Traceable standard solutions might be preferred.

A.4 Standard solutions

The following standard solutions for the five elements, i.e. arsenic (As), cadmium (Cd), chromium (Cr), lead (Pb), and zinc (Zn) shall be prepared.

A.4.1 Standard solution of 100 µg/l

Pipette 50 µl of standard stock solution of the element standard ([A.3.6](#)) in a 50 ml volumetric flask. Add 5 % nitric acid solution ([A.3.5](#)) to bring the total volume of 50 ml.

A.4.2 Standard solution of 500 µg/l

Pipette 250 µl of standard stock solution of the element standard ([A.3.6](#)) in a 50 ml volumetric flask. Add 5 % nitric acid solution ([A.3.5](#)) to bring the total volume of 50 ml.

A.4.3 Standard solution of 1 000 µg/l

Pipette 500 µl of standard stock solution of the element standard ([A.3.6](#)) in a 50 ml volumetric flask. Add 5 % nitric acid solution ([A.3.5](#)) to bring the total volume of 50 ml.

A.5 Laboratory reagent blank

The procedure is identical to that of sample solution preparation and is carried out concurrently but without the sample.

A.6 Determination

A.6.1 General

A.6.1.1 Set up the instrument with proper operating parameters established from the manufacturer's instruction manual. Allow the instrument to achieve thermal stability before beginning. Instructions provided by the manufacturer should be followed.

A.6.1.2 Initiate the appropriate operating configuration of the computer.

A.6.1.3 Profile and calibrate the instrument according to the manufacturer's recommended procedures using the standard solutions (A.4).

A.6.1.4 Begin the sample run by flushing the system with the reagent blank (A.5) between each sample.

A.6.2 Recommended wavelengths and important spectral interferences

Table A.1 lists the recommended wavelengths and the important spectral interferences.

Table A.1 — Recommended wavelengths and the important spectral interferences

Element	Wavelength nm	Interfering elements
As	188,979	Al, Cr, Fe, Ti
	193,696	Al, Co, Fe, W, V
	197,197	Al, Co, Fe, Pb, Ti
Cd	214,441	As, Cr, Fe, Sc, Sb
	226,502	As, Co, Fe, Ni
	228,802	As, Co, Sc
Cr	205,559	Be, Fe, Mo, Ni, Ti
	267,719	Mn, P, V
	283,563	Fe, Mo, V, W
	284,324	Fe
Pb	220,353	Al, Co, Fe, Ti
	283,305	Cr, Fe
Zn	202,548	Cr, Cu, Co, Ni
	206,200	Cr
	213,857	Cu, Fe, Ni
NOTE 1 The choice of wavelengths for a specific instrument should be carried out with respect to the manufacturer's recommendation.		
NOTE 2 Wavelengths in this table are taken from ISO 11885:2007.		

A.6.3 Limit of detection

A.6.3.1 The limit of detection, expressed as the concentration or the quantity, is derived from the smallest measure that can be detected with reasonable certainty for a given analytical procedure (IUPAC).

NOTE IUPAC - International Union of Pure and Applied Chemistry.

A.6.3.2 The limit of detection (LOD) shall be calculated using Formula (A.1):

$$\text{LOD} = 3 \times sd \quad (\text{A.1})$$

where *sd* is the standard deviation of the outlier-free results of at least three measurements of a reagent blank solution (A.5).

A.6.3.3 Actual working detection limits are dependent on the type of instrumentation, detection device and sample introduction system used, and on the sample matrix. Therefore, these concentrations can vary between different instruments.

A.7 Expression of results

State as many significant figures as acceptable, but not more than three significant figures, according to the precision of the measuring values.

EXAMPLE 1 Lead (Pb) 0,042 µg/ml.

EXAMPLE 2 Zinc (Zn) 3,9 µg/ml.

Annex B (normative)

Determination of potassium permanganate consumption

B.1 Principle

Determination of the amount of a material that is oxidized by potassium permanganate after the glove sample is extracted in water.

B.2 Apparatus

Use typical laboratory apparatus and, in particular, the following.

B.2.1 Erlenmeyer flask, of 100 ml capacity.

B.2.2 Balance, accurate up to 0,000 1 g.

B.3 Reagents

Use only reagents of recognized analytical grade, except for reference materials and distilled water.

B.3.1 Potassium permanganate standard solution (KMnO₄), 0,002 M.

B.3.2 Sulphuric acid (H₂SO₄), containing 1:2 of H₂SO₄:H₂O.

B.3.3 Sodium oxalate standard solution (Na₂C₂O₄), 0,005 M.

B.3.4 Distilled water.

B.4 Standard solutions

B.4.1 Potassium permanganate standard solution (0,002 M)

Dissolve approximately 0,33 g of potassium permanganate in water to bring the total volume to 1 000 ml. Store in a light-blocking stoppered bottle. When needed, use 0,005 M sodium oxalate solution to standardize.

B.4.2 Sodium oxalate standard solution (0,005 M)

Dissolve 0,670 0 g of anhydrous sodium oxalate in water to bring the total volume to 1 000 ml. Store in a light-blocking stoppered bottle. Use within a month of preparation.

B.5 Determination

Add 100 ml of water, 5 ml of sulphuric acid, 5 ml of potassium permanganate into an Erlenmeyer flask. Boil for 5 min, then discard the solution and wash the flask with water.

Add 100 ml of sample solution, 5 ml of sulphuric acid, and 10 ml of potassium permanganate. Boil for 5 min. For a blank solution, use 100 ml of distilled water instead of the sample solution.

Immediately after boiling, remove the flask from the hot plate and add 10 ml of sodium oxalate to decolourise the solution. Titrate the solution with 0,002 M potassium permanganate until a slight red colour remains in the solution without fading away.

B.6 Expression of result

The potassium permanganate consumption is determined using Formula (B.1):

$$\text{Potassium permanganate consumed } (\mu\text{g/ml}) = \frac{(a-b) \times 0,316 \times f \times 1\,000}{100} \quad (\text{B.1})$$

where

- a* is the amount of 0,002 M potassium permanganate used for the sample solution test, expressed in millilitres;
- b* is the amount of 0,002 M potassium permanganate used for the blank test, expressed in millilitres;
- f* is the factor for 0,002 M potassium permanganate.

Annex C **(normative)**

Determination of evaporated residue

C.1 Principle

Determination of the amount of substances transported from the sample into an extraction solution.

C.2 Apparatus

Use typical laboratory apparatus and, in particular, the following.

C.2.1 Erlenmeyer flasks, of 100 ml, 250 ml, and 500 ml capacity.

C.2.2 Evaporating dish.

C.2.3 Water bath.

C.2.4 Desiccators.

C.2.5 Balance, accurate up to 0,000 1 g.

C.3 Reagents

C.3.1 Ethanol (C₂H₆O), 10 %.

C.3.2 Distilled water.

C.4 Determination

Place an empty evaporating dish in a normal oven for 1 h at 105 °C, let it cool in a desiccator and weigh. Place 100 ml of a sample solution in the evaporation dish and heat on a water bath until the solution evaporates to dryness.

After drying, place the evaporating dish in the oven for further 2 h at 105 °C, let it cool in a desiccator and re-weigh.

For a blank solution, place 100 ml of the same the extraction medium in an evaporation dish and conduct the test using the same procedure.

C.5 Expression of result

The evaporation residue is determined using Formula (C.1):

$$\text{Evaporation residue } (\mu\text{g/ml}) = \frac{(a-b) \times 1\,000}{v} \quad (\text{C.1})$$

where

- a* is the amount of residue obtained from the sample solution, expressed in milligrams;
- b* is the amount of residue obtained from the blank solution, expressed in milligrams;
- v* is the volume of the sample solution used, expressed in millilitres.

Annex D (normative)

Determination of phthalate content

D.1 Principle

To extract, identify and quantify monomeric phthalates (with wider application to other types of plasticisers) contained in PVC samples. The extraction method uses Soxhlet extraction apparatus with diethyl ether. The total diethyl ether extractable plasticiser content is calculated by mass with gas chromatography-mass spectroscopy (GC-MS) detection to identify and quantify individual phthalates.

D.2 Apparatus

Use typical laboratory apparatus and, in particular, the following.

- D.2.1 **Balance**, accurate up to 0,000 1 g.
- D.2.2 **Oven**.
- D.2.3 **Soxhlet extractor with siphon cup**.
- D.2.4 **Soxhlet thimble**.
- D.2.5 **Condenser**.
- D.2.6 **Steam bath**.
- D.2.7 **Desiccator**.
- D.2.8 **Flat bottom flask**, of 150 ml capacity.
- D.2.9 **Volumetric flask**, of 200 ml capacity.
- D.2.10 **Gas chromatography-mass spectrometer**.

D.3 Reagents

Use reagents of analytical grade.

- D.3.1 **Diethyl ether**.
- D.3.2 ***n*-hexane**.
- D.3.3 **Di-isononyl phthalate (DINP)**, CAS No. 28553-12-0.
- D.3.4 **Di-(2-ethylhexyl) phthalate (DEHP)**, CAS No. 117-81-7.

D.3.5 Di-*n*-octyl phthalate (DNOP), CAS No. 117-84-0.

D.3.6 Di-iso-decyl phthalate (DIDP), CAS No. 26761-40-0.

D.3.7 Butyl benzyl phthalate (BBP), CAS No. 85-68-7.

D.3.8 Di-butyl phthalate (DBP), CAS No. 84-74-2.

D.4 Standard solutions

Prepare a series of individual stock standard solutions of the individual phthalate esters in *n*-hexane as shown in [Table D.1](#).

Table D.1 — Stock solutions

Phthalate ester	DIDP	DINP	DBP	BBP	DNOP	DEHP
Concentration, µg/ml	5 000	5 000	200	200	200	200

Where appropriate from the stock standard solutions, prepare two sets of five phthalate esters GC-MS calibration solutions in *n*-hexane to the maximum linear concentration shown in [Table D.2](#) (Calibration Set 1), and [Table D.3](#) (Calibration Set 2).

Table D.2 — Calibration Set 1

Phthalate ester	DINP	DBP	BBP	DEHP
Concentration, µg/ml	5 000	20	20	20

Table D.3 — Calibration Set 2

Phthalate ester	DIDP	DNOP
Concentration, µg/ml	5 000	20

D.5 Determination

D.5.1 Sampling, extraction, and gravimetric analysis for phthalate plasticisers

D.5.1.1 Place the sample in a pre-weighed 150 ml flat bottom flask and heat in an oven at $(105 \pm 5) ^\circ\text{C}$ for (30 ± 5) min. Allow to cool in a desiccator.

D.5.1.2 Weigh the flask and sample. Use a scalpel or other appropriate cutting utensil to cut a representative portion from the sample into small pieces, $\Phi < 5$ mm.

D.5.1.3 Weigh accurately $(2 \pm 0,2)$ g of the pieces into a Soxhlet thimble and add cotton wool to the top of the thimble.

D.5.1.4 Add approximately (50 ± 10) ml of diethyl ether into the flask. Reflux gently for $6 \text{ h} \pm 30$ min. Allow sufficient time for the diethyl ether to cool.

D.5.1.5 Evaporate the diethyl ether completely by mean of steam bath.

D.5.1.6 Place the flask in an oven at $(105 \pm 5) ^\circ\text{C}$ for (30 ± 5) min. Allow to cool in a desiccator and weigh.

D.5.1.7 Repeat the drying and cooling cycles until the difference between two consecutive weighings are not more than 0,0005 g. A blank solution shall be run consecutively.

D.5.2 Preparation of sample extract solution for gas chromatography-mass spectrometry (GC-MS)

D.5.2.1 To the weighed extract ([D.5.1](#)), add (50 ± 2) ml of *n*-hexane.

D.5.2.2 Place a stopper to the flask and swirl to completely dissolve the extract.

D.5.2.3 Decant the solution into a 200 ml volumetric flask, repeatedly rinsing the flask with *n*-hexane.

D.5.2.4 Add *n*-hexane to the volumetric flask to bring the total volume to 200 ml.

D.5.2.5 Prepare (if necessary) further diluted solutions using *n*-hexane such that the final concentration in solution is within the linear calibration concentration for phthalate present.

D.5.2.6 Transfer a portion of the *n*-hexane solution into a capped vial for GC-MS analysis.

D.5.2.7 The samples can be analysed for phthalate plasticisers by conditioning the GC-MS as follows.

For gas chromatograph (GC) Model 5890¹⁾ with a Hewlett Packard 5971A²⁾ Mass Selective Device (MSD) with scan range 50 atomic mass unit to 500 atomic mass unit, and column 30 m, 0,25 mm I.D. and 0,15 µm film thickness, 50 % dimethyl to 50 % diphenyl-polysiloxane, e.g. DB-17HT.

Carrier gas:	Helium
Flow rate:	0,8 ml/min
Injector temperature:	290 °C
Injection volume:	2 µl
Injection type:	Splitless
Detector:	MSD
Transfer line temperature:	280 °C
MSD mode:	Electron impact
Temperature programme:	40 °C for 4 min. From 40 °C to 300 °C at 10 °C/min. Isothermal 4,00 min. Total run time is 34 min.

1) This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of the product named. Equivalent products can be used if they can be shown to lead to the same results.

2) This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of the product named. Equivalent products can be used if they can be shown to lead to the same results.

Because of the differences between various makers and models of satisfactory instruments, the instructions provided by the manufacturer of the particular instrument can be used.

D.6 Expression of results

D.6.1 Compare the obtained GC-MS spectra to known spectra of phthalate ester standards to allow qualitative identification of phthalate ester plasticisers or any other compounds.

D.6.2 Plot a calibration graph of the response against the known standard concentrations.

D.6.3 From the calibration graph determine the response of phthalate ester found in the blank and sample. Interpolate the concentration of phthalate ester in µg/ml correcting for any dilutions as follows.

a) Gravimetric analysis:

$$\% \text{ extract (m/m)} = \frac{w_E}{w_S} \times 100 \quad (\text{D.1})$$

where

w_E is the weight of the extract, expressed in grams;

w_S is the weight of the sample, expressed in grams.

b) GC-MS analysis:

$$\% \text{ extract (m/m)} = \frac{E_S}{w_S} \times \frac{200 \text{ ml}}{10\,000} \times d_f \quad (\text{D.2})$$

where

E_S is the extract of the solution, expressed in micrograms per millilitres;

w_S is the weight of the sample, expressed in grams;

d_f is the dilution factor.

Annex E (informative)

Precision

E.1 General

An interlaboratory test programme (ITP) for precision evaluation was conducted using the precision procedures and guidelines described in ISO/TR 9272:2005.

E.2 Details of test programmes

The precisions were determined for determination of heavy metal, determination of potassium permanganate consumption, and determination of evaporated residue. The results are given in [Tables E.2, E.3](#), and E.4, respectively.

NOTE For the determination of heavy metal, only the precision of Zn element was determined. Other heavy metals, i.e. As, Cd, Cr, and Pb were reported as “not detected” by all participating laboratories.

A type 1 precision was evaluated using three different gloves (Material 1 to Material 3), supplied to each of the laboratory participating in the ITP on each of two test days and one week apart. Each test was run duplicate and the average was obtained. The precision analysis was based on test result data, i.e. two test result values per laboratory. Details of the materials being tested are given in [Table E.1](#).

Table E.1 — Details of gloves used for ITP

Material No.	Gloves
1	Powder-free, natural latex gloves
2	Pre-powdered, natural latex gloves
3	Powder-free, nitrile latex gloves

E.3 Precision results

Table E.2 — Precision for the determination of heavy metal - Zn element ($\mu\text{g/ml}$)

Material	Mean level	Within laboratory			Between laboratories			No. of laboratories
		s_r	r	(r)	s_R	R	(R)	
1	5,59	0,87	2,43	43,5	1,45	4,07	72,8	4
2	9,42	1,25	3,51	37,2	2,91	8,15	86,5	4
3	10,7	3,48	9,75	91,2	13,5	37,9	354	4
Average		-	5,23	57,3	-	16,7	171	-

s_r within-laboratory standard deviation (in measurement units);

r repeatability (in measurement units);

(r) repeatability (in percent of mean level);

s_R between-laboratory standard deviation (for total between-laboratory variation in measurement units);

R reproducibility (in measurement units);

(R) reproducibility (in percent of mean level).

Table E.3 — Precision for the determination of potassium permanganate consumption (µg/ml)

Material	Mean level	Within laboratory			Between laboratories			No. of laboratories
		s_r	r	(r)	s_R	R	(R)	
1	11,0	0,67	1,87	17,1	3,43	9,61	87,6	5
2	7,59	1,44	4,03	53,1	1,32	3,71	48,9	5
3	4,55	0,87	2,43	53,4	5,65	15,8	348	5
Average		-	2,78	41,2	-	9,71	162	-

s_r within-laboratory standard deviation (in measurement units);
 r repeatability (in measurement units);
(r) repeatability (in percent of mean level);
 s_R between-laboratory standard deviation (for total between-laboratory variation in measurement units);
 R reproducibility (in measurement units);
(R) reproducibility (in percent of mean level).

Table E.4a — Precision for the determination of evaporation residue - extraction by water (µg/ml)

Material	Mean level	Within laboratory			Between laboratories			No. of laboratories
		s_r	r	(r)	s_R	R	(R)	
1	80,3	16,6	46,3	57,7	37,3	104	130	5
2	107	17,4	48,9	45,6	49,6	139	130	5
3	58,4	9,03	25,3	43,3	67,5	189	324	5
Average		-	40,2	48,9	-	144	195	-

s_r within-laboratory standard deviation (in measurement units);
 r repeatability (in measurement units);
(r) repeatability (in percent of mean level);
 s_R between-laboratory standard deviation (for total between-laboratory variation in measurement units);
 R reproducibility (in measurement units);
(R) reproducibility (in percent of mean level).

Table E.4b — Precision for the determination of evaporation residue - extraction by 10 % ethanol (µg/ml)

Material	Mean level	Within laboratory			Between laboratories			No. of laboratories
		s_r	r	(r)	s_R	R	(R)	
1	78,7	22,6	63,2	80,6	58,2	163	208	5
2	91,3	9,36	26,2	28,7	54,8	154	168	5
3	45,3	9,01	25,2	55,7	51,1	143	316	5
Average		-	38,2	55,0	-	153	231	-

s_r within-laboratory standard deviation (in measurement units);
 r repeatability (in measurement units);
(r) repeatability (in percent of mean level);
 s_R between-laboratory standard deviation (for total between-laboratory variation in measurement units);
 R reproducibility (in measurement units);
(R) reproducibility (in percent of mean level).

Bibliography

- [1] ISO 6486-2:1999, *Ceramic ware, glass-ceramic ware and glass dinnerware in contact with food — Release of lead and cadmium — Part 2: Permissible limits*
- [2] ISO 11885:2007, *Water quality — Determination of selected elements by inductively coupled plasma optical emission spectrometry (ICP-OES)*
- [3] IEC 62321:2008 *Electronic products – Determination of levels of six regulated substances (lead, mercury, cadmium, polybrominated biphenyls, polybrominated diphenyl ethers)*
- [4] ISO/TS 13530, *Water quality — Guidance on analytical quality control for chemical and physicochemical water analysis*
- [5] ISO/TR 9272:2005, *Rubber and rubber products — Determination of precision for test method standards*
- [6] YOON F.K., & CHUAH P.G. eds. *Notes on NR Examination Glove Manufacture*. Rubber Research Institute of Malaysia, 1988
- [7] *Food Contact Rubber 2 – Products, Migration and Regulation*, Rapra Review Reports Martin J. Forrest. Volume 16, Number 2, 2006
- [8] *Guideline for Drinking - Water Quality*, Volume 2- Health Criteria and Other Supporting Information, World Health Organization, Geneva, 1984
- [9] *Specifications and Standards for Foods, Food Additives*, under the Food Sanitation Law (Abstract) JETRO, January 2003
- [10] BfR Recommendation XXI. Commodity Articles Based on Natural and Synthetic Rubber

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™