

Carbonaceous products for the production of aluminium — Baked anodes and shaped carbon products — Determination of the coefficient of linear thermal expansion

ICS 71.100.10

National foreword

This British Standard reproduces verbatim ISO 14420:2005 and implements it as the UK national standard.

The UK participation in its preparation was entrusted to Technical Committee CII/24, Raw materials for the aluminium industry, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the ISO title page, pages ii to iv, pages 1 to 5 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 24 August 2005

© BSI 24 August 2005

INTERNATIONAL
STANDARD

ISO
14420

First edition
2005-07-01

**Carbonaceous products for the
production of aluminium — Baked
anodes and shaped carbon products —
Determination of the coefficient of linear
thermal expansion**

*Produits carbonés utilisés pour la production de l'aluminium — Anodes
cuites et produits carbonés formés — Détermination du coefficient de
dilatation thermique*



Reference number
ISO 14420:2005(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14420 was prepared by Technical Committee ISO/TC 226, *Materials for the production of primary aluminium*.

Introduction

This International Standard is based on DIN 51909:1984 prepared by the committee NMP 281 "Prüfverfahren für Kohlenstoff und Graphit" in DIN Deutsches Institut für Normung e.V., Berlin.

Carbonaceous products for the production of aluminium — Baked anodes and shaped carbon products — Determination of the coefficient of linear thermal expansion

1 Scope

This International Standard specifies a method to determine the coefficient of linear thermal expansion of carbonaceous or graphite materials (solid materials) for the production of aluminium between 20 °C and 300 °C. It applies to baked anodes and shaped carbon products.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6906, *Vernier callipers reading to 0,02 mm*

ISO 3611, *Micrometer callipers for external measurement*

DIN 1333, *Presentation of numerical data*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

linear thermal expansion coefficient

thermal expansion coefficient $\alpha(\vartheta)$ correlated with the length change of a body with temperature

NOTE The linear thermal expansion coefficient is calculated from the following formula.

$$\alpha(\vartheta) = \frac{1}{l} \cdot \frac{dl}{d\vartheta} \quad (1)$$

where

$\alpha(\vartheta)$ is the linear expansion coefficient;

l is the length of the test specimen at temperature ϑ ;

$\frac{dl}{d\vartheta}$ is the length change with temperature.

3.2

average linear thermal expansion coefficient

average linear expansion coefficient $\alpha(\vartheta_1, \vartheta_2)$ correlated with the length change of a body with temperature

NOTE The average linear expansion coefficient is calculated from the following formula

$$\alpha(\vartheta_1; \vartheta_2) = \frac{1}{l_1} \cdot \frac{l_2 - l_1}{\vartheta_2 - \vartheta_1} = \frac{1}{l_1} \cdot \frac{\Delta l}{\Delta \vartheta} \quad (2)$$

$$\Delta \vartheta = \vartheta_2 - \vartheta_1 \quad (3)$$

$$\Delta l = l_2 - l_1 \quad (4)$$

where

ϑ_1 is the lower limit of the temperature interval, in °C;

ϑ_2 is the upper limit of the temperature interval, in °C;

l_1 is the length of the test specimen, in mm, at temperature ϑ_1 ;

l_2 is the length of the test specimen at temperature ϑ_2 ;

α is the mean linear thermal expansion coefficient, in units of 1/K, of the sample holder and the push-rod for the temperature range under consideration.

4 Principle

The average linear thermal expansion coefficient is determined by means of a push-rod dilatometer. The test specimen is contained in a sample holder made from low-expansivity material (such as flint glass). It is heated in a furnace and the length change is transmitted to a mechanical, optical, or electronic measuring system outside the furnace by a push-rod.

The average linear thermal expansion coefficient is calculated from the measured length change, the original length, and the temperature change of the test specimen, taking the expansion of the sample holder and the push-rod into account. Unless otherwise stated, the determination is performed between a lower limit for the temperature interval of 20 °C (i.e. room temperature) and an upper limit for the temperature interval of 300 °C max.

5 Apparatus

5.1 Dilatometer, with sample holder and push-rod, for example, made from flint glass, as well as a mechanical, optical or electronic length-measurement device (error limits $\pm 0,5 \mu\text{m}$), for temperatures above 300 °C in a vacuum or in a protective gas atmosphere;

5.2 Furnace, capable of holding the temperature constant to within $\pm 0,5 \%$ over the length of the test specimen;

5.3 Temperature-measuring device, for example, a thermocouple with indicating instrument, accurate to within $\pm 0,5 \%$, to determine the average test-specimen temperature;

5.4 Instrument for measuring lengths, with error limit of $\pm 0,2 \%$, for example vernier calliper according to ISO 6906 or micrometer calliper according to ISO 3611;

5.5 Calibration samples, made from materials with known thermal expansivity in the range of the material to be measured and made with similar geometry. The thermal expansivity of calibration samples shall have been predetermined by the producer of the measuring equipment or by a recognised calibration authority.

6 Specimens

Prepare a test specimen of cylindrical or prismatic geometry. The cylinder diameter or the prism transverse edge length shall be at least twice the diameter of the largest structural constituent (for example maximum grain size) of the material to be examined, and in no case smaller than 4 mm (typically 30 to 50 mm). The length of the test specimens shall be at least 25 mm, but preferably should be 50 mm to 120 mm.

The test specimens shall be machined on all surfaces by turning or grinding, so that the surfaces in contact with the push-rod do not deviate from plane parallelism by more than 0,2 mm.

A hole of minimum 1 mm depth may be drilled in the middle of a long side of the test specimen to hold the joint of the thermocouple.

Remove existing stresses in a test specimen by annealing at 1 000 °C in a non-oxidizing atmosphere.

7 Procedure

7.1 Calibration

Calibrate the dilatometer according to 7.2 using calibrated samples.

7.2 Measurement

Measure the sample length l_1 of the test specimen at temperature ϑ_1 .

Insert the test specimen into the dilatometer, taking care that the specimen ends are firmly in contact with the push-rod.

Insert the joint of the thermocouple into the hole in the side of the test specimen where required.

Measure the original length l_1 of the test specimen at the lower limit of the temperature interval ϑ_1 . If the push-rod planes contacting the specimen end surfaces are not spherically or conically shaped, use connecting pieces to realize a point contact to the specimen end planes.

At the beginning of the measurement, set the measuring system to zero by either adjusting the zero point of the apparatus, or marking on the recording chart or the photosensitive paper. When using double dilatometers, with the two dilatometer motions recorded orthogonally, the assignment of the recording axes to the dilatometers shall also be determined and recorded.

Position the furnace (which may be preheated) around the sample holder. Allow the test specimen to attain the upper limit of the temperature interval ϑ_2 . Then measure and record the length of the test specimen l_2 .

If the upper limit of the temperature interval ϑ_2 is above 300 °C, avoid oxidation of the test specimen by applying a suitable protection gas or vacuum.

8 Evaluation

Calculate the average linear expansion coefficient, in units of 1/K, according to the following equation:

$$\alpha(\vartheta_1; \vartheta_2) = \frac{1}{l_1} \cdot \frac{l_2 - l_1}{\vartheta_2 - \vartheta_1} - \alpha_k = \frac{1}{l_1} \cdot \frac{\Delta l}{\Delta \vartheta} - \alpha_k \quad (5)$$

where

ϑ_1 is the lower limit of the temperature interval, in °C;

ϑ_2 is the upper limit of the temperature interval, in °C;

l_1 is the length of the test specimen, in mm, at temperature ϑ_1 ;

l_2 is the length of the test specimen, in mm, at temperature ϑ_2 .

α_k is the mean linear thermal expansion coefficient, in units of 1/K, of the sample holder and the push-rod for the temperature range under consideration.

Rounding to the last significant decimal place shall be done in accordance with DIN 1333.

9 Test report

The test report shall include the following information:

- a) type and marking of specimens;
- b) a reference to this International Standard;
- c) pretreatment of the specimens, if relevant;
- d) number of specimens;
- e) temperature range of measurement;
- f) average linear thermal expansion coefficient, in units of $10^{-6} \times K^{-1}$, rounded to the nearest $0,1 \times 10^{-6} \times K^{-1}$, individual values, mean value;
- g) agreed conditions deviating from this International Standard;
- h) test date.

10 Precision

The precision of this method has been calculated according to ASTM E691, resulting in the following values:

The repeatability:

$$r = 0,1 \mu\text{m/mK}$$

The reproducibility:

$$R = 0,17 \mu\text{m/mK}$$

Bibliography

- [1] DIN 863-1, *Verification of geometrical parameters — Micrometers — Part 1: Standard design micrometer callipers for external measurement; concepts, requirements, testing*
- [2] DIN 1319-3, *Fundamentals of metrology — Part 3: Evaluation of measurements of a single measurand, measurement uncertainty*
- [3] DIN 51045-1, *Determination of the thermal expansion of solids — Part 1: Basic rules*
- [4] DIN 51045-2, *Determination of the change of length of solids by thermal effect; testing of fired fine ceramic materials*
- [5] DIN 51045-3, *Determination of the change of length of solids by thermal effect; testing of non-fired fine ceramic materials*
- [6] DIN 51045-4, *Determination of the change of length of solids by thermal effect; testing of fired ordinary ceramic materials*
- [7] DIN 51045-5, *Determination of the change of length of solids by thermal effect; testing of non-fired ordinary ceramic materials*
- [8] DIN 51909:1998, *Testing of carbon materials — Determination of coefficient of linear thermal expansion — Solid materials*
- [9] ASTM C372, *Standard method of test for linear thermal expansion of fired whiteware products by the dilatometer method* (reapproved 1970)
- [10] ASTM E691, *Standard Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method*
- [11] KOHLRAUSCH, F., *Praktische Physik*, Stuttgart 1968, Vol. 1, pp. 316 to 319, Chapter 4.3.2 "Wärmeausdehnung"
- [12] METZ, A., *A new all-purpose dilatometer according to Bollenrath* (in German), ATM 303 (1961) R 61 to R 72
- [13] THORMANN, P., *Investigations with a dilatometer in the field of ceramic raw materials and materials* (in German), *Ber. dt. Keram. Ges.* 46 (1969), pp. 583 to 586
- [14] THORMANN, P., *Precision of dilatometric investigations and their significance in ceramic laboratories* (in German), *Ber. dt. Keram. Ges.* 47 (1970), pp. 769 to 773
- [15] OTTO, J. and THOMAS, W., *The thermal Expansion of Quartz Glass in the Temperature Range 0 to 1060°C* (in German), *Z. f. Phys.* 175 (1963), pp. 334 to 337

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.