

BS ISO 15028:2014



BSI Standards Publication

**Plastics — Aromatic
isocyanates for use in the
production of polyurethanes —
Determination of hydrolysable
chlorine**

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 15028:2014. It supersedes BS ISO 15028:2004 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/42, Fibre reinforced thermosetting plastics and prepregs.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 81990 2

ICS 83.080.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2014.

Amendments issued since publication

Date	Text affected
------	---------------

**Plastics — Aromatic isocyanates for
use in the production of polyurethanes
— Determination of hydrolysable
chlorine**

*Plastiques — Isocyanates aromatiques pour utilisation dans
la production de polyuréthannes — Détermination du chlore
hydrolysable*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
Introduction		v
1 Scope		1
2 Normative references		1
3 Terms and definitions		1
4 Principle		1
5 Interference		2
6 Sampling		2
7 Test conditions		2
8 Reagents		2
9 Apparatus		2
10 Procedure		3
11 Expression of results		3
12 Precision and bias		3
12.1 Precision.....		3
12.2 Bias.....		4
13 Test report		4
Bibliography		5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information.

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 12, *Thermosetting materials*.

This second edition cancels and replaces the first edition (ISO 15028:2004), which has been technically revised.

Introduction

No International Standard for the determination of hydrolysable chlorine in isocyanates has been published. The main sources of hydrolysable chlorine in isocyanates are carbamoyl chloride and dissolved phosgene from the manufacturing process. Both of these compounds react with alcohols and water, forming ureas, carbamates, carbon dioxide and hydrochloric acid. These acidic materials neutralize basic catalysts used in polyurethane production, thus adversely affecting processing properties. This test method is based on and is technically equivalent to ASTM D 4663.

Plastics — Aromatic isocyanates for use in the production of polyurethanes — Determination of hydrolysable chlorine

SAFETY STATEMENT — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory requirements.

1 Scope

This International Standard specifies a method for the determination of the hydrolysable-chlorine content of toluene-2,4-diisocyanate, toluene-2,6-diisocyanate or mixtures of the two. This test method may also be applied to other isocyanates of suitable solubility, such as crude or refined polymeric isocyanates.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*

ISO 4787, *Laboratory glassware — Volumetric instruments — Methods for testing of capacity and for use*

ISO 6353-2, *Reagents for chemical analysis — Part 2: Specifications — First series*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

polyurethane

polymer prepared by the reaction of an organic di- or polyisocyanate with compounds containing two or more hydroxyl groups

3.2

hydrolysable chlorine

organic or inorganic chlorine compounds formed in the production of isocyanates that react with methanol under the conditions of the test to liberate hydrogen chloride

4 Principle

The hydrolysable chlorine reacts with methanol, liberating hydrogen chloride. The titratable chlorides are then determined potentiometrically using a standard silver nitrate solution.

5 Interference

Thiocyanate, cyanide, sulfide, bromide, iodide and other substances capable of reacting with silver ions, as well as substances capable of reducing silver ions in acid solution, will interfere with the determination.

6 Sampling

Since organic isocyanates react with atmospheric moisture, take special precautions in sampling. Usual sampling methods (for example sampling an open drum with a thief), even when conducted rapidly, can cause contamination of the sample with insoluble ureas; therefore, blanket the sample with a dry inert gas (e.g. nitrogen, argon or dried air) at all times.

WARNING — Organic isocyanates are hazardous when absorbed through the skin, or when the vapours are breathed in. Provide adequate ventilation and wear protective gloves and eyeglasses.

7 Test conditions

Since isocyanates react with moisture, keep the laboratory humidity low preferably below 50 % relative humidity.

NOTE If the relative humidity is greater than 50 % relative humidity, work quickly to minimize exposure of the sample to the air.

8 Reagents

Reagent-grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of ISO 6353-2. Other grades may be used, provided that it is first determined that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

Unless otherwise indicated, references to water shall be understood to mean grade 2 water as defined by ISO 3696:1987.

8.1 Concentrated nitric acid, HNO_3 , specific gravity 1,42, conforming to ISO 6353-2.

8.2 Methanol, CH_3OH , conforming to ISO 6353-2.

8.3 Silver nitrate, standard solution (0,01 M).

Standardize with standard hydrochloric acid, either gravimetrically or potentiometrically, frequently enough to detect changes of 0,000 5 M.

9 Apparatus

9.1 Titrator, automatic (preferred) or manual, equipped with a silver/silver chloride electrode pair and a 50 ml burette, the latter conforming to ISO 385.

9.2 Pipette, 50 ml, one-mark, conforming to ISO 648.

9.3 Beakers, 400 ml, conforming to ISO 4787.

9.4 Magnetic stirrer, equipped with an inert stirring bar, **or equivalent stirrer**.

9.5 Laboratory balance, capable of weighing out test portions to within $\pm 0,01$ g.

10 Procedure

10.1 Weigh (by difference to the nearest 0,01 g) 9 g to 11 g of the sample (or 18 g to 22 g of the sample if the hydrolysable-chlorine content is expected to be less than 0,01 %) from a sampling weighing bottle into a clean, dry 400 ml beaker. Add 50 ml of methanol and stir. Stir continually while the reaction starts, at which point the beaker will become warm and crystals may form on the sides of the beaker (see the Note). Fill the beaker half-full with water (add the water quickly to keep the reactants from solidifying and to minimize the loss of HCl) and boil gently for 30 min.

NOTE Some isocyanates will not react readily and slight warming may be necessary to initiate the reaction. Other isocyanates may react, as indicated by warming of the reactants, but may not form crystals.

10.2 Wash the sides of the beaker with water and remove and rinse the stirring bar, adding the rinsings to the beaker. Cool the beaker in an ice bath to about 10 °C and add 10 drops of HNO₃. Titrate potentiometrically with 0,01 M AgNO₃ (8.3) using a silver/silver chloride electrode pair (see 9.1) **with stirring**. If the chloride content is greater than 0,2 %, use 0,1 M instead of 0,01 M AgNO₃ solution.

Statistical data were developed in a round robin in which cooling to 10 °C was used. Other laboratories report that cooling to about 20 °C is sufficient. A temperature of 20 °C may be used if it is established that the results do not differ statistically from results obtained with cooling to 10 °C.

11 Expression of results

Calculate the hydrolysable chlorine, as a percentage by mass, as follows:

$$\text{Hydrolysable chlorine} = 3,55 \times V \times c/m$$

where

V is the volume of AgNO₃ solution required to titrate the test portion, in ml;

c is the exact concentration of the AgNO₃ solution, in mol/l;

m is the mass of the test portion taken, in g;

3,55 is a constant combining the atomic mass of chlorine (35,5), the conversion from mg to g (1 000), and the conversion to percent (100).

12 Precision and bias

12.1 Precision

The precision statement is based on a limited round robin conducted among three laboratories; therefore, this test method should not be used as a referee test method in cases of dispute.

12.1.1 Repeatability

It is estimated that duplicate results obtained by the same analyst using the same equipment on the same day should be considered as suspect if they differ by more than 0,000 5 % at hydrolysable-chlorine concentrations of 0,001 % to 0,2 %.

12.1.2 Reproducibility

It is estimated that results reported by different laboratories should be considered as suspect if they differ by more than 0,003 % hydrolysable chlorine.

12.2 Bias

Bias is the difference between the expectation of the test results and an accepted reference value. There are no recognized standards by which to estimate the bias of this test method.

13 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) all details necessary to identify the product analysed (such as manufacturer, product type, lot or notebook numbers and date of manufacture, as required);
- c) the result obtained, expressed as % hydrolysable chlorine to the nearest 0,001 % hydrolysable chlorine;
- d) the date of the analysis;
- e) any incident or detail not stipulated in this International Standard which may have influenced the result.

Bibliography

- [1] ASTM D 4663, *Standard Test Method for Polyurethane Raw Materials Determination of Hydrolyzable Chlorine of Isocyanates*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™