BS ISO 15096:2014



BSI Standards Publication

Jewellery — Determination of silver in 999 $^{0}/_{00}$ silver jewellery alloys — Difference method using ICP-OES



BS ISO 15096:2014 BRITISH STANDARD

National foreword

This British Standard is the UK implementation of ISO 15096:2014. It supersedes BS ISO 15096:2008 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/53, Specifications and test methods for jewellery and horology.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 74807 3 ICS 39.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2014.

Amendments/corrigenda issued since publication

Date Text affected

INTERNATIONAL STANDARD

ISO 15096:2014 15096

Second edition 2014-12-15

Jewellery — Determination of silver in 999 $^0/_{00}$ silver jewellery alloys — Difference method using ICP-OES

Joaillerie, bijouterie — Dosage de l'argent dans de l'argent 999 º/oo — Méthode de la differénce utilisant ICP OES



BS ISO 15096:2014 **ISO 15096:2014(E)**



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Published in Switzerland

Con	tents	Page
Forew	vord	iv
Intro	luction	v
1	Scope	1
2	Normative references	
3	Principle	1
4	Sampling	
5	Reagents	
6	Apparatus	
7	Procedure 7.1 Sample solution 7.2 Silver matrix calibration solutions (10 g/l) 7.3 Aqua regia matrix calibration solutions	2
	7.4 Measurements	3
8	Calculation and expression of results 8.1 Calibration curves 8.2 Calculation 8.3 Repeatability	3
9	Test report	
-	x A (normative) Wavelengths	
	graphy	

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: <u>Foreword - Supplementary information</u>.

The committee responsible for this document is ISO/TC 174, Jewellery.

This second edition cancels and replaces the first edition (ISO 15096:2008), which has been technically revised with the following changes:

- a) change in the scope that this method is the referee method;
- b) addition of silver and silver nitrate in <u>Clause 5</u>;
- c) addition of a warning in <u>Clause 7</u> that suitable health and safety procedures should be followed;
- d) change of sample solution in 7.1;
- e) split of 7.2 "Calibration solution" into 7.2 "Silver matrix calibration solutions" and 7.3 "Aqua regia matrix calibration solutions";
- f) change of 8.2 "Method of calculation";
- g) change of repeatability to 0,1 ‰;
- h) amendment of wavelengths in Table A.1;
- i) standard editorially revised.

Introduction

The following definitions apply in understanding how to implement an ISO International Standard and other normative ISO deliverables (TS, PAS, IWA).

- "shall" indicates a requirement;
- "should" indicates a recommendation;
- "may" is used to indicate that something is permitted;
- "can" is used to indicate that something is possible, for example, that an organization or individual is able to do something.

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.1 defines a requirement as an "expression in the content of a document conveying criteria to be fulfilled if compliance with the document is to be claimed and from which no deviation is permitted."

ISO/IEC Directives, Part 2 (sixth edition, 2011), 3.3.2 defines a recommendation as an "expression in the content of a document conveying that among several possibilities, one is recommended as particularly suitable without mentioning or excluding others, or that a certain course of action is preferred, but not necessarily required, or that (in the negative form) a certain possibility or course of action is deprecated, but not prohibited."

Jewellery — Determination of silver in 999 $^{0}/_{00}$ silver jewellery alloys — Difference method using ICP-OES

1 Scope

This International Standard specifies the analytical procedure for the determination of silver with a nominal content of at least 999 % (parts per thousand) by measuring specific elements listed in Table A.1.

This International Standard specifies a method intended to be used as the recommended method for the determination of fineness in 999 ‰ silver alloys covered by ISO 9202.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11596, Jewellery — Sampling of precious metal alloys for and in jewellery and associated products

3 Principle

The sample is weighed and dissolved in nitric acid to prepare a 10 g/l solution. The suspension, which can be present in that solution, is isolated by centrifugation and dissolved in aqua regia. Both solutions are analysed separately by ICP-OES and the total content of each impurity in the sample is obtained by adding together the results of the two analyses. The silver content is obtained by subtraction of the total content of impurities in the sample from $1\ 000\ \%$.

4 Sampling

The sampling procedure shall be performed in accordance with ISO 11596.

5 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

- **5.1 Hydrochloric acid** (HCl), approximately 30 % to 37 % HCl (mass fraction).
- **5.2 Nitric acid** (HNO₃), approximately 65 % to 70 % HNO₃ (mass fraction).
- **5.3 Stock solution 1** (shall not contain any chloride), all elements given in <u>Table A.1</u> (100 mg/l each) in 1 mol/l HNO₃ (<u>5.2</u>). The solution should be prepared just before use.
- **5.4 Stock solution 2** (may contain both chlorides and nitrates), Al, Au, Cr, Fe, Mg, Ni, Pt, and Sn (100 mg/l each) in 1 mol/l HCl (5.2) or HNO₃ (5.3). The solution should be prepared just before use.
- **5.5** Aqua regia (should be prepared just before use).

Mix three volumes of hydrochloric acid (5.2) and one volume of nitric acid (5.3).

BS ISO 15096:2014 **ISO 15096:2014(E)**

- **5.6 Silver**, of 999,9 ‰ minimum or;
- **5.7 Silver nitrate**, of photographic quality.

6 Apparatus

- 6.1 Customary laboratory apparatus.
- **6.2 ICP OES**, with
- fixed and/or scanning channels,
- optical resolution of 0,02 nm for the relevant elements and a detection limit of 0,05 mg/l or better, and
- capability of background correction.

NOTE For preferably used wavelength, see Annex A.

- **6.3 Analytical balance**, with a reading accuracy of 0,1 mg.
- **6.4 Centrifuge**, suitable for 10 ml to 50 ml tubes and rotating at 3 000 r/min (revolution per minute) or more.

7 Procedure

WARNING — Suitable health and safety procedures should be followed.

7.1 Sample solution

Each sample has to be analysed twice and shall be prepared as follows.

Weigh approximately 500 mg of the sample portion to the nearest 0,1 mg, transfer into a 50 ml beaker, and add 7,5 ml of $\rm H_2O$ and 7,5 ml of $\rm HNO_3$ (5.2). Heat gently until complete dissolution of the sample and continue to heat to expel the nitrogen oxides. Add 10 ml of water. After cooling to room temperature, transfer the solution from the 50 ml beaker to the centrifuge tube. Centrifuge the mixture at 3 000 r/min for 5 min and transfer the liquid phase into a 50 ml volumetric flask. Add 5 ml of water to the residue, centrifuge the mixture again at 3 000 r/min for 5 more minutes, and add the newly formed liquid phase to the 50 ml volumetric flask. This operation is repeated for three times. Make up the volume of the solution with water to 50 ml. Analyse this solution without delay using the calibration solutions specified in 7.2.

Add 2 ml of freshly prepared aqua regia (5.5) to the residue after centrifugation. Heat at 80 °C for 2 h. Cool to room temperature, transfer to a 5 ml volumetric flask, rinse with water, and make up with water to 5 ml. Analyse this solution using the aqua regia calibration solutions specified in 7.3.

7.2 Silver matrix calibration solutions (10 g/l)

Blank solution 1. Weigh approximately 500 mg of silver (5.6) or approximately 787 mg of silver nitrate (5.7) and dissolve as specified in 7.1. Allow to cool and make up to 50 ml with water and mix thoroughly.

Calibration solution 1. Weigh approximately 500 mg of silver (5.6) or approximately 787 mg of silver nitrate (5.7) and dissolve as specified in 7.1. Allow to cool and add 2,5 ml of the stock solution 1 (5.3) and make up the solution up to 50 ml with water and mix thoroughly. This solution is unstable and should be prepared just before use.

7.3 Aqua regia matrix calibration solutions

Blank solution 2. Transfer 20 ml of aqua regia (5.5) into a 50 ml volumetric flask. Make up to 50 ml with water and mix thoroughly.

Calibration solution 2. Transfer 20 ml of aqua regia (5.5) into a 50 ml volumetric flask, add 2,5 ml of the stock solution 2 (5.4), make up to 50 ml with water, and mix thoroughly.

7.4 Measurements

Set up the instrument in accordance with the manufacturer's instructions and choose appropriate background correction positions. A clean torch, spray chamber, and sample uptake tubes shall be used and the plasma shall be stabilized also before use, following the recommendations of the instruments manufacturer.

Spray the calibration solutions 1 and 2 in accordance with the defined instrument calibration procedure and then run the analytical procedure for the sample solutions. The result shall be displayed with enough decimal places to provide an accurate indication of concentrations at the detection limits of the relevant elements.

Each solution shall have a stabilization time of at least 30 s followed by five integrations of at least 5 s each for the determination of the net intensities (i.e. background-corrected).

The rinsing time between each measurement shall be sufficient to allow the signal of each impurity to come back to the baseline.

Each analysis (silver 10 g/l and aqua regia) has to be carried out separately with the calibration solutions specified in 7.2 and 7.3 .

8 Calculation and expression of results

8.1 Calibration curves

Calculate the calibration curves for each element using the blank solutions and the calibration solutions.

8.2 Calculation

By means of the calibration curves (see 8.2), convert the net intensity values into concentration values for both analyses in silver 10 g/l matrix and aqua regia matrix using Formula (1) to calculate the mass ratio of each relevant element (W_i).

$$W_{i} = \frac{c_{i,Ag} \times V_{s,Ag}}{m_{s}} + \frac{c_{i,ar} \times V_{s,ar}}{m_{s}}$$

$$\tag{1}$$

where

 $c_{i,Ag}$ is the concentration of element *i* in the silver (10 g/l) matrix sample solution, in mg/l;

 $V_{s,Ag}$ is the volume of the silver (10 g/l) matrix sample solution, in litres (0,05 l as defined in 7.1);

 $c_{i,ar}$ is the concentration of element *i* in the aqua regia matrix sample solution, in mg/l;

 $V_{s,ar}$ is the volume of the aqua regia matrix sample solution, in litres (0,005 l as defined in 7.1);

 $m_{\rm S}$ is the mass of the metallic sample, in milligrams.

The detection limit is defined as three standard deviations of the concentration of each individual element measured in the blank solution for the corresponding matrix.

BS ISO 15096:2014 **ISO 15096:2014(E)**

The silver fineness (W_{sp}), expressed in parts per thousand (%), is thus calculated using Formula (2):

$$W_{\rm sp} = 1000 - \left(\sum w_{\rm i} \times 1000\right) \tag{2}$$

where

 Σ^{w_i} is the sum of the mass portion of each element found above its detection limit.

8.3 Repeatability

The results of duplicate determinations shall not deviate more than 0.1 % of the precious metal fineness. If the variation is greater than this, the assay shall be repeated.

9 Test report

The test report shall include at least the following information:

- a) identification of the sample including source, date of receipt, form of sample;
- b) sampling procedure;
- c) the method used by reference to this International Standard, i.e. ISO 11490;
- d) precious metals content of the sample, in parts per thousand (‰) by mass, as single values and mean values, with the result reported with four significant figures;
- e) if relevant, any deviations from the method specified in this International Standard;
- f) any unusual features observed during the determination;
- g) date of test;
- h) identification of the laboratory carrying out this analysis;
- i) signature of the laboratory manager and operator.

Annex A (normative)

Wavelengths

Other wavelengths than those specified in <u>Table A.1</u> can be used. In such cases, attention shall be paid to spectral interferences. This table is not exhaustive. If other elements are present, they shall be analysed.

Table A.1 — Silver

Element	Wavelength nm	Alternative nm	Element	Wavelength nm	Alternative nm
Al	396,152		Ni	231,604	352,454
As	193,759a		Pb	220,353	168,220
Au	267,595	242,795	Pd	340,458	360,955
Bi	223,061		Pt	265,945	306,471
Cd	228,802	226,502	Sb	206,833	217,581
Со	228,616	238,892	Seb	196,090	203,985
Cr	205.560	283,563	Sic	251,611	
Cu	324,754		Sn	189,989	
Fe	259,940		Те	214,281	238,578
Mg	280,270	285,213	Ti	336,121	
Mn	260,569	257,610	Zn	206,200	213,856

The used wavelength depends on the type of apparatus, e.g. 193,695 is also commonly used for As.

b The used wavelength depends on the type of apparatus, e.g. 196,026 is also commonly used for Se.

c All vessels and reagent bottles shall be PTFE or plastic.

Bibliography

[1] ISO 9202:1991, Jewellery — Fineness of precious metal alloys





British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

