

BS ISO 15380:2016



BSI Standards Publication

**Lubricants, industrial oils and related products (class L) —
Family H (Hydraulic systems)
— Specifications for hydraulic fluids in categories HETG,
HEPG, HEES and HEPR**

National foreword

This British Standard is the UK implementation of ISO 15380:2016. It supersedes BS ISO 15380:2011 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee MCE/18, Fluid power systems and components.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 87554 0

ICS 75.100

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2016.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

**Lubricants, industrial oils and
related products (class L) — Family H
(Hydraulic systems) — Specifications
for hydraulic fluids in categories
HETG, HEPG, HEES and HEPR**

*Lubrifiants, huiles industrielles et produits connexes (classe L) —
Famille H (Systèmes hydrauliques) — Spécifications applicables aux
fluides hydrauliques des catégories HETG, HEPG, HEES et HEPR*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Sampling	3
4 Requirements of environmentally acceptable hydraulic fluids	3
Annex A (informative) Guidelines for changing fluids from mineral-based oils to environmentally acceptable fluids	13
Annex B (informative) Additional information on shear stability	17
Annex C (informative) Disposal of hydraulic fluids	18
Bibliography	19

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 28, *Petroleum products and related products of synthetic or biological origin*, Subcommittee SC 4, *Classifications and specifications*.

This third edition cancels and replaces the second edition (ISO 15380:2011), which has been technically revised.

Introduction

The specifications for hydraulic fluids based upon mineral oils (H) are described in ISO 11158[1] while the specifications for fire-resistant hydraulic fluids (HF) are given in ISO 12922[2]. This International Standard gives specifications for environmentally acceptable hydraulic fluids (HE). These fluids are readily biodegradable and have a low eco-toxicity. They are designed to minimize the impact upon the environment in the event of a leak or spill.

This International Standard contains three informative annexes. [Annex A](#) contains guidelines for changing fluids from mineral-based oils to environmentally acceptable fluids. [Annex B](#) contains additional information on shear stability. [Annex C](#) covers the disposal of hydraulic fluids.

Lubricants, industrial oils and related products (class L) — Family H (Hydraulic systems) — Specifications for hydraulic fluids in categories HETG, HEPG, HEES and HEPR

WARNING — The handling and use of products as specified in this International Standard can be hazardous if suitable precautions are not observed. This International Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this International Standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. The environmentally acceptable fluids should not present any significant hazard to health when used correctly in hydraulic equipment, observing the supplier's handling recommendations.

1 Scope

This International Standard specifies the requirements for environmentally acceptable hydraulic fluids and is intended for hydraulic systems, particularly hydraulic fluid power systems. The purpose of this International Standard is to provide guidance for suppliers and users of environmentally acceptable hydraulic fluids and for the direction of original equipment manufacturers of hydraulic systems.

This International Standard stipulates the requirements for environmentally acceptable hydraulic fluids at the time of delivery.

Classification of fluids used in hydraulic application is defined in ISO 6743-4. This International Standard encompasses only four of the categories of environmentally acceptable fluids covered by ISO 6743-4. These categories are HETG, HEPG, HEES and HEPR. The minimum content of base fluid for each category shall not be less than 70 % (m/m).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2049, *Petroleum products — Determination of colour (ASTM scale)*

ISO 2160, *Petroleum products — Corrosiveness to copper — Copper strip test*

ISO 2592, *Determination of flash and fire points — Cleveland open cup method*

ISO 3016, *Petroleum products — Determination of pour point*

ISO 3104, *Petroleum products — Transparent and opaque liquids — Determination of kinematic viscosity and calculation of dynamic viscosity*

ISO 3170, *Petroleum liquids — Manual sampling*

ISO 3448, *Industrial liquid lubricants — ISO viscosity classification*

ISO 3675, *Crude petroleum and liquid petroleum products — Laboratory determination of density — Hydrometer method*

ISO 4259, *Petroleum products — Determination and application of precision data in relation to methods of test*

ISO 4263-1, *Petroleum and related products — Determination of the ageing behaviour of inhibited oils and fluids — TOST test — Part 1: Procedure for mineral oils*

ISO 4263-3, *Petroleum and related products — Determination of the ageing behaviour of inhibited oils and fluids using the TOST test — Part 3: Anhydrous procedure for synthetic hydraulic fluids*

ISO 4406, *Hydraulic fluid power — Fluids — Method for coding the level of contamination by solid particles*

ISO 6072, *Rubber — Compatibility between hydraulic fluids and standard elastomeric materials*

ISO 6245, *Petroleum products — Determination of ash*

ISO 6247, *Petroleum products — Determination of foaming characteristics of lubricating oils*

ISO 6296, *Petroleum products — Determination of water — Potentiometric Karl Fischer titration method*

ISO 6341, *Water quality — Determination of the inhibition of the mobility of *Daphnia magna* Straus (Cladocera, Crustacea) — Acute toxicity test*

ISO 6614, *Petroleum products — Determination of water separability of petroleum oils and synthetic fluids*

ISO 6618, *Petroleum products and lubricants — Determination of acid or base number — Colour-indicator titration method*

ISO 6619, *Petroleum products and lubricants — Neutralization number — Potentiometric titration method*

ISO 6743-4, *Lubricants, industrial oils and related products (class L) — Classification — Part 4: Family H (Hydraulic systems)*

ISO 7120, *Petroleum products and lubricants — Petroleum oils and other fluids — Determination of rust-preventing characteristics in the presence of water*

ISO 7346-2, *Water quality — Determination of the acute lethal toxicity of substances to a freshwater fish [*Brachydanio rerio* Hamilton-Buchanan (Teleostei, Cyprinidae)] — Part 2: Semi-static method*

ISO 8192, *Water quality — Test for inhibition of oxygen consumption by activated sludge for carbonaceous and ammonium oxidation*

ISO 9120, *Petroleum and related products — Determination of air-release properties of steam turbine and other oils — Impinger method*

ISO 9439, *Water quality — Evaluation of ultimate aerobic biodegradability of organic compounds in aqueous medium — Carbon dioxide evolution test*

ISO 10634, *Water quality — Guidance for the preparation and treatment of poorly water-soluble organic compounds for the subsequent evaluation of their biodegradability in an aqueous medium*

ISO 11500, *Hydraulic fluid power — Determination of the particulate contamination level of a liquid sample by automatic particle counting using the light-extinction principle*

ISO 12185, *Crude petroleum and petroleum products — Determination of density — Oscillating U-tube method*

ISO 12937, *Petroleum products — Determination of water — Coulometric Karl Fischer titration method*

ISO 14593, *Water quality — Evaluation of ultimate aerobic biodegradability of organic compounds in aqueous medium — Method by analysis of inorganic carbon in sealed vessels (CO₂ headspace test)*

ISO 14635-1, *Gears — FZG test procedures — Part 1: FZG test method A/8,3/90 for relative scuffing load-carrying capacity of oils*

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*

ISO 20763, *Petroleum and related products — Determination of anti-wear properties of hydraulic fluids — Vane pump method*

DIN 51554-3, *Testing of mineral oils; Test of susceptibility to ageing according to Baader; Testing at 95 °C*

ASTM D2532, *Standard Test Method for Viscosity and Viscosity Change After Standing at Low Temperature of Aircraft Turbine Lubricants*

3 Sampling

Sampling of hydraulic fluids for the purpose of this International Standard shall be carried out in accordance with the pertinent procedure specified in ISO 3170. A representative test specimen should be taken for analysis.

Any drum, barrel, tanker compartment or other type of container delivered to the end user may be sampled and analyzed at the purchaser's discretion.

4 Requirements of environmentally acceptable hydraulic fluids

For the purpose of this International Standard, hydraulic fluids shall be triglycerides, polyglycols, synthetic esters, polyalphaolefins and related hydrocarbon products. The classification of these hydraulic oils shall be in accordance with ISO 6743-4 for categories HETG, HEPG, HEES and HEPR. The minimum content of base fluid for each category shall not be less than 70 % (*m/m*).

Fluid classification should correspond to the major base stock component.

When tested using prescribed methods, the fluids' characteristics shall comply with limiting values set out in [Table 1](#) to [Table 5](#), where applicable.

The appearance of the delivered oils shall be clear and bright and free of any visible particulate matter when viewed under normal visible light at ambient temperature. The cleanliness level shall be expressed according to ISO 4406 and ISO 11500.

The precision (repeatability and reproducibility) of the test methods in this International Standard and the interpretation of the results shall be in accordance with ISO 4259, which shall be consulted in instances of uncertainty or dispute.

The environmental behaviour specifications for categories HETG, HEPG, HEES and HEPR are given in [Table 1](#).

Table 1 — Environmental behaviour requirements for categories HETG, HEPG, HEES and HEPR

Characteristic of test	Unit	Requirement	Test method or applicable standard
Biodegradability, 28 days, min.	%	60	ISO 14593 or ISO 9439
Toxicity ^a			
Acute fish toxicity, 96 h, LC50, min.	mg/l	100	ISO 7346-2
Acute Daphnia toxicity, 48 h, EC50, min.	mg/l	100	ISO 6341
Bacterial inhibition, 3 h, EC50, min.	mg/l	100	ISO 8192
^a Water-soluble fluids shall be tested according to the test method cited. Fluids with low water solubility shall be tested using water-accommodated fractions, prepared according to ISO 10634.			

The biodegradability and aquatic toxicity tests shall be performed in a laboratory operating in accordance with ISO/IEC 17025 or according to Good Laboratory Practice (GLP).

All other detailed specifications of each category mentioned in this International Standard are provided in [Table 2](#) to [Table 5](#), respectively and as indicated below:

- [Table 2](#): category HETG;
- [Table 3](#): category HEPG;
- [Table 4](#): category HEES;
- [Table 5](#): category HEPR.

All of the categories listed above pertain to lubricants, industrial oils and related products of Group HE, i.e. environmentally acceptable hydraulic fluids, a typical application of which is in general hydraulic systems. The composition of each category is specified in the title of the tables. These elements are taken from ISO 6743-4.

Table 2 — Specifications for type HETG hydraulic fluids, triglycerides

Characteristic of test	Unit	Requirement				Test method or applicable standard
		22	32	46	68	ISO 3448
Viscosity grade						
Density at 15 °C	kg/m ³	— ^a	— ^a	— ^a	— ^a	ISO 12185 ISO 3675
Colour ^b	—	— ^a	— ^a	— ^a	— ^a	ISO 2049
Appearance at 25 °C	—	Clbr ^c	Clbr ^c	Clbr ^c	Clbr ^c	—
Ash content, max.	% (m/m)	— ^d	— ^d	— ^d	— ^d	ISO 6245
Flash point Cleveland open cup, min.	°C	165	175	185	195	ISO 2592
Kinematic viscosity at -20 °C, max.	mm ² /s	— ^d	— ^d	— ^d	— ^d	ISO 3104
at 0 °C, max.	mm ² /s	300	420	780	1 400	
at 40 °C, min. to max.	mm ² /s	19,8 to 24,2	28,8 to 35,2	41,4 to 50,6	61,2 to 74,8	
at 100 °C, min.	mm ² /s	4,1	5,0	6,1	7,8	
Pour point, max.	°C	— ^d	— ^d	— ^d	— ^d	ISO 3016
Low temperature fluidity after 7 days	°C	— ^d	— ^d	— ^d	— ^d	ASTM D2532
Acid number, ^e max.	mg KOH/g	— ^d	— ^d	— ^d	— ^d	ISO 6618 ISO 6619
Water content	mg/kg	1 000	1 000	1 000	1 000	ISO 12937 ISO 6296
Cleanliness level, max	d	— ^d	— ^d	— ^d	— ^d	ISO 4406 ISO 11500
Copper corrosion, 100 °C 3 h, max.	rating	2	2	2	2	ISO 2160
Rust prevention, procedure A, 24 h	—	Pass	Pass	Pass	Pass	ISO 7120
Foam at 24 °C, max. (Sequence I)	ml	150/0	150/0	150/0	150/0	ISO 6247
at 93 °C, max. (Sequence II)	ml	80/0	80/0	80/0	80/0	
at 24 °C, max. (Sequence III)	ml	150/0	150/0	150/0	150/0	
Air release, 50 °C, max.	min	7	7	10	10	ISO 9120
Water separation Time to 3 ml emulsion at 54 °C, max.	min	— ^d	— ^d	— ^d	— ^d	ISO 6614

Table 2 (continued)

Characteristic of test	Unit	Requirement				Test method or applicable standard
		22	32	46	68	
Viscosity grade						ISO 3448
Elastomer compatibility ^f after 1 000 h at given temperature						
NBR 1	°C	60	80	80	80	
HNBR	°C	60	80	80	80	
FKM 2	°C	60	80	80	80	
AU ^g	°C	60	80	80	80	
Change in shore A hardness, max.	grade	±10	±10	±10	±10	ISO 6072
Change in volume, max.	%	-3 to +10	-3 to +10	-3 to +10	-3 to +10	
Change in elongation, max.	%	30	30	30	30	
Change in tensile strength, max.	%	30	30	30	30	
Oxidation stability:						
Time to reach ΔTAN = 2 mg KOH/g, min. Baader test, 95 °C, 72 h	h	— ^{ad}	— ^{ad}	— ^{ad}	— ^{ad}	ISO 4263-3 DIN 51554-3
Increase in viscosity at 40 °C, max.	%	20	20	20	20	
Load-carrying properties, FZG A/8,3/90, min.	stage	— ^h	10	10	10	ISO 14635-1
Vane pump, Procedure A ⁱ						
Ring, max.	mg	120	120	120	120	ISO 20763
Vane, max.	mg	30	30	30	30	
<p>a Report.</p> <p>b For purposes of identification, dye may be used by agreement between supplier and end user.</p> <p>c “Clear and bright” is abbreviated as Clbr.</p> <p>d Criteria of performance or values of characteristics to be negotiated between supplier and end user.</p> <p>e The initial acid number is given by the base fluids and the additives.</p> <p>f The requirements for two of the listed elastomer types shall be met. The values are minimum requirements for standard reference elastomers. The elastomers are suitable for guidance and selection of the correct sealing material. Other materials and/or test conditions may be agreed between supplier and customer. The applicability to the behaviour of the elastomer used in practice should be considered.</p> <p>g No hydrolytic stabilized elastomer exists for AU. Manufacturers produce stabilized AU materials for practical applications. It is recommended that users clarify this point with the elastomer manufacturer.</p> <p>h Not applicable to viscosity grade 22.</p> <p>i There are currently no precision data for the method when non-Eaton/Vickers test cartridges (e.g. Conestoga USA, Inc. and Tokimec) are used. Consequently, no absolute mass loss limits can be stipulated until the precision of V104C pump cartridges from the new supplier has been determined. In the interim, the limits previously established for Eaton/Vickers cartridges may be used for guidance. It should be noted that ISO 20763 supersedes BS 2000: Part 281, IP 281 and DIN 51389. For fluids evaluated under the aforementioned methods, the test data are considered to remain valid and no re-testing against ISO 20763 is required.</p>						

Table 3 — Specifications for type HEPG hydraulic fluids, polyglycols

Characteristic of test	Unit	Requirement				Test method or applicable standard
		22	32	46	68	
Viscosity grade						ISO 3448
Density at 15 °C	kg/m ³	— ^a	— ^a	— ^a	— ^a	ISO 12185 ISO 3675
Colour ^b	—	— ^a	— ^a	— ^a	— ^a	ISO 2049
Appearance at 25 °C	—	Clbr ^c	Clbr ^c	Clbr ^c	Clbr ^c	—
Ash content, max.	% (m/m)	— ^d	— ^d	— ^d	— ^d	ISO 6245
Flash point Cleveland open cup, min.	°C	165	175	185	195	ISO 2592
Kinematic viscosity at -20 °C, max.	mm ² /s	— ^d	— ^d	— ^d	— ^d	ISO 3104
at -0 °C, max.	mm ² /s	300	420	780	1 400	
at -40 °C, max.	mm ² /s	19,8 to 24,2	28,8 to 35,2	41,4 to 50,6	61,2 to 74,8	
at 100 °C, min.	mm ² /s	4,1	5,0	6,1	7,8	
Pour point, max.	°C	-21	-18	-15	-12	ISO 3016
Low temperature fluidity after 7 days	°C	— ^d	— ^d	— ^d	— ^d	ASTM D2532
Acid number, ^e max.	mg KOH/g	— ^d	— ^d	— ^d	— ^d	ISO 6618 ISO 6619
Water content, max.	mg/kg	5 000	5 000	5 000	5 000	ISO 12937 ISO 6296
Cleanliness level, max	d	— ^d	— ^d	— ^d	— ^d	ISO 4406 ISO 11500
Copper corrosion, 100 °C 3 h, max.	rating	2	2	2	2	ISO 2160
Rust prevention, procedure A, 24 h	—	Pass	Pass	Pass	Pass	ISO 7120
Foam at 24 °C, max. (Sequence I)	ml	150/0	150/0	150/0	150/0	ISO 6247
at 93 °C, max. (Sequence II)	ml	80/0	80/0	80/0	80/0	
at 24 °C, max. (Sequence III)	ml	150/0	150/0	150/0	150/0	
Air release, 50 °C, max.	min	7	7	10	10	ISO 9120
Elastomer compatibility ^f after 1 000 h at given temperature						ISO 6072
NBR 1	°C	60	80	—	—	
HNBR	°C	60	80	100	100	
FKM 2	°C	60	80	100	100	
Change in shore A hardness, max.	grade	±10	±10	±10	±10	
Change in volume, max.	%	-3 to +10	-3 to +10	-3 to +10	-3 to +10	
Change in elongation, max.	%	30	30	30	30	
Change in tensile strength, max.	%	30	30	30	30	

Table 3 (continued)

Characteristic of test	Unit	Requirement				Test method or applicable standard
		22	32	46	68	
Viscosity grade						ISO 3448
Oxidation stability: TOST test, time to reach Δ TAN = 2 mg KOH/g, min.	h	1 000	1 000	1 000	1 000	ISO 4263-3
Load-carrying properties, FZG A/8,3/90, min.	stage	—g	10	10	10	ISO 14635-1
Vane pump, Procedure A ^h						
Ring, max.	mg	120	120	120	120	ISO 20763
Vane, max.	mg	30	30	30	30	
<p>a Report.</p> <p>b For purposes of identification, dye may be used by agreement between supplier and end user.</p> <p>c “Clear and bright” is abbreviated as Clbr.</p> <p>d Criteria of performance or characteristics values to be negotiated between supplier and end user.</p> <p>e The initial acid number is given by the base fluids and the additives.</p> <p>f The requirements for two of the listed elastomer types shall be met. The values are minimum requirements for standard reference elastomers. The elastomers are suitable for guidance and selection of the correct sealing material. Other materials and/or test conditions may be agreed upon between supplier and customer. The applicability to the behaviour of the elastomer used in practice should be considered.</p> <p>g Not applicable to Viscosity Grade 22.</p> <p>h There are currently no precision data for the method when non-Eaton/Vickers test cartridges (e.g. Conestoga USA, Inc. and Tokimec) are used. Consequently, no absolute mass loss limits can be stipulated until the precision of V104C pump cartridges from the new supplier has been determined. In the interim, the limits previously established for Eaton/Vickers cartridges may be used for guidance. It should be noted that ISO 20763 supersedes BS 2000: Part 281, IP 281 and DIN 51389. For fluids evaluated under the aforementioned methods, the test data are considered to remain valid and no re-testing against ISO 20763 is required.</p>						

Table 4 — Specifications for type HEES hydraulic fluids, synthetic esters

Characteristic of test	Unit	Requirement					Test method or applicable standard
		22	32	46	68	100	
Viscosity grade							ISO 3448
Density at 15 °C	kg/m ³	— ^a	— ^a	— ^a	— ^a	— ^a	ISO 12185 ISO 3675
Colour ^b	—	— ^a	— ^a	— ^a	— ^a	— ^a	ISO 2049
Appearance at 25 °C	—	Clbr ^c	Clbr ^c	Clbr ^c	Clbr ^c	Clbr ^c	-
Ash content, max.	% (m/m)	— ^d	— ^d	— ^d	— ^d	— ^d	ISO 6245
Flash point							
Cleveland open cup, min.	°C	165	175	185	195	205	ISO 2592
Kinematic viscosity at -20 °C, max.	mm ² /s	— ^d	— ^d	— ^d	— ^d	— ^d	ISO 3104
at 0 °C, max.	mm ² /s	300	420	780	1 400	1 500	
at 40 °C, min. to max.	mm ² /s	19,8 to 24,2	28,8 to 35,2	41,4 to 50,6	61,2 to 74,8	90,0 to 110	
at 100 °C, min.	mm ² /s	4,1	5,0	6,1	7,8	10,0	
Pour point, max.	°C	-21	-18	-15	-12	-9	ISO 3016
Low temperature fluidity after 7 days	°C	— ^d	— ^d	— ^d	— ^d	— ^d	ASTM D2532
Acid number ^e , max.	mg KOH/g	— ^d	— ^d	— ^d	— ^d	— ^d	ISO 6618 ISO 6619
Water content, max.	mg/kg	1 000	1 000	1 000	1 000	1 000	ISO 12937 ISO 6296
Cleanliness level, max	d	— ^d	— ^d	— ^d	— ^d	— ^d	ISO 4406 ISO 11500
Copper corrosion, 100 °C, 3 h, max.	rating	2	2	2	2	2	ISO 2160
Rust prevention, procedure A, 24 h		Pass	Pass	Pass	Pass	Pass	ISO 7120
Foam at 24 °C, max. (Sequence I)	ml	150/0	150/0	150/0	150/0	150/0	ISO 6247
at 93 °C, max. (Sequence II)	ml	80/0	80/0	80/0	80/0	80/0	
at 24 °C, max. (Sequence III)	ml	150/0	150/0	150/0	150/0	150/0	
Air release, 50 °C, (75°C for ISO VG 100), max.	min	7	7	10	10	14	ISO 9120
Water separation Time to 3 ml emulsion at 54 °C, max.	min	— ^d	— ^d	— ^d	— ^d	— ^d	ISO 6614

Table 4 (continued)

Characteristic of test	Unit	Requirement					Test method or applicable standard
		22	32	46	68	100	
Viscosity grade							ISO 3448
Elastomer compatibility ^f after 1 000 h at given temperature							ISO 6072
NBR 1	°C	60	80	80	—	—	
AU	°C	60	80	80	—	—	
HNBR	°C	60	80	80	100	100	
FKM 2	°C	60	80	80	100	100	
Change in shore A hardness, max.	grade	±10	±10	±10	±10	±10	
Change in volume, max.	%	-3 to +10	-3 to +10	-3 to +10	-3 to +10	-3 to +10	
Change in elongation, max.	%	30	30	30	30	30	
Change in tensile strength, max.	%	30	30	30	30	30	
Oxidation stability: Modified TOST, dry TOST, time to reach Δ TAN = 2 mg KOH/g, min.	h	— ^{ad}	— ^{ad}	— ^{ad}	— ^{ad}	— ^{ad}	ISO 4263-3 DIN 51554-3
Baader test, 110 °C, 72 h Increase in viscosity at 40 °C, max.	%	20	20	20	20	20	
Load-carrying properties, FZG A/8,3/90, min.	stage	— ^g	10	10	10	10	ISO 14635-1
Vane pump. Procedure A ^h							ISO 20763
Ring, max.	mg	120	120	120	120	120	
Vane, max.	mg	30	30	30	30	30	
<p>a Report.</p> <p>b For purposes of identification, dye may be used by agreement between supplier and end user.</p> <p>c “Clear and bright” is abbreviated as Clbr.</p> <p>d Criteria of performance or values of characteristics to be negotiated between supplier and end user.</p> <p>e The initial acid number is given by the base fluids and the additives.</p> <p>f The requirements for two of the listed elastomer types shall be met. The values are minimum requirements for standard reference elastomers. The elastomers are suitable for guidance and selection of the correct sealing material. Other materials and/or test conditions may be agreed upon between supplier and customer. The applicability to the behaviour of the elastomer used in practice should be considered.</p> <p>g Not applicable to Viscosity Grade 22.</p> <p>h There are currently no precision data for the method when non-Eaton/Vickers test cartridges (e.g. Conestoga USA, Inc. and Tokimec) are used. Consequently, no absolute mass loss limits can be stipulated until the precision of V104C pump cartridges from the new supplier has been determined. In the interim, the limits previously established for Eaton/Vickers cartridges may be used for guidance. It should be noted that ISO 20763 supersedes BS 2000: Part 281, IP 281 and DIN 51389. For fluids evaluated under the aforementioned methods, the test data are considered to remain valid and no re-testing against ISO 20763 is required.</p>							

Table 5 — Specifications for type HEPR hydraulic fluids, polyalphaolefins and other synthetic hydrocarbons

Characteristic of test	Unit	Requirement				Test method or applicable standard
		22	32	46	68	
Viscosity grade						ISO 3448
Density at 15 °C	kg/m ³	— ^a	— ^a	— ^a	— ^a	— ^a
Colour ^b	—	— ^a	— ^a	— ^a	— ^a	ISO 2049
Appearance at 15 °C	—	Clbr ^c	Clbr ^c	Clbr ^c	Clbr ^c	—
Ash content, max.	% (m/m)	— ^d	— ^d	— ^d	— ^d	ISO 6245
Flash point Cleveland open cup, min.	°C	165	175	185	195	ISO 2592
Kinematic viscosity at -20 °C, max.	mm ² /s	— ^d	— ^d	— ^d	— ^d	ISO 3104
at 0 °C, max.	mm ² /s	300	420	780	1 400	
at 40 °C, min. to max.	mm ² /s	19,8 to 24,2	28,8 to 35,2	41,4 to 50,6	61,2 to 74,8	
at 100 °C, min.	mm ² /s	4,1	5,0	6,1	7,8	
Pour point, max.	°C	-21	-18	-15	-12	ISO 3016
Low temperature fluidity after 7 days	°C	— ^d	— ^d	— ^d	— ^d	ASTM D2532
Acid number ^e , max.	mg KOH/g	— ^d	— ^d	— ^d	— ^d	ISO 6618 ISO 6619
Water content	mg/kg	1 000	1 000	1 000	1 000	ISO 12937 ISO 6296
Cleanliness level, max	d	— ^d	— ^d	— ^d	— ^d	ISO 4406 ISO 11500
Copper corrosion, 100 °C, 3 h, max.	rating	2	2	2	2	ISO 2160
Rust prevention, procedure A, 24 h		Pass	Pass	Pass	Pass	ISO 7120
Foam at 24 °C, max. (Sequence I)	ml	150/0	150/0	150/0	150/0	ISO 6247
at 93 °C, max. (Sequence II)	ml	80/0	80/0	80/0	80/0	
at 24 °C, max. (Sequence III)	ml	150/0	150/0	150/0	150/0	
Air release, 50 °C, max.	min	7	7	10	10	ISO 9120
Water separation Time to 3 ml emulsion at 54 °C, max.	min	— ^d	— ^d	— ^d	— ^d	ISO 6614

Table 5 (continued)

Characteristic of test	Unit	Requirement				Test method or applicable standard
		22	32	46	68	
Viscosity grade						ISO 3448
Elastomer compatibility ^f after 1 000 h at given temperature						ISO 6072
NBR 1	°C	60	80	—	—	
HNBR	°C	60	80	100	100	
FKM 2	°C	60	80	100	100	
Change in shore A hardness, max.	grade	±10	±10	±10	±10	
Change in volume, max.	%	-3 to +10	-3 to +10	-3 to +10	-3 to +10	
Change in elongation, max.	%	30	30	30	30	
Change in tensile strength, max.	%	30	30	30	30	
Oxidation stability: TOST test, time to reach ΔTAN = 2 mg KOH/g, min.	h	1 000	1 000	1 000	1 000	ISO 4263-1
Load carrying properties, FZG A/8,3/90, min.	Stage	—g	10	10	10	ISO 14635-1
Vane pump, Procedure A ^h						ISO 20763
Ring, max.	mg	120	120	120	120	
Vane, max.	mg	30	30	30	30	
<p>a Report.</p> <p>b For purposes of identification, dye may be used by agreement between supplier and end user.</p> <p>c “Clear and bright” is abbreviated as Clbr.</p> <p>d Criteria of performance or values of characteristics to be negotiated between supplier and end user.</p> <p>e The initial acid number is given by the base fluids and the additives.</p> <p>f The requirements for two of the listed elastomer types shall be met. The values are minimum requirements for standard reference elastomers. The elastomers are suitable for guidance and selection of the correct sealing material. Other materials and/or test conditions may be agreed upon between supplier and customer. The applicability to the behaviour of the elastomer used in practice should be considered.</p> <p>g Not applicable to Viscosity Grade 22.</p> <p>h There are currently no precision data for the method when non-Eaton/Vickers test cartridges (e.g. Conestoga USA, Inc. and Tokimec) are used. Consequently, no absolute mass loss limits can be stipulated until the precision of V104C pump cartridges from the new supplier has been determined. In the interim, the limits previously established for Eaton/Vickers cartridges may be used for guidance. It should be noted that ISO 20763 supersedes BS 2000: Part 281, IP 281 and DIN 51389. For fluids evaluated under the aforementioned methods, the test data are considered to remain valid and no re-testing against ISO 20763 is required.</p>						

Annex A
(informative)

**Guidelines for changing fluids from mineral-based oils to
environmentally acceptable fluids**

Table A.1 — Guidelines for changing fluids from mineral-based oils to environmentally acceptable fluids

Change of liquid pressure medium		Elements to be checked to determine whether the installation is suitable for the use of environmentally acceptable hydraulic fluids						Measures during and after changeover		
from	to	Reservoir ^a temperature	Seals, plastics, adhesives	Metallic materials	Filter elements ^c	Paint coating	Remaining residual volumed, max	Periods between oil changes	Periods between filter changes	
HH HL HM HV HD ^g Engine oils	HETG	-10 °C to +70 °C	Industrial elastomers ^e	Lead, tin and zinc in pure form are to be avoided. Alloys of these metals are subject to possible corrosion ^f in conjunction with aged liquids and at elevated temperatures.	Zinc-coated filter elements are subject to attack.	Compatibility with paint coating.	2 % (target). This is to ensure thorough cleaning, emptying and flushing of the installation. 1 %	Periods between changes depend upon the installation and the application and have to be agreed with the manufacturer of the liquid. In order to determine the length of time between changeovers, running investigations, for instance of water content, solid particle contamination, viscosity, NN and IR, as well as spectrographic analyses, are necessary.	Filter change when converting to the new liquid and after 50 h. Further changes have to be established bearing in mind the installation and application details.	
HH HL HM HV HD ^g Engine oils	HEES	-20 °C to +80 °C	Industrial elastomers ^e Plastics and soluble adhesive compounds.	Lead, tin and zinc in pure form are to be avoided. Alloys of these metals are subject to possible corrosion ^f in conjunction with aged liquids and at elevated temperatures.	Paper filter cartridges and zinc-coated filter elements are subject to attack.	Compatibility with paint coating.	2 % (target). This is to ensure thorough cleaning, emptying and flushing of the installation. 1 %	Periods between changes depend upon the installation and the application and have to be agreed with the manufacturer of the liquid. In order to determine the length of time between changeovers, running investigations, for instance of water content, solid particle contamination, viscosity, NN and IR, as well as spectrographic analyses, are necessary.	Filter changes when converting to the new liquid and after 50 h. Further changes have to be established bearing in mind the installation and application details.	

Table A.1 (continued)

Change of liquid pressure medium		Elements to be checked to determine whether the installation is suitable for the use of environmentally acceptable hydraulic fluids						Measures during and after changeover		
from	to	Reservoir ^{ab} temperature	Seals, plastics, adhesives	Metallic materials	Filter elements ^c	Paint coating	Remaining residual volume ^d , max	Periods between oil changes	Periods between filter changes	
HH HL HM HV HD ^g Engine oils	HEPR	-30 °C to +100 °C	Industrial elastomers ^e Plastics and soluble adhesive compounds. An abrupt change from a mineral oil-based fluid to a HEPR-based product could lead to leakage of gaskets. This can lead to sealing problems.	Lead, tin and zinc in pure form are to be avoided. Alloys of these metals are subject to possible corrosion ^f in conjunction with aged liquids and at elevated temperatures.	Paper filter cartridges and zinc-coated filter elements are subject to attack.	Compatibility with paint coating.	2 % (target). This is to ensure thorough cleaning, emptying and flushing of the installation. 1 %	Periods between changes depend upon the installation and the application and have to be agreed with the manufacturer of the liquid. In order to determine the length of time between changeovers, running investigations, for instance of water content, solid particle contamination, viscosity, NN and IR, as well as spectrographic analyses, are necessary.	Filter changes when converting to the new liquid and after 50 h. Further changes have to be established bearing in mind the installation and application details.	
HH HL HM HV HD ^g Engine oils	HEPG ^h	-20 °C to +80 °C	Industrial elastomers ^e Plastics and soluble adhesive compounds. Non-resistant e.g. poly-carbonates, poly-methacrylates	Frictional combinations with aluminium. Lead, tin and zinc in pure form are to be avoided as well as frictional combinations with aluminium. Alloys of these metals are subject to possible corrosion ^f in conjunction with aged liquids and at elevated temperatures.	Filter elements. Suction filters. Paper filter cartridges and zinc-coated filter elements are subject to attack.	Compatibility with paint coating.	1 % (target). This is to ensure thorough cleaning, emptying and flushing of the installation. 0,50 %	Periods between changes depend upon the installation and the application and have to be agreed with the manufacturer of the liquid. In order to determine the length of time between changeovers, running investigations, for instance of water content, solid particle contamination, viscosity, NN and IR, as well as spectrographic analyses, are necessary.	Filter changes when converting to the new liquid and after 50 h. Further changes have to be established bearing in mind the installation and application details. Higher percentages of mineral oil shorten the periods between changes.	

Table A.1 (continued)

Change of liquid pressure medium	Elements to be checked to determine whether the installation is suitable for the use of environmentally acceptable hydraulic fluids						Measures during and after changeover			
	from	to	Reservoir ^{ab} temperature	Seals, plastics, adhesives	Metallic materials	Filter elements ^c	Paint coating	Remaining residual volume ^d , max	Periods between oil changes	Periods between filter changes
<p>NOTE When changing from HETG, HEES and HEPR to HEPG, it is recommended for users to proceed in the same way as when changing from HL, HH, HM, HV to HEPG, due to possible miscibility problems.</p> <p>a Higher temperatures have an unfavourable influence on compatibility with seals and ageing characteristics.</p> <p>b In hydrosystems, temperatures of up to 25 °C and higher can be permitted for a short time or locally.</p> <p>c Manufacturer to be consulted for suitability.</p> <p>d The number of flushes depends upon the installation. It is possible that the residual volumes quoted cause filtration or foaming problems.</p> <p>e Recommended industrial elastomers. Refer to footnote c.</p> <p>f At present, there is no recognized procedure for assessment.</p> <p>g HD stands for heavy duty. To include fluid discrepancy and detergency.</p> <p>h A density of more than 1 g/ml requires a reduction of about 20 % in the maximum permitted rotary speed of self-priming pumps.</p>										

Annex B (informative)

Additional information on shear stability

Type HEES and HEPG hydraulic fluids containing polymers may be tested against shear stability by test methods according to ISO 20844^[3].

Requirements and test conditions should be agreed upon between the supplier and end user.

Annex C (informative)

Disposal of hydraulic fluids

All HE fluids for disposal should be collected in separate containers and discarded in a responsible manner in compliance with government regulations and industrial safety standards.

The suppliers of HE fluids should provide end users with recommended guidelines/procedures for the safe disposal of fluids.

Bibliography

- [1] ISO 11158:2009, incorporating corrigendum March 2010, *Lubricants, industrial oils and related products (class L) — Family H (Hydraulic systems) — Specifications for categories HH, HL, HM, HV and HG*
- [2] ISO 12922:2012, *Lubricants, industrial oils and related products (class L) — Family H (Hydraulic systems) — Specifications for hydraulic fluids in categories HFAE, HFAS, HFB, HFC, HFDR and HFDU*
- [3] ISO 20844, *Petroleum and related products — Determination of the shear stability of polymer-containing oils using a diesel injector nozzle*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK