

BS ISO 15646:2014



BSI Standards Publication

## Re-sintering test for $\text{UO}_2$ , $(\text{U,Gd})\text{O}_2$ and $(\text{U,Pu})\text{O}_2$ pellets

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 15646:2014.

The UK participation in its preparation was entrusted to Technical Committee NCE/9, Nuclear fuel cycle technology.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.  
Published by BSI Standards Limited 2014

ISBN 978 0 580 76906 1  
ICS 27.120.30

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2014.

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------

---

INTERNATIONAL  
STANDARD

**ISO**  
**15646**

First edition  
2014-06-15

---

---

**Re-sintering test for  $UO_2$ ,  $(U,Gd)O_2$   
and  $(U,Pu)O_2$  pellets**

*Test de refrittage pour pastilles  $UO_2$ ,  $(U,Gd)O_2$  et  $(U,Pu)O_2$*



Reference number  
ISO 15646:2014(E)



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Brief description of procedure</b> .....	<b>1</b>
<b>3 Incidents</b> .....	<b>1</b>
<b>4 Apparatus</b> .....	<b>1</b>
4.1 Equipment for measuring density.....	1
4.2 Heat treatment furnace.....	2
<b>5 Reagents</b> .....	<b>2</b>
<b>6 Sampling</b> .....	<b>2</b>
<b>7 Procedure</b> .....	<b>2</b>
7.1 Density measurements before heat treatment.....	2
7.2 Heat treatment.....	3
7.3 Density measurements after heat treatment.....	3
<b>8 Evaluation</b> .....	<b>3</b>
<b>9 Precision of the procedure</b> .....	<b>4</b>
<b>10 Test report</b> .....	<b>4</b>
<b>Annex A (informative) Relationship between pellet mass evolution and O/M ratio evolution</b> .....	<b>5</b>
<b>Bibliography</b> .....	<b>6</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 85, *Nuclear energy, nuclear technologies, and radiological protection*, Subcommittee SC 5, *Nuclear fuel cycle*.

# Re-sintering test for $\text{UO}_2$ , $(\text{U,Gd})\text{O}_2$ and $(\text{U,Pu})\text{O}_2$ pellets

## 1 Scope

This International Standard describes a procedure for measuring the densification of  $\text{UO}_2$ ,  $(\text{U,Gd})\text{O}_2$ , and  $(\text{U,Pu})\text{O}_2$  pellets, achieved by heat treatment under defined conditions.

The densification of fuel in power operation is an important design feature. Essentially, it is dependent on structural parameters such as pore size, spatial pore distribution, grain size, and in the case of  $(\text{U,Gd})\text{O}_2$  and  $(\text{U,Pu})\text{O}_2$ , oxide phase structure. A thermal re-sintering test can be used to characterize the dimensional behaviour of the pellets under high temperature. The results of this test are used by the fuel designer to predict dimensional behaviour in the reactor, because thermal densification in the reactor is also dependent on these structural parameters, albeit in a differing manner in terms of quantity.

On the assumption of the prediction, it is necessary to correlate the results of this test by some correlation rules, because the results of this test vastly depend on the re-sintering conditions (such as heat treatment temperature, treatment time, gas content, and partial oxygen pressure).

## 2 Brief description of procedure

The density of nuclear fuel pellets is measured before the re-sintering test. Afterwards, the pellets are subjected to heat treatment in a furnace under specified conditions with regard to temperature, time, and sintering atmosphere. After cooling, the density is remeasured.

The oxygen/metal molar ratio should remain constant during the re-sintering test. The difference between the two density measurements shall be used to assess the thermal stability of the pellet lot.

## 3 Incidents

Minor chipping can occur during pellet handling. Densities of visibly chipped pellets shall not be measured using the geometric method, as the results will be inaccurate.

Densities of such chipped pellets can be measured using the buoyancy method.

## 4 Apparatus

Specifically for  $(\text{U,Pu})\text{O}_2$ , all operations shall be performed in glove boxes.

### 4.1 Equipment for measuring density

The same method shall be used before and after the re-sintering of pellets.

In [4.1.1](#) and [4.1.2](#), two different measurement methods are mentioned as examples. Other methods can be used if they meet the customer uncertainty requirement.

#### 4.1.1 Geometric measurement of density

A dial test indicator or micrometer with precision of 1  $\mu\text{m}$  shall be used in order to measure the diameter and the height.

Analytical balance with readability of  $\pm 1$  mg for weighing the pellets.

#### 4.1.2 Measurement of density using buoyancy method

See ISO 3369.

#### 4.2 Heat treatment furnace

A programmable furnace able to reach temperatures of about 1 800 °C under gas scavenging and to hold a homogeneous temperature of the sintering area shall be used. It is advisable to use two different thermocouples for furnace control and monitoring.

### 5 Reagents

#### 5.1 Gas.

The furnace gas shall ensure a constant oxygen/heavy metal ratio. Usually, the re-sinter test employs a similar furnace atmosphere to that used when the pellets were sintered during manufacture. The test furnace shall be qualified to prove that the oxygen/heavy metal ratio of the fuel tested does not change by more than  $\pm 0,005$ . The following are examples of furnace atmospheres that can be used.

NOTE Heavy metal = U, U+Pu, or U+Gd, depending on the concerned product.

- For  $\text{UO}_2$  fuel:
  - pure hydrogen (purification better than a volume fraction of 99,99 %);
  - mixture of noble gas (purification better than a volume fraction of 99,99 %) with at least 3 % hydrogen.
- For  $(\text{U,Pu})\text{O}_2$  and  $(\text{U,Gd})\text{O}_2$  fuels:
  - pure argon (purification better than a volume fraction of 99,99 %);
  - pure argon (purification better than a volume fraction of 99,99 %) with 7 % hydrogen, humidified as required to maintain fuel stoichiometry;
  - argon with 4 % hydrogen and  $\text{CO}_2$  as required to maintain fuel stoichiometry;
  - dry cracked ammonia gas (75 %  $\text{H}_2$ -25 %  $\text{N}_2$  by volume) with gas mixture purity of at least 99,9 % by volume and a dew point less than  $-40$  °C.

**5.2 Degassed water**, distilled and degassed (e.g. by boiling) water as buoyancy test fluid, or distilled water to which a wetting agent (soap) has been added to eliminate any microbubbles.

### 6 Sampling

In case of using the geometric method for the density measurement, the selected pellets shall be free of any visible defects liable to bias the density measurements (e.g. chipping, cracking, thumbnail cracks, etc.). In case of using the buoyancy method for the density measurement, the pellets with these visible defects can be kept.

### 7 Procedure

#### 7.1 Density measurements before heat treatment

The density of the fuel pellets has to be measured prior to the heat treatment. Of all the procedures available, geometric density measurements and the buoyancy method have been proven most satisfactory for routine quality control inspection. The geometric method is preferable where the pellets have a large fraction of open pores (i.e. pores having a connection to the pellet surface). Pellets that have sustained



chipping are better measured using the buoyancy method or the penetration immersion method as defined in ISO 9278.

## 7.2 Heat treatment

Following the density measurement, the pellets, after position identification to ensure traceability, are subjected to heat treatment in the furnace using the following parameters.

- Heating rate: <15 °C/min (at higher rates the pellets could burst). A heating rate of 5 °C/min is recommended in order to be sure not to burst the pellets.
- Heat treatment temperature: shall be specified jointly by the customer/fuel designer and the fuel vendor. As example, temperatures of the order of 1 700 °C are generally applied.
- Treatment time: shall be specified jointly by the customer/fuel designer and the fuel vendor. As example, residence time of the order of 24 h is generally applied.
- Suitable treatment atmosphere (see Examples 1 to 3).

EXAMPLE 1 For UO<sub>2</sub> pellets, pure hydrogen (5.1) or mixtures of noble gas with at least 3 % hydrogen (5.1) can be used.

EXAMPLE 2 For (U, Gd)O<sub>2</sub> and (U, Pu)O<sub>2</sub> pellets, a shift in stoichiometry of pellets occurs during treatment when using dry hydrogen or dry hydrogen/noble gas mixtures. This can be avoided by using a gas atmosphere with a suitable oxygen partial pressure which keeps the stoichiometry constant during re-sintering. Adjusting the oxygen partial pressure can be done by admixing CO<sub>2</sub> in appropriate proportions to the re-sinter atmosphere or by using wet hydrogen or wet hydrogen/noble gas mixtures.

EXAMPLE 3 A pure argon atmosphere can be used.

NOTE For (U, Gd)O<sub>2</sub> pellets, if necessary, an adjustment of the initial oxygen/heavy metal (U+Gd) ratio can be performed by heat treatment of the pellets at 150 °C in air during a holding time of 5 h. The heat-up rate shall be low enough to avoid cracking especially at high Gd contents. The annealing step ensures the adjustment of the equilibrium stoichiometry for (U,Gd)O<sub>2</sub> fuel pellets with a Gd content up to 10 % by mass.

- Cool down rate: <15 °C/min.
- Records: For each re-sintering run, the temperature profile is recorded. If the temperature profile satisfies the heat treatment condition specified above, the results of the re-sintering test are accepted.

## 7.3 Density measurements after heat treatment

Following the cooling, the pellets are removed from the furnace and their densities shall be remeasured with the same method used before the heat treatment.

## 8 Evaluation

The re-sinter densification is determined by calculating the difference between the densities before and after the heating treatment. When measuring density, the mass of the pellets shall be measured prior to and upon completion of the heat treatment.

To check that the O/M ratio has not changed in excess of the tolerance of ±0,005, it is necessary to verify that the pellet mass difference, before and after the heat test, is below the following limit:

$$\text{Mass difference} \leq \frac{\text{Mass pellet before test}}{\text{Oxide molar mass}} \times \text{O}_2 \text{ molar mass} \times \text{O/M Changing tolerance} \quad (1)$$

The demonstration of Formula (1) is in [Annex A](#).

In case of mixed oxide (MOX) pellets, the calculation is performed using Formula (2):

$$\text{Mass difference} \leq \frac{\text{Mass pellet before test}}{(238 + 2 \times 16)} \times (2 \times 16) \times 0,005 \quad (2)$$

$$\text{Mass difference} \leq 0,00059 \times \text{Mass pellet before test}$$

It is a good practice to monitor the mean change of all measured pellet mass as a result of re-sintering and check that this does not differ statistically significantly from zero. A significant change would indicate a fault with the furnace atmosphere (e.g. due to leakage). The absolute value of the difference from zero should be lower than the maximum mass difference accepted for one pellet [see Formula (1)].

The density can be calculated through the ratio of measured density to the theoretical density.

The density measurement shall be made according to the specified methods as mutually agreed upon between the buyer and the seller (see ISO 9278).

## 9 Precision of the procedure

The precision of the overall procedure is determined by the precision of the method used to measure density. The repeatability standard deviation in DIN 55 350 for the buoyancy and the penetration immersion method (in turn defined in ISO 9278) is 0,1 %.

Nevertheless, due to the difficulty in weighing a pellet in liquid, in the course of the buoyancy density measurement method, the uncertainty can reach 0,2 %.

## 10 Test report

The test report with reference to this International Standard shall contain the following information:

- all data necessary for the identification of the sample;
- the result of test;
- the location and date of test;
- the recorded profile of temperature.

## Annex A (informative)

### Relationship between pellet mass evolution and O/M ratio evolution

Assumption 1: It is considered that UO<sub>2</sub> pellets and MOX pellets are equivalent with regard to the O/M ratio evolution, because MOX pellets contains around 90 % of UO<sub>2</sub> and because the molar weight of U is near that of Pu.

Assumption 2: The maximum acceptable evolution of the O/M ratio during the re-sintering test is 0,01.

Chemical formula:



Molar balance:

$$n_{\text{UO}_2} = n_{\text{UO}_{2,01}} \quad (\text{A.2})$$

$$\frac{m_{\text{UO}_2}}{M_{\text{UO}_2}} = \frac{m_{\text{UO}_{2,01}}}{M_{\text{UO}_{2,01}}} \quad (\text{A.3})$$

$$m_{\text{UO}_{2,01}} = \frac{m_{\text{UO}_2}}{M_{\text{UO}_2}} \times M_{\text{UO}_{2,01}} \quad (\text{A.4})$$

Mass difference:

$$\Delta m = m_{\text{UO}_{2,01}} - m_{\text{UO}_2} \quad (\text{A.5})$$

$$\Delta m = \frac{m_{\text{UO}_2}}{M_{\text{UO}_2}} \times M_{\text{UO}_{2,01}} - m_{\text{UO}_2} \quad (\text{A.6})$$

$$\Delta m = m_{\text{UO}_2} \times \left( \frac{M_{\text{UO}_{2,01}}}{M_{\text{UO}_2}} - 1 \right) \quad (\text{A.7})$$

$$\Delta m = m_{\text{UO}_2} \times \left( \frac{M_{\text{UO}_2} + 0,01 \times M_{\text{O}} - M_{\text{UO}_2}}{M_{\text{UO}_2}} \right) \quad (\text{A.8})$$

$$\Delta m = m_{\text{UO}_2} \times \frac{0,01 \times M_{\text{O}}}{M_{\text{UO}_2}} \quad (\text{A.9})$$

$$\Delta m = m_{\text{pellet}} \times \frac{0,01 \times 16}{270} \quad (\text{A.10})$$

## Bibliography

- [1] ISO 3369, *Impermeable sintered metal materials and hardmetals — Determination of density*
- [2] ISO 9278, *Nuclear energy — Uranium dioxide pellets — Determination of density and volume fraction of open and closed porosity*







# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™