



BSI Standards Publication

**Nuclear energy —
Determination of total
hydrogen content in PuO_2
and UO_2 powders and UO_2 ,
 $(\text{U,Gd})\text{O}_2$ and $(\text{U,Pu})\text{O}_2$
sintered pellets — Inert gas
extraction and conductivity
detection method**

National foreword

This British Standard is the UK implementation of ISO 15651:2015.

The UK participation in its preparation was entrusted to Technical Committee NCE/9, Nuclear fuel cycle technology.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 75462 3

ICS 27.120.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

Nuclear energy — Determination of total hydrogen content in PuO_2 and UO_2 powders and UO_2 , $(\text{U,Gd})\text{O}_2$ and $(\text{U,Pu})\text{O}_2$ sintered pellets — Inert gas extraction and conductivity detection method

Énergie nucléaire — Dosage de la teneur totale en hydrogène de poudres de PuO_2 et UO_2 , et de pastilles frittées d' UO_2 , $(\text{U,Gd})\text{O}_2$ et $(\text{U,Pu})\text{O}_2$ — Méthode d'extraction par gaz inerte et méthode de mesure de la conductivité





COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
1 Scope		1
2 Normative references		1
3 Principle		1
4 Interference		1
5 Reagents and materials		1
6 Apparatus		2
7 Sampling		2
7.1 Sampling procedure		2
7.1.1 Powders.....		2
7.1.2 Pellet.....		3
7.2 Preparation.....		3
7.2.1 Powder.....		3
7.2.2 Pellet.....		3
8 Procedure		3
8.1 Blank test		3
8.2 Calibration		3
8.2.1 Calibration of the analyser		3
8.2.2 Check of the calibration		3
8.3 Determination		4
9 Calculation		4
10 Precision		4
11 Test report		5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 85, *Nuclear Energy*, Subcommittee SC 5, *Fuel Technology*.

Nuclear energy — Determination of total hydrogen content in PuO₂ and UO₂ powders and UO₂, (U,Gd)O₂ and (U,Pu)O₂ sintered pellets — Inert gas extraction and conductivity detection method

1 Scope

This International Standard describes a procedure for measuring the total hydrogen content of UO₂ and PuO₂ powders (up to 2 000 µg/g oxide) and of UO₂ and (U,Gd)O₂ and (U,Pu)O₂ pellets (up to 10 µg/g oxide). The total hydrogen content results from adsorbed water, water of crystallization, hydrocarbon, and other hydrogenated compounds which can exist as impurities in the fuel.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/IEC Guide 98-3:2008, *Uncertainty of measurement — Part 3: Guide to the expression of uncertainty in measurement (GUM: 1995)*

3 Principle

The total hydrogen content is determined using a hydrogen analyser. The hydrogen analyser is based on the carrier gas method using argon or nitrogen as carrier gas. The samples to be analysed are heated up to a temperature of more than 1 770 °C in a graphite crucible. At that temperature, all volatile components are removed. The hydrogen containing compounds are cracked and released as hydrogen, oxygen, nitrogen, and carbon monoxide. The released gas is purified in the carrier gas stream, for example by oxidation and adsorption columns. The hydrogen is separated by chromatographic means and analysed in a thermal conductivity cell.

4 Interference

The temperature of >1 770 °C should be reached in a short time, within approximately 5 s; if not, the decomposition of the released water to hydrogen and oxygen might not be complete.

At temperatures of more than 2 200 °C, carbon dioxide is released because of a reduction of UO₂ by graphite according to the reaction below; carbon dioxide will interfere with the thermal conductivity measurement.



5 Reagents and materials

Use reagents of recognized analytical grade. The reagents and materials below serve as examples to be used according to manufacturer recommendation.

5.1 Carrier gas. Use argon with a purity of a volume fraction ≥99,995 % or nitrogen with a purity of a volume fraction ≥99,998 %.

5.2 Calibration gas. If calibration is performed with gas, use Argon or nitrogen with certified hydrogen content or carrier gas mixed with a known amount of hydrogen with a purity of a volume fraction $\geq 99,999\%$.

5.3 Reference material.¹⁾ If calibration or calibration check is performed with a standard material, use a reference material with certified hydrogen content (e.g. titanium or zirconium).

5.4 Copper(II) oxide, CuO purifies the carrier gas (Ar/N₂), converting H₂ to H₂O.

5.5 Absorption media for H₂O. After converting H₂ to H₂O (§5.4), anhydrous [Mg(ClO₄)₂] is used to trap H₂O.

5.6 Oxidation reagent for CO, Schutze reagent (iodine pentoxide over silica gel) preceded by Hopcalite [manganese oxide/copper(II) oxide] oxidizes CO to CO₂ present in the carrier gas or extracted during measurement.

5.7 Absorption media for CO₂, sodium hydroxide over clay or equivalent will then absorb the CO₂.

5.8 Flux reagents for reference material. Tin, copper, or nickel granules are used as flux to accelerate the melting of reference material.

6 Apparatus

6.1 Hydrogen analyser. It will consist in a furnace capable to reach temperature of at least 2 200 °C, a thermal conductivity cell and gas purifying systems.

6.2 High purity graphite crucible, suitable for the appropriate sample types.

The impurity content should not exceed 2 µg/g.

6.3 Hydrogen free tin, copper, or nickel capsules.

6.4 Balance, with precision of 1 mg.

7 Sampling

7.1 Sampling procedure

7.1.1 Powders

Sampling is done with a tube shaped powder sampler having an inner diameter of more than 2,5 times of the maximum powder particle size. The sample shall be exposed to ambient conditions for not longer than 5 min because alterations of the powder sample due to moisture adsorption or desorption or oxidation have to be avoided. The sample has to be stored in tight containers. The gas volume in the container should be as low as possible. In case the analysis is not performed immediately after the sampling, the sample mass has to be controlled before and after storage period prior to the analysis. These precautions can be relaxed if the analysis process is made under controlled gas environment (glove box environment).

1) Reference materials are available for example from "National Institute of Standard and Technology (NIST)" or "LECO Corporation". This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of these products.

7.1.2 Pellet

When sampling the fuel pellets, ensure that pellets are not contaminated with H₂; use metal forceps or pincers for sampling pellets. The sample should be representative for the manufacturing process (e.g. storage of the pellets).

7.2 Preparation

7.2.1 Powder

Powder samples can be filled into capsules (6.3) which are subsequently closed. Alternatively, the powder samples can be inserted as pressed bodies ("green pellets" prepared without additives).

NOTE A compromise solution between precision and sustainable development (wastes recycling) is to delete the use of capsules.

7.2.2 Pellet

Sintered fuel pellets can be analysed without any preparation step. If the pellets are dried before the rod filling in the rod fabrication process, the sample should be dried before analysis to be representative of manufacturing conditions.

8 Procedure

8.1 Blank test

The analyser is checked by performing blank measurements proving the integrity of the purifying units and the tightness of the equipment. Blank values exceeding the analyser detection limit require adequate measures of correction.

8.2 Calibration

8.2.1 Calibration of the analyser

Hydrogen analyser shall be calibrated before sample measurement. There are two possibilities of calibration:

- calibration with gas;
- calibration with certified standards.

The calibration will depend on the type of analyser, it can be performed by the analyser manufacturer and/or the final user. The calibration range and the number of standards will depend on the equipment, the final use, and the range of available standards.

In case of calibration with gas, a well-defined volume of the calibration gas (5.2), which is corrected on standard conditions, is inserted and analysed. This calibration is performed three times.

In the case of calibration with certified standards, they are weighed to the nearest 1 mg accuracy.

8.2.2 Check of the calibration

To check the calibration of the equipment, reference material (5.3) is weighed to the nearest 1 mg accuracy [flux reagents (5.8) can be used to help for fusion]. The released hydrogen is determined. The measured values can differ from the certified values by not more than the total uncertainty of the analysis process. If not, the calibration is repeated.

8.3 Determination

Weigh the sample to the nearest 1 mg.

The empty graphite crucible is purified in a carrier gas stream during at least 30 s by heating at a temperature above the analysis temperature.

Insert sample (sintered pellet, green pellet, encapsulated powder) into the analyser.

Purge with carrier gas during at least 30 s.

The sample is dropped into the crucible and heated up to at least 1 770 °C.

The hydrogen content is measured, during at least 60 s to extract H₂ from all the hydrogenated compounds.

9 Calculation

Calculate the hydrogen mass fractions (µg/g sample) using Formula (1):

$$w_{H_2} = \frac{m_{H_2}}{m} \quad (1)$$

where

w_{H_2} is the hydrogen mass fractions, in µg/g sample;

m_{H_2} is the mass of the hydrogen in µg, corrected of the blank;

m is the mass of the sample, in g.

If a result expressed as µg hydrogen per g U, µg hydrogen per g(U+Pu), or µg hydrogen per g(U+Gd) is required, the results are converted as follows:

$$\left[w_{H_2} \right]_M \text{ } \mu\text{g} / \text{g}M = \frac{(H \text{ } \mu\text{g} / \text{oxide}) \times 100}{\% M \text{ content of sample}} \quad (2)$$

where

$\left[w_{H_2} \right]_M$ is the hydrogen mass fractions, in µg /gM;

M is U or (U+Pu) or (U+Gd).

10 Precision

The repeatability standard deviation, S_r , of the hydrogen detection system can reach $s_r = 0,18\text{ppm} \rightarrow \text{RSD} = 15 \%$ relative in the following conditions:

- 10 measurements of a reference material;
- same calibration with H₂-gas during the 10 measurements; and
- reference material of about 10 g with 1,2 µg/g of H₂;

The total uncertainty, taking into account the accuracy of the reference material and the precision error of the calibration (mainly influenced by the kinetics of moisture release and of H₂O-reduction on the

hot graphite crucible), can reach 35 % relative or more if the measurement result is very close to the detection limit.

11 Test report

The test report shall include the following information:

- a) identification of sample;
- b) the method used by reference to this International Standard, (i.e. ISO 15651);
- c) the results and the form in which they are expressed;
- d) the detection limit;
- e) any deviations from the procedure;
- f) any unusual features observed;
- g) the location and date of the test.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™