

BS ISO 16014-4:2012



BSI Standards Publication

Plastics — Determination of average molecular mass and molecular mass distribution of polymers using size-exclusion chromatography

Part 4: High-temperature method

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 16014-4:2012. It supersedes BS ISO 16014-4:2003 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/21, Testing of plastics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 65174 8

ICS 83.080.01

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2012.

Amendments issued since publication

Date	Text affected
------	---------------

**Plastics — Determination of average
molecular mass and molecular mass
distribution of polymers using size-
exclusion chromatography —**

**Part 4:
High-temperature method**

*Plastiques — Détermination de la masse moléculaire moyenne
et de la distribution des masses moléculaires des polymères par
chromatographie d'exclusion stérique —*

Partie 4: Mesurage aux températures élevées





COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
5.1 Eluent	1
5.2 Reagent for column evaluation	1
5.3 Molecular mass standards	2
5.4 Reagent for flow rate marker (internal standard)	2
5.5 Additives	2
6 Apparatus	2
6.1 General	2
6.2 Eluent reservoir	2
6.3 Pumping system	2
6.4 Injector	2
6.5 Columns	2
6.6 Detector	3
6.7 Tubing	3
6.8 Temperature-control unit	3
6.9 Recorder and plotter	3
6.10 Data-processing system	3
6.11 Other components	3
7 Procedure	3
7.1 Preparation of solutions of molecular mass standards	3
7.2 Preparation of sample solutions	4
7.3 Preparation of solutions for column performance evaluation	4
7.4 Setting up the apparatus	5
7.5 Operating parameters	5
7.6 Number of determinations	5
8 Data acquisition and processing	5
9 Expression of results	6
10 Precision	6
10.1 General	6
10.2 Experimental conditions	6
10.3 Results of round-robin test	7
11 Test report	7
Annex A (informative) Further information on applicability of method	8
Annex B (informative) Further information on reagents	9
Annex C (informative) Further information on the round-robin test	10
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16014-4 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This second edition cancels and replaces the first edition (ISO 16014-4:2003), which has been technically revised. The main changes are as follows:

- a) the normative references have been updated;
- b) Subclause 6.1 (concerning the general requirements for the apparatus) has been revised;
- c) further information on the round-robin test carried out in 1999 has been added (see Annex C).

ISO 16014 consists of the following parts, under the general title *Plastics — Determination of average molecular mass and molecular mass distribution of polymers using size-exclusion chromatography*:

- *Part 1: General principles*
- *Part 2: Universal calibration method*
- *Part 3: Low-temperature method*
- *Part 4: High-temperature method*
- *Part 5: Method using light-scattering detection*

Plastics — Determination of average molecular mass and molecular mass distribution of polymers using size-exclusion chromatography —

Part 4: High-temperature method

1 Scope

This part of ISO 16014 specifies a method for determining the average molecular mass and the molecular mass distribution of polymers by size-exclusion chromatography (SEC) using an organic eluent at temperatures between 60 °C and 180 °C. The average molecular mass and the molecular mass distribution are calculated from a calibration curve prepared using polymer standards. Therefore, this test method is classified as a relative method (see ISO 16014-1:2012, Annex A).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 16014-1:2012, *Plastics — Determination of average molecular mass and molecular mass distribution of polymers using size-exclusion chromatography — Part 1: General principles*

ISO 16014-2, *Plastics — Determination of average molecular mass and molecular mass distribution of polymers using size-exclusion chromatography — Part 2: Universal calibration method*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472 and in ISO 16014-1 apply.

4 Principle

See ISO 16014-1:2012, Clause 4.

5 Reagents

5.1 Eluent

For a general discussion of eluents, see ISO 16014-1:2012, 5.1.

For examples of eluents used for SEC measurements at temperatures > 60 °C, see Annex B.

5.2 Reagent for column evaluation

See ISO 16014-1:2012, 5.2.

There are several low molecular mass compounds that can be used, for example diphenylmethane when 1,2-dichlorobenzene is used as eluent or ethylbenzene when 1,2,4-trichlorobenzene is used as eluent.

5.3 Molecular mass standards

See ISO 16014-1:2012, 5.3.

Some examples of commercially available molecular mass standards are given in Annex B.

5.4 Reagent for flow rate marker (internal standard)

See ISO 16014-1:2012, 5.4.

An example of a compound suitable for use as a flow rate marker is 2,6-di-*tert*-butyl-4-methylphenol when 1,2-dichlorobenzene or 1,2,4-trichlorobenzene is used as eluent.

5.5 Additives

Phenol-type antioxidants such as 2,6-di-*tert*-butyl-4-methylphenol should preferably be added to avoid degradation of the polymer sample. For further examples of antioxidants, see Annex B.

6 Apparatus

6.1 General

A schematic diagram of an SEC system is shown in ISO 16014-1:2012, Figure 1.

Either commercially available or assembled SEC systems may be used, provided they meet the component requirements specified and have the capability to maintain a constant column temperature between 60 °C and 180 °C. However, components connected upstream of the injector, such as the eluent reservoir, the pumping system and tubing, does not need to be kept at the same temperature as the columns.

6.2 Eluent reservoir

See ISO 16014-1:2012, 6.2.

As mentioned in 6.1, it is not necessary to keep the eluent reservoir at the same temperature as the columns.

6.3 Pumping system

See ISO 16014-1:2012, 6.3.

In order to maintain the flow rate accurate to within $\pm 0,3$ %, the pumping system shall be kept at a constant temperature. As mentioned in 6.1, it is not, however, necessary to keep the pumping system at the same temperature as the columns.

6.4 Injector

See ISO 16014-1:2012, 6.4.

In order to ensure that the polymer solution remains clear, without any precipitation, the injector temperature-control equipment shall be capable of keeping the injector at the same temperature, to within ± 1 °C, as the columns. As manual injection is impossible at such temperatures, an automatic injection system shall be used.

6.5 Columns

See ISO 16014-1:2012, 6.5.

Organic or inorganic packing materials may be used, and there are no limitations on particle size or shape except that, when analysing high molecular mass and/or shear-sensitive polymers, the particle size should be large enough for no rupture of the polymer chain to occur during elution of the polymers.

The set of columns used shall have a theoretical plate number $> 12\ 000/m$, and the resolution factor R shall be $> 1,5$ close to the polymer peak. The asymmetry factor shall be within the range $1,00 \pm 0,15$. The set of columns used should preferably cover the whole range of molecular masses being determined, and the calibration curve shall be as linear as possible (the correlation factor shall be very close to 1). Determination of the theoretical plate number, the resolution factor and the asymmetry factor of the columns shall be carried out as described in ISO 16014-1:2012, 6.5.

The column temperature-control equipment shall be capable of keeping the columns within $\pm 0,5$ °C of the operating temperature, which shall be between 60 °C and 180 °C.

6.6 Detector

See ISO 16014-1:2012, 6.6.

The detector temperature-control equipment shall be capable of keeping the detector within $\pm 0,5$ °C of the temperature set, in order to meet the requirements for flow rate and baseline stability (sensitivity). It is recommended that the columns and detector be kept at the same temperature.

6.7 Tubing

See ISO 16014-1:2012, 6.7.

The temperature of the tubing shall be kept constant and high enough to ensure that the column performance requirements are met, but it is not necessary to keep the tubing at the same temperature as the column.

6.8 Temperature-control unit

One of the important factors in SEC is that all components need to be kept at a constant temperature and, with the method described in this part of ISO 16014, some of them need to be kept at a high temperature. Therefore, an accurate temperature-control system is essential to meet the performance requirements for SEC.

6.9 Recorder and plotter

See ISO 16014-1:2012, 6.9.

6.10 Data-processing system

See ISO 16014-1:2012, 6.10.

6.11 Other components

In addition to the components described above, a column guard filter, a pressure monitor, a pulse damper or related components can be used, if necessary.

7 Procedure

7.1 Preparation of solutions of molecular mass standards

The molecular mass standards used to prepare the calibration curve should preferably be selected so as to cover the range of molecular masses of the polymer being analysed and so that there are at least two standards in each molecular mass decade. Solutions may be prepared which contain more than one narrow molecular mass distribution standard, but only if the standards are perfectly separated from each other on the chromatogram. Solutions of standards of molecular mass $> 1\ 000\ 000$ shall be prepared separately.

If molecular mass standards having the same chemical structure as the polymer being analysed are not available, the calibration curve may be prepared using standards consisting of a different type of polymer, and a universal calibration curve prepared for this different type of polymer (see ISO 16014-2).

If gentle shaking and/or stirring or heating is required to accelerate dissolution, the duration shall be as short as possible to avoid any rupture of the polymer chains.

Filtration of the solutions is recommended to protect the column from clogging. In such cases, membrane filters or sintered-metal filters with a pore size between 0,2 μm and 1 μm shall be used. If solid material is observed on the filter, indicating incomplete dissolution, repeat the dissolution process. If a membrane filter is used, the membrane and backing shall be inert to the solvent being used.

In general, use solutions within 48 h of preparation. However, longer storage times are allowed if the solution is kept in a cool, dark place to prevent polymer degradation and solvent evaporation.

Recommended concentrations for solutions of molecular mass standards are as follows:

$M_p < 5 \times 10^4$	0,4 mg/cm ³
$5 \times 10^4 \leq M_p < 10^6$	0,2 mg/cm ³
$10^6 \leq M_p$	0,1 mg/cm ³

If a viscometric detector is used, higher molecular mass standard concentrations are required in the lower molecular mass region. Sample elution times should preferably be measured at lower concentrations, however.

7.2 Preparation of sample solutions

Prepare sample solutions by weighing accurately 10 mg to 250 mg of sample into a 10 cm³ to 50 cm³ flask. Add eluent and, if necessary, an internal standard and dissolve, in the same way as for the molecular mass standard solutions, within 30 min. In general, samples with molecular masses $> 10^5$ have a slow rate of dissolution, however, and it might be necessary to continue beyond 30 min to ensure complete dissolution. Filtration of solutions is recommended to avoid clogging of the column.

If solid material is observed on the filter, indicating incomplete dissolution, repeat the dissolution process. Following preparation, transfer sample solutions to vials and store at room temperature.

The sample must be heated sufficiently to dissolve it completely. Excessive or long heating shall be avoided, however, as this might lead to thermal or oxidative degradation. The optimum dissolution temperature and time should preferably be determined experimentally. For example, except for high molecular mass or high-density samples, polyethylene can be dissolved in 1,2-dichlorobenzene by heating at 140 °C for 1,5 h. Polyethylene with a molecular mass $> 10^6$ is more difficult to dissolve, requiring higher temperatures and longer times.

Before injection, sample solutions may be kept at a temperature between room temperature and the dissolution temperature. The temperature of the injector shall be sufficiently high, and the dwell time of the solution in the injector sufficiently long, to ensure that the sample remains dissolved and no precipitate forms, but the temperature shall not be so high, or the dwell time so long, that degradation of the sample occurs.

Sample solution concentrations shall not exceed the following limits:

$M_w < 1 \times 10^5$	5,0 mg/cm ³
$1 \times 10^5 \leq M_w < 10^6$	2,0 mg/cm ³
$10^6 \leq M_w$	0,5 mg/cm ³

7.3 Preparation of solutions for column performance evaluation

Prepare a 10 mg/cm³ solution of a suitable low molecular mass compound to determine the theoretical plate number, asymmetry factor and resolution factor of the set of columns.

7.4 Setting up the apparatus

Place the amount of eluent required for the SEC measurements in the reservoir and degas. Flush all the SEC components, except for the columns, with fresh eluent. Connect the set of columns into the system. Inspect all connections for leakage under the test conditions.

Keep the system at the test conditions (e.g. flow rate, detection sensitivity and temperature) until a flat baseline is obtained, with no drift or noise.

7.5 Operating parameters

7.5.1 Flow rate

A flow rate of approximately 1 cm³/min is recommended for a series of two or three high-performance columns of approximately 30 cm in length and 8 mm in diameter. For high molecular mass and/or shear-sensitive polymers, the flow rate should preferably be reduced so that no chain rupture will occur during elution of the polymer.

7.5.2 Injection masses and injection volumes

The mass of polymer sample and volume of sample solution injected depend on the column dimensions and the detector sensitivity. The optimum sample injection mass has been found experimentally to be approximately 0,01 mg per cubic centimetre of empty column (without packing). The maximum mass injected shall be < 0,1 mg per cubic centimetre of empty column. The maximum injection volume shall be < 0,01 cm³ per cubic centimetre of empty column.

The injection volumes of the solutions of molecular mass standards shall be the same as for the sample solution.

The recommended injection volume of the solution of low molecular mass compound is the same as that of the sample solution.

7.5.3 Temperature of, and dwell time in, injector

The temperature of the injection port should be the same as that of the columns, and it shall be demonstrated that the dwell time of sample solutions in the injector (including the autosampler, if used) does not cause degradation of the sample.

7.5.4 Column temperature

The column temperature should be selected based mainly on the solubility of the sample, the viscosity and boiling point of the eluent, and the ambient temperature.

7.5.5 Detector sensitivity

The signal intensity depends on the amount of sample injected and on the specific refractive index increment dn/dc for an RI detector and the absorbance per unit mass concentration for a UV detector. The detector sensitivity should be set to obtain a strong peak signal for the sample to ensure accurate data handling.

The linear relationship between solute concentration and peak height shall be maintained by keeping the sensitivity at the same setting.

7.6 Number of determinations

Carry out at least two sample runs to demonstrate the repeatability of the positions and shapes of the peaks in the chromatogram.

8 Data acquisition and processing

See ISO 16014-1:2012, Clause 8.

9 Expression of results

See ISO 16014-1:2012, Clause 9.

10 Precision

10.1 General

The precision of this test method was determined in round-robin testing carried out in 1999 in accordance with ISO 5725-1 and ISO 5725-2.

10.2 Experimental conditions

The test samples, which included three types of polyethylene and one type of polypropylene, and the calibration standards of narrow molecular mass distribution were distributed to the participating laboratories by the organizer. The details of the round-robin were as follows:

Polymer samples	Sample A	Polyethylene (high molecular mass, broad MMD sample)
	Sample E	Polyethylene (narrow MMD sample, NIST SRM-1475)
	Sample F	Polyethylene (low molecular mass, broad MMD sample)
	Sample G	Polypropylene (broad MMD sample)
Calibration		14 polystyrene standards
Column packing material		Polystyrene gel
Eluents		1,2-Dichlorobenzene and 1,2,4-trichlorobenzene
Column temperature		135 °C or 140 °C
Number of laboratories		11

NOTE The higher column temperature of 140 °C was used for the PE samples containing components of molecular mass $> 1 \times 10^6$.

10.3 Results of round-robin test

The results, expressed as repeatability and reproducibility, are summarized in Table 1. The raw data are shown in Annex C.

Table 1 — Results of round-robin test for high-temperature SEC

Polymer	Average values of M_n and M_w^a		Repeatability, s_r^a		Reproducibility, s_R^a	
			%		%	
	Tosoh ^b	PL ^c	Tosoh ^b	PL ^c	Tosoh ^b	PL ^c
Sample A (polyethylene)	$M_n = 130\ 000$ (5/11) ^d	$M_n = 145\ 000$ (6/10)	1,72	2,19	7,21	14,22
	$M_w = 526\ 000$ (9/11)	$M_w = 574\ 000$ (9/10)	2,18	3,08	11,35	12,95
Sample E (polyethylene)	$M_n = 39\ 200$ (11/11)	$M_n = 39\ 100$ (10/10)	3,50	4,68	11,26	11,99
	$M_w = 120\ 000$ (10/11)	$M_w = 128\ 000$ (10/10)	1,40	1,52	9,75	13,23
Sample F (polyethylene)	$M_n = 57\ 400$ (10/11)	$M_n = 55\ 100$ (10/10)	3,26	7,15	14,55	14,56
	$M_w = 218\ 000$ (11/11)	$M_w = 239\ 000$ (10/10)	1,67	2,14	7,86	11,21
Sample G (polypropylene)	$M_n = 68\ 100$ (10/11)	$M_n = 69\ 100$ (10/10)	5,86	5,73	21,33	17,49
	$M_w = 323\ 000$ (9/11)	$M_w = 363\ 000$ (10/10)	1,29	2,34	4,59	11,24

NOTE Sample A shows a very low standard deviation for M_n because of the existence of six outliers. If the results from all 11 of the laboratories are used, this gives a value of s_R of 35,61 % for M_n . Sample A was found to be unsuitable because it contains components of extremely high molecular mass beyond the effective range of the calibration curve.

^a Outliers were eliminated by Grubbs' and Cochran's methods^{[1],[3]}.

^b Polystyrene calibration standards supplied by Tosoh Co. (Japan).

^c Polystyrene calibration standards supplied by Polymer Laboratories Ltd. (United Kingdom).

^d Numbers in brackets indicate (total minus outliers)/(total number of laboratories).

11 Test report

See ISO 16014-1:2012, Clause 11.

In addition to the information required by ISO 16014-1:2012, 11.2, on the apparatus and measurement parameters, the test report shall contain the following:

- the temperature of the injection port and the dwell time of the sample solution in it;
- the temperature at which the sample was dissolved and the length of time necessary.

Annex A (informative)

Further information on applicability of method

The method described in this part of ISO 16014 is suitable for measurements at temperatures between 60 °C and 180 °C and assumes the sample is a linear homopolymer. However, because it is a relative method, it is also applicable to non-linear homopolymers, such as branched, star-shaped, comb-like, stereo-regular and stereo-irregular polymers, and to other types of polymer, such as random, block, graft and heterophasic copolymers. The method is applicable to molecular masses ranging from that of the monomer to 3 000 000, but is not applicable to samples that contain > 30 % of components having a molecular mass < 1 000.

The method cannot be used with water as eluent, i.e. for water-soluble polymers, or at column temperatures > 180 °C (e.g. for polyphenylenesulfide) or with polymers that exhibit appreciable secondary effects such as adsorption of the polymer molecules on the column packing material or repulsion between the polymer molecules and the packing material.

Annex B (informative)

Further information on reagents

B.1 Examples of suitable eluents

The following are examples of eluents for SEC measurements at temperatures > 60 °C:

- a) 1,2-dichlorobenzene;
- b) 1,2,4-trichlorobenzene;
- c) 1-chloronaphthalene;
- d) toluene;
- e) *N,N*-dimethylformamide.

B.2 Narrow molecular mass distribution standards

See ISO 16014-1, Annex B.

B.3 Additives

The following are examples of additives which may be added to the sample as an antioxidant for SEC measurements at temperatures > 60 °C:

- 2,6-Di-*tert*-butyl-4-methylphenol
- 4-Hydroxymethyl-2,6-di-*tert*-butylphenol
- 1,1,3-Tri(*tert*-butylhydroxymethylphenyl)butane
- 4,4'-Thio-*bis*-(6-*tert*-butyl-*m*-cresol)

Inorganic salts like lithium bromide are also used as additives in high-temperature SEC when *N,N*-dimethylformamide is used as eluent.

Annex C (informative)

Further information on the round-robin test

C.1 Raw data from round-robin test

Tables C.1 to C.4 present the raw data (molecular mass averages and variances) obtained in the round-robin test. Three sample runs (see 7.6) were carried out for each determination (i.e. $n = 3$).

Table C.1 — Molecular mass averages and variances obtained for polyethylene (sample A)

Laboratory	$M_n (\times 10^{-4})$		$M_w (\times 10^{-4})$	
	Average	Variance	Average	Variance
Sample A (polyethylene)				
Calibration: polystyrene standards (Tosoh)				
A	2,29	(0,015 7)	57,4	0,26
B	2,06	(0,007 2)	48,4	0,21
E	1,29	0,000 1	49,9	0,21
F	1,38	(0,061 0)	45,5	(9,62)
G	1,19	0,000 7	54,6	2,73
H	1,42	0,000 8	58,4	1,95
I	1,40	0,000 8	46,8	2,21
J	(1,75)	0,000 4	43,7	0,08
K	(3,17)	0,008 7	(114,9)	0,64
L	1,35	0,000 1	61,9	3,18
M	1,30	(0,030 4)	51,9	0,97
Sample A (polyethylene)				
Calibration: polystyrene standards (Polymer Laboratories)				
A	1,57	0,001 9	52,2	3,87
B	(2,21)	0,001 7	58,9	2,50
F	1,40	(0,038 1)	47,5	10,89
G	1,21	0,000 7	62,0	3,50
H	1,55	0,000 2	71,9	1,78
I	1,43	0,000 7	54,0	3,06
J	1,74	0,000 4	50,3	0,12
K	(3,32)	(0,009 9)	(135,1)	0,88
L	1,24	0,002 1	61,8	2,22
M	1,30	(0,008 1)	58,1	0,20
NOTE Values in brackets are outliers.				

Table C.2 — Molecular mass averages and variances obtained for polyethylene (sample E)

Laboratory	$M_n (\times 10^{-4})$		$M_w (\times 10^{-4})$	
	Average	Variance	Average	Variance
Sample E (polyethylene)				
Calibration: polystyrene standards (Tosoh)				
A	4,64	0,008	13,0	0,08
B	4,13	0,016	13,4	0,01
E	3,80	0,004	12,6	0,01
F	3,28	0,035	10,8	0,00
G	4,07	0,028	12,3	0,06
H	3,28	0,081	10,6	0,07
I	3,90	0,001	11,8	0,00
J	3,63	0,003	10,0	0,01
K	4,58	0,002	13,6	(0,46)
L	3,82	0,010	12,6	0,01
M	3,98	0,020	12,6	0,02
Sample E (polyethylene)				
Calibration: polystyrene standards (Polymer Laboratories)				
A	3,19	0,003	10,2	0,01
B	4,38	0,033	15,1	0,03
F	3,40	0,038	11,9	0,00
G	4,14	0,029	13,3	0,08
H	3,42	0,074	11,5	0,09
I	3,98	0,002	12,8	0,01
J	3,67	0,003	10,7	0,02
K	4,63	0,082	14,9	0,04
L	4,17	0,020	14,2	0,09
M	4,08	0,052	13,0	0,00
NOTE Values in brackets are outliers.				

Table C.3 — Molecular mass averages and variances obtained for polyethylene (sample F)

Laboratory	$M_n (\times 10^{-4})$		$M_w (\times 10^{-4})$	
	Average	Variance	Average	Variance
Sample F (polyethylene)				
Calibration: polystyrene standards (Tosoh)				
A	7,32	0,009	23,80	0,244
B	5,31	0,109	21,90	0,003
E	5,19	0,003	21,10	0,004
F	5,68	0,022	19,30	0,223
G	5,90	0,005	22,30	0,513
H	3,87	(0,445)	20,30	0,111
I	5,33	0,095	20,10	0,003
J	6,14	0,013	21,60	0,001
K	6,82	0,061	25,40	0,061
L	4,57	0,000	22,10	0,166
M	5,11	0,033	21,70	0,135
Sample F (polyethylene)				
Calibration: polystyrene standards (Polymer Laboratories)				
A	5,17	0,033	19,0	0,19
B	5,77	0,312	25,0	0,27
F	5,90	0,024	21,6	0,28
G	6,05	0,005	24,7	0,67
H	4,17	0,347	23,0	0,16
I	5,45	0,105	22,4	0,00
J	6,25	0,015	23,9	0,00
K	6,62	0,546	29,2	0,39
L	4,24	0,163	25,2	0,10
M	5,52	0,006	24,7	0,53
NOTE Values in brackets are outliers.				

Table C.4 — Molecular mass averages and variances obtained for polypropylene (sample G)

Laboratory	$M_n (\times 10^{-4})$		$M_w (\times 10^{-4})$	
	Average	Variance	Average	Variance
Sample G (polyethylene)				
Calibration: polystyrene standards (Tosoh)				
A	9,69	0,062	34,70	0,10
B	6,89	0,086	31,80	0,62
E	7,27	0,001	32,20	0,02
F	6,35	0,194	32,60	(1,40)
G	6,60	0,032	32,90	0,49
H	4,00	0,139	31,50	0,06
I	5,99	0,439	30,60	0,12
J	8,08	0,172	30,20	0,08
K	10,49	(1,299)	41,60	0,15
L	6,57	0,096	34,10	0,03
M	6,68	0,370	32,40	0,05
Sample G (polyethylene)				
Calibration: polystyrene standards (Polymer Laboratories)				
A	7,18	0,139	28,5	0,01
B	7,36	0,012	37,3	1,42
F	6,64	0,203	36,1	1,69
G	6,77	0,036	36,8	0,65
H	4,46	0,156	36,4	0,19
I	6,15	0,467	34,5	0,16
J	8,26	0,194	33,8	0,10
K	8,96	0,191	45,0	2,06
L	6,55	0,007	38,0	0,79
M	6,74	0,161	36,3	0,15
NOTE Values in brackets are outliers.				

Bibliography

- [1] GRUBBS, F.E., and BECK, G.: *Technometrics*, **14**, p. 847 (1972)
- [2] ISO 5725-1, *Accuracy (trueness and precision) of measurement methods and results — Part 1: General principles and definitions*
- [3] ISO 5725-2, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™