

BS ISO 16131:2012



BSI Standards Publication

Leather — Upholstery leather characteristics — Selection of leather for furniture

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 16131:2012.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 66012 2

ICS 59.140.99; 97.140

Compliance with a British Standard cannot confer immunity from legal obligations.

In particular, attention is drawn to:

Statutory Instrument 1988 No. 1324, The Furniture and Furnishings (Fire) (Safety) Regulations 1988;

Statutory Instrument 1989 No. 2358, The Furniture and Furnishings (Fire) (Safety) (Amendment) Regulations 1989;

Statutory Instrument 1993 No. 207, The Furniture and Furnishings (Fire) (Safety) (Amendment) Regulations 1993; and

Statutory Instrument 2010 No. 2205, The Furniture and Furnishings (Fire) (Safety) (Amendment) Regulations 2010.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 29 February 2012.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 16131:2012

ISO
16131

First edition
2012-02-01

**Leather — Upholstery leather
characteristics — Selection of leather for
furniture**

*Cuir — Caractéristiques des cuirs pour garniture — Sélection des cuirs
pour l'ameublement*



Reference number
ISO 16131:2012(E)

© ISO 2012



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16131 was prepared by Technical Committee ISO/TC 120, *Leather*, Subcommittee SC 2, *Tanned leather*.

It is based on EN 13336:2004, *Leather — Upholstery leather characteristics — Guide for selection of leather for furniture*.

Leather — Upholstery leather characteristics — Selection of leather for furniture

1 Scope

This International Standard specifies sampling and test methods, and gives recommended values for, upholstery leather for furniture.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-B02, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test*

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 2419, *Leather — Physical and mechanical tests — Sample preparation and conditioning*

ISO 2588, *Leather — Sampling — Number of items for a gross sample*

ISO 3377-1, *Leather — Physical and mechanical tests — Determination of tear load — Part 1: Single edge tear*

ISO 4044, *Leather — Chemical tests — Preparation of chemical test samples*

ISO 4045, *Leather — Chemical tests — Determination of pH*

ISO 5402-1, *Leather — Determination of flex resistance — Part 1: Flexometer method*

ISO 8191-1, *Furniture — Assessment of the ignitability of upholstered furniture — Part 1: Ignition source: smouldering cigarette*

ISO 8191-2, *Furniture — Assessment of the ignitability of upholstered furniture — Part 2: Ignition source: match-flame equivalent*

ISO 11640, *Leather — Tests for colour fastness — Colour fastness to cycles of to-and-fro rubbing*

ISO 11641, *Leather — Tests for colour fastness — Colour fastness to perspiration*

ISO 11644, *Leather — Test for adhesion of finish*

ISO 15700, *Leather — Tests for colour fastness — Colour fastness to water spotting*

ISO 17233, *Leather — Physical and mechanical tests — Determination of cold crack temperature of surface coatings*

3 General principles

This International Standard considers the performance of different types of leather intended for upholstery. The characteristics, recommended values, and test methods are specified in Tables A.1, A.2, and A.3. Subsidiary characteristics are stated in Table A.4.

4 Sampling

4.1 When possible, the location and identification of laboratory samples shall be in accordance with ISO 2418.

4.2 The number of samples shall be by agreement between the interested parties except in cases of dispute when the number of samples shall be in accordance with ISO 2588. If the lot size of the leathers is high, the maximum number of samples shall be five.

5 Conditioning and sampling preparation

Leather samples shall be conditioned and prepared for physical, mechanical and fastness tests in accordance with ISO 2419.

Leather samples for chemical tests shall be conditioned and prepared in accordance with ISO 4044.

6 Characteristics, test methods, and recommended values

The essential characteristics stated in Tables A.1, A.2, and A.3 shall all be taken into account, even if they can have different relative weight in the process of evaluation relative to use. The subsidiary characteristics stated in Table A.4 shall be agreed by the parties concerned according to the intended end use of the leather.

7 Test report

The test report shall contain at least the following information:

- a) reference to this International Standard;
- b) all information necessary for the complete identification of the sample;
- c) the sampling method used, if required;
- d) date and place of the test;
- e) test results and number of test specimens;
- f) conditioning and test atmosphere used;
- g) any deviation from this International Standard.

Annex A (normative)

Selection criteria for upholstery leather for furniture

A.1 Essential characteristics, recommended values, and test methods for upholstery leather for furniture

See Tables A.1 to A.3.

Table A.1 — Aniline, suède and nubuck

Leather characteristic	Recommended value	Test method
Colour fastness to — to-and-fro rubbing, dry, 50 cycles, grey scale — to-and-fro rubbing, wet, 20 cycles, grey scale — perspiration, 20 cycles, grey scale	Change of leather colour and pad staining ≥ 3 ≥ 3 ≥ 3	ISO 11640 ISO 11640 ISO 11641 in which perspiration solution is defined
	While these values are typical of those expected, it is advisable to issue appropriate guidance with upholstered furniture to inform consumers of likely performance as well as in-service care and maintenance instructions to avoid unnecessary problems.	
Colour fastness to — light, blue scale	≥ 3	ISO 105-B02
pH of water extract If the pH value is below 4, Δ pH	$\geq 3,2$ $\leq 0,7$	ISO 4045
Tear strength, N	≥ 20	ISO 3377-1

Table A.2 — Semi-aniline

Leather characteristic	Recommended value	Test method
Colour fastness to — to-and-fro rubbing, dry, 500 cycles, grey scale — to-and-fro rubbing, wet, 80 cycles, grey scale — perspiration, 50 cycles, grey scale	Change of leather colour and pad staining ≥4 3 to 4 3 to 4 While these values are typical of those expected, it is advisable to issue appropriate guidance with upholstered furniture to inform consumers of likely performance as well as in-service care and maintenance instructions to avoid unnecessary problems.	ISO 11640 ISO 11640 ISO 11641 in which perspiration solution is defined
Colour fastness to — light, blue scale	≥4	ISO 105-B02
Finish adhesion, dry, N/10 mm	≥2	ISO 11644
pH of water extract If the pH value is below 4, ΔpH	≥3,2 ≤0,7	ISO 4045
Tear strength, N	≥20	ISO 3377-1

Table A.3 — Pigmented

Leather characteristic	Recommended value	Test method
Colour fastness to — to-and-fro rubbing, dry, 500 cycles, grey scale — to-and-fro rubbing, wet, 250 cycles, grey scale — perspiration, 80 cycles, grey scale	Change of leather colour and pad staining ≥4	ISO 11640
	3 to 4 3 to 4	ISO 11640 ISO 11641 in which perspiration solution is defined
	While these values are typical of those expected, it is advisable to issue appropriate guidance with upholstered furniture to inform consumers of likely performance as well as in-service care and maintenance instructions to avoid unnecessary problems.	
Colour fastness to — light, blue scale	≥5	ISO 105-B02
Finish adhesion, N/10 mm	≥2	ISO 11644
Flexing endurance	≥50 000 cycles (no finish damage cracks)	ISO 5402-1
pH of water extract If the pH value is below 4, ΔpH	≥3,2 ≤0,7	ISO 4045
Tear strength, N	≥20	ISO 3377-1

A.2 Subsidiary characteristics, recommended values, and test methods for upholstery leather for furniture

See Table A.4.

Table A.4 — All leather types

Leather characteristic	Recommended value	Test method
Burning behaviour	Pass	ISO 8191-1 and ISO 8191-2 No soaking
Cold crack resistance of finish, -15 °C	No finish cracks	ISO 17233
Colour fastness to water spotting, grey scale	≥3 (No permanent swelling)	ISO 15700

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™