

**BS ISO 16172:2011**



**BSI Standards Publication**

# **Continuous hot-dip metallic-coated steel sheet for corrugated steel pipe**

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 16172:2011. It supersedes BS ISO 16172:2006 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/109, Coated and Uncoated Flat Products to be Used for Cold Forming.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2011

ISBN 978 0 580 72836 5

ICS 77.140.50

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2011.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

---

---

**Continuous hot-dip metallic-coated steel  
sheet for corrugated steel pipe**

*Tôles en acier revêtues en continu par immersion à chaud pour tuyaux  
d'acier strié*





## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms, definitions and abbreviations .....</b>	<b>1</b>
<b>3.1 Terms and definitions .....</b>	<b>1</b>
<b>3.2 Abbreviations .....</b>	<b>2</b>
<b>4 Requirements .....</b>	<b>2</b>
<b>4.1 Chemical composition .....</b>	<b>2</b>
<b>4.2 Mechanical properties .....</b>	<b>2</b>
<b>5 Coating requirements .....</b>	<b>3</b>
<b>5.1 Coating mass .....</b>	<b>3</b>
<b>5.2 Coating adhesion .....</b>	<b>3</b>
<b>5.3 Surface treatment .....</b>	<b>3</b>
<b>6 Dimension and tolerances .....</b>	<b>3</b>
<b>6.1 Thickness .....</b>	<b>3</b>
<b>6.2 Length .....</b>	<b>4</b>
<b>6.3 Flat sheet .....</b>	<b>4</b>
<b>6.4 Other dimensions .....</b>	<b>4</b>
<b>7 Sampling .....</b>	<b>4</b>
<b>7.1 Chemical composition .....</b>	<b>4</b>
<b>7.2 Mechanical properties .....</b>	<b>4</b>
<b>7.3 Coating tests .....</b>	<b>5</b>
<b>8 Test methods .....</b>	<b>5</b>
<b>8.1 Tensile tests .....</b>	<b>5</b>
<b>8.2 Coating mass .....</b>	<b>5</b>
<b>9 Resubmission .....</b>	<b>5</b>
<b>10 Workmanship .....</b>	<b>5</b>
<b>11 Inspection and acceptance .....</b>	<b>6</b>
<b>12 Certification .....</b>	<b>6</b>
<b>13 Marking .....</b>	<b>6</b>
<b>14 Information to be supplied by the purchaser .....</b>	<b>6</b>
<b>Bibliography .....</b>	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16172 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 12, *Continuous mill flat rolled products*.

This second edition cancels and replaces the first edition (ISO 16172:2006), which has been technically revised.

# Continuous hot-dip metallic-coated steel sheet for corrugated steel pipe

## 1 Scope

This International Standard specifies the requirements for steel sheet used in the manufacture of corrugated steel pipe for storm sewers, culverts, drains, and similar uses. It covers sheet which is metallic coated by the continuous hot-dip process and is furnished in coils, flat cut lengths, and corrugated cut lengths.

Several metallic-coated materials are covered which relies on users to determine which product best serves their needs. Four different metallic coatings are included:

- zinc coated;
- zinc-5 % aluminium-mischmetal alloy coated;
- 55 % aluminum-zinc alloy coated;
- Al-Si alloy coated.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1460, *Metallic coatings — Hot dip galvanized coatings on ferrous materials — Gravimetric determination of the mass per unit area*

ISO 2178, *Non-magnetic coatings on magnetic substrates — Measurement of coating thickness — Magnetic method*

ISO 3497, *Metallic coatings — Measurement of coating thickness — X-ray spectrometric methods*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 16163, *Continuously hot-dipped coated steel sheet products — Dimensional and shape tolerances*

## 3 Terms, definitions and abbreviations

For the purposes of this document, the following terms, definitions and abbreviations apply.

### 3.1 Terms and definitions

#### 3.1.1

##### **fabricator**

⟨for corrugated metal pipe⟩ the organization that produces the finished pipe

#### 3.1.2

##### **fabricator**

⟨for structural plate pipe⟩ the organization that processes flat sheets and other items necessary for the field assembly of finished products

### 3.1.3

#### **manufacturer**

(for corrugated metal pipe) the organization that produces the metal sheet from which pipe is made

### 3.1.4

#### **purchaser**

(for corrugated metal pipe) the person or agency that purchases the finished pipe

NOTE With regard to this International Standard for sheet for corrugated steel pipe, the fabricator may also be considered as the purchaser of the sheet, where that term is used in this International Standard. Such an interpretation will not restrict the purchaser of finished pipe from enforcing any provisions of this specification.

### 3.1.5

#### **normal spangle coating**

coating formed as a result of the unrestricted growth of zinc or zinc alloy crystals during normal solidification of the coating

### 3.1.6

#### **minimized spangle coating**

a finer metallurgical coating formed as a result of treatment to restrict the formation of the normal coarse-grain coating structure of the Zn-5Al-MM coating type

## 3.2 Abbreviations

Zn: zinc

Zn-5Al-MM: zinc-5 % aluminum-mischmetal alloy

55Al-Zn: 55 % aluminum-zinc alloy

Al-Si: aluminum-silicon alloy

## 4 Requirements

### 4.1 Chemical composition

The chemical composition (heat analysis) of the base metal shall conform to the requirements of Table 1.

### 4.2 Mechanical properties

The metallic-coated sheet shall conform to the requirements listed in Table 2.

**Table 1 — Chemical composition**

<b>Element</b>	<b>Heat analysis</b>	<b>Product analysis</b>
Sulfur, max., %	0,05	0,06
Sum of carbon, manganese, phosphorus, sulfur and silicon, max., %	0,70	0,74



**Table 2 — Mechanical property requirements (*properties of flat sheet prior to fabrication*)<sup>a</sup>**

Tensile strength <sup>b</sup> , min., MPa	310
Yield strength <sup>b</sup> , min. MPa	230
Elongation, in 50 mm <sup>c</sup> , min., %	20
<p><sup>a</sup> To determine conformance with this specification, round each value for tensile strength and yield strength to the nearest 1 MPa and each value for elongation to the nearest 1 %.</p> <p><sup>b</sup> Yield strength and tensile strength are based on the thickness of the base metal. If tests are made after coating, determine the base metal thickness after stripping the coating from the ends of the specimen contacting the grips of the tension-testing machine prior to tensile testing.</p> <p><sup>c</sup> The elongation requirement does not apply to material tested after corrugating.</p>	

## 5 Coating requirements

### 5.1 Coating mass

The coating mass shall comply with the requirements listed in Table 3. The coating mass is the total amount of coating on both sides of the sheet, expressed in grams per square metre.

### 5.2 Coating adhesion

The adhesion of the coating shall be such that no peeling or flaking occurs while the coated sheet is being corrugated and formed into pipe.

### 5.3 Surface treatment

A surface treatment may be applied to the metallic-coated sheet to minimize the hazard of wet-storage stain during shipment and storage. However, the inhibiting characteristics of the treatment are limited and, if a shipment is received wet, the material shall be used immediately or dried.

**Table 3 — Coating mass (*total both sides*)**

Type	Coating mass		Equivalent coating thickness <sup>a</sup>	
	Triple spot, average, min. g/m <sup>2</sup>	Single spot, min. g/m <sup>2</sup>	Triple spot, average, min. µm	Single spot, min. µm
Zn	610	550	86	78
Zn-5Al-MM	640	550	93	80
55Al-Zn	210	180	56	48
Al-Si	305	275	95	86
<p><sup>a</sup> Coating thicknesses are approximate, for information only. Conversions are based on the following relationships: Zn coating: 1 g/m<sup>2</sup> = 0,141 5 µm; Zn-5Al-MM: 1 g/m<sup>2</sup> = 0,146 0 µm; 55Al-Zn coating: 1 g/m<sup>2</sup> = 0,266 36 µm; Al-Si coating: 1 g/m<sup>2</sup> = 0,331 28 µm.</p>				

## 6 Dimension and tolerances

### 6.1 Thickness

Sheet thickness shall conform to the dimensions specified in Table 4. The thickness of the sheet includes both the base metal and the coating.

## 6.2 Length

Permissible variations in the length of cut-length sheets, both flat and corrugated, shall be in accordance with ISO 16163.

## 6.3 Flat sheet

Permissible variations in the width and camber of flat sheet material shall be in accordance with ISO 16163. The flatness tolerances are given in Table 5.

## 6.4 Other dimensions

### 6.4.1 Corrugated configurations

Corrugations shall form smooth continuous curves and tangents. The dimensions of the corrugated sheet shall be in accordance with Table 6.

### 6.4.2 Corrugated sheet width

The covering width of corrugated sheet shall be in accordance with Table 7. The covering width is the distance between the crests of the extreme corrugations. The lip dimension of corrugated sheet shall be in accordance with Table 8 and is measured along the radial curvature from the crest of the corrugation to the edge of the sheet. There is no established tolerance for overall width, since the covering width and lip dimensions are the governing factors for the formed product.

**Table 4 — Coated-steel-sheet thickness requirements**

Specified thickness	Minimum thickness
mm	mm
1,0	0,9
1,3	1,2
1,6	1,5
2,0	1,8
2,8	2,6
3,5	3,3
4,3 <sup>a</sup>	4,0
NOTE Thickness is measured not less than 10 mm from an edge. On corrugated sheet, thickness is measured on the tangents of corrugations.	
<sup>a</sup> Aluminum-silicon-alloy-coated sheet is not available in these thicknesses.	

## 7 Sampling

### 7.1 Chemical composition

An analysis of each heat shall be made by the manufacturer to determine compliance with the requirements of Table 1.

### 7.2 Mechanical properties

One representative sample from each lot shall be used for the tensile test to determine conformance with the requirements of Table 2. Mechanical property tests shall be conducted on the sheet prior to corrugating or other fabrication, whenever possible. If the tests are made after corrugating, the specimens shall be taken on

the tangents of corrugations and used for the determination of tensile and yield strength only. A lot consists of 50 t or less of sheet of the same quality rolled to the same thickness and coating condition.

## 7.3 Coating tests

### 7.3.1 Coating mass

Test specimens shall be taken from each lot from a sample piece approximately 300 mm in length on the as-coated width. Three specimens are cut from the sample, one from the mid-width position and one from each side, not closer than 25 mm from the side edge. The minimum specimen area shall be 1 200 mm<sup>2</sup>.

### 7.3.2 Triple-spot test

The triple-spot test result shall be the average coating mass found on the three specimens taken according to 7.3.1.

### 7.3.3 Single-spot test

The single-spot test result shall be the minimum coating mass found on any one of the three specimens used for the triple-spot test.

## 8 Test methods

### 8.1 Tensile tests

The tests shall be conducted in accordance with the methods specified in ISO 6892-1.

### 8.2 Coating mass

The manufacturer shall conduct tests using methods deemed necessary to ensure that the material complies with the requirements listed in Table 3. Commonly used methods include those given in ISO 1460, ISO 3497 or ISO 2178. Coating mass is determined by converting coating thickness measurements made with magnetic gauges (ISO 2178) or by X-ray spectrometry (ISO 3497) using the relationship "100 g/m<sup>2</sup> = 0,015 mm". The test methods in ISO 2178 and ISO 3497 may be used as a basis for acceptance but not for rejection. In cases of dispute, ISO 1460 shall be used as the referee method.

## 9 Resubmission

**9.1** The manufacturer may resubmit, for acceptance, the products that have been rejected during earlier inspection because of unsatisfactory properties after they have been subjected to a suitable treatment (for example; selection, heat treatment) which, on request, will be indicated to the purchaser. In this case, the tests should be carried out as if they applied to a new lot.

**9.2** The manufacturer has the right to present the rejected products for a new examination, for compliance with the requirements for another quality or grade.

## 10 Workmanship

The metallic-coated steel in corrugated cut lengths shall be free from amounts of laminations, surface flaws and other imperfections that will be detrimental to subsequent appropriate processing. Processing for shipment in coils does not afford the manufacturer the opportunity to observe readily or to remove defective portions, as can be carried out in the cut-length product.

## 11 Inspection and acceptance

**11.1** While not usually required for products covered by this International Standard, the purchaser may specify that inspection and tests for acceptance be observed prior to shipment from the manufacturer's works. In these cases, the manufacturer shall afford the purchaser's inspector all reasonable facilities to determine that the steel is being furnished in accordance with this International Standard.

**11.2** Steel that is reported to be defective after arrival at the user's works shall be set aside, properly and correctly identified, and adequately protected.

## 12 Certification

**12.1** A manufacturer's certification shall be furnished to the purchaser when specified in the purchase order or contract. The certification shall be in accordance with, and make reference to, the provisions of this International Standard.

**12.2** The test results, including chemical composition, mechanical properties, coating type, and coating mass for each heat and coating lot, shall be maintained by the manufacturer for seven years without regard to whether a certification was furnished. The test results shall be made available to the fabricator and purchaser upon request.

## 13 Marking

**13.1** Each 0,5 to 1,5 m of sheet in coils or cut lengths shall be identified by showing the following:

Name of manufacturer

Brand name (if appropriate)

Specified thickness

Coating type (Zn, Zn-5Al-MM, 55Al-Zn, Al-Si)

Specified coating mass

Identifying symbols relating to a specific heat number and coating lot number

Applicable ISO designation number, i.e. ISO 16172:2011

**13.2** The above marking shall be removed or obliterated, or the sheet remarked "nonspecification" on each 0,5 to 1,5 m of sheet in a coating lot or heat for which control tests, as prescribed herein, show nonconformance to this International Standard.

## 14 Information to be supplied by the purchaser

**14.1** All sheet, both flat and formed, covered by this International Standard shall be ordered only according to the specified thicknesses in Table 4 on coated-steel-sheet thickness requirements.

**14.2** All material furnished in accordance with this International Standard shall be surface treated, unless otherwise specified in the purchaser order.

**14.3** To specify requirements adequately using this International Standard, enquiries and orders shall include the following information:

a) a reference to this International Standard, i.e., ISO 16172:2011;

- b) name of material used;
- c) coating type and, where appropriate, class;
- d) dimensions: for cut lengths, thickness; width; either flat or overall corrugated; length; pitch; and depth of corrugations, if corrugated; for coils, thickness; width; coil requirements (maximum outside diameter, acceptable inside diameter);
- e) certification, if required.

NOTE 1 Abbreviations may be used to describe the coating type.

NOTE 2 A typical ordering description is as follows: steel sheet for corrugated pipe in accordance with ISO 16172:2011, aluminum-silicon alloy coating, 45 000 kg, 2,77 by 700 mm by coil, 1 500 mm max. outside diameter, 600 mm inside diameter, 7 000 kg max., certified.

**Table 5 — Flatness tolerances (cut lengths only)**

Specified thickness mm	Specified width mm	Flatness tolerance (Maximum deviation from a horizontal flat surface) mm
1,6 and thicker	up to 1 500, inclusive	13
1,3 and thinner	up to 900, inclusive	13
	over 900 to 1 500, inclusive	19

NOTE This table also applies to sheets cut to length from coils by the fabricator when adequate flattening measures are performed.

**Table 6 — Corrugation size**

Nominal size mm	Maximum pitch <sup>a</sup> mm	Minimum depth <sup>b</sup>	Radius of curvature mm	
			nominal	minimum
68 by 13	73	12	17	13
75 by 25	83	24	14	13
125 by 25	135	24	40	36

<sup>a</sup> Pitch is measured from the crest of corrugations, at 90° to the direction of the corrugations.

<sup>b</sup> Depth is measured as the vertical distance from a straight edge resting on the corrugation crests to the bottom of the intervening valley.

**Table 7 — Covering width tolerance for corrugated sheet**

Covering width mm	Tolerance over and under mm
up to 600	6
over 600 to 900	10
over 900 to 1200	13

**Table 8 — Lip dimension of corrugated sheet**

<b>Nominal-corrugation-size pipe</b> mm	<b>For riveted pipe construction</b> mm	<b>For spot-welded construction</b> mm
68 by 13	19	11
75 by 25	22	13
125 by 25	22	13

## Bibliography

- [1] ISO 3575, *Continuous hot-dip zinc-coated carbon steel sheet of commercial and drawing qualities*
- [2] ISO 4998, *Continuous hot-dip zinc-coated carbon steel sheet of structural quality*
- [3] ISO 5000, *Continuous hot-dip aluminium-silicon-coated cold-reduced carbon steel sheet of commercial and drawing qualities*
- [4] ISO 9364, *Continuous hot-dip 55 % aluminium/zinc alloy-coated steel sheet of commercial, drawing and structural qualities*
- [5] ISO 14788, *Continuous hot-dip zinc-5 % aluminium alloy coated steel sheet*
- [6] ASTM A929/A929M, *Standard Specification for Steel Sheet, Metallic-Coated by the Hot-Dip Process for Corrugated Steel Pipe<sup>1)</sup>*

---

1) This document is recognized by ISO/TC17/SC12 to cover a subject similar to that of this International Standard. This information is given for the convenience of users of this International Standard and constitutes neither an endorsement of the document by TC17/SC12 or ISO, nor a statement regarding its degree of equivalence with this International Standard.







# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™