

Information and documentation — Boxes, file covers and other enclosures, made from cellulosic materials, for storage of paper and parchment documents

ICS 01.140.20; 55.220; 85.080.30

BSI

License copy: The University of Hong Kong, The University of Hong Kong, Version correct as of 24/01/2010 03:44, (C



National foreword

This British Standard is the UK implementation of ISO 16245:2009.

The UK participation in its preparation was entrusted to Technical Committee IDT/2, Information and documentation.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2010.

© BSI 2009

Amendments/corrigenda issued since publication

Date	Comments

ISBN 978 0 580 59482 3



INTERNATIONAL STANDARD

ISO
16245

First edition
2009-12-01

Information and documentation — Boxes, file covers and other enclosures, made from cellulosic materials, for storage of paper and parchment documents

*Information et documentation — Boîtes, chemises et autres contenants
en matériaux cellulosiques, pour le stockage des documents sur papier
et parchemin*



Reference number
ISO 16245:2009(E)

© ISO 2009

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

**This document is now
PUBLIC**

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16245 was prepared by Technical Committee ISO/TC 46, *Information and documentation*.



Introduction

Boxes and file covers are available in several different materials. Those made of cellulosic materials are the most commonly used enclosures for long term storage of paper and parchment documents. Experience has shown that properties of the enclosure are of great importance to the protection, permanence and durability of the documents. This International Standard specifies a number of basic requirements relevant to the material composition and construction of cellulose based boxes and file covers.

The purpose of boxes and file covers is to hold and contain documents in prescribed order or grouping, to provide a protective container, and to facilitate identification, transport and storage. Preferably, the same file covers and boxes can be used from storage at the place of work to the final archive storage. Moreover, it is possible to transport, handle and lend the volume as a unit.

Boxes, through their design and construction, protect documents from environmental risks such as light, rapid temperature and moisture changes and dust, as well as from damage related to handling. File covers further protect documents by enclosing them with materials specified for their preservation qualities. However, even high quality file covers and boxes can not compensate for poor storage conditions.

This International Standard can be used as a specification. It can also be incorporated as an element into other specifications, used in trade, or in other national or International Standards for more specialized purposes.



Information and documentation — Boxes, file covers and other enclosures, made from cellulosic materials, for storage of paper and parchment documents

1 Scope

This International Standard specifies requirements for boxes and file covers, made of cellulosic material, to be used for long term storage of documents on paper or parchment.

This International Standard is applicable to boxes made of solid or corrugated board and to file covers made of paper or board.

This International Standard can also be applicable to other types of enclosure for long term storage such as cases, portfolios, tubes and envelopes made of cellulosic material.

This International Standard is not applicable to storage of photographic materials.

NOTE ISO 18902 contains requirements on storage materials for photographs.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the references document (including any amendments) applies.

ISO 5-3, *Photography and graphic technology — Density measurements — Part 3: Spectral conditions*

ISO 5-4, *Photography and graphic technology — Density measurements — Part 4: Geometric conditions for reflection density*

ISO 535, *Paper and board — Determination of water absorptiveness — Cobb method*

ISO 536, *Paper and board — Determination of grammage*

ISO 4046-3:2002, *Paper, board, pulps and related terms — Vocabulary — Part 3: Paper-making terminology*

ISO 5626:1993, *Paper — Determination of folding endurance*

ISO 9706:1994, *Information and documentation — Paper for documents — Requirements for permanence*

ISO 12048:1994, *Packaging — Complete, filled transport packages — Compression and stacking tests using a compression tester*

3 Terms, definitions and symbols

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4046-3 pertaining to paper-making properties and the following apply.

3.1.1

box

storage container intended to protect documents and facilitate their shelving and handling

3.1.2

file cover

folded sheet of paper or board used for housing of and as a separating agent for document(s)

3.2 Symbols

Cob_{60}	The calculated mass of water absorbed in 60 s by 1 m ² of paper or board under specified conditions
D_R	Reflection density
S_A	Spectral power of the influx spectrum, reflection
s_V	Visual spectral responsivity
V	Spectral luminous efficiency
p_{max}	Maximum pressure

4 Requirements for boxes

4.1 General

Materials used shall not contain or form any substances, or have physical characteristics, which may be harmful to the documents being stored.

4.2 Board

Two types of board for boxes are specified:

- type A;
- type B.

Type A board shall meet the requirements specified in ISO 9706:1994, 5.3 (for alkali reserve), 5.4 (for the Kappa number), 5.5 (for the pH value), and shall be neutral sized or alkaline sized. All layers of board shall meet these requirements. Layers of corrugated board shall be measured individually. Solid board need not be separated. The test values of unseparated solid board, together with the manufacturer's warrant of the use of an alkaline process and the use of rag or bleached chemical pulp for all layers are acceptable.

Type B board shall meet the requirements specified in ISO 9706:1994, 5.3 (for the alkali reserve), 5.5 (for the pH value), and shall be neutral sized or alkaline sized. Type B board has no restriction in Kappa number and no limit in lignin content. All layers of board shall meet these requirements. Layers of corrugated board shall be measured individually. Solid board need not be separated. The test values of unseparated solid board, together with the manufacturer's warrant of the use of an alkaline process for all layers are accepted.

This document is now
POOBLIC

If a board used for boxes consists of two or more layers of different types, where at least one layer does not meet the requirements for type A board, the board shall be classified as type B.

Boxes made of type A board may be used without file covers. Boxes made of type B board are intended to be used together with file covers as specified in Clause 5.

The box shall be marked on the exterior, either:

- a) "Board ISO 16245-A" for boxes made of type A board, or
- b) "Board ISO 16245-B" for boxes made of type B board.

4.3 Cloth covering

A box may be covered with cloth. The cloth used, including pre-printed, shall be coated or impregnated with a non-migratory resinous substance, e.g. acrylic resin. The cloth shall be highly resistant to folding, tearing and rubbing. They shall be light resistant and suitable for direct lettering. The surface shall be non-friable with the surface fibres fully coated.

4.4 Lining

A box may be lined with paper. The paper used shall meet the requirements in 5.2, except for the grammage.

4.5 Colour

The board and lining should preferably not contain optical brightening agents, dyes or pigments.

However, if such board or lining is used, there shall be no bleeding of optical brightening agents, dyes or pigments when tested in accordance with the method specified in 5.8.

The covering may be coloured but shall then meet the requirements of 5.8.

4.6 Surface

The $Cobb_{60}$ value shall be determined in accordance with ISO 535. The $Cobb_{60}$ value for the exterior of uncovered boxes shall not be higher than 25.

The surface shall be capable of being marked.

4.7 Adhesives

Adhesives used for production of board or boxes shall not contain external plasticizers. The manufacturer shall specify the type of adhesive used and shall confirm the absence of plasticizer.

NOTE Experience has shown that starch or co-polymer of ethene and vinyl acetate (EVA) without external plasticizers is acceptable. An alkaline buffering agent, e.g. calcium carbonate, can be added to an EVA adhesive to neutralize adverse effects of possible acetic acid emission following application.

4.8 Manufacturer's joints and fasteners

Use of manufacturer's joints for box assembly such as rivets, wire stitches or staples should be avoided. However, if metal manufacturer's joints are required, they shall be of a non-corrosive material, e.g. stainless steel.

If fasteners are used, they shall be of a non-corrosive material, e.g. stainless steel.

4.9 Design

The box shall be designed so that it encloses file covers and documents and provides for their easy access and removal. The box shall not be air-tight.

No damage to the documents shall be caused by rivets, staples, etc., used in the construction of the box. If the box is provided with a facility for pulling the box out from the shelf, the construction shall not be such that the documents can be damaged. The box opening shall be designed so as to avoid any damage to the documents when they are taken from the box.

The box shall withstand repeated opening and closing at least 300 times. The design should enable both vertical and horizontal storage, the vertical storage with the short or long side down. If the box is optimized for use in one position, this shall be indicated on the exterior of the box.

4.10 Strength

The box shall resist a pressure of at least 20 kPa.

Test the strength of the box as follows. Use five empty boxes and test each box separately. If they are assembled by the manufacturer, test them as delivered. If they are not assembled, assemble them according to the manufacturer's instruction. Use a compression tester in accordance with ISO 12048:1994, Clause 4. Condition the boxes at (23 ± 2) °C, (50 ± 5) % RH and carry out the test in the same atmospheric conditions. Position the box in the orientation(s) for which it is designed to be used or transported. Apply the load by movement of the platens at a relative speed of (10 ± 3) mm/min until compression test failure occurs. Record and determine the maximum pressure p_{\max} . The mean value of the maximum pressure from the five tests shall not be less than 20 kPa.

NOTE For an area of 320 mm × 245 mm, the pressure of 20 kPa corresponds to a load of approximately 160 kg of mass.

4.11 Dimensions

The internal dimensions of boxes shall be larger than the dimensions of the file covers and documents they contain and shall permit easy retrieval.

NOTE Dimensions of boxes, including tolerances, are typically provided by the user at the time of procurement.

5 Requirements for file covers

5.1 General

Materials used shall not contain or form any substances, or have physical characteristics, which may be harmful to the documents being stored.


5.2 Paper and board

Paper and board shall be neutral sized or alkaline sized and meet the requirements in ISO 9706:1994, 5.3, 5.4 and 5.5.

The grammage of the paper and board shall be determined in accordance with ISO 536. The grammage shall be at least 100 g/m².

The paper and board shall not contain optical brightening agents.

Archival paper, as defined and specified in ISO 11108, also meets the requirements in ISO 9706, but is generally superior in durability.



5.3 Colour

The paper and board should preferably not contain dyes or pigments. However, if coloured paper or board is used, there shall be no bleeding of dyes or pigments when tested in accordance with the method described in 5.8.

Coloured file covers shall have a tone and colour intensity such that they provide for easy reading by eye, copying, microfilming or scanning. The optical density of the file cover (ISO 5 visual density), $D_R(S_A:s_V)$, shall not be higher than 0,20 when determined as specified in ISO 5-3 and ISO 5-4.

NOTE The rendering of the information when copying, microfilming or scanning is dependent both on the density of the file cover and the density of the image.

5.4 Adhesives

Adhesives should be avoided. However, if adhesives are required, they shall not contain external plasticizers. The manufacturer shall specify the type of adhesive used and shall confirm the absence of plasticizer.

NOTE Experience has shown that starch or co-polymer of ethene and vinyl acetate (EVA) without external plasticizers is acceptable. An alkaline buffering agent, e.g. calcium carbonate, may be added to an EVA adhesive to neutralize adverse effects of possible acetic acid emission following application.

5.5 Fasteners

Use of fasteners such as rivets, wire stitches or staples should be avoided. However, if metal fasteners are required, they shall be of a non-corrosive material, e.g. stainless steel.

5.6 Strength

The folding endurance of the paper shall be determined in accordance with ISO 5626. Paper with thickness up to 0,25 mm shall have a folding endurance in any direction (machine and cross) of at least 1,9 when determined with the instrument specified in ISO 5626:1993, A.1, or of at least 1,7 when determined with one of the instruments specified in ISO 5626:1993, A.2, A.3 or A.4.

Paper and board with thickness over 0,25 mm shall be scored, e.g. a straight channel pressed into the surface of paper so as to make folding of the paper possible or easier.

5.7 Dimensions

The dimensions of file covers shall be larger than the dimensions of the documents they contain and shall be compatible with the dimensions of boxes.

NOTE Dimensions of file covers, including tolerances, are typically provided by the user at the time of procurement.

5.8 Bleeding

Testing of materials containing optical brightening agents, dyes or pigments shall be performed as follows.

Soak two pieces of filter paper Whatman No. 1 of size approximately 80 mm × 80 mm in deionized water at 20 °C to 25 °C. Place one of the pieces on a flat plate of e.g. aluminium or inert glass. Cut a piece of size 40 mm × 40 mm of the material to be tested and put it on the filter paper. Cover with the other filter paper and put a flat plate of aluminium or inert glass on the top. Load with 12 kPa (this approximately corresponds to a weight of mass of 2 kg). Remove the load and the sample after 20 min and allow the two filter papers to dry in a hanging position.

Inspect the filter papers visually under daylight conditions. No transfer of colour to the filter paper is acceptable.

Inspect the filter papers and an unexposed piece of filter paper simultaneously under a UV lamp. No fluorescence from the exposed filter paper is acceptable.



6 Test report

The test report shall include the following:

- a) a reference to this International Standard, ISO 16245:2009;
- b) the identification of the material tested;
- c) the date and place of testing;
- d) any other observations made that may be of importance to the capacity of the boxes or file covers to protect the enclosed documents;
- e) any deviations from this International Standard and any circumstances that may have affected the results;
- f) the test results obtained when testing as specified in
 - 1) 4.2, 4.6, 4.9 and 4.10 for all archive boxes,
 - 2) 4.2, 4.5, 4.6, 4.9 and 4.10 for coloured archive boxes,
 - 3) 5.2 and 5.6 for all file covers,
 - 4) 5.2, 5.3 and 5.6 for coloured file covers;
- g) a statement that the item meets or fails to meet the requirements of this International Standard; in the latter case the specific reason shall be stated.



Bibliography

- [1] ISO 5127, *Information and documentation — Vocabulary*
- [2] ISO 11108, *Information and documentation — Archival paper — Requirements for permanence and durability*
- [3] ISO 18902, *Imaging materials — Processed imaging materials — Albums, framing and storage materials*
- [4] EN 923, *Adhesives — Terms and definitions*



Licensed copy: The University of Hong Kong, The University of Hong Kong, Version correct as of 24/01/2010 03:44, (C

BS ISO 16245:2009
ISO 16245:2009(E)

BSI

ICS 01.140.20

Price based on 7 pages



© ISO 2009 – All rights reserved



BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com

