

BS ISO 16532-3:2010



BSI Standards Publication

Paper and board — Determination of grease resistance

Part 3: Turpentine test for voids in glassine
and greaseproof papers

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 16532-3:2010.

The UK participation in its preparation was entrusted to Technical Committee PAI/11, Methods of test for paper, board and pulps.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 61004 2

ICS 85.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2011.

Amendments issued since publication

Date	Text affected
------	---------------

**Paper and board — Determination of
grease resistance —**

**Part 3:
Turpentine test for voids in glassine and
greaseproof papers**

Papier et carton — Détermination de l'imperméabilité aux graisses —

*Partie 3: Essai à la térébenthine pour papiers glassine et papiers
ingraissables*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle.....	1
5 Reagents.....	2
6 Apparatus	2
7 Sampling.....	2
8 Conditioning	3
9 Preparation of test pieces.....	3
10 Procedure	3
11 Observation intervals	3
12 Expression of results	4
13 Test report	4
Annex A (informative) Precision.....	5
Bibliography.....	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16532-3 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

ISO 16532 consists of the following parts, under the general title *Paper and board — Determination of grease resistance*:

- *Part 1: Permeability test*
- *Part 2: Surface repellency test*
- *Part 3: Turpentine test for voids in glassine and greaseproof papers*

Introduction

The resistance of paper and board to penetration by fats, greases and oils in paper and board is of particular importance for certain purposes, for example the packaging of food. The packaging should not only provide an effective grease barrier, but should also prevent the formation of aesthetically unacceptable grease spots on the packaging surfaces.

Paper and board — Determination of grease resistance —

Part 3:

Turpentine test for voids in glassine and greaseproof papers

1 Scope

This part of ISO 16532 specifies a method for the determination of the grease resistance of paper and board. It provides an accelerated comparison of the relative rates at which oils or greases, such as those commonly found in foodstuffs, can be expected to penetrate voids in papers such as greaseproof or glassine, where the grease or oil resistance is provided by mechanical means only. It is not applicable to grades of paper or board that are given grease or oil resistance by means of a coating or internal treatment for which ISO 16532-1 or ISO 16532-2 apply.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning the samples*

ISO 536, *Paper and board — Determination of grammage*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

grease resistance

ability of the paper or board to resist the formation of surface spots or stains, or the permeation of grease through the sheet

3.2

voids

places in the paper where the arrangement of the fibres is such that oil or grease can penetrate the sheet

4 Principle

The test piece is placed on a sheet of coated paper on a flat surface and a small mound of sand is placed on the test piece. The sand is then saturated with coloured turpentine. The time taken for a stain to appear on the coated paper beneath the sand is noted.

5 Reagents

- 5.1 Pure gum spirits of turpentine**, with a density of 860 kg/m³ to 875 kg/m³ at 20 °C.
- 5.2 Anhydrous calcium chloride**.
- 5.3 Oil-soluble dye** (for example Sudan red).
- 5.4 Sand**, Ottawa cement-testing sand, screened to pass an 800 µm screen but retained on a 630 µm screen.

NOTE Ottawa cement-testing sand is available commercially from some laboratory suppliers.

5.5 Test solution: to 100 ml of turpentine (5.1), add 5 g of anhydrous calcium chloride (5.2) and 1,0 g of oil-soluble dye (5.3) and store in a stoppered bottle (6.7). Shake well, and let the solution stand for at least 10 h, shaking occasionally. Then filter through a dry filter paper at a temperature of 23 °C ± 1 °C, and store in the stoppered bottle (6.7). Ensure that the bottle is airtight.

6 Apparatus

- 6.1 Tube of any rigid material**, 25 mm internal diameter and at least 25 mm in height, the ends of which have been smoothed.
- 6.2 Automatic pipette**, of appropriate maximum volume, calibrated to deliver 1,1 ml of test solution.
- 6.3 Printing paper**, flat, white, coated and calendered sheet or sheets of a convenient size to support at least 10 test pieces.
- A grammage of 100 g/m² to 120 g/m² is recommended (see ISO 536).
- 6.4 Stopwatch or timer**, accuracy ± 0,5 s.
- 6.5 Watch glass**, diameter 76 mm.
- 6.6 Scoop**, of capacity 5 g. Verify the capacity of the scoop by weighing 2 charges of sand (5.4) on an analytical balance (6.8): each charge should weigh (5,0 ± 0,1) g. The design of the scoop should preferably facilitate the pouring of the sand (5.4) into the tube (6.1).
- 6.7 Stoppered glass bottle**, of capacity 100 ml.
- 6.8 Analytical balance**, of minimum capacity 10 g and with a scale interval of 0,01 g; accuracy class ordinary (III)¹⁾.

7 Sampling

If the test is being made on a lot of paper or board, the sample shall be selected in accordance to ISO 186. If the test is being made on another type of sample, report the source of the sample and, if possible, the sampling procedure used. Make sure that the test pieces taken are representative of the paper or board sample.

1) Accuracy classes for non-automatic weighing instruments are described in OIML R 76-1^[5].

8 Conditioning

Condition the sample in accordance with ISO 187. The alternative conditions specified in ISO 187 shall not be used, as it has been determined that the temperature has a strong influence on the test results. Thus only $23\text{ °C} \pm 1\text{ °C}$ shall be used. Place the bottle of test solution (5.5) in the conditioned atmosphere and allow its temperature to come into equilibrium.

9 Preparation of test pieces

Prepare from the conditioned sample, in the same conditioned atmosphere (see Clause 8), ten test pieces of $100\text{ mm} \times 100\text{ mm}$, identifying, if possible, five pieces as the top side and five pieces as the wire side. Mark the first side of each test piece as side 1.

10 Procedure

10.1 Place a coated paper sheet or sheets (6.3), on a smooth, flat horizontal surface. Then, alternatively place the first marked side (top side if known or side 1 if unknown) of a test piece, followed by the other side, such that no test piece extends beyond the edge of the coated paper.

10.2 Rest one end of the tube (6.1) squarely on a test piece and with the scoop (6.6) put $5,0\text{ g} \pm 0,1\text{ g}$ of the sand (5.4) in the tube. Remove the tube immediately after addition of the sand by carefully lifting it vertically.

NOTE The purpose of the tube is solely to ensure that a uniform sand pile is applied to the test piece.

10.3 Add $1,1\text{ ml} \pm 0,05\text{ ml}$ of the test solution (5.5) to the sand pile, using an automatic pipette (6.2). Start the timing device (6.4) as the last drop of test solution leaves the pipette.

10.4 At specific intervals (see Clause 11), gently slide the test piece to a new unexposed position of the coated paper and examine the previously exposed position for signs of staining. The first sign of staining, which indicates that the test solution (5.5) has penetrated the test piece, is the end-point of the test.

10.5 Record the time elapsed from the addition of the test solution (5.5) to the sand until the first sign of staining of the coated paper. If staining has not occurred after 30 min (1 800 s), terminate the test.

If it takes longer than 120 s for the test solution (5.5) to penetrate the test piece, cover the sand pile with the watch glass (6.5).

10.6 Repeat 10.2 to 10.4 for the remaining test pieces.

NOTE If the first pair of tests show that the end-point times exceed 900 s, the test may be expedited by placing the remaining 8 test pieces on the coated paper, adding sand (5.4) and then test solution (5.5), followed by starting the timer (6.4) as in 10.3 at 10 s intervals.

11 Observation intervals

Make observations at least at the following intervals:

- every 15 s between 0 and 1 min;
- every 1 min between 1 min and 5 min;
- every 5 min between 5 min and 30 min.

If the end-point times for the first two test pieces exceed 15 min, make observations every 5 min, starting at 15 min.

12 Expression of results

Calculate the mean penetration time, in seconds, for all test pieces to two significant figures. If the results from the two sides can be distinguished, either as top and wire sides or by a clear difference in the values, then calculate separately the means of the two sides. Also note the maximum and minimum values.

If, in the calculation of any mean values, one or more results is greater than 1 800 s (30 min), include these values as 1 800 and report the mean as $> X$ (where $>$ indicates greater than). For maximum values greater than 1 800 s, record as $> 1\ 800$.

EXAMPLE Assuming that it is not possible to identify the top and wire sides, record as follows:

	Side 1	Other side
	1 800	600
	1 700	550
	1 600	500
	1 700	600
	1 800	500
Mean	$> 1\ 700$	550
Minimum	1 600	500
Maximum	$> 1\ 800$	600

13 Test report

The test report shall include the following information:

- a reference to this part of ISO 16532 (i.e. ISO 16532-3:2010);
- all information for the complete identification of the sample;
- the date and place of testing;
- when possible, identification of the side or sides tested;
- for each sample the mean, and maximum and minimum values, and if applicable, individual results for the two sides;
- any departure from this part of ISO 16532 or any other circumstances that might have affected the results.

Annex A (informative)

Precision

A.1 General

In 2008, five paper samples of varying greaseproof levels were subjected to an international round-robin in which 10 laboratories participated. Five tests were carried out on both the top side and wire side of each sample. The results were statistically analysed for repeatability and reproducibility and are summarized in Tables A.1 and A.2.

For samples 3 to 5, no significant difference between results for the two sides were found, therefore the repeatability and reproducibility values are mean values of both sides.

The calculations have been made according to ISO/TR 24498^[2] and TAPPI T 1200^[4].

The repeatability standard deviation indicated in Table A.1 is the “pooled” repeatability standard deviation, that is, the standard deviation calculated as the root-mean-square of the standard deviations of the participating laboratories. This differs from the conventional definition of repeatability in ISO 5725-1^[1].

The repeatability and reproducibility limits reported are estimates of the maximum difference which should be expected in 19 of 20 instances, when comparing two test results for material similar to those described under similar test conditions. These estimates may not be valid for different materials or different test conditions.

Repeatability and reproducibility limits are calculated by multiplying the repeatability and reproducibility standard deviations by 2,77.

NOTE $2,77 = 1,96\sqrt{2}$, provided that the test results have a normal distribution and that the standard deviation s is based on a large number of tests.

A.2 Repeatability

Table A.1 — Estimation of the repeatability of the test method

Sample	Mean value s	Standard deviation s_r s	Coefficient of variation CV %	Repeatability limit r s
1, wire side ^a	1 403	177	12,6	490
2	> 1 800	Not calculated ^b	Not calculated ^b	Not calculated ^b
3	82,8	35,4	43,0	98,2
4	1 141	197	14,0	549
5	22,4	4,6	20,7	12,8

^a Almost all results for the top side were > 1 800 s.
^b Repeatability values have not been calculated, since all results were > 1 800 s.

A.3 Reproducibility

Table A.2 — Estimation of the reproducibility of the test method

Sample	Mean value s	Standard deviation s_R s	Coefficient of variation CV %	Reproducibility limit R s
1, wire side ^a	1 403	580	41,3	1 609
2	> 1 800	Not calculated ^b	Not calculated ^b	Not calculated ^b
3	82,8	51,8	62,5	143
4	1 141	466	33,0	1 295
5	22,4	12,9	58,0	36,0

^a Almost all results for the top side were > 1 800 s.
^b Reproducibility values have not been calculated, since all results were > 1 800 s.

Bibliography

- [1] ISO 5725-1:1994, *Accuracy (trueness and precision) of measurement methods and results — Part 1: General principles and definitions*
- [2] ISO/TR 24498:2006, *Paper, board and pulps — Estimation of uncertainty for test methods*
- [3] TAPPI Test Method T 454 om-06, *Turpentine test for voids in glassine and greaseproof papers*
- [4] TAPPI Test Method T 1200 sp-07, *Interlaboratory Evaluation of Test Methods to Determine TAPPI Repeatability and Reproducibility*
- [5] International Recommendation OIML R 76-1, *Non-automatic weighing instruments — Part 1: Metrological and technical requirements — Tests*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™