

BS ISO 17278:2013



BSI Standards Publication

# Rubber, raw natural — Determination of the gel content of technically specified rubber (TSR)

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 17278:2013.

The UK participation in its preparation was entrusted to Technical Committee PRI/23, Test methods for rubber and non-black compounding ingredients.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 77068 5

ICS 83.040.10

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2013.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

---

---

**Rubber, raw natural — Determination  
of the gel content of technically  
specified rubber (TSR)**

*Caoutchouc naturel brut — Détermination de la teneur en gel des  
caoutchoucs spécifiés techniquement (TSR)*





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Principle</b> .....	<b>1</b>
<b>4 Terms and definitions</b> .....	<b>1</b>
<b>5 Reagent</b> .....	<b>1</b>
<b>6 Apparatus</b> .....	<b>2</b>
<b>7 Conditions</b> .....	<b>2</b>
<b>8 Procedure</b> .....	<b>2</b>
8.1 Number of test samples .....	2
8.2 Procedure .....	2
<b>9 Expression of the result</b> .....	<b>3</b>
<b>10 Precision</b> .....	<b>3</b>
<b>11 Test report</b> .....	<b>3</b>
<b>Annex A (informative) Precision</b> .....	<b>5</b>
<b>Bibliography</b> .....	<b>7</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. [www.iso.org/directives](http://www.iso.org/directives)

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. [www.iso.org/patents](http://www.iso.org/patents)

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

# Rubber, raw natural — Determination of the gel content of technically specified rubber (TSR)

## 1 Scope

This International Standard specifies a method for the determination of gel content for technically specified rubbers (TSR).

**WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.**

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable to its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2000,<sup>1)</sup> *Rubber, raw natural — Guidelines for the specification of technically specified rubber (TSR)*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

## 3 Principle

An LoV-TSR sample is dissolved in toluene under specified conditions, and the gel content is calculated as the percentage mass fraction of the insoluble part of the rubber.

## 4 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 4.1

#### **technically specified rubber**

#### **TSR**

natural rubber obtained from the latex of *Hevea brasiliensis* (typically processed into block rubber), and having properties complying with the criteria for the grade concerned

## 5 Reagent

Use only reagents of recognized analytical grade.

### 5.1 Toluene, analytical grade.

**CAUTION — The solvent might evaporate from the flask or tube when it is handled. Therefore, handling this solvent should be done only when permitted by local health and safety regulation and only in a well-ventilated appropriate place.**

---

1) Under preparation. (Revision of ISO 2000:2003)

## 6 Apparatus

**6.1 Laboratory centrifuge**, capable of rotating at a minimum of 14 000 r/min (revolutions per minute).

If the above speed cannot be attained a minimum speed of 8 000 r/min may be used with a longer running time (8.2.4).

NOTE When the centrifugal rotational frequency (rotational speed) is 14 000 r/min, the gravitational acceleration is 22 000 G. When the centrifugal rotation speed is 8 000 r/min, the gravitational acceleration is 7 000 G.

**6.2 Screw-cap centrifuge tubes**, with a minimum capacity of 30 cm<sup>3</sup>, capable of withstanding the centrifuge conditions and of being heated to a temperature greater than 110 °C.

**6.3 Balance**, capable of accurately weighing to ±0,1 mg.

**6.4 Laboratory oven**, gravity convection type, capable of controlling the temperature to ±10 °C.

**6.5 Weighing container**, i.e. an aluminium box or plate for weighing.

## 7 Conditions

Laboratory conditions shall be controlled in accordance with ISO 23529.

## 8 Procedure

### 8.1 Number of test samples

Two samples shall be taken in accordance with Clause 7 of ISO 2000.1)

### 8.2 Procedure

**8.2.1** Take a test sample from a bale without milling of mass calculated at the ratio of 0,1 g per 30 cm<sup>3</sup> of toluene.

NOTE When the volume of a centrifuge tube is 50 cm<sup>3</sup>, the volume of toluene is 30 cm<sup>3</sup> (see 8.2.3), and the sample weight is 0,1 g.

**8.2.2** Cut the test sample into approximately 1 mm<sup>3</sup>-sized pieces using clean scissors. Weigh the prepared test sample to the nearest 0,1 mg ( $m_0$ ). Place the pieces in a clean centrifuge tube (6.2), which has previously been heated at 100 °C for 1 h and stored in a desiccator.

**8.2.3** Add toluene to the tube until it is 60 % full. Cap it and shake by hand for a few seconds. Then, allow it to stand for 16 h to 20 h in dark conditions without stirring at (25 ± 2) °C.

**8.2.4** After this period, shake the tube up and down for 60 s to disperse the jelly-like precipitate on the bottom.

Before placing the tubes in the centrifuge machine, all tubes shall be filled up with fresh toluene, so that the volume of solution is the same in all tubes.

NOTE A centrifuge tube is usually filled up with solution to minimize the dead space created at the top of the tube because of the vacuum-pressured environment during rotation.

Place the tubes in the centrifuge machine and operate the machine at 14 000 r/min for 2 h.

If the rotating capacity of the centrifuge machine is below 14 000 r/min, operate the machine at 8 000 r/min for 6 h.



A set temperature of centrifuge is usually indicated in the operation manual for safety reasons. If not, it may be set to between 0 °C and 25 °C.

**8.2.5** Remove the tube from the machine and pipette the liquid from the tube held at approximately 45°. Caution shall be taken to prevent pipetting the precipitate.

**8.2.6** Add 1 ml to 3 ml of acetone to the precipitate so that it can be easily peeled from the bottom of the tube. Leave to stand for over 30 s and then pipette the liquid from the tube.

**8.2.7** Peel off the precipitate remaining at the bottom of the tube with a spatula or a spatula-like stick and move it into the container (6.5) which has been cleaned and weighed to the nearest 1 mg ( $m_1$ ). A limited amount of acetone may be used to rinse the spatula, if necessary.

**8.2.8** Store the container in a fume cupboard for 30 min to allow the solvent to evaporate, in order to prevent flashing of the solvent during heating. Place the container containing the precipitate in the oven and dry it at the temperature of 110 °C for 1 h.

**8.2.9** Take the container out of the oven and allow it to cool in a desiccator for 30 min.

**8.2.10** Weigh the container containing the dry precipitate to the nearest 0,1 mg ( $m_2$ ).

**8.2.11** Repeat the procedure in 8.2.8, 8.2.9 and 8.2.10 until the loss in mass between two successive weighings is less than 0,2 mg. Note the period of drying time for the first test piece and use it for the next test piece for the series of testing. Record the final mass ( $m_2$ ).

## 9 Expression of the result

To determine the gel content, use Formula (1) and round the result to one decimal place.

$$G = \frac{(m_2 - m_1)}{m_0} \times 100 \quad (1)$$

where

$G$  is the gel content, as a percentage (%);

$m_0$  is the mass of the original test piece (8.2.2), in grams (g);

$m_1$  is the mass of the empty container (8.2.7), in grams (g);

$m_2$  is the mass of the container containing dry precipitate (8.2.10), in grams (g).

Take an average of two gel content values.

## 10 Precision

For the precision, see [Annex A](#).

## 11 Test report

The test report shall include the following:

- a) a reference to this International Standard, i.e. ISO 17278.
- b) all details necessary for identification of the test sample;
- c) the test method;
- d) the laboratory temperature;

- e) the centrifuge diameter, the temperature, the speed and the running time of the test;
- f) details of any operation not specified in this International Standard;
- g) the results;
- h) the number of test pieces tested;
- i) the individual test results;
- j) the mean result;
- k) the details of any unusual features noted during the determination;
- l) the date of the test.

## Annex A (informative)

### Precision

#### A.1 General

An interlaboratory test programme (ITP) for the precision evaluation of the test method for TSR gel content was planned and conducted in January and February of 2011. The calculations were carried out in accordance with ISO/TR 9272. Ten laboratories from five countries participated in this ITP.

Three TSR samples with different levels of gel content were prepared for this ITP as shown in [Table A.1](#). They were sent out to each laboratory with instructions to carry out the test as soon as the samples were received. The test was carried out on two different days at one-week intervals with two tests each day ( $n = 2$ ).

The precision results as determined by this ITP should not be used for acceptance/rejection testing of any group of materials or products without documentation that the results are applicable to those particular materials or products and the specific test protocol of this test method.

**Table A.1 — TSR sample**

	Sample A	Sample B	Sample C
Gel content level	Low	Medium	High
NOTE Each sample should be appropriately stored in a conditioned place until all the tests are completed.			

The precision results are given in [Table A.2](#). These results were obtained using outlier deletion procedures as described in ISO/TR 9272.

#### A.2 Repeatability

The repeatability,  $r$ , of the test method was established as the appropriate value tabulated in [Table A.2](#) for each material. Two single test results that differ by more than the value shall be considered suspect, and it is recommended that some appropriate investigative action be taken.

#### A.3 Reproducibility

The reproducibility,  $R$ , of the test method was established as the appropriate value tabulated in [Table A.2](#) for each material. Two single test results that differ by more than the value shall be considered suspect, and it is recommended that some appropriate investigative action be taken.

**Table A.2 — Precision for gel content**

Material	Mean %	Within laboratory			Between laboratories			Number of laboratories
		$s_r$	$r$	( $r$ )	$s_R$	$R$	( $R$ )	
A	0,80	0,14	0,39	48,8	0,45	1,27	158,8	8
B	5,20	0,26	0,75	14,4	1,52	4,31	82,9	8
C	8,20	0,56	1,57	19,1	2,02	5,71	69,6	9

Number of replicates  $n = 2$ ;

$s_r$  is the repeatability standard deviation;

$s_R$  is the reproducibility standard deviation;

$r$  is the repeatability, in measurement units;

( $r$ ) is the repeatability, as a percentage (these values represent relative percentage, i.e. per cent of a percent);

$R$  is the reproducibility, in measurement units;

( $R$ ) is the reproducibility, as a percentage (these values represent relative per cent, i.e. per cent of a percent).

## Bibliography

- [1] ISO/TR 9272, *Rubber and rubber products — Determination of precision for test method standards*





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™