

BS ISO 17299-3:2014



BSI Standards Publication

# Textiles — Determination of deodorant property

Part 3: Gas chromatography method

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of ISO 17299-3:2014.

The UK participation in its preparation was entrusted to Technical Committee TCI/80, Chemical testing of textiles.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 76087 7

ICS 59.080.01

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2015.

**Amendments issued since publication**

| Date | Text affected |
|------|---------------|
|------|---------------|

---

INTERNATIONAL  
STANDARD

**ISO**  
**17299-3**

First edition  
2014-03-15

---

---

**Textiles — Determination of  
deodorant property —**

**Part 3:  
Gas chromatography method**

*Textiles — Détermination des propriétés de neutralisation d'odeurs —  
Partie 3: Méthode par chromatographie en phase gazeuse*



Reference number  
ISO 17299-3:2014(E)

© ISO 2014



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

| <b>Contents</b>  |   | Page      |
|--|---|-----------|
| <b>Foreword</b> .....                                      |   | <b>iv</b> |
| <b>Introduction</b> .....                                  |   | <b>v</b>  |
| <b>1</b>   | <b>Scope</b> .....                                      | <b>1</b>  |
| <b>2</b>   | <b>Normative references</b> .....                       | <b>1</b>  |
| <b>3</b>   | <b>Principle</b> .....                                  | <b>1</b>  |
| <b>4</b>   | <b>Reagents</b> .....                                   | <b>1</b>  |
| <b>5</b>   | <b>Materials and apparatus</b> .....                    | <b>2</b>  |
| <b>6</b>   | <b>Testing environment</b> .....                        | <b>2</b>  |
| <b>7</b>   | <b>Test procedure</b> .....                             | <b>2</b>  |
|  | 7.1 General.....  | 2         |
|  | 7.2 Preparation of specimen.....                        | 2         |
|  | 7.3 Method A.....                                       | 2         |
|  | 7.4 Method B.....                                       | 4         |
|  | 7.5 Concentration measurement of testing gas by GC..... | 5         |
| <b>8</b>   | <b>Calculation of odour reduction rate</b> .....        | <b>5</b>  |
| <b>Annex A (informative) GC parameter</b> .....            |   | <b>6</b>  |
| <b>Annex B (informative) Round-robin test result</b> ..... |   | <b>7</b>  |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 38, *Textiles*.

ISO 17299 consists of the following parts, under the general title *Textiles — Determination of deodorant property*:

- *Part 1: General principle*
- *Part 2: Detector tube method*
- *Part 3: Gas chromatography method*
- *Part 4: Condensation sampling analysis*
- *Part 5: Metal-oxide semiconductor sensors method*

## Introduction

This part of ISO 17299 describes a gas chromatography testing method for concentration measurement of odour chemicals in deodorant testing. This is the most general testing method that could be carried out in many testing laboratories globally if they have gas chromatography.

To avoid duplication, the major stream of the testing procedure is described in ISO 17299-1. This part of ISO 17299 describes a specific procedure for the gas chromatography testing method.





# Textiles — Determination of deodorant property —

## Part 3: Gas chromatography method

### 1 Scope

This part of ISO 17299 specifies a gas chromatography test method for the deodorant testing of all textile products. This method applies to the odour component chemicals, such as indole, isovaleric acid, nonenal, and acetic acid with added sodium chloride (NaCl). Two preparation methods are described in this test method:

- an odour chemical is applied in a container avoiding contact with a specimen in method A. Each chemical is tested separately;
- an odour chemical is injected directly on to the specimen in a container in method B. The chemicals tested in this method are a mixture of acetic acid and sodium chloride (NaCl).

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

### 3 Principle

Concentration of the gaseous odour component chemicals of the gas in containers with or without a test specimen after a designated contacting time is measured by gas chromatography (GC). The reduction rate of concentration of odour chemicals in the container is calculated from the concentration data with a specimen and without a specimen.

### 4 Reagents

Unless otherwise specified, analytical grades shall be used.

- 4.1 **Acetic acid (CH<sub>3</sub>COOH)**, reagent with a purity of 99,7 %.
- 4.2 **Indole (C<sub>8</sub>H<sub>7</sub>N)**, reagent.
- 4.3 **Isovaleric acid**, reagent with a purity of 98,0 %.
- 4.4 **2-Nonenal (C<sub>9</sub>H<sub>16</sub>O)**, reagent with a purity of 95,0 %.
- 4.5 **Diluent gas**, nitrogen gas from a nitrogen gas cylinder with a purity of at least 99,99 %.
- 4.6 **NaCl**, reagent grade.
- 4.7 **Ethanol**, reagent grade.
- 4.8 **Water**, grade 3 of ISO 3696.

## 5 Materials and apparatus

- 5.1 **Conical flask**, with a capacity of 500 ml, made of glass.
- 5.2 **Sealing film**, capable of expanding with no air permeability [e.g. Parafilm<sup>1)</sup>].
- 5.3 **Injection vial**, with a capacity of 22 ml, with a rubber stopper and aluminium cap.
- 5.4 **Injection syringe**, capable of injecting at 8 µl and 850 µl in volume.
- 5.5 **Gastight syringe**.
- 5.6 **Heating oven**, capable of heating at 80 °C ± 2 °C for 30 min.
- 5.7 **Gas chromatography (GC) apparatus**, with a flame ionization detector (FID) or mass selective detector (MSD).
- 5.8 **Rubber stopper and aluminium cap**.

## 6 Testing environment

The testing environment used in this test is a room temperature of 20 °C and a relative humidity of 65 % in accordance with ISO 139.

## 7 Test procedure

### 7.1 General

Two preparation methods are described in this clause as method A and method B. One method shall be selected with the consent of the concerned parties.

### 7.2 Preparation of specimen

The dimension or mass of specimen for the textile products is shown in [Table 1](#).

**Table 1 — Dimension or mass of specimen**

| Kind of specimen                           | Dimension or mass of specimen            |   |
|--|--|---|
|  | Method A                                 | Method B                                  |
| Fabrics (woven, knit, nonwoven, and tapes) | 50 cm <sup>2</sup> ± 2,5 cm <sup>2</sup> | 25 cm <sup>2</sup> ± 1,25 cm <sup>2</sup> |
| Yarns, fibres, and feather                 | 0,5 g ± 0,025 g                          | —   |

NOTE In the case of multi-layer products, the edge and non-treated layer (or not concerned layer) can be covered with aluminium sheets to avoid contact with the odorous atmosphere, or the product can be folded in two with the layer that is not concerned inside, in method A.

### 7.3 Method A

7.3.1 Prepare six conical flasks (5.1) with 500 ml: three conical flasks are used for testing with a specimen and three conical flasks are used for testing without a specimen as a control test.

7.3.2 Clean the flasks by using nitrogen gas or clean air more than five times of volume of the flask.

---

1) Parafilm is an example of a suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

### 7.3.3 Preparation of the odour component chemical solution.

The test is performed for each odour component chemical independently.

Prepare the odour component chemical solutions for the test separately as the following.

#### 7.3.3.1 Indole

Dissolve 20 g of the indole reagent (4.2) into 1 l of ethanol (4.7).

#### 7.3.3.2 Isovaleric acid

Dissolve 20 g of isovaleric acid reagent (4.3) into 1 l of ethanol (4.7).

#### 7.3.3.3 Nonenal

Dissolve 10 g of nonenal reagent (4.4) into 1 l of ethanol (4.7).

### 7.3.4 Testing with specimen

#### 7.3.4.1 Preparation of specimen

Take three specimens from the sample for one chemical test as shown in [Table 1](#).

#### 7.3.4.2 Placement of specimen

Put each specimen in a conical flask (5.1) to lie flat on the bottom.

#### 7.3.4.3 Nitrogen purge

Purge the air of the conical flask by blowing of 1 000 ml of nitrogen gas.

Seal the mouth of the conical flask by using sealing film (5.2).

#### 7.3.4.4 Insertion of testing odour component chemical solution

Take 5 µl of the odour component chemical solution prepared in [7.3.3.1](#), [7.3.3.2](#), or [7.3.3.3](#), by using the injection syringe (5.4) through the sealing film and inject the testing solution into the conical flask at the bottom edge of the conical flask, avoiding contact with the specimen.

#### 7.3.4.5 Sealing of the microsyringe hole

Seal the hole of the microsyringe by the sealing film (5.2) over the original seal.

#### 7.3.4.6 Contacting time

Keep the conical flask still for 2 h, without agitation or stirring of the testing gas.

### 7.3.5 Testing without specimen

For testing without a specimen, repeat the procedure from [7.3.4.2](#) to [7.3.4.6](#) without a specimen.

### 7.3.6 Sampling of the testing gas

**7.3.6.1** After 2 h of contacting time, hold the mouth part of the conical flask and shake approximately 20 times for 20 s vigorously for both flasks of testing gases with and without a specimen.

**7.3.6.2** Insert a gastight syringe (5.5) vertically into the centre of the sealing film of the mouth of the conical flask and insert the needle by approximately 4 cm inside the conical flask.

**7.3.6.3** Take the testing gas from inside the conical flask by the gastight syringe.

The amount of sampling gas depends on the model of the gas chromatography apparatus used.

NOTE When the gastight syringe is used repeatedly, the repeated suction and discharge is recommended for several times to avoid the influence of residual gases in the syringe.

## **7.4 Method B**

### **7.4.1 Preparation of vials**

**7.4.1.1** Prepare six injection vials (5.3) with 22 ml: three vials are used for testing with a specimen and three vials are used for testing without a specimen for a control test.

**7.4.1.2** Clean the vials by using nitrogen gas (4.5) or clean air more than five times of the volume of the vial.

### **7.4.2 Preparation of acetic acid and NaCl solution**

Prepare acetic acid and NaCl solution with 1 g/l of acetic acid (4.1) and 9 g/l of NaCl (4.6) in 1 l of water.

### **7.4.3 Preparation of specimen**

Take three specimens from the sample for one test and make a roll respectively.

### **7.4.4 Testing with specimen**

#### **7.4.4.1 Placement of specimen**

Place each roll of specimen vertically in the three injection vials and seal the injection vials with rubber stoppers and aluminium caps (5.8).

#### **7.4.4.2 Injection of the acetic acid and NaCl solution**

Take 850 µl of the acetic acid and NaCl solution with the injection syringe for each test and inject on to the fabric directly for three vials with a specimen through the rubber stoppers (5.8) by using the injection syringe (5.5).

#### **7.4.4.3 Contacting time**

Place the six vials with the following sequence:

- vial with specimen;
- vial without specimen;
- vial with specimen;
- vial without specimen;
- vial with specimen;
- vial without specimen.

Place them in the heating oven at a temperature of 80 °C ± 2 °C for 30 min ± 3 min.

### **7.4.5 Testing without specimen**

Repeat the procedure in 7.4.4.1 to 7.4.4.3 without a specimen.

#### 7.4.6 Sampling of the odour testing gas

Take 1 ml of odour testing gas after contacting time from each vial, with or without a specimen, by using the injection syringe (5.5).

### 7.5 Concentration measurement of testing gas by GC

#### 7.5.1 General

The testing gas obtained in 7.3.5 or 7.4.6 is injected into the column of the gas chromatograph, and the concentration of the odour component chemical is detected by a hydrogen flame ionization detector (FID). The peak area value of the FID spectrum is obtained as the value proportional to the chemical concentration of the testing gas.

#### 7.5.2 Peak area of FID spectrum of testing gas with specimen

Measure the peak area of the FID spectrum for three testing gases with a specimen by GC and take an average which is denoted as  $S_m$ .

#### 7.5.3 Concentration of testing gas without specimen

Measure the peak area of the FID chromatogram for three testing gases without a specimen by GC and take an average which is denoted as  $S_b$ .

## 8 Calculation of odour reduction rate

Calculate the odour reduction rate according to the Formula (1).

$$ORR = \frac{(S_b - S_m)}{S_b} \times 100 \quad (1)$$

where

$ORR$  is the odour reduction rate, as a percentage;

$S_m$  is the average peak area of FID of the testing gas with a specimen;

$S_b$  is the average peak area of FID spectrum of the testing gas without a specimen.

## **Annex A** **(informative)**

### **GC parameter**

Capillary column: DB-5 [Agilent J&W<sup>2)</sup>], length: 30 m, inside diameter: 0,53 mm

Film thickness: 1,0 µm

Injector system: split or splitless

Injector temperature: 250 °C

Carrier gas: helium

Temperature programme: 120 °C (constant for nonenal and indole), 70 °C (constant for isovaleric acid)

Injection volume: 1,0 ml

Detection: FID

---

2) Agilent J&W is an example of a suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

## Annex B (informative)

### Round-robin test result

#### B.1 Round-robin test

##### B.1.1 General

The odour reduction rate (*ORR*) % was calculated in [Tables B.1](#) to [B.4](#) from the data of the peak area of FID spectrum, with and without a specimen, by using method A.

##### B.1.2 Samples

Polyester woven fabric:

- B-1 treated by a low concentration of deodorant substance;
- B-2 treated by a medium concentration of deodorant substance;
- B-3 treated by a high concentration of deodorant substance.

##### B.1.3 Tested odour chemical gases

- Isovaleric acid
- Nonenal

#### B.2 Test result

##### B.2.1 Isovaleric acid

###### B.2.1.1 Testing gas peak area of FID spectrum without a specimen

**Table B.1 — Isovaleric acid testing gas peak area without a specimen**

| Testing laboratory | Peak area without a specimen |              |              |                           |        |
|--------------------|------------------------------|--------------|--------------|---------------------------|--------|
|                    | <i>n</i> = 1                 | <i>n</i> = 2 | <i>n</i> = 3 | Mean <i>S<sub>b</sub></i> | STD    |
| A                  | 72 126                       | 71 236       | 72 879       | 72 080                    | 822    |
| B                  | 104 694                      | 119 187      | 96 260       | 106 714                   | 11 596 |
| C                  | 46 951                       | 52 161       |              | 49 556                    | 3 684  |
| D                  | 528 459                      | 403 396      | 415 600      | 449 152                   | 68 953 |
| E                  | 6 874                        | 6 954        | 9 363        | 7 730                     | 1 414  |
| F                  | 70 420                       | 61 609       | 50 627       | 60 885                    | 9 916  |

###### B.2.1.2 Testing gas peak area of FID spectrum with specimen B-1 and *ORR* %

*ORR* % is the reduction rate which is calculated by using data from [Tables B.1](#), [B.2](#), [B.3](#), and [B.4](#).

**Table B.2 — Isovaleric testing gas peak area with specimen B-1 and ORR %**

| Testing laboratory       | With the specimen B-1 |              |              |            |        |        |
|--------------------------|-----------------------|--------------|--------------|------------|--------|--------|
|                          | Peak area             |              |              |            |        | ORR %  |
|                          | <i>n</i> = 1          | <i>n</i> = 2 | <i>n</i> = 3 | Mean $S_m$ | STD    |        |
| A                        | 40 091                | 38 270       |              | 39 181     | 1 288  | 45,6   |
| B                        | 59 738                | 60 480       | 57 467       | 59 228     | 1 570  | 44,5   |
| C                        | 37 806                | 34 122       |              | 35 964     | 2 605  | 27,4   |
| D                        | 317 345               | 233 397      | 314 013      | 288 252    | 47 535 | 35,8   |
| E                        | 4 692                 | 5 093        | 4 690        | 4 825      | 232    | 37,6   |
| F                        | 29 759                | 47 152       | 42 656       | 39 856     | 9 028  | 34,5   |
| Mean                     |                       |              |              |            |        | 37,6 % |
| STD (standard deviation) |                       |              |              |            |        | 6,8 %  |

**Table B.3 — Isovaleric acid testing gas peak area with specimen B-2 and ORR %**

| Testing laboratory | With the specimen B-2 |              |              |            |       |        |
|--------------------|-----------------------|--------------|--------------|------------|-------|--------|
|                    | Peak area             |              |              |            |       | ORR %  |
|                    | <i>n</i> = 1          | <i>n</i> = 2 | <i>n</i> = 3 | Mean $S_m$ | STD   |        |
| A                  | 18 678                | 17 753       |              | 18 216     | 654   | 74,7   |
| B                  | 21 760                | 25 134       | 22 624       | 23 173     | 1 753 | 78,3   |
| C                  | 13 526                | 14 639       |              | 14 083     | 787   | 71,6   |
| D                  | 131 928               | 148 631      | 149 447      | 143 335    | 9 887 | 68,1   |
| E                  | 2 658                 | 1 946        | 2 482        | 2 362      | 371   | 69,4   |
| F                  | 15 049                | 8 942        | 13 214       | 12 402     | 3 133 | 79,6   |
| Mean               |                       |              |              |            |       | 73,6 % |
| STD                |                       |              |              |            |       | 4,7 %  |

**Table B.4 — Isovaleric acid testing gas peak area with specimen B-3 and ORR %**

| Testing laboratory | With the specimen B-3 |              |              |            |       |        |
|--------------------|-----------------------|--------------|--------------|------------|-------|--------|
|                    | Peak area             |              |              |            |       | ORR %  |
|                    | <i>n</i> = 1          | <i>n</i> = 2 | <i>n</i> = 3 | Mean $S_m$ | STD   |        |
| A                  | 5 415                 | 4 888        |              | 5 152      | 373   | 92,9   |
| B                  | 12 554                | 9 859        | 12 093       | 11 502     | 1 441 | 89,2   |
| C                  | 6 020                 | 4 757        |              | 5 389      | 893   | 89,1   |
| D                  | 77 878                | 71 864       | 70 236       | 73 326     | 4 025 | 83,7   |
| E                  | 675                   | 1 067        | 673          | 805        | 227   | 89,6   |
| F                  | 6 014                 | 6 761        | 8 039        | 6 938      | 1 024 | 88,6   |
| Mean               |                       |              |              |            |       | 88,8 % |
| STD                |                       |              |              |            |       | 3,0 %  |



## B.2.2 Nonenal

### B.2.2.1 Testing gas peak area of FID spectrum without specimen

**Table B.5 — Nonenal testing gas peak area without specimen**

| Testing laboratory | Without-specimen peak area |              |              |                           |        |
|--------------------|----------------------------|--------------|--------------|---------------------------|--------|
|                    | <i>n</i> = 1               | <i>n</i> = 2 | <i>n</i> = 3 | Mean <i>S<sub>b</sub></i> | STD    |
| A                  | 126 192                    | 140 473      | 139 504      | 135 390                   | 7 980  |
| B                  | 62 654                     | 60 752       | 64 023       | 62 476                    | 1 643  |
| C                  | 17 313                     | 18 097       | 18 961       | 18 124                    | 824    |
| D                  | 123 996                    | 132 853      | 132 963      | 129 937                   | 5 146  |
| E                  | 40 412                     | 43 557       | 29 935       | 37 968                    | 7 132  |
| F                  | 67 373                     | 64 031       | 86 967       | 72 790                    | 12 391 |

### B.2.2.2 Testing gas peak area of FID spectrum with specimens

**Table B.6 — Nonenal testing gas peak area with specimen B-1 and *ORR* %**

| Testing laboratory | With the specimen B-1 |              |              |                           |       | <i>ORR</i> % |
|--------------------|-----------------------|--------------|--------------|---------------------------|-------|--------------|
|                    | Peak area             |              |              |                           |       |              |
|                    | <i>n</i> = 1          | <i>n</i> = 2 | <i>n</i> = 3 | Mean <i>S<sub>m</sub></i> | STD   |              |
| A                  | 56 752                | 59 570       | 53 820       | 56 714                    | 2 875 | 58,1         |
| B                  | 21 307                | 20 539       | 22 646       | 21 497                    | 1 066 | 65,6         |
| C                  | 6 759                 | 6 550        | 6 514        | 6 608                     | 132   | 63,5         |
| D                  | 58 474                | 57 387       | 56 127       | 57 329                    | 1 175 | 55,9         |
| E                  | 15 651                | 13 074       | 14 093       | 14 273                    | 1 298 | 62,4         |
| F                  | 31 801                | 26 290       | 23 649       | 27 247                    | 4 159 | 62,6         |
| Mean               |                       |              |              |                           |       | 61,3 %       |
| STD                |                       |              |              |                           |       | 3,6 %        |

**Table B.7 — Nonenal testing gas peak area with specimen B-2 and *ORR* %**

| Testing laboratory | With the specimen B-2 |              |              |                           |       | <i>ORR</i> % |
|--------------------|-----------------------|--------------|--------------|---------------------------|-------|--------------|
|                    | Peak area             |              |              |                           |       |              |
|                    | <i>n</i> = 1          | <i>n</i> = 2 | <i>n</i> = 3 | Mean <i>S<sub>m</sub></i> | STD   |              |
| A                  | 24 321                | 29 846       | 21 600       | 25 256                    | 4 202 | 81,3         |
| B                  | 8 541                 | 7 009        | 7 227        | 7 592                     | 829   | 87,8         |
| C                  | 3 008                 | 2 805        | 3 282        | 3 032                     | 239   | 83,3         |
| D                  | 30 509                | 34 059       | 32 601       | 32 390                    | 1 784 | 75,1         |
| E                  | 7 450                 | 7 534        | 6 729        | 7 238                     | 443   | 80,9         |
| F                  | 15 490                | 12 710       | 11 020       | 13 073                    | 2 257 | 82,0         |
| Mean               |                       |              |              |                           |       | 81,7         |
| STD                |                       |              |              |                           |       | 4,1          |

**Table B.8 — Nonenal testing gas peak area with specimen B-3 and ORR %**

| Testing laboratory | With the specimen B-3 |              |              |            |       |        |
|--------------------|-----------------------|--------------|--------------|------------|-------|--------|
|                    | Peak area             |              |              |            |       | ORR %  |
|                    | <i>n</i> = 1          | <i>n</i> = 2 | <i>n</i> = 3 | Mean $S_m$ | STD   |        |
| A                  | 9 095                 | 12 776       | 9 392        | 10 421     | 2 045 | 92,3   |
| B                  | 3 870                 | 3 875        | 3 572        | 3 772      | 174   | 94,0   |
| C                  | 1 511                 | 1 411        | 1 369        | 1 430      | 73    | 92,1   |
| D                  | 14 974                | 14 057       | 13 896       | 14 309     | 582   | 89,0   |
| E                  | 2 781                 | 2 264        | 2 378        | 2 474      | 272   | 93,5   |
| F                  | 8 248                 | 6 383        | 7 135        | 7 255      | 938   | 90,0   |
| Mean               |                       |              |              |            |       | 91,8 % |
| STD                |                       |              |              |            |       | 2,0 %  |

### B.2.3 Summary of test result

**Table B.9 — Summary of the test result**

| Sample          | ID code                           | B-1  | B-2    | B-3  |
|-----------------|-----------------------------------|------|--------|------|
|                 | Deodorant treatment concentration | Low  | Medium | High |
| Isovaleric acid | ORR (%)                           | 37,6 | 73,6   | 88,8 |
|                 | STD (%)                           | 6,8  | 4,7    | 3,0  |
| Nonenal         | ORR (%)                           | 61,3 | 81,7   | 91,8 |
|                 | STD (%)                           | 3,6  | 4,1    | 2,0  |







# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™