



BSI Standards Publication

Rubber — Determination of magnesium content of field and concentrated natural rubber latices by titration (cyanide-free method)

National foreword

This British Standard is the UK implementation of ISO 17403:2014.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Rubber - Raw, natural and synthetic, including latex and carbon black.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 77082 1

ICS 83.040.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2014.

Amendments issued since publication

Date	Text affected
------	---------------

**Rubber — Determination of
magnesium content of field and
concentrated natural rubber latices by
titration (cyanide-free method)**

*Caoutchouc — Détermination par titrage de la teneur en magnésium
du latex de plantation et du latex concentré de caoutchouc naturel
(méthode sans cyanure)*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Apparatus	1
5	Reagents	2
6	Method A — Determination of magnesium content of field latex	2
6.1	Principle.....	2
6.2	Procedure.....	3
6.3	Number of determinations.....	3
6.4	Calculation of results.....	3
6.5	Expression of result.....	3
7	Method B — Determination of magnesium content of concentrated latex	4
7.1	Principle.....	4
7.2	Procedure.....	4
7.3	Number of determinations.....	4
7.4	Calculation of results.....	5
7.5	Expression of result.....	5
8	Test report	5
Annex A (informative) Precision		7
Bibliography		10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information.

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw material (including latex) for use in the rubber industry*.

Rubber — Determination of magnesium content of field and concentrated natural rubber latices by titration (cyanide-free method)

1 Scope

This International Standard specifies a cyanide-free titration method for the determination of the magnesium content in field and concentrated natural rubber latex.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 124, *Latex, rubber — Determination of total solids content*

ISO 648, *Laboratory glassware — Single-volume pipettes*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

natural rubber latex concentrate

natural rubber latex from *Hevea brasiliensis* containing ammonia and/or other preservatives, which has been subjected to some process of concentration

3.2

field natural rubber latex

natural rubber latex with or without a preservative and prior to concentration or any other processing

Note 1 to entry: The preservative is added to maintain the original state of the latex as it came from the tree.

3.3

magnesium content

content of magnesium equivalent to alkaline-earth metals, mainly magnesium and calcium, present in all soluble forms that may be titrated with ethylenediaminetetraacetic acid in field or concentrated natural rubber latex

4 Apparatus

4.1 **Burette**, 50 cm³ graduated.

4.2 **Analytical balance**, accurate to 0,1 mg.

4.3 **Volumetric pipettes**, of capacities 2 cm³, 5 cm³ and 10 cm³ complying with the requirements of ISO 648, class A.

5 Reagents

Use reagents of recognized analytical quality. And, wherever water is specified, use distilled water or water of equivalent purity.

5.1 Magnesium sulfate solution.

Dissolve 1,232 4 g magnesium sulfate heptahydrate ($\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$) in water and make up to 1 dm³ in a flask. 1 cm³ of this solution contains magnesium which is equivalent to 1 cm³ of 0,005 mol/dm³ EDTA.

5.2 EDTA solution, 0,005 mol/dm³.

Dissolve approximately 1,86 g of sodium salt of ethylenediaminetetraacetic acid (EDTA) in water and make up to 1 dm³. Standardize against the standard solution of magnesium sulfate specified in [5.1](#).

5.3 Masking agent solution.

Dissolve sufficient sodium hydrogen sulphide hydrate ($\text{NaHS} \cdot x\text{H}_2\text{O}$) to give at least 1,68 g sodium hydrogen sulfide (NaHS). Transfer into a 100 cm³ volumetric flask and make up to volume with water. 1 cm³ of this solution is equivalent to 1 cm³ of 0,3 mol/dm³ NaHS.

NOTE If the number of hydrate groups is not indicated ($x\text{H}_2\text{O}$), NaHS content may be calculated from the percentage of NaHS assay in the specification data. For example, if the percentage of NaHS assay equals 60,0 %, 2,80 g of $\text{NaHS} \cdot x\text{H}_2\text{O}$ is necessary to give 1,68 g of NaHS.

5.4 Eriochrome black T indicator.

Grind together, in a small pestle and mortar, 0,3 g of Eriochrome black T and 100 g of sodium or potassium chloride to give a homogeneous mixture.

5.5 Buffer solution of ammonium chloride/ammonium hydroxide.

Dissolve 67,5 g of ammonium chloride (NH_4Cl) in 250 cm³ of deionized water, mix with 570 cm³ of 25 % ammonium hydroxide (NH_4OH) and make up to 1 dm³ with deionized water. The solution should have a pH of about 10,5.

5.6 Standardization of EDTA.

Pipette 10 cm³ of the standard magnesium sulfate solution into a beaker. Add 200 cm³ of water and adjust the pH to 10,3 by adding 6 cm³ of the buffer solution. Add 0,1 g of Eriochrome black T indicator and titrate with EDTA solution.

5.7 Calcium hydroxide powder.

6 Method A — Determination of magnesium content of field latex

6.1 Principle

This method determines the soluble concentration of divalent alkaline earth ions present in the latex after the dilution. The results are expressed as magnesium content on the assumption that other divalent alkaline earth ions, such as calcium, are only present at the micromolar concentration level.

The latex is diluted with water. The soluble magnesium content in the latex is determined by titration with the sodium salt of EDTA in the presence of $\text{NH}_4\text{Cl}/\text{NH}_4\text{OH}$ buffer using sulfide releasing agent as masking agent and Eriochrome Black T as indicator.

The magnesium content is expressed as a percentage of the total solids content of latex.

6.2 Procedure

Weigh approximately 2,0 g of the field latex into a conical flask and dilute to 100 cm³ with water.

Add 2,0 cm³ of ammonium chloride/ammonium hydroxide buffer solution to keep the pH of latex solution between 10,0 and 10,5.

Then add 1,0 cm³ of 0,3 mol/dm³ NaHS to the latex solution, mix well and leave the solution for at least 10 s.

Add 0,1 g of Eriochrome black T indicator to the latex solution and mix well.

Then titrate with the standard 0,005 mol/dm³ EDTA solution until the colour of the solution loses the last trace of red and becomes pure blue.

At the end of titration, add approximately 0,5 g of calcium hydroxide into the mixture, shake well and leave for at least 1 min before disposing.

NOTE If the pH value of the solution is higher than 11 after adding 2,0 cm³ of ammonium chloride/ammonium hydroxide buffer solution, the volume of buffer could be reduced in order to keep pH value in the range of 10,0 to 10,5.

6.3 Number of determinations

Carry out the procedure in duplicate, using separate test portions obtained from the same batch of homogenized sample.

6.4 Calculation of results

Calculate the magnesium content expressed as a percentage of the latex or a percentage of the total solid content using the following formula:

$$Mg_{\text{latex}} = \frac{M_{\text{EDTA}} \times V_{\text{EDTA}} \times 24,31 \times 100}{1\,000 \times W}$$

or

$$Mg_{\text{TSC}} = \frac{M_{\text{EDTA}} \times V_{\text{EDTA}} \times 24,31 \times 10\,000}{1\,000 \times W \times \text{TSC}}$$

where

Mg_{latex} is the magnesium content expressed as a percentage of the latex, in percent (%);

Mg_{TSC} is the magnesium content expressed as a percentage of the total solid content, in percent (%);

M_{EDTA} is the concentration of EDTA solution used, in moles per cubic decimetre (mol/dm³);

V_{EDTA} is the volume of EDTA solution used, in cubic centimetres (cm³);

W is the mass, of field latex taken, in grams (g);

TSC is the total solid content of field latex, expressed in percent (%).

6.5 Expression of result

The test result is the average of two determinations, rounded to two decimal places when the magnesium concentration is expressed as a percentage.

7 Method B — Determination of magnesium content of concentrated latex

7.1 Principle

Serum from concentrated latex is prepared by diluting 10 g of concentrated latex in 10 cm³ water, before coagulating with acetic acid. A certain portion of serum is then buffered to pH in the range of 10,0 to 10,5. Then masking agent, NaHS, and Eriochrome black T indicator are added before titration with ethylenediaminetetraacetic acid.

7.2 Procedure

7.2.1 Test portion

Take a portion of thoroughly mixed concentrated latex containing about 10,0 g of total solids. Determine the total solid content (TSC) of concentrated latex according to ISO 124.

7.2.2 Preparation of test solution

Dilute 10,0 g of concentrated latex sample with 10,0 cm³ water and coagulate with 5,0 cm³ of 25 % acetic acid solution until clear serum is obtained.

Pipette 10,0 cm³ of serum into a conical flask and add 4,0 cm³ of ammonium chloride/ammonium hydroxide buffer solution pH 10,5 to raise the pH to the range of 10,0 to 10,5.

Add 1,0 cm³ of masking agent solution, 0,3 mol/dm³ NaHS, to the latex solution and mix well for at least 10 s. Add 0,1 g of Eriochrome black T indicator to the latex solution and mix well.

Titrate the residual magnesium content present in the resultant serum with the sodium salt of ethylenediaminetetraacetic acid (EDTA) in the presence of a buffer using Eriochrome Black T as indicator.

At the end of titration, add approximately 0,5 g of calcium hydroxide into the mixture, shake well and leave for at least 1 min before disposing.

NOTE If the pH value of solution is higher than 11 after adding 4,0 cm³ of ammonium chloride/ammonium hydroxide buffer solution, the volume of buffer could be reduced in order to keep pH value in the range of 10,0 to 10,5. The end-point is a little difficult to detect with latex and it is advisable to have an over-titrated solution at hand for comparison.

7.3 Number of determinations

Carry out the procedure in duplicate, using separate test portions obtained from the same batch of homogenized sample.

7.4 Calculation of results

Calculate the magnesium content, expressed as a percentage on the total solid content, using the following formula:

$$Mg_{\text{Based on TSC}} = \frac{M_{\text{EDTA}} \times V_{\text{EDTA}} \times 24,31 \times W_{\text{Total serum}} \times 100}{1000 \times V_{\text{Pipetted serum}} \times \left(\frac{W_{\text{Latex sample}} \times TSC}{100} \right)}$$

where

- $Mg_{\text{Based on TSC}}$ is the magnesium content expressed as a percentage of the total solid content, in percent (%);
- M_{EDTA} is the concentration of EDTA, in moles per cubic decimetre (mol/dm³);
- V_{EDTA} is the volume of EDTA in titration, in cubic centimetres (cm³);
- $V_{\text{Pipetted serum}}$ is the volume of pipetted serum, in cubic centimetres (cm³);
- $W_{\text{Latex sample}}$ is the mass of the latex sample, in grams (g);
- TSC is the total solid content, expressed in percent (%);
- $W_{\text{Total serum}}$ is the mass of total serum, in grams (g):

$$W_{\text{Total serum}} = W_{\text{Latex sample}} - \left(\frac{W_{\text{Latex sample}} \times TSC}{100} \right) + V_{\text{Added water}} + V_{\text{Added acid}}$$

where

- $V_{\text{Added water}}$ is the volume of water added to dilute the sample at the beginning of the procedure (7.2.2), in cubic centimetres (cm³);
- $V_{\text{Added acid}}$ is the volume of 25 % acetic acid added to the serum for coagulation (7.2.2), in cubic centimetres (cm³).

7.5 Expression of result

The test result is taken as the average of two determinations, rounded to three decimal places when the concentration is expressed in % magnesium on the TSC.

8 Test report

The test report shall include the following information:

- a reference to this International Standard, i.e. ISO 17403;
- all details necessary for the complete identification of the product tested;
- the method of sampling;
- the type of instruments used;
- the results obtained and the units in which they are expressed;
- any unusual features noted during the determination;

- g) any operations not included in this International Standard to which reference is made, as well as any incident which might have affected the results.

Annex A (informative)

Precision

A.1 Method A — Determination of magnesium content of field latex

A.1.1 The precision of the test method was determined in accordance with ISO/TR 9272[1]. Refer to this document for terminology and other statistical details.

A.1.2 The precision data are given in [Table A.1](#). The precision parameters should not be used for acceptance or rejection of any group of materials without documentation that the parameters are applicable to those particular materials and specific test protocols of the test method. The precision is expressed on the basis of a 95 % confidence level for the values established for repeatability r and reproducibility R .

A.1.3 The results contained in [Table A.1](#) are average values and give an estimate of the precision of this test method. The results were obtained from an interlaboratory test programme (ITP) carried out in 2012 where six laboratories took part in performing duplicate analyses on two samples namely A and B which were prepared from high-ammonia latex.

Before the bulk was sub-sampled into three bottles labelled A, B and C, it was filtered and homogenized by thorough stirring. Thus essentially samples A, B and C were the same and were treated as such in the statistical computations. Each participating laboratory was required to carry out the test using these two samples, on the dates given to them.

A.1.4 A Type 1 precision was evaluated based on the method of sampling used for the ITP.

A.1.5 Repeatability: the repeatability r (in measurement units) of the test method has been established as the appropriate value tabulated in [Table A.1](#). Two single test results, obtained in the same laboratory under normal test method procedures that differ by more than the tabulated r (for any given level) should be considered to have come from different, or non-identical, sample populations.

A.1.6 Reproducibility: the reproducibility R (in measurement units) of the test method has been established as the appropriate value tabulated in [Table A.1](#). Two single test results, obtained in the same laboratory under normal test method procedures that differ by more than the tabulated R (for any given level) should be considered to have come from different, or non-identical, sample populations.

A.1.7 Bias: in test method terminology, bias is the difference between an average test value and the reference (or true) test property value. Reference values do not exist for this test method since the value (of the test property) is exclusively defined by the test method. Bias cannot therefore be determined for this particular method.

Table A.1 — Level 1 and type 1 precision data for magnesium content in field latex

Material	Mean	Within-laboratory			Between laboratories			Number of laboratories
		s_r	r	(r)	s_R	R	(R)	
A	0,020	0,002	0,004	21,3	0,009	0,026	131,0	6
B	0,039	0,002	0,006	14,4	0,012	0,033	83,6	6
C	0,068	0,002	0,004	6,4	0,020	0,056	82,4	6

s_r is the within-laboratory standard deviation (in measurement units);
 r is the repeatability (in measurement units);
(r) is the relative repeatability;
 s_R is the between-laboratory standard deviation (for total between-laboratory variation in measurement units);
 R is the reproducibility (in measurement units);
(R) is the relative reproducibility.

A.2 Method B — Determination of magnesium content of concentrated natural rubber latex

A.2.1 The precision of the test method was determined in accordance with ISO/TR 9272[1]. Refer to this document for terminology and other statistical details.

A.2.2 The precision data are given in [Table A.2](#). The precision parameters should not be used for acceptance or rejection of any group of materials without documentation that the parameters are applicable to those particular materials and specific test protocols of the test method. The precision is expressed on the basis of a 95 % confidence level for the values established for repeatability r and reproducibility R .

A.2.3 The results contained in [Table A.2](#) are average values and give an estimate of the precision of this test method. The results were obtained from an ITP carried out in 2012 where eight laboratories took part in performing duplicate analyses on two samples namely D and E which were prepared from high-ammonia latex. Before the bulk was sub-sampled into two bottles labelled D and E, it was filtered and homogenized by thorough stirring. Thus essentially, samples D and E were the same and were treated as such in the statistical computations. Each participating laboratory was required to carry out the test using these two samples, on the dates given to them.

A.2.4 A Type 1 precision was evaluated based on the method of sampling used for the ITP.

A.2.5 Repeatability: the repeatability r (in measurement units) of the test method has been established as the appropriate value tabulated in [Table A.2](#). Two single test results, obtained in the same laboratory under normal test method procedures that differ by more than the tabulated r (for any given level) should be considered to have come from different, or non-identical, sample populations.

A.2.6 Reproducibility: the reproducibility R (in measurement units) of the test method has been established as the appropriate value tabulated in [Table A.2](#). Two single test results, obtained in the same laboratory under normal test method procedures that differ by more than the tabulated R (for any given level) should be considered to have come from different, or non-identical, sample populations.

A.2.7 Bias: in test method terminology, bias is the difference between an average test value and the reference (or true) test property value. Reference values do not exist for this test method since the value (of the test property) is exclusively defined by the test method. Bias cannot therefore be determined for this particular method.

Table A.2 — Level 1 and type 1 precision data for magnesium content in concentrated latex

Material	Mean	Within-laboratory			Between laboratories			Number of laboratories
		s_r	r	(r)	s_R	R	(R)	
D	0,004 2	0,000 3	0,001	18,15	0,002	0,005	118,90	8
E	0,007 2	0,000 2	0,001	8,96	0,002	0,006	85,59	8

s_r is the within-laboratory standard deviation (in measurement units);
 r is the repeatability (in measurement units);
 (r) is the relative repeatability;
 s_R is the between-laboratory standard deviation (for total between-laboratory variation in measurement units);
 R is the reproducibility (in measurement units);
 (R) is the relative reproducibility.

Bibliography

- [1] ISO/TR 9272, *Rubber and rubber products — Determination of precision for test method standards*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™