

BS ISO 18098:2013



BSI Standards Publication

**Thermal insulating products
for building equipment and
industrial installations —
Determination of the apparent
density of preformed pipe
insulation**

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 18098:2013.

The UK participation in its preparation was entrusted to Technical Committee B/540/8, Mirror committee for ISO/TC 163 - Thermal Performance and Energy use in the built Environment.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 79587 9

ICS 91.100.60

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2013.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
18098

First edition
2013-04-15

**Thermal insulating products for
building equipment and industrial
installations — Determination of the
apparent density of preformed pipe
insulation**

*Produits isolants thermiques pour l'équipement du bâtiment et les
installations industrielles — Détermination de la masse volumique
apparente des coquilles isolantes préformées*



Reference number
ISO 18098:2013(E)

© ISO 2013



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Apparatus.....	1
6 Test specimens.....	2
6.1 Dimensions of test specimens.....	2
6.2 Number of test specimens.....	2
6.3 Preparation of test specimens.....	2
6.4 Conditioning of test specimens.....	2
7 Procedure.....	3
7.1 Test conditions.....	3
7.2 Test procedure.....	3
8 Calculation and expression of results.....	3
9 Accuracy of measurement.....	4
10 Test report.....	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18098 was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 1, *Test and measurement methods*.

ISO 18098 includes the original EN 13470 prepared by Technical Committee CEN/TC 88, *Thermal insulating materials and products*. However, the following have been modified to reflect conditions for tropical countries:

- [6.4](#) “Conditioning of test specimens”;
- [7.1](#) “Test conditions”; and
- [Clause 10](#) “Test report”.

Introduction

This International Standard is one of a series of existing European Standards on test methods for products used to insulate building equipment and industrial installations which comprises the following group of International Standards:

ISO standard	Title	Respective EN standard
ISO 12623	<i>Thermal insulating products for building equipment and industrial installations — Determination of short-term water absorption by partial immersion of preformed pipe insulation</i>	EN 13472
ISO 12624	<i>Thermal insulating products for building equipment and industrial installations — Determination of trace quantities of water soluble chloride, fluoride, silicate, sodium ions and pH</i>	EN 13468
ISO 12628	<i>Thermal insulating products for building equipment and industrial installations — Determination of dimensions, squareness and linearity of preformed pipe insulation</i>	EN 13467
ISO 12629	<i>Thermal insulating products for building equipment and industrial installations — Determination of water vapour transmission properties of preformed pipe insulation</i>	EN 13469
ISO 18096	<i>Thermal insulating products for building equipment and industrial installations — Determination of maximum service temperature for preformed pipe insulation</i>	EN 14707
ISO 18097	<i>Thermal insulating products for building equipment and industrial installations — Determination of maximum service temperature</i>	EN 14706
ISO 18098	<i>Thermal insulating products for building equipment and industrial installations — Determination of the apparent density of preformed pipe insulation</i>	EN 13470
ISO 18099	<i>Thermal insulating products for building equipment and industrial installations — Determination of the coefficient of thermal expansion</i>	EN 13471

A further series of existing European Standards on test methods was adopted by ISO. This “package” of standards comprises the following group of interrelated standards:

ISO standard	Title	Respective EN standard
ISO 12344	<i>Thermal insulating products for building applications — Determination of bending behaviour</i>	EN 12089
ISO 12968	<i>Thermal insulation products for building applications — Determination of the pull-off resistance of external thermal insulation composite systems (ETICS) (foam block test)</i>	EN 13495
ISO 29465	<i>Thermal insulating products for building applications — Determination of length and width</i>	EN 822
ISO 29466	<i>Thermal insulating products for building applications — Determination of thickness</i>	EN 823
ISO 29467	<i>Thermal insulating products for building applications — Determination of squareness</i>	EN 824
ISO 29468	<i>Thermal insulating products for building applications — Determination of flatness</i>	EN 825
ISO 29469	<i>Thermal insulating products for building applications — Determination of compression behaviour</i>	EN 826
ISO 29470	<i>Thermal insulating products for building applications — Determination of the apparent density</i>	EN 1602
ISO 29471	<i>Thermal insulating products for building applications — Determination of dimensional stability under constant normal laboratory conditions (23 degrees C/50 % relative humidity)</i>	EN 1603
ISO 29472	<i>Thermal insulating products for building applications — Determination of dimensional stability under specified temperature and humidity conditions</i>	EN 1604
ISO 29764	<i>Thermal insulating products for building applications — Determination of deformation under specified compressive load and temperature conditions</i>	EN 1605
ISO 29765	<i>Thermal insulating products for building applications — Determination of tensile strength perpendicular to faces</i>	EN 1607
ISO 29766	<i>Thermal insulating products for building applications — Determination of tensile strength parallel to faces</i>	EN 1608
ISO 29767	<i>Thermal insulating products for building applications — Determination of short-term water absorption by partial immersion</i>	EN 1609
ISO 29768	<i>Thermal insulating products for building applications — Determination of linear dimensions of test specimens</i>	EN 12085
ISO 29769	<i>Thermal insulating products for building applications — Determination of behaviour under point load</i>	EN 12430
ISO 29770	<i>Thermal insulating products for building applications — Determination of thickness for floating-floor insulating products</i>	EN 12431
ISO 29771	<i>Thermal insulating materials for building applications — Determination of organic content</i>	EN 13820
ISO 29803	<i>Thermal insulation products for building applications — Determination of the resistance to impact of external thermal insulation composite systems (ETICS)</i>	EN 13497

The Application of Agreement on technical cooperation between ISO and CEN (Vienna Agreement), Modes 1, 2, 4, and 5, was not approved by CEN/TC 88 and the necessity not seen by its stakeholders.

This International Standard is one of a series of standards which specify test methods for determining dimensions and properties of thermal insulating materials and products. The original EN 13470 supports a series of product standards for thermal insulating materials and products which derive from the Council Directive of 21 December 1988 on the approximation of laws, regulations, and administrative provisions of the Member States relating to construction products (Directive 89/106/EEC) through the consideration of the essential requirements.

This International Standard has been prepared for products used to insulate building equipment and industrial installations, but it may also be applied to products used in other areas.

Thermal insulating products for building equipment and industrial installations — Determination of the apparent density of preformed pipe insulation

1 Scope

This International Standard specifies the equipment and procedures for determining the apparent overall density and the apparent core density under reference conditions. It is applicable to full-size thermal insulating products and test specimens of preformed pipe insulation.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 12628, *Thermal insulating products for building equipment and industrial installations — Determination of dimensions, squareness and linearity of preformed pipe insulation*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

apparent overall density

ρ_a

mass per unit volume of a product, including all surface skins formed during production, but excluding any facings and/or coatings

3.2

apparent core density

ρ_c

mass per unit volume of the core of a product after all surface skins formed during production and all facings and/or coatings have been removed

4 Principle

The density is determined as the quotient of the mass and the volume of the test specimen.

5 Apparatus

5.1 **Balance**, capable of determining the mass of a test specimen to an accuracy of 0,5 %.

5.2 **Equipment**, for the determination of the dimensions of preformed pipe insulation (see [7.2](#)).

6 Test specimens

6.1 Dimensions of test specimens

The test specimens shall be full-size products or parts of them, or test specimens used for other tests.

When the apparent overall density is being determined using test specimens cut from a product with surface skins formed during production, the ratio of the area of the surface skin to the total volume shall be the same for the test specimen as for the product.

The size of a test specimen should preferably be as large as possible, commensurate with the apparatus available and with the shape of the original product. The size of the test specimens may also be specified in other test methods.

6.2 Number of test specimens

The number of test specimens for full-size products shall be as specified in the relevant product standard. If test specimens from other tests are used, the number shall be as specified in the test method. If the number is not specified, then at least three test specimens shall be used.

NOTE In the absence of a product standard or any other international technical specification, the number of test specimens may be agreed between parties.

6.3 Preparation of test specimens

The test specimens shall be cut by methods that do not change the original structure of the product.

The location from which the test specimens are taken shall be such that the density obtained is representative of the density of the product.

For determining the apparent overall density, any facings and/or coatings shall be removed from the product. For determining the apparent core density, any surface skins formed during production and any facings and/or coatings shall be removed from the product.

When it is not possible to remove the facings and/or coatings without influencing the apparent density of the product, the mass of the facings and/or coatings shall be deducted by calculation.

NOTE Special methods of preparation, when needed, are given in the relevant product standard.

6.4 Conditioning of test specimens

The test specimens shall be conditioned at (23 ± 2) °C and (50 ± 5) % relative humidity (RH) until constant mass is achieved.

The time for conditioning and the required accuracy of the constant mass measurements shall be given in the relevant product standard.

NOTE 1 If it can be shown that temperature and humidity has negligible influence on the determination of the density, then the conditioning can be carried out at (23 ± 5) °C.

NOTE 2 The conditioning time can be shortened by pre-drying the test specimen in a ventilated drying chamber at a prescribed temperature. Appropriate procedures may be given in the relevant product standard.

In tropical countries, different conditioning and testing conditions can be relevant. In this case, the conditions shall be (27 ± 5) °C and (65 ± 5) % RH.

7 Procedure

7.1 Test conditions

The test shall be carried out at (23 ± 2) °C and (50 ± 5) % RH.

NOTE If it can be shown that temperature and humidity has negligible influence on the determination of the density, the testing can be carried out at (23 ± 5) °C.

In tropical countries, different conditioning and testing conditions can be relevant. In this case, the conditions shall be (27 ± 5) °C and (65 ± 5) % RH.

7.2 Test procedure

Measure the linear dimensions of full-size products and test specimens in accordance with ISO 12628. Calculate the volumes of the test specimens from these measurements.

Weigh each test specimen to an accuracy of 0,5 % and record its mass in kilogrammes. If the facings and/or coatings are retained, the mass of the product shall be calculated by deducting the mass of the facings and/or coatings and adhesives, if any, from the overall mass.

If a higher accuracy for dimensions of full-size products is needed, it shall be specified in the relevant product standard.

8 Calculation and expression of results

Calculate the apparent overall density, ρ_a , or apparent core density, ρ_c , in kilogrammes per cubic metre using the formula:

$$\rho = \frac{m}{V} \quad (1)$$

where

m is the mass of the test specimen, in kilogrammes;

V is the volume of the test specimen, in cubic metres.

The calculation of V for a full-size pipe insulation is made as follows:

$$V = l \times \frac{\pi}{4} \times (D_o^2 - D_i^2) \quad (2)$$

where

l is the length of the test specimen, in metres;

D_o is the outside diameter, in metres;

D_i is the inside diameter, in metres.

ρ (ρ_a or ρ_c) for the test specimen is given to three significant figures.

Calculate the arithmetic mean value of the density from the results for all test specimens and express the value to three significant figures.

For some products, the determination of the volume used for the calculation of the density of test specimens, with an irregular or complicated shape, can be made measuring the quantity of displaced

water during the complete immersion in water at (23 ± 2) °C. In this case, the mass should be determined before the volume determination.

9 Accuracy of measurement

NOTE It has not been possible to include a statement on the accuracy of the method in this edition of this International Standard, but it is intended to include such a statement when this International Standard is next revised.

10 Test report

The test report shall include the following information:

- a) a reference to this International Standard (i.e. ISO 18098:2013);
- b) product identification:
 - 1) product name, factory, manufacturer, or supplier;
 - 2) production code number;
 - 3) type of product;
 - 4) packaging;
 - 5) form in which the product arrived at the laboratory;
 - 6) other information as appropriate, e.g. nominal dimensions;
- c) test procedure:
 - 1) pre-test history and sampling, e.g. who sampled and where;
 - 2) conditioning;
 - 3) conditioning and testing conditions in tropical countries, if applicable;
 - 4) drying conditions;
 - 5) presence of facings, the mass of the facing, and the method of removal, if necessary;
 - 6) presence of surface skins and the method of removal, if necessary;
 - 7) presence of densification, stratification, or defects of the test specimens;
 - 8) any deviation from [Clauses 6](#) and [7](#);
 - 9) date of testing;
 - 10) general information relating to the test;
 - 11) events which may have affected the results;

NOTE Information about the apparatus and identity of the technician should be available in the laboratory, but it need not be recorded in the report.
- d) results:
 - 1) all individual values and the mean value.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™