

BS ISO 18314-1:2015



BSI Standards Publication

Analytical colorimetry

Part 1: Practical colour measurement

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 18314-1:2015.

The UK participation in its preparation was entrusted to Technical Committee STI/1, Pigments.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 86039 3

ICS 87.060.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2015.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 18314-1:2015

ISO
18314-1

First edition
2015-06-01

Analytical colorimetry —
Part 1:
Practical colour measurement

Analyse colorimétrique —

Partie 1: Mesurage pratique de la couleur



Reference number
ISO 18314-1:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Sample preparation	1
4 Sample measurement	2
4.1 General.....	2
4.2 Recommended colourimetric conditions.....	2
5 Calibration	2
5.1 General.....	2
5.2 Environmental conditions.....	2
5.3 White calibration.....	2
5.4 Black calibration.....	3
5.5 Control measurement.....	3
5.6 Storage of the calibration standards.....	3
6 Apparatus	3
6.1 Spectrophotometer.....	3
6.2 Tristimulus colourimeter.....	3
7 Selection of appropriate measurement geometry	3
Bibliography	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 256, *Pigments, dyestuffs and extenders*

ISO 18314 consists of the following parts, under the general title *Analytical colorimetry*:

- *Part 1: Practical colour measurement*
- *Part 2: Saunderson correction, solutions of the Kubelka-Munk equation, tinting strength, hiding power*
- *Part 3: Special indices*

Analytical colorimetry —

Part 1: Practical colour measurement

1 Scope

This part of ISO 18314 specifies the method for determining the colour coordinates of a paint film. This method is only applicable to paint films that appear to be uniformly of one colour, i.e. monochromatic, when examined with normal vision. Paint films that do not completely hide a non-transparent substrate represent an opaque system and can be measured by using the procedure in this part of ISO 18314.

Luminescent paint films, transparent paint films, and translucent paint films (for example for display or lamp glass), retroreflecting paint films (for example for traffic signs), and metallic paint films are outside the scope of this part of ISO 18314.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Sample preparation

Take a representative sample of the paint to be tested as described in accordance with ISO 15528.

Examine and prepare the sample for testing in accordance with ISO 1513.

Prepare the test panels in accordance with ISO 1514. Apply the coating always in the same way (e.g. by spraying, brushing, or with application bars), dry or stove and, if necessary, condition the paint film as directed in the manufacturer's instructions or as otherwise agreed.

If the paint film is of reversible temperature-dependent colour, the temperature of the test sample should be maintained at (23 ± 2) °C by appropriate measures (for example by the use of a thermostatically controlled sample holder). Paint films of irreversible temperature-dependent colour should be postconditioned, until the colour does not change any more. In the case of paint films that do not completely hide the substrate, the colour depends on the colour of the substrate and the film thickness, which should be determined by one of the procedures given in ISO 2808.

The paint film sample shall not be scratched and shall be free from dust and grease (e.g. fingerprints).

For process control of painted articles take representative test samples. The number of samples shall be agreed upon between the parties.

4 Sample measurement

4.1 General

For highly precise measurement results, the samples shall be plane. Dependent on sample size, multiple readings shall be taken. The individual measurements shall exclude trends and outliers. The aperture size of the instrument shall be as large as possible.

For measurements taken on curved samples, the geometrical conditions specified for plane samples are no longer applicable. Measurement uncertainty and deviation of results from those of plane surfaces will increase as curvature increases. When selecting the measurement area on curved surfaces, the smallest possible curvature (biggest curvature radius) shall be placed on the smallest possible measuring aperture. To increase repeatability, the use of a customized sample holder is recommended.

Comparison of samples with different surface properties (e.g. texture, gloss) may lead to different results depending on the measuring geometry of the instrument (see [Clause 7](#)).

4.2 Recommended colourimetric conditions

The measurements shall be performed for the following conditions:

- Illuminant: D65 (for determination of metamerism additional illuminants are needed);
- Observer: 10°;
- Colour space: CIELAB or DIN 99
- Colour differences: It is important to take into consideration that CIELAB colour space is not visually uniform for small colour differences. Therefore, the use of the colour difference correction formula CIEDE2000 or the new colour space DIN 99 are recommended.

NOTE Standard illuminant D65 is defined in ISO 11664-2. Standard colourimetric observer for 10° is defined in ISO 11664-1. CIELAB is defined in ISO 11664-4. The DIN 99 formula is defined in DIN 6176. The CIEDE2000 formula is defined in ISO 11664-6.

5 Calibration

5.1 General

The correct calibration of colour measuring instruments is one of the main requirements for achieving reproducible results. An incorrect or insufficient calibration can have a major impact, and may lead to wrong results.

In order to achieve the highest accuracy, both the basic conditions of calibration (temperature, positioning of the calibration standard) and the instructions of the manufacturer regarding the calibration have to be strictly followed.

5.2 Environmental conditions

The calibration shall be carried out under the same environmental conditions as the sample measurement taken thereafter.

5.3 White calibration

The white standard is made of a durable material, like ceramic, glass, or enamel. The calibration standard that is used for the day-to-day calibration process shall be the one provided by the instrument manufacturer. It has reflectance values that are traceable to a national standard. The white calibration shall be done according to the instrument vendor's recommendations, usually when beginning to work

with the instrument and after breaks. When performing extended measurement series and/or under strongly varying environmental conditions (for example temperature) the white calibration shall be repeated in regular intervals.

Proper identification shall be used to match the standard with the instrument to make certain that only the correct standard is used for calibration.

5.4 Black calibration

A black calibration standard is a standard which has low to no reflectance (for example a black light trap). Black calibration is used to establish a known zero point for the instrument. The black or zero reflectance calibration shall be performed with the black standard supplied by the instrument manufacturer. A black calibration is always done together with a white calibration. Some instruments perform the black calibration internally, thus eliminating the need for separate black calibration.

5.5 Control measurement

After certain time intervals it is recommended to verify the accuracy of the measurements through the use of coloured control standards. The instructions of the manufacturer shall be followed.

The white calibration standard may not be used for control measurements.

5.6 Storage of the calibration standards

All the calibration standards shall be protected from light, mechanical damage, or dirt. Calibration standards that are scratched or damaged in any way shall be replaced immediately. Dirty standards are to be cleaned according to the instructions of the manufacturer. Under common usage a calibration standard can typically be used for one year. Then it is recommended to have the manufacturer of the instrument verify that the values are still within the specifications.

6 Apparatus

6.1 Spectrophotometer

Measurements shall preferably be done with spectrophotometers. The spectral measuring range shall be at least 400 nm to 700 nm. The spectral step width and optical bandwidth shall be ≤ 20 nm (preferable 5 nm to 10 nm).

6.2 Tristimulus colourimeter

Tristimulus colourimeters can be used for applications that do not require control of metamerism.

7 Selection of appropriate measurement geometry

The perceived colour of an object is a combination of first surface reflection (Fresnel) and typically diffuse reflection from the volume. The first surface reflection (approximately 4 % of the incident light) is only dependent on the refractive ratio not on the colorants. Surface texture determines the angular scattering of the first surface reflection.

The $di:8^\circ$ geometry measures the total first surface reflection independent of the surface texture.

The $45^\circ:0^\circ$ geometry only measures the scattered part of the first surface reflection in the direction of 0° .

[Table 1](#) gives the recommended measurement geometries for paint with different properties depending on the objective to be achieved.

Table 1 — Recommended measurement geometries

Sample properties		Recommended measurement geometries	
Material	Surface	Final inspection	Colorants control
		Goal: correlation to visual perception	Goal: independence of surface differences
Paint: opaque and translucent	Mat	45°:0°	di:8°
	Silk mat	45°:0°	di:8°
	High gloss	45°:0°, de:8°	di:8°, (45°:0°, de:8°)
	Textured	45°:0°	di:8°
	Bronzing	45°:0°	
	Orange peel	45°:0°	di:8°
Paint: transparent on high gloss metal	High gloss	di:8°	di:8°
Paint: transparent on mat substrate	High gloss	45°:0°	di:8°
Paste: measurement through high gloss glass	Glass high gloss	45°:0°, de:8°	45°:0°, de:8°

d = diffuse; i = specular included; e = specular excluded

Bibliography

- [1] ISO 11664-1, *Colorimetry — Part 1: CIE standard colorimetric observers*
- [2] ISO 11664-2, *Colorimetry — Part 2: CIE standard illuminants*
- [3] ISO 11664-4, *Colorimetry — Part 4: CIE 1976 L*a*b* Colour space*
- [4] ISO 11664-6, *Colorimetry — Part 6: CIEDE2000 Colour-difference formula*
- [5] ISO 18314-2, *Analytical colourimetry — Part 2: Saunderson correction, solutions of the Kubelka-Munk equation, tinting strength, hiding power*
- [6] ISO 18314-3, *Analytical colorimetry — Part 3: Special indices*
- [7] CIE 15:2004¹⁾, *Colorimetry, 3rd edition, ISBN 3 901 906 33 9*
- [8] DIN 6176, *Colorimetric evaluation of colour differences of surface colours according to DIN99 formula*

1) Available from CIE (International commission on illumination): CIE Central Bureau, Kegelgasse 27, A-1030 Vienna, Austria; www.cie.co.at

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™