

BS ISO 18515:2014



BSI Standards Publication

Carbonaceous materials for the production of aluminium — Cathode blocks and baked anodes — Determination of compressive strength

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 18515:2014. It supersedes BS ISO 18515:2007 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee CII/24, Raw materials for the aluminium industry.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 81221 7

ICS 71.100.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2014.

Amendments issued since publication

Date	Text affected
------	---------------

**Carbonaceous materials for the
production of aluminium —
Cathode blocks and baked anodes
— Determination of compressive
strength**

Produits carbonés utilisés pour la production de l'aluminium — Blocs cathodiques et anodes cuites — Détermination de la résistance à la compression





COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
6 Test specimen	2
6.1 Sampling and sample preparation	2
6.2 Size geometry	2
7 Procedure	2
8 Calculation and expression of results	3
9 Precision	3
10 Test report	3
Bibliography	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 226.

This second edition cancels and replaces the first edition (ISO 18515:2007), of which it constitutes a minor revision.

Carbonaceous materials for the production of aluminium — Cathode blocks and baked anodes — Determination of compressive strength

1 Scope

This International Standard specifies a method to determine the compressive strength of solid carbon and graphite materials at room temperature.

NOTE ISO 18515 is based on DIN 51910.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 8007-1, *Carbonaceous materials used in the production of aluminium — Sampling plans and sampling from individual units — Part 1: Cathode blocks*

ISO 8007-2, *Carbonaceous materials used in the production of aluminium — Sampling plans and sampling from individual units — Part 2: Prebaked anodes*

ISO 8007-3, *Carbonaceous materials used in the production of aluminium — Sampling plans and sampling from individual units — Part 3: Sidewall blocks*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 compressive strength

σ_{dB}

ratio of the maximum force (F_{\max}) during a compressive experiment leading to fracture and the initial cross-section, A , of the specimen

Note 1 to entry: The compressive strength is calculated as the quotient of the maximum force at fracture of the specimen under the conditions of the compressive strength method.

$$\sigma_{dB} = \frac{F_{\max}}{A}$$

where

F_{\max} is the maximum force in newton;

A is the initial cross-section, in meter squared.

Note 2 to entry: The compressive strength is expressed in Mega Pascal (MPa).

Note 3 to entry: Generally, the maximum force displayed on the test machine and the force at fracture is similar, if they are different, the term refers to the maximum force displayed.

4 Principle

The compressive strength is determined using cylindrical or cubic test specimens. A test specimen with plane parallel end planes is pressed between the pressure plates of a testing machine. The compressive strength is calculated from the maximum force and the initial cross-section of the test specimen.

5 Apparatus

5.1 Compression-testing machine, which meets at least the demands of class 2, in accordance with ISO 7500-1.

5.2 Measuring device, with two pressure plates.

The device shall ensure a uniform load over the surface by cardanic suspension.

5.3 Measuring device (e.g. vernier calliper, in accordance with ISO 13385-1), capable of measuring the linear dimensions of the test specimens with an accuracy of $\pm 0,5$.

6 Test specimen

6.1 Sampling and sample preparation

Sampling shall be in accordance with the appropriate method, i.e. ISO 8007-1, ISO 8007-2, ISO 8007-3, or be agreed with the applicant. The number of specimens shall be defined with respect to the homogeneity of the material to be tested.

6.2 Size geometry

Cylindrical cubic test specimens of any size can be used, subject only to the requirement that the smallest dimension shall be at least three times the diameter of the largest structural constituent (e.g. maximum grain size) of the material to be tested, but not smaller than 5 mm. When cylindrical test specimens are used, their height shall be equal to the diameter (isometrical cylinders). Similarly, when using hollow cylinders, the height shall be equal to the outer diameter

7 Procedure

7.1 Perform all measurements at room temperature, i.e. in the range 10 °C to 35 °C.

7.2 Choose the measuring range of the testing machine, such that the expected maximum force is at least 1/10 of full scale. Centre the test specimen on the support.

Increase the force uniformly and shock-free at a rate (velocity of the force bearing) of about 5 mm/min until the test specimen fractures. Determine the maximum force.

8 Calculation and expression of results

The compressive strength, σ_{dB} , expressed in MPa, is calculated according to Formula (1):

$$\sigma_{dB} = \frac{F}{A} \quad (1)$$

where

- F is the maximum force, expressed in N;
- A is the initial cross-section, expressed in mm².

9 Precision

A round robin was carried out with participants from 10 laboratories who submitted results for two materials, with four parallels for each. The precision calculation is according to document ISO/TC 226 N 1515.

The precision is given at the 95 % confidence level.

Repeatability, $r = 5,7$ MPa.

Reproducibility, $R = 9,8$ MPa (between laboratories).

NOTE The test samples had similar material averages and it was not possible to determine the dependence on the material average.

Repeatability: Given a number of anodes, all with a compression strength of 42,0 MPa, measured by the same operator in the same laboratory, the difference between two measurements will be within the range $42,0 \text{ MPa} \pm 5,7 \text{ MPa}$ in 95 out of 100 instances.

Reproducibility: Given a number of anodes, all with a compression strength of 42,0 MPa, measured by different laboratories, the difference between two measurements will be within the range $42,0 \text{ MPa} \pm 9,8 \text{ MPa}$ in 95 out of 100 instances.

10 Test report

The test report shall contain the following information:

- a) a reference to this International Standard, (i.e. ISO 18515:2014);
- b) type, position, and orientation of test specimens during the sampling procedure;
- c) designation of the test specimens;
- d) number of test specimens;
- e) linear dimensions of test specimens, in millimetres;
- f) compressive strength, σ_{dB} , in MPa, rounded to the nearest 0,1 MPa, individual values and mean value;
- g) additionally agreed conditions deviating from this International Standard;
- h) test date.

Bibliography

- [1] ISO 13385-1, *Geometrical product specifications (GPS) — Dimensional measuring equipment — Part 1: Callipers; Design and metrological characteristics*
- [1] DIN 51910, *Testing of carbonaceous materials — Determination of compressive strength — Solid materials*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™