

BS ISO 18573:2012



BSI Standards Publication

Conveyor belts — Test atmospheres and conditioning periods

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 18573:2012. It supersedes BS ISO 18573:2003 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/67, Conveyor belts.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 77353 2

ICS 53.040.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2012.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
18573

Second edition
2012-11-01

**Conveyor belts — Test atmospheres
and conditioning periods**

*Courroies transporteuses — Atmosphères d'essai et durées de
conditionnement*



Reference number
ISO 18573:2012(E)

© ISO 2012



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Preconditioning	1
5 Standard atmospheres for conditioning and testing	2
6 Time interval between production and commencement of testing	2
7 Conditioning	2
7.1 Temperature and humidity control.....	2
7.2 Temperature control only.....	3
7.3 Temperatures greater than or less than the standard laboratory test temperature.....	3
7.4 Position of test pieces during conditioning.....	3
8 Testing	3
Bibliography	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18573 was prepared by Technical Committee ISO/TC 41, *Pulleys and belts (including veebelts)*, Subcommittee SC 3, *Conveyor belts*.

This second edition cancels and replaces the first edition (ISO 18573:2003), of which it constitutes a minor revision.

Introduction

The conditioning of test pieces prior to testing is commonly accepted as an essential practice in most, but not necessarily all, methods of test. Its purpose is to provide a common ground base for the commencement of the test and to remove an unnecessary variable in the search for the optimum precision for the particular test.

In order to meet these objectives, it is essential to standardize as many of the variables as possible.

Conveyor belts, other than steel cord conveyor belts, contain a textile element. This can be highly hydrophobic or somewhat more hydrophilic. Similarly, the polymer layer or cover can be thermoplastic or subject to thermal ageing. Each of these factors can have a significant effect on the property of the conveyor belt. These factors need to be taken into account when making a decision as to whether conditioning is necessary and, if so, what the most appropriate conditions would be. The provisions given in ISO 139^[1], ISO 23529^[2] and ISO 2231^[3] have been taken into account in the preparation of this International Standard.

Conveyor belts — Test atmospheres and conditioning periods

1 Scope

This International Standard specifies the temperature, humidity and time conditions used for the conditioning and testing of all types of conveyor belt, irrespective of whether they have plastics or rubber covers. It also specifies the requirements for the time interval to be observed between production and testing of conveyor belt test pieces.

Special conditions applicable to a particular test or material or simulating a particular climatic environment are not included.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 21183-1, *Light conveyor belts — Part 1: Principal characteristics and applications*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

standard atmosphere

specified temperature and humidity in which samples are conditioned and tested

NOTE See Clause 5.

3.2

standard condition

condition reached by a conveyor belt test piece when it is in equilibrium with a standard atmosphere

3.3

moisture equilibrium

condition reached by a conveyor belt test piece when, after free exposure to air in motion, there is no appreciable change in mass

3.4

conditioning

exposure of a test piece to a standard atmosphere for a stipulated period of time immediately before testing, in order to improve the reproducibility of test results

3.5

thermal equilibrium

condition reached by a conveyor belt test piece when it is at a uniform temperature throughout its mass and is within 1 °C of the temperature of its environment

4 Preconditioning

If the textile element of the conveyor belt is of a highly hygroscopic material or if the method of test is highly sensitive to differences in the moisture content of the test piece, it is highly desirable that moisture equilibrium be approached from the dry side of the moisture hysteresis curve. This shall be

achieved by preconditioning the test pieces in an atmosphere having a relative humidity of no greater than 10 % and a temperature of between 60 °C and 70 °C.

NOTE Air at 65 % relative humidity and 20 °C, when heated at constant pressure to between 60 °C and 70 °C, has a relative humidity of approximately 5 %. Higher temperatures can lead to changes in the properties of some polymers.

5 Standard atmospheres for conditioning and testing

The conditioning treatment required for each individual test should be stated in the relevant test method.

The use of one of the following atmospheres shall be fixed by the particular standard or specification for each test. The choice of one of these alternatives will depend on the prevalent usage in individual countries and the variant used shall be reported in the test report.

a) Atmosphere A

- temperature 20 °C ± 2 °C
- relative humidity 65 % ± 5 %

b) Atmosphere B

- temperature 23 °C ± 2 °C
- relative humidity 50 % ± 5 %

c) Atmosphere C (tropical)

- temperature 27 °C ± 2 °C
- relative humidity 65 % ± 5 %

d) Atmosphere D (temperate temperature control only)

- temperature 23 °C ± 2 °C or 20 °C ± 2 °C

e) Atmosphere E (tropical temperature control only)

- temperature 27 °C ± 2 °C

6 Time interval between production and commencement of testing

For all test purposes, the time between completion of production and the commencement of testing shall be no less than 24 h; this period is to include the conditioning periods given in Clause 7. For light conveyor belts (as specified in ISO 21183-1) this period shall be extended to 5 days (120 h).

Whenever possible, the maximum time between production and commencement of testing shall not exceed 3 months.

NOTE Test results obtained on a product where the tests are conducted more than 3 months apart, can exhibit higher variations in repeatability and reproducibility than duplicate tests conducted within this timescale.

7 Conditioning

7.1 Temperature and humidity control

If both the temperature and humidity need to be controlled (Atmospheres A, B or C; see Clause 5), the conditioning period shall be no less than 16 h immediately before testing. For light conveyor belts (as specified in ISO 21183-1), this conditioning period shall be extended to no less than 48 h. In the event of dispute, these conditioning periods shall be extended to no less than 72 h.

7.2 Temperature control only

If only the temperature needs to be controlled (Atmospheres D and E; see Clause 5), the conditioning period shall be no less than 3 h immediately before testing. In the event of dispute, this conditioning period shall be extended to no less than 72 h.

7.3 Temperatures greater than or less than the standard laboratory test temperature

If a temperature other than the standard laboratory temperature is specified without the need to control the humidity, the conditioning time shall be a period sufficient for the test piece to reach temperature equilibrium with the environment, or a period required by the specification covering the material or product being tested.

Guidance on the selection of conditioning times, which will ensure that equilibrium is reached, is given in ISO 23529[2].

7.4 Position of test pieces during conditioning

During the conditioning period, the test pieces shall be positioned in such a manner that, as far as possible, the whole surface of the test piece is exposed without imposing any stress/strain on the test piece, and, unless otherwise specified in the method of test, the test pieces shall be conditioned in the absence of light or ionizing radiation.

8 Testing

Unless otherwise specified, testing shall be carried out at the same temperature and humidity at which the conditioning was performed.

Bibliography

- [1] ISO 139, *Textiles — Standard atmospheres for conditioning and testing*
- [2] ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*
- [3] ISO 2231, *Rubber- or plastics-coated fabrics — Standard atmospheres for conditioning and testing*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™