

BS ISO 18752:2014



BSI Standards Publication

Rubber hoses and hose assemblies — Wire- or textile-reinforced single-pressure types for hydraulic applications — Specification

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 18752:2014. It supersedes BS ISO 18752:2012 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/66, Rubber and plastics tubing, hoses and hose assemblies.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 84400 3

ICS 23.040.70

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2014.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
18752

Third edition
2014-04-01

**Rubber hoses and hose assemblies —
Wire- or textile-reinforced single-
pressure types for hydraulic
applications — Specification**

*Tuyaux et flexibles en caoutchouc — Types hydrauliques avec
armature de fils métalliques tressés — Spécifications*



Reference number
ISO 18752:2014(E)

© ISO 2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
4.1 Classes.....	2
4.2 Grades and types.....	2
5 Materials and construction	3
5.1 Hoses.....	3
5.2 Hose assemblies.....	3
6 Dimensions and tolerances	4
6.1 Diameters.....	4
6.2 Cover thickness.....	6
6.3 Concentricity.....	6
7 Physical properties	7
7.1 Fluid resistance of rubber compounds.....	7
7.2 Performance requirements.....	7
8 Frequency of testing	10
9 Marking	10
9.1 Hoses.....	10
9.2 Hose assemblies.....	10
10 Recommendations for packaging and storage	11
11 Test report	11
Annex A (normative) Type tests and routine tests	12
Annex B (informative) Production acceptance tests	13
Annex C (informative) Recommendations for tolerances on lengths of hose assemblies	14
Annex D (informative) Information to be provided by hose manufacturer	15
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Hoses (rubber and plastics)*.

This third edition cancels and replaces the second edition (ISO 18752:2012), of which it constitutes a minor revision, to include data of "Class 490" in [Table 7](#).

Rubber hoses and hose assemblies — Wire- or textile-reinforced single-pressure types for hydraulic applications — Specification

1 Scope

This International Standard specifies requirements for ten classes, four grades and seven types of wire- or textile-reinforced hydraulic hoses and hose assemblies of nominal sizes ranging from 5 to 102. Each class has a single maximum working pressure for all sizes. Such hoses are suitable for use with hydraulic fluids HH, HL, HM, HR and HV as defined in ISO 6743-4 at temperatures ranging from $-40\text{ }^{\circ}\text{C}$ to $+100\text{ }^{\circ}\text{C}$ for types AS, AC, BS and BC and $-40\text{ }^{\circ}\text{C}$ to $+120\text{ }^{\circ}\text{C}$ for types CS, CC and DC.

This International Standard does not include requirements for the connection ends. It is limited to the performance of hoses and hose assemblies. The hose assembly maximum working pressure is governed by the lowest maximum working pressure of the components.

NOTE It is the responsibility of the user, in consultation with the hose manufacturer, to establish the compatibility of the hose with the fluid to be used.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 6803, *Rubber or plastics hoses and hose assemblies — Hydraulic-pressure impulse test without flexing*

ISO 7233, *Rubber and plastics hoses and hose assemblies — Determination of resistance to vacuum*

ISO 7326:2006, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*

ISO 8033:2006, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 8331, *Rubber and plastics hoses and hose assemblies — Guidelines for selection, storage, use and maintenance*

ISO 10619-1, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature*

ISO 10619-2:2011, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures*

ISO 17165-1, *Hydraulic fluid power — Hose assemblies — Part 1: Dimensions and requirements*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

4 Classification

4.1 Classes

Ten classes of hose are specified, distinguished by their maximum working pressure, as shown in [Table 1](#). Each class may be manufactured in up to 14 nominal sizes.

Table 1 — Classes and nominal sizes

Class	35	70	140	210	250	280	350	420	490	560
MWPa (MPa)	3,5	7	14	21	25	28	35	42	49	56
MWPa (bar)	35	70	140	210	250	280	350	420	490	560
Nominal size										
5	X	X	X	X	X	X	X	X	N/A	N/A
6,3	X	X	X	X	X	X	X	X	N/A	N/A
8	X	X	X	X	X	X	X	X	N/A	N/A
10	X	X	X	X	X	X	X	X	N/A	N/A
12,5	X	X	X	X	X	X	X	X	N/A	N/A
16	X	X	X	X	X	X	X	X	X	X
19	X	X	X	X	X	X	X	X	X	X
25	X	X	X	X	X	X	X	X	X	X
31,5	X	X	X	X	X	X	X	X	X	X
38	X	X	X	X	X	X	X	X	N/A	N/A
51	X	X	X	X	X	X	X	X	N/A	N/A
63	X	X	X	X	X	X	X	N/A	N/A	N/A
76	X	X	X	N/A	N/A	N/A	N/A	N/A	N/A	N/A
102	X	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A

NOTE X = Applicable; N/A = Not applicable.

^a Maximum working pressure.

4.2 Grades and types

Hoses are classified into four grades according to their resistance to impulse: A, B, C and D. Each grade is classified by outside diameter into standard types (AS, BS and CS) and compact types (AC, BC, CC and DC), as shown in [Table 2](#).

Table 2 — Grades and types

Grade	Type ^a	Resistance to impulse		
		Temperature °C	Impulse pressure (% of MWP ^b)	Minimum number of cycles
A	AS	100	133 %	200 000
	AC			
B	BS	100	133 %	500 000
	BC			
C	CS	120	133 % and 120 % ^c	500 000
	CC			
D	DC	120	133 %	1 000 000

^a Standard or compact, e.g. CS is grade C and standard type.
As shown in [Table 4](#) and [Table 8](#), standard types have larger outside diameters and larger bend radii and compact types have smaller outside diameters and smaller bend radii.

^b Maximum working pressure.

^c 120 % of the MWP shall be used for classes 350, 420, 490 and 560 instead of 133 %.

Each class includes one of each type or both as shown in [Table 3](#).

Table 3 — Type and maximum working pressure

Class		35	70	140	210	250	280	350	420	490	560
MWP ^a (MPa)		3,5	7	14	21	25	28	35	42	49	56
MWP ^a (bar)		35	70	140	210	250	280	350	420	490	560
Grade	Type										
A	AS	X	X	X	X	X	X	X	X	N/A	N/A
	AC	X	X	X	X	X	X	X	X	N/A	N/A
B	BS	X	X	X	X	X	X	X	X	N/A	N/A
	BC	X	X	X	X	X	X	X	X	N/A	N/A
C	CS	N/A	N/A	N/A	X	X	X	X	X	N/A	N/A
	CC	N/A	N/A	N/A	X	X	X	X	X	X	X
D	DC	N/A	N/A	N/A	X	X	X	X	X	N/A	N/A

NOTE X = Applicable; N/A = Not applicable.

^a Maximum working pressure.

5 Materials and construction

5.1 Hoses

Hoses shall consist of a hydraulic-fluid-resistant rubber lining, one or multiple layers of steel wire or textile and an oil-, abrasion- and weather-resistant rubber cover. A layer of other materials on the rubber cover is allowed for improved resistance to abrasion or other.

5.2 Hose assemblies

Hose assemblies shall only be manufactured using hose fittings which conform to the requirements of [7.2.1](#), [7.2.4](#) and [7.2.5](#).

Follow the manufacturer's instructions for the proper preparation and fabrication of hose assemblies.

6 Dimensions and tolerances

6.1 Diameters

When measured in accordance with ISO 4671, the diameters of hoses shall conform to the values given in [Table 4](#).

Table 4 — Diameters of hoses

Nom- inal size	Inside diameter (all classes) mm		Maximum outside diameter of hose mm																				
			Class 35		Class 70		Class 140		Class 210		Class 250		Class 280		Class 350		Class 420		Class 490		Class 560		
			Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	
5	4,6	5,4	14	11	14	11	17	15	17	15	17	15	17	15	17	15	17	15	17	15	17	—	—
6,3	6,1	7,0	17	14	17	14	19	15	19	15	19	15	19	15	19	15	19	15	19	15	19	—	—
8	7,7	8,5	19	15	19	15	20	16	20	16	20	16	20	16	20	16	20	16	20	16	20	—	—
10	9,3	10,1	21	17	21	17	23	19	23	19	23	19	23	19	23	19	23	19	23	19	23	—	—
12,5	12,3	13,5	24	21	24	22	26	22	26	22	26	22	26	22	26	22	26	22	26	22	26	—	—
16	15,5	16,7	27	25	27	25	29	25	29	25	29	25	29	25	29	25	29	25	29	25	29	—	30
19	18,6	19,8	31	28	31	29	33	29	33	29	33	29	33	29	33	29	33	29	33	29	33	—	36
25	25,0	26,4	40	36	40	38	41	38	41	39	41	39	41	39	41	39	41	39	41	39	41	—	45
31,5	31,4	33,0	53	45	53	45	56	49	53	49	54	49	54	49	54	49	54	49	54	49	54	—	52
38	37,7	39,3	59	56	59	56	59	56	59	56	59	56	59	56	59	56	59	56	59	56	59	—	—
51	50,4	52,0	72	69	72	69	73	70	72	70	73	70	73	70	73	70	73	70	73	70	73	—	—
63	63,1	65,1	84	—	84	—	85	—	85	—	90	—	90	—	90	—	90	—	90	—	90	—	—
76	74,6	77,8	100	—	100	—	100	—	100	—	—	—	—	—	—	—	—	—	—	—	—	—	—
102	100,0	103,2	130	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—

6.2 Cover thickness

When measured in accordance with ISO 4671, the outer cover thickness of hoses shall conform to the values given in [Table 5](#). Standard types may be produced with either thick or thin covers, the tolerance limits for thin-cover standard types being the same as the tolerance limits for compact types.

Table 5 — Cover thickness

Nominal size	Cover thickness mm					
	Standard (thick cover)		Standard (thin cover)		Compact	
	min.	max.	min.	max.	min.	max.
5	1,5	3,2	0,8	1,5	0,8	1,5
6,3	1,5	3,2	0,8	1,5	0,8	1,5
8	1,5	3,2	0,8	1,5	0,8	1,5
10	1,5	3,2	0,8	1,5	0,8	1,5
12,5	1,5	3,2	0,8	1,5	0,8	1,5
16	1,5	3,2	0,8	1,5	0,8	1,5
19	1,5	3,2	0,8	1,5	0,8	1,5
25	1,5	4,6	1,0	2,0	1,0	2,0
31,5	1,8	4,6	1,0	2,0	1,0	2,0
38	1,8	4,6	1,3	2,5	1,3	2,5
51	1,8	4,6	1,3	2,5	1,3	2,5
63	1,8	5,0	—	—	—	—
76	1,8	5,0	—	—	—	—
102	1,8	5,0	—	—	—	—

6.3 Concentricity

When measured in accordance with ISO 4671, the concentricity of hoses shall conform to the values given in [Table 6](#).

Table 6 — Concentricity of hoses

Nominal size	Maximum variation in wall thickness	
	between internal diameter and outside diameter	between internal diameter and reinforcement diameter
	mm	mm
5 and 6,3	0,8	0,5
Over 6,3 and up to and including 19	1,0	0,7
Over 19 and up to and including 63	1,3	0,9
Over 63	1,5	1,1

7 Physical properties

7.1 Fluid resistance of rubber compounds

7.1.1 Test pieces

Fluid resistance tests shall be carried out on moulded sheets of lining and cover compound having a minimum thickness 2 mm and a cure state equivalent to that of the hose.

7.1.2 Oil resistance

For all grades, when tested in accordance with ISO 1817 by immersion in IRM 903 oil for 168 h at a temperature of 100 °C, the percentage change in volume ΔV of the lining shall be between 0 % and + 25 % for braid-construction and textile-reinforced hoses and between 0 % and + 60 % for spiral-wire-reinforced hoses.

For all grades, when tested in accordance with ISO 1817 by immersion in IRM 903 oil for 168 h at a temperature of 70 °C, the percentage change in volume ΔV of the cover shall be between 0 % and + 100 %.

7.2 Performance requirements

7.2.1 Hydrostatic requirements

When determined in accordance with ISO 1402, the maximum working pressure, the proof pressure and the minimum burst pressure of hoses and hose assemblies shall conform to the values given in [Table 7](#).

Table 7 — Maximum working pressure, proof pressure and minimum burst pressure

Class	Maximum working pressure		Proof pressure		Minimum burst pressure	
	MPa	bar	MPa	bar	MPa	bar
35	3,5	35	7	70	14	140
70	7	70	14	140	28	280
140	14	140	28	280	56	560
210	21	210	42	420	84	840
250	25	250	50	500	100	1 000
280	28	280	56	560	112	1 120
350	35	350	70	700	140	1 400
420	42	420	84	840	168	1 680
490	49	490	98	980	196	1 960
560	56	560	112	1 120	224	2 240

7.2.2 Change in length

When determined in accordance with ISO 1402, the change in length of hoses at the maximum working pressure shall not exceed + 2 % or – 4 %.

7.2.3 Minimum bend radius

When determined in accordance with ISO 10619-1, the minimum bend radius shall conform to the values given in [Table 8](#).

When bent to the minimum bend radius given in [Table 8](#) and measured on the inside of the bend, the flatness shall not exceed 10 % of the original outside diameter.

7.2.4 Resistance to impulse

7.2.4.1 The resistance to impulse shall be determined in accordance with ISO 6803. The test fluid temperature shall be 100 °C for grades A and B and 120 °C for grades C and D.

7.2.4.2 For grade A, when tested at an impulse pressure equal to 133 % of the maximum working pressure, the hose shall withstand a minimum of 200 000 impulse cycles.

For grade B, when tested at an impulse pressure equal to 133 % of the maximum working pressure, the hose shall withstand a minimum of 500 000 impulse cycles.

For grade C, when tested at an impulse pressure equal to 133 % of the maximum working pressure (classes 35 to 280) or 120 % of the maximum working pressure (classes 350, 420, 490 and 560), the hose shall withstand a minimum of 500 000 impulse cycles.

For grade D, when tested at an impulse pressure equal to 133 % of the maximum working pressure, the hose shall withstand a minimum of 1 000 000 impulse cycles.

7.2.4.3 There shall be no leakage or other malfunction before reaching the specified number of cycles.

7.2.4.4 This test shall be considered a destructive test and the test piece shall be destroyed after the test.

7.2.5 Leakage of hose assemblies

When tested in accordance with ISO 1402, there shall be no leakage or evidence of failure. This test shall be considered a destructive test and the test piece shall be destroyed after the test.

7.2.6 Cold flexibility

When tested in accordance with method B of ISO 10619-2:2011 at a temperature of – 40 °C, there shall be no cracking of the lining or cover. The test piece shall not leak or crack when subjected to a proof pressure test in accordance with ISO 1402 after regaining ambient temperature.

7.2.7 Adhesion between components

When tested in accordance with ISO 8033, the adhesion between lining and reinforcement, and between cover and reinforcement shall not be less than 2,5 kN/m.

Test pieces shall be type 5 for lining and reinforcement and type 2, 6 or 8 for cover and reinforcement as described in Table 1 of ISO 8033:2006.

7.2.8 Vacuum resistance

When tested in accordance with ISO 7233, hoses and hose assemblies shall conform to the values given in [Table 9](#). This requirement is only applicable to classes 35, 70, 140 and 210.

Table 8 — Minimum bend radius

Nominal size	Minimum bend radius mm																				
	Class 35		Class 70		Class 140		Class 210		Class 250		Class 280		Class 350		Class 420		Class 490		Class 560		
	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	Stan- dard	Com- pact	
5	90	60	90	60	90	60	90	60	90	75	90	75	90	75	90	75	90	75	90	—	—
6,3	100	75	100	75	100	75	100	75	100	75	100	75	100	75	100	75	100	75	100	—	—
8	115	85	115	85	115	85	115	85	115	85	115	85	115	85	115	85	115	85	115	—	—
10	130	90	130	90	130	90	130	90	130	90	130	90	130	90	130	90	130	90	130	—	—
12,5	180	130	180	130	180	130	180	130	180	130	180	130	180	130	180	130	180	130	180	—	—
16	200	150	200	150	200	170	200	170	200	200	170	200	200	170	200	200	170	200	200	250	250
19	240	180	240	180	240	200	240	200	240	240	200	240	240	200	240	240	200	240	240	280	260
25	300	230	300	230	300	250	300	250	300	300	250	300	300	250	300	300	250	300	300	350	330
31,5	420	280	420	280	420	420	420	420	420	420	420	420	420	420	420	420	420	420	420	450	460
38	500	500	500	500	500	500	500	500	500	500	500	500	500	500	500	500	500	500	500	—	—
51	630	630	630	630	630	630	630	630	630	630	630	630	630	630	630	630	630	630	630	650	—
63	760	—	760	—	760	—	760	—	760	—	760	—	760	—	760	—	760	—	760	—	—
76	840	—	840	—	840	—	840	—	840	—	840	—	840	—	840	—	840	—	840	—	—
102	1 000	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—

Table 9 — Degree of vacuum

Nominal size	Negative gauge pressure (classes 35, 70, 140 and 210 only)	
	max.	
	kPa	bar
5 to 25	– 80	– 0,8
31,5 and over	– 60	– 0,6

7.2.9 Ozone resistance

When tested in accordance with method 1 or 2 of ISO 7326:2006, no cracking or deterioration of the cover shall be visible under $\times 2$ magnification.

8 Frequency of testing

Type testing and routine testing shall be carried out as specified in [Annex A](#).

Type tests are those tests required to confirm that a particular hose design, manufactured by a particular method, meets all the requirements of this International Standard. The tests shall be repeated at a maximum of five-year intervals, or whenever a change in the method of manufacture or materials used occurs. They shall be performed on all sizes, and on all classes and types except those of the same size and construction.

Routine tests are tests required to be carried out on each length of finished hose prior to dispatch.

Production acceptance tests are tests, specified in [Annex B](#), which should preferably be carried out to control the quality of manufacture. The frequencies specified in [Annex B](#) are given as a guide only.

9 Marking

9.1 Hoses

Hoses meeting the requirements of this International Standard shall be marked at least once every 760 mm with at least the following information:

- the manufacturer's name or identification, e.g. XXX;
- the number of this International Standard, i.e. ISO 18752;
- the type, e.g. AS¹⁾;
- the nominal size, e.g. 16;
- the maximum working pressure, in megapascals and in bars, or in ether, with the units indicated, e.g. 28 MPa (280 bar);
- the quarter and last two digits of the year of manufacture, e.g. 3Q13.

EXAMPLE XXX/ISO 18752/AS/16/28 MPa (280 bar)/3Q13

9.2 Hose assemblies

Hose assemblies using hose in accordance with this International Standard shall be manufactured and marked in accordance with ISO 17165-1.

1) If the thin-cover variant is concerned, add "T", e.g. AST.

10 Recommendations for packaging and storage

These are given in ISO 8331.

11 Test report

When requested by the purchaser, the manufacturer or supplier shall supply a test report with each length or batch of hoses supplied to the purchaser.

Annex A (normative)

Type tests and routine tests

[Table A.1](#) gives the tests to be carried out for type testing and routine testing as defined in [Clause 8](#).

Table A.1

Property	Type testing	Routine testing
Compound tests		
Oil resistance test for cover	X	N/A
Oil resistance test for lining	X	N/A
Hose tests		
Visual examination (inside and outside)	X	X
Measurement of inside diameter	X	X
Measurement of outside diameter	X	X
Measurement of outer cover thickness	X	X
Measurement of concentricity	X	X
Minimum bend radius test	X	N/A
Proof test	X	X
Burst test	X	N/A
Change in length test	X	N/A
Impulse test	X	N/A
Leakage test	X	N/A
Cold bend test	X	N/A
Adhesion test	X	N/A
Vacuum test	X	N/A
Ozone resistance test	X	N/A
NOTE X = Test to be carried out; N/A = Not applicable.		

Annex B (informative)

Production acceptance tests

[Table B.1](#) gives the suggested frequency for production tests (see [Clause 8](#)), to be carried out per batch or per 10 batches as indicated in the table. A batch is defined as 3 000 m of hose.

Table B.1 — Recommended test frequency

Property	Production test	
	Per batch	Per 10 batches
Compound tests		
Oil resistance test for cover	N/A	N/A
Oil resistance test for lining	N/A	X
Hose tests		
Visual examination (inside and outside)	X	X
Measurement of inside diameter	X	X
Measurement of outside diameter	X	X
Measurement of outer cover thickness	X	X
Measurement of concentricity	X	X
Minimum bend radius test	N/A	N/A
Proof test	X	X
Burst test	X	X
Change in length test	X	X
Impulse test	N/A	N/A
Leakage test	X	X
Cold bend test	N/A	N/A
Adhesion	X	X
Vacuum test	N/A	N/A
Ozone resistance test	N/A	N/A
NOTE X = Test to be carried out; N/A = Not applicable.		

Annex C (informative)

Recommendations for tolerances on lengths of hose assemblies

The tolerances on the lengths of hose assemblies should conform to ISO 17165-1:2007, Table 6.

Annex D (informative)

Information to be provided by hose manufacturer

The following information should be provided by the hose manufacturer on hoses supplied to a purchaser.

- a) manufacturer's name;
- b) hose designation;
- c) size (inside diameter);
- d) maximum working pressure;
- e) type (including information on cover variant);
- f) minimum inside diameter;
- g) maximum inside diameter;
- h) minimum outside diameter of reinforcement;
- i) maximum outside diameter of reinforcement;
- j) minimum outside diameter;
- k) maximum outside diameter;
- l) reinforcement material;
- m) hose construction;
- n) minimum bend radius.

Bibliography

- [1] ISO 1436, *Rubber hoses and hose assemblies — Wire-braid-reinforced hydraulic types for oil-based or water-based fluids — Specification*
- [2] ISO 3862, *Rubber hoses and hose assemblies — Rubber-covered spiral-wire-reinforced hydraulic types for oil-based or water-based fluids — Specification*
- [3] ISO 4079, *Rubber hoses and hose assemblies — Textile-reinforced hydraulic types for oil-based or water-based fluids — Specification*
- [4] ISO 4397, *Fluid power connectors and associated components — Nominal outside diameters of tubes and nominal hose sizes*
- [5] ISO 6743-4, *Lubricants, industrial oils and related products (class L) — Classification — Part 4: Family H (Hydraulic systems)*
- [6] ISO 11237, *Rubber hoses and hose assemblies — Compact wire-braid-reinforced hydraulic types for oil-based or water-based fluids — Specification*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™