

BS ISO 19043:2015



BSI Standards Publication

Natural rubber latex concentrate — Determination of total phosphate content by spectrophotometric method

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 19043:2015.

The UK participation in its preparation was entrusted to Technical Committee PRI/23, Test methods for rubber and non-black compounding ingredients.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.

Published by BSI Standards Limited 2015

ISBN 978 0 580 84998 5

ICS 83.040.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
19043

First edition
2015-09-01

**Natural rubber latex concentrate —
Determination of total phosphate
content by spectrophotometric method**

*Concentré de latex de caoutchouc naturel — Détermination de la
teneur totale en phosphate par méthode spectrophotométrique*



Reference number
ISO 19043:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Principle	1
4	Apparatus	1
5	Reagents	1
6	Procedure	2
6.1	General.....	2
6.2	Determination of total solids content.....	2
6.3	Preparation of standard phosphate solutions.....	2
6.4	Determination of phosphate content.....	2
7	Expression of results	3
8	Precision data	3
9	Test report	3
Annex A (informative) Precision data		4
Bibliography		6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

Natural rubber latex concentrate — Determination of total phosphate content by spectrophotometric method

1 Scope

This International Standard specifies a method for the determination of total phosphate content of natural rubber latex concentrate. This method is not necessarily suitable for latex from natural sources other than the *Hevea brasiliensis*.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 124, *Latex, rubber — Determination of total solids content*

ISO 648, *Laboratory glassware — Single-volume pipettes*

3 Principle

Approximately 20 g of concentrated latex, of which the total solids content has been determined, is coagulated with hydrochloric acid.

The coagulated latex is removed and the serum filtered through filter paper.

The residual phosphate present in a known volume of the serum is determined by measuring absorbance with a spectrophotometer at wavelength 470 nm.

4 Apparatus

4.1 Balance, accurate to 0,1 mg.

4.2 Volumetric pipettes, of capacity 10 cm³ and 25 cm³, complying with the requirements of ISO 648, class A.

5 Reagents

Use reagents of recognized analytical grade and deionized water or water of equivalent purity.

5.1 Hydrochloric acid 37 %.

5.2 Hydrochloric acid 1:24.

Mix 40 ml of 37 % hydrochloric acid (5.1) with deionized water and make up to 1 000 ml.

5.3 Vanadate molybdate.

a) Dissolve 25 g ammonium molybdate in 300 ml deionized water.

- b) Dissolve 1,25 g ammonium metavanadate in 300 ml deionized water. Heat to dissolve completely. Cool to room temperature before mixing with 330 ml of 37 % hydrochloric acid and leave to cool.
- c) Mix solutions [5.3 a\)](#) and [5.3 b\)](#) and make up to 1 000 ml with deionized water.

5.4 Potassium dihydrogen phosphate (stock solution).

Dissolve 2,196 8 g potassium dihydrogen phosphate and make up to 1 000 ml with deionized water. The phosphorous concentration of this solution will be 500 ppm.

6 Procedure

6.1 General

Carry out the procedure in duplicate, using separate test portions obtained from the same homogenized sample.

The difference between two readings shall not exceed 30 mg/kg.

6.2 Determination of total solids content

Determine the total solids content of the concentrated latex in accordance with ISO 124.

6.3 Preparation of standard phosphate solutions

6.3.1 From the 500 ppm stock solution ([5.4](#)), pipette 0 ml, 1 ml, 2 ml, 3 ml, 4 ml, 5 ml, 10 ml then dilute with deionized water and make up to 50 ml to make the first dilution of concentrations 0 ppm, 10 ppm, 20 ppm, 30 ppm, 40 ppm, 50 ppm, 100 ppm, respectively.

6.3.2 Pipette 10 ml of each solution ([6.3.1](#)) into 50 ml volumetric flasks. Into each flask add 10 ml vanadate molybdate ([5.3](#)). Then make up the volume to 50 ml with hydrochloric acid solution ([5.2](#)). The final concentrations will be 0 ppm, 2 ppm, 4 ppm, 6 ppm, 8 ppm, 10 ppm and 20 ppm.

6.3.3 Leave the solutions ([6.3.2](#)) for 20 min and filter the total 50 ml solutions through an 8 µm pore size filter paper¹⁾ and measure absorbance with a spectrophotometer at wavelength 470 nm. Measure in duplicate with different portion and take the average values.

Use 0 ppm solution as a blank.

Prepare a calibration curve by plotting the concentration of potassium dihydrogen phosphate at 0 ppm, 2 ppm, 4 ppm, 6 ppm, 8 ppm, 10 ppm and 20 ppm ([6.3.2](#)) against the absorbance after measuring absorbance with a spectrophotometer at wavelength 470 nm. Determine the slope from the calibration curve (S).

6.4 Determination of phosphate content

Weigh about 20 g (*W*) of homogenous concentrated latex to the nearest 0,1 mg in a 100 ml beaker. Coagulate with 25 ml hydrochloric acid solution ([5.2](#)) and warm in water bath without stirring at 70 °C for 5 min to coagulate the latex completely.

Squeeze coagulum with a glass rod to obtain the serum as much as possible and filter the serum through the 8 µm pore size filter paper.

1) Whatman No.40 is an example of a suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

Pipette 10 cm³ of the filtered serum (V_{pipette}) into 50 ml volumetric flask and add 10 cm³ of vanadate molybdate (5.2), then dilute with HCl solution (5.1) to 50 cm³.

Wait for 20 min. Filter the solution through a filter paper.

Measure absorbance with a spectrophotometer at wavelength 470 nm against the blank (without latex).

7 Expression of results

The phosphate content, P , expressed in mg/kg, is calculated using the following equation:

$$P = \frac{0,05 \times Abs \times V_{\text{total}} \times 3,066\ 1 \times 1\ 000}{S \times A \times V_{\text{pipette}}}$$

where

Abs is the absorbance with spectrophotometer at wavelength 470 nm;

S is the calibration curve slope versus the phosphate concentration;

V_{pipette} is the volume of serum pipetted from total serum to volumetric flask;

3,066 1 is the constant of conversion of P to PO₄³⁻.

with:

$V_{\text{total}} = 25 + (W - A)$ assuming that the density of serum = 1 g/ml;

$$A = \frac{W \times TSC}{100}$$

8 Precision data

See [Annex A](#).

9 Test report

The test report shall include the following:

- a) a reference to this International Standard;
- b) all details necessary for the identification of the sample;
- c) all details necessary for the complete identification of the product tested;
- d) the results and the units in which they have been expressed;
- e) the date of the test;
- f) any unusual features noted during the determination;
- g) any operations not included in this International Standard to which reference is made, as well as any incident which might have affected the results.

Annex A (informative)

Precision data

A.1 The precision of the test method was determined in accordance with ISO/TR 9272[1]. Refer to this document for terminology and other statistical details.

A.2 The precision data are given in [Table A.1](#). The precision parameters should not be used for acceptance or rejection of any group of materials without documentation that the parameters are applicable to those particular materials and specific test protocols of the test method. The precision is expressed on the basis of a 95 % confidence level for the values established for repeatability r and reproducibility R .

A.3 The results contained in [Table A.1](#) are average values and give an estimate of the precision of this test method. The results were obtained from an interlaboratory test programme (ITP) carried out in 2014 where six laboratories took part in performing duplicate analyses on three samples which were low, medium and high concentration of phosphate content.

A.4 A Type 1 precision was evaluated based on the method of sampling used for the ITP.

A.5 Repeatability: the repeatability r (in measurement units) of the test method has been established as the appropriate value tabulated in [Table A.1](#). Two single test results, obtained in the same laboratory under normal test method procedures that differ by more than the tabulated r (for any given level) should be considered to have come from different, or non-identical, sample populations.

A.6 Reproducibility: the reproducibility R (in measurement units) of the test method has been established as the appropriate value tabulated in [Table A.1](#). Two single test results, obtained in the same laboratory under normal test method procedures that differ by more than the tabulated R (for any given level) should be considered to have come from different, or non-identical, sample populations.

A.7 Bias: in test method terminology, bias is the difference between an average test value and the reference (or true) test property value. Reference values do not exist for this test method since the value (of the test property) is exclusively defined by the test method. Bias cannot therefore be determined for this particular method.

Table A.1 — Precision for phosphate content in latex

Material	Mean	Within laboratory			Between laboratories			Number of laboratories
		s_r	r	(r)	s_R	R	(R)	
Low content	162	21	58	35,98	28	78	48,31	6
Medium content	235	24	67	28,56	44	125	53,32	6
High content	298	65	65	22,83	53	152	51,14	6

s_r is the within-laboratory standard deviation (in measurement units);
 r is the repeatability (in measurement units);
 (r) is the relative repeatability;
 s_R is the between-laboratory standard deviation (for total between-laboratory variation in measurement units);
 R is the reproducibility (in measurement units);
 (R) is the relative reproducibility.

Bibliography

- [1] ISO/TR 9272, *Rubber and rubber products — Determination of precision for test method standards*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™