

BS ISO 19861:2015



BSI Standards Publication

Buildings and civil engineering works — Sealants — Determination of curing behaviour

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 19861:2015.

The UK participation in its preparation was entrusted to Technical Committee B/547, Sealants for building and construction.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 88088 9

ICS 91.100.50

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
19861

First edition
2015-11-01

**Buildings and civil engineering
works — Sealants — Determination of
curing behaviour**

*Bâtiments et ouvrages de génie civil — Mastics — Détermination du
comportement de durcissement*



Reference number
ISO 19861:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Test materials	1
5.1 One part sealants	1
5.2 Multi component sealants.....	1
6 Preparation of test specimens	2
6.1 General.....	2
6.2 One part sealants	2
6.3 Multi component sealants.....	2
7 Conditioning of test specimens	2
8 Test procedure	2
8.1 One part sealants	2
8.2 Multi component sealants.....	2
9 Expression of results	3
9.1 One part sealants	3
9.2 Multi component sealants.....	3
10 Test report	3

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 59, *Buildings and civil engineering works*, Subcommittee SC 8, *Sealants*.

Buildings and civil engineering works — Sealants — Determination of curing behaviour

1 Scope

This International Standard specifies a method for the determination of the curing behaviour of sealants used in joints in building construction.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 6927, *Buildings and civil engineering works — Sealants — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6927 apply.

4 Principle

Test specimens are prepared such that the sealant to be will be subjected to a curing environment. A one part sealant has the time recorded when its cure in depth reaches 2 mm. A multi component sealant has the time recorded to reach 33 % of its ultimate hardness.

5 Test materials

5.1 One part sealants

5.1.1 Plastic or metal cylindrical cups, 35 mm - 75 mm internal diameter; 35 mm - 50 mm deep, wall thickness 1 mm - 3 mm.

5.1.2 Measuring device, scaled to 0,5 mm.

5.2 Multi component sealants

5.2.1 Draw down device, capable of producing a 6 mm minimum constant thickness of the sealant.

5.2.2 Indentation hardness measurement device, capable of measurements on the A scale.

Extremely soft sealants that measure less than 5 on the A scale should be measured on the 00 scale.

6 Preparation of test specimens

6.1 General

The sealant and test materials shall be brought to (23 ± 2) °C over 24 h.

6.2 One part sealants

6.2.1 Fifteen test specimens shall be prepared. For each specimen the cup shall be filled with the sealant and tooled flat.

6.2.2 The following precautions shall be taken:

- a) the formation of air bubbles shall be avoided;
- b) the sealant shall be pressed on the inner surfaces of the substrates;
- c) the sealant surface shall be tooled so that it is flush with the top of the open cup.

6.3 Multi component sealants

6.3.1 A tooled slab of sealant 6 mm minimum thick, 50 mm wide and 300 mm long on a flat non-absorbing surface is required.

6.3.2 The instructions of the sealant manufacturer concerning the mixing procedure for multi-component sealants shall be followed.

7 Conditioning of test specimens

The test specimens shall be extruded, tooled and cured at a temperature of (23 ± 2) °C and relative humidity (RH) of (50 ± 10) %.

8 Test procedure

8.1 One part sealants

The cured skin on top of three cups shall be removed at the following intervals, 16 h, 24 h, 48 h, 72 h, 96 h and 168 h. The cured skin is wiped of uncured sealant. The thickness of each specimen shall be measured and recorded.

8.2 Multi component sealants

The measurement of hardness is performed according to ISO 868. The sealant shall be extruded onto a flat surface and tooled to 6 mm minimum thickness. The hardness of the air side extruded cured slab of sealant shall be measured three times at the following intervals: Once prior to and twice after the manufacturer recommended cure time for 33 % ultimate hardness at (23 ± 2) °C and (50 ± 10) % RH (hardness at 28 days cure). One measurement shall be made 4 h to 8 h prior to the predicted time, one measurement shall be made at the predicted time, and two final measurements shall be taken, rather evenly spaced, over the subsequent 24 h. The test may cease when two subsequent hardness readings are within 3 % of final hardness (generally published on manufacturer's literature).

9 Expression of results

9.1 One part sealants

The raw data and the average of thickness at each time shall be plotted and the time to achieve 2 mm of cure in depth shall be determined through linear interpolation of the two closest data points.

9.2 Multi component sealants

The raw data and the average hardness of the extruded cured slab of sealant at each time shall be plotted. The time to reach 33 % of the sealants hardness at 28 days shall be determined through linear interpolation of the two closest data points.

The lab is not discouraged from taking additional data points to draw a more accurate curve in lieu of the linear interpolations suggested in this method. Additional data taken should be included in the report. Non-linear cure materials may not be able to be tested 4 h to 8 h before the predicted time of 33 % hardness due to their fast cure and should be tested appropriately.

10 Test report

The test report shall include the following information:

- a) the name of the test laboratory;
- b) the date of the test and test number;
- c) the reference to this International Standard, i.e. ISO 19861;
- d) the name of the sealant, the type (chemical family), and colour;
- e) the batch of sealant from which the test specimens were produced;
- f) the type of sealant one part or multi component;
- g) the cure in depth at 16 h, 24 h, 48 h, 72 h, 96 h and 168 h for one part sealants;
- h) the time to reach 2 mm of cure in depth, for one part sealants;
- i) the hardness at the intervals chosen in [8.2](#) for multi component sealants;
- j) the time to reach 33 %, of the ultimate hardness (hardness at 28 days cure) and the scale of hardness used for multicomponent sealants;
- k) any deviations from this International Standard.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™