



BSI Standards Publication

**Aluminium oxide primarily
used for the production of
aluminium — Determination
of alpha alumina content —
Method using X-ray diffraction
net peak areas**

National foreword

This British Standard is the UK implementation of ISO 19950:2015.

The UK participation in its preparation was entrusted to Technical Committee CII/24, Raw materials for the aluminium industry.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 88353 8

ICS 71.100.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

**Aluminium oxide primarily used
for the production of aluminium —
Determination of alpha alumina
content — Method using X-ray
diffraction net peak areas**

*Oxyde d'aluminium principalement utilisé pour la production
d'aluminium — Dosage de la teneur en alumine alpha — Méthode
utilisant la diffraction à rayons X des surfaces de pic net*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	1
5 Apparatus	2
6 Procedure	2
7 Calculation and expression of results	4
8 Precision	5
9 Test report	6
Annex A (informative) Results of interlaboratory test program	7
Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 226, *Materials for the production primary aluminium*.

Introduction

This International Standard is based on an Australian Standard AS 2879.3-2010, *Alumina — Determination of alpha alumina content by X-ray diffraction*.

Aluminium oxide primarily used for the production of aluminium — Determination of alpha alumina content — Method using X-ray diffraction net peak areas

1 Scope

This International Standard sets out an X-ray diffraction method for the determination of the alpha alumina content of smelter grade alumina. The method is applicable to smelter grade alumina containing alpha phase at levels up to 50 %. The percentage by mass of alpha alumina is determined on an “as received” basis.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

AS 4538.2, *Guide to the sampling of alumina — Preparation of samples*

3 Principle

The integrated peak areas of the (012) and (116) lattice plane reflections (nominal d spacings 0,348 nm and 0,160 nm) are measured for the test sample and a 100 % alpha alumina calibration standard. The ratio between the net peak area intensities for the test sample and for the standard is determined and the alpha alumina content calculated from this ratio.

4 Reagents

4.1 General

During the analysis, only reagents of recognized analytical reagent grade and only distilled water, or water of equivalent purity, shall be used.

4.2 100 % alpha alumina calibration standard, prepared in accordance with either [4.2.1](#) or [4.2.2](#).

4.2.1 A commercially available, certified 100 % alpha alumina calibration standard suitable for diffraction analysis.

4.2.2 An in-house produced 100 % alumina calibration standard prepared in accordance with [6.1](#) and using the following reagents.

4.2.2.1 Hydrochloric acid (100 g/l).

4.2.2.2 Smelter grade alumina.

NOTE The type of alumina used as the base for the 100 % alpha alumina calibration standard can affect the peak areas measured. Grades of the base alumina other than smelter grade can yield different peak area intensities.

5 Apparatus

5.1 X-ray diffractometer.

5.2 Hydraulic press, suitable for preparing mounts.

5.3 Rotary divider or riffle.

5.4 Grinding mill, capable of grinding alumina to a particle size of 90 % less than 45 μm .

5.5 In-house alpha aluminium apparatus, prepared as follows (see [5.5.1](#) to [5.5.5](#)). Necessary only if alpha aluminium standard ([4.2.2](#)) is to be prepared in accordance with [6.1](#).

5.5.1 Platinum dish and lid.

5.5.2 Coarse filter paper.

5.5.3 Drying oven, capable of being controlled at (105 ± 5) °C.

5.5.4 Magnetic stirrer.

5.5.5 Electric furnace, capable of being controlled at $(1\ 300 \pm 50)$ °C. Necessary only if the 100 % alpha alumina calibration standard ([4.2.2](#)) is to be prepared in-house in accordance with [6.1](#).

6 Procedure

6.1 Preparation of 100 % alpha alumina calibration standard

The calibration standard shall be prepared as follows.

- a) Weigh out approximately 100 g of smelter grade alumina ([4.2.2.2](#)).
- b) Transfer to a 600 ml beaker and add 250 ml of hydrochloric acid ([4.2.2.1](#)). Stir the solution at ambient temperature for 3 h using the magnetic stirrer ([5.5.4](#)).
- c) Filter the alumina slurry through a coarse filter paper ([5.5.2](#)). Wash the paper and the residue thoroughly three or four times with water to remove entrained hydrochloric acid.

NOTE 1 This washing procedure reduces the soda and other impurities in the alumina. Soda will react to form a beta alumina phase on calcining which will reduce the alpha phase content.

- d) Dry the alumina residue in the drying oven ([5.5.3](#)) at (105 ± 5) °C for 2 h. Transfer the dried alumina residue to a platinum dish ([5.5.1](#)). Cover the dish with the platinum lid.
- e) Transfer the dish into the electric furnace ([5.5.5](#)) at 300 °C. Raise the furnace temperature over a period of at least one hour to $(1\ 300 \pm 50)$ °C. Maintain at $(1\ 300 \pm 50)$ °C for 48 h.

NOTE 2 Raising the temperature gradually will prevent the ejection of material from the dish.

- f) Remove the dish from the furnace and allow to cool to room temperature. Transfer the 100 % alpha alumina calibration standard to a sealed container.

6.2 Preparation of the test portion and calibration standard

The test portion and calibration standard shall be prepared as follows.

- a) Prepare a portion of the test sample of a suitable mass for the grinding mill (5.4) by using the riffle or rotary divider (5.3) in accordance with AS 4538.2. Take particular care to avoid loss of fine particles through dusting.
- b) Grind the test portion and if necessary the calibration standard, to a particle size of 90 % less than 45 µm in the grinding mill (5.4).
- c) Prepare duplicate mounts of the test portion and the calibration standard for XRD analysis (see Note 2). A hydraulic press (5.2) may be used for this.
- d) Visually inspect each mount for imperfections such as cracks or areas with an uneven surface finish and discard if any imperfections can be seen. In this case prepare a new mount [(see 6.2 c)].

NOTE 1 Commercially available, certified 100 % alpha alumina calibration standards typically have particle sizes less than 45 µm however in-house produced calibration standards will typically need to be ground.

NOTE 2 Instructive information on sample preparation can be found in the References [1] and [2].

6.3 Measurement

The measurement procedure shall be as follows.

- a) Set the X-ray diffractometer (5.1) conditions for the determination of alpha alumina phase (corundum) content.
- b) Typical diffractometer settings and 2 theta (2θ) angular scan settings are given in Table 1 and Table 2.
- c) Ensure that the scanning ranges and background positions are corrected for the actual 2 theta (2θ) diffractometer alignment.
- d) Measure the integrated peak intensity and individual 2θ background intensities to allow calculation of net peak area of the (012) and (116) reflections as per [Clause 7 a)], for each mount.
- e) Ensure a calibration standard (4.2) mount is measured at least at the beginning and end of each batch.

Table 1 — Typical diffractometer settings

Excitation radiation	Co Kα1	Cu Kα1
Tube voltage	40 kV	45 kV
Tube amperage	40 mA	40 mA
Measurement	Fixed area method	Fixed area method
Time per step	3 seconds	3 seconds
Step size	0,02°	0,02°
Background measurement time	6 seconds per peak	6 seconds per peak

Table 2 — Typical 2θ scan settings

hkl	d-spacing (Å)	Theoretical peak position (°2θ) ^a		Scanning range (°2θ)		Background (°2θ)	
		Cu Kα1	Co Kα1	Cu Kα1	Co Kα1	Cu Kα1	Co Kα1
012	3,48	25,58	29,79	25,2 to 26,0	29,3 to 30,2	24,9 to 26,4	28,9 to 30,7
116	1,60	57,50	67,91	57,0 to 58,1	67,3 to 68,6	56,7 to 58,4	66,9 to 68,9

^a The alpha Al₂O₃ (corundum) theoretical peak positions are from the ICDD file no 46-1212, year 2003 (see Reference [3]).

NOTE 1 The background 2θ angle positions are outside the scanning ranges used to determine the integrated peak area. This is to ensure that for the 100 % alpha alumina calibration sample measurement, the background positions are clear of the very large alpha alumina peak.

NOTE 2 Background intensities will be much higher for smelter grade aluminas than for 100 % alpha alumina calibration samples. This is due to the significant contribution to background from intermediate alumina phases in smelter grade aluminas.

7 Calculation and expression of results

The alpha alumina content of each test sample shall be calculated separately from each of the two peaks (012) and (116) separately, as below. They are then averaged.

a) Calculate the net integrated peak area, I_{net} for each test portion from Formula (1):

$$I_{net} = I_p - I_b \quad (1)$$

where

I_p is the integrated peak intensity, i.e the sum of the individual step measurements, in cps;

I_b is the integrated background intensity, in cps.

I_b is calculated using:

$$I_b = \left(\frac{2\theta_{diff}}{2\theta_{step}} + 1 \right) \times \left(\frac{I_{b1} + I_{b2}}{2} \right) \quad (2)$$

where

I_{b1} is the intensity at the low-angle background position b1, in cps;

I_{b2} is the intensity at the high-angle background position b2, in cps;

$2\theta_{diff}$ is the scanning range, the difference between the 2θ angle finish and start positions, in °;

$2\theta_{step}$ is the scanning step size, in °.

b) Calculate the average intensity for the 100 % alpha alumina calibration standard, $I_{net(100),av}$ from Formula (3):

$$I_{\text{net}(100),\text{av}} = \frac{\left(\sum_{i=1}^n I_{\text{net}} \right)}{n} \quad (3)$$

where

$I_{\text{net},100}$ net peak intensity in cps, for an individual calibration standard measurement, calculated as per Formula (1);

n number of measurements carried out on the calibration standards.

- c) Calculate the alpha content for each peak of each test portion, as a percentage by mass, from Formula (4):

$$\% \text{ alpha alumina} = \frac{I_{\text{net}}}{I_{\text{net}(100),\text{av}}} \times 100 \quad (4)$$

- d) Average the alpha content for both peaks (012) and (116) of each test portion and express to the nearest integer.

8 Precision

A test program to determine precision of the method was carried out in accordance with AS 2850[5] by one analyst from each of eight different laboratories. Results of the interlaboratory test program are shown in [Annex A](#). Four repetitions were carried out by each laboratory on each of four test samples of different refinery aluminas. The means, within-laboratory repeatability “ r ” and between-laboratory reproducibility “ R ” at the 95 % confidence level were calculated for the four samples. These are given in [Table 3](#).

Table 3 — Alpha alumina results from test program

Sample ID	Mean α alumina content, %	Repeatability r	Reproducibility R
S-123	2,9	0,8	1,4
S-124	24,5	0,8	2,9
S-125	1,5	0,8	1,1
S-126	9,2	1,2	1,8

From this data, the overall precision expected of this method at the 95 % confidence level is given in [Table 4](#). Note that reproducibility “ R ” was shown to be a function of the alpha content of the sample.

Repeatability “ r ” was typically 0,8, but the “ r ” of 1,2 obtained for sample S-126 indicates a likely sample dependency for “ r ”. The S-126 sample was obtained by mixing two process streams (rotary calcined and flash calcined aluminas) from the same refinery. The other samples were from single process streams at other refineries.

Table 4 — Precision data for alpha alumina determination

Repeatability r	Typically 0,8
Reproducibility R	$R = 0,08 \alpha + 1,0$ Where “ α ” is % alpha alumina content of the sample

9 Test report

The test report shall contain the following information:

- a) identification of the sample;
- b) date on which sample was taken;
- c) date on which the test was carried out;
- d) alpha alumina content of the test sample, expressed as a percentage by mass of the sample;
- e) the number of acceptable results from which the mean value has been calculated;
- f) any unusual observations made during the course of the test which may have had an effect on the result;
- g) a reference to this International Standard, i.e. ISO 19950.

Annex A (informative)

Results of interlaboratory test program

A test program using this method was conducted according to AS 2850 on four different refinery aluminas by participants from eight Australian and international alumina refineries and research and development centres. Different 100 % calibration standards and X-ray tube types were also used. Results were provided in quadruplicate by each laboratory and are shown below. The within-laboratory means and standard deviations are also given.

Table A.1 — Results of alpha alumina method test program

percent alpha alumina

Sample ID	Lab	1	2	3	4	5	6	7	8
	100 % Calibration standard	As per AS 2879.3	As per AS 2879.3	As per AS 2879.3	As per AS 2879.3	Baicolox UHP Al2O3	As per AS 2879.3	NIST 676	NIST 676
Sample ID	X-ray tube used	Co	Cu	Cu	Not given	Not given	Co	Not given	Cu
S-123	1	2,88	2,94	2,21	2,82	2,69	4,26	2,90	2,69
	2	2,83	3,19	2,20	2,84	2,60	2,70	3,23	2,78
	3	2,84	2,81	2,14	2,84	2,77	3,99	3,11	2,86
	4	2,83	3,03	2,32	2,62	2,31	3,80	2,99	2,90
	Mean	2,84	2,99	2,22	2,78	2,59	3,69	3,06	2,81
	1SD	0,02	0,16	0,07	0,11	0,20	0,68	0,14	0,09
S-124	1	24,40	24,71	22,44	24,02	24,54	25,81	24,93	23,83
	2	24,22	25,27	22,36	24,37	24,45	25,65	24,92	24,18
	3	24,79	25,24	22,55	24,62	24,73	25,64	25,09	24,71
	4	24,64	25,09	22,34	24,45	24,69	26,69	24,99	24,24
	Mean	24,51	25,08	22,42	24,36	24,60	25,95	24,98	24,24
	1SD	0,25	0,26	0,10	0,25	0,13	0,50	0,08	0,36
S-125	1	1,22	1,78	1,02	1,17	1,27	2,29	1,22	1,24
	2	1,36	2,10	1,19	1,13	1,29	2,38	1,21	1,96
	3	1,40	1,84	1,09	1,08	1,33	1,94	1,34	1,47
	4	1,27	1,87	1,22	1,49	1,47	0,97	1,30	1,58
	Mean	1,31	1,90	1,13	1,21	1,34	1,90	1,27	1,56
	1SD	0,08	0,14	0,09	0,19	0,09	0,65	0,06	0,30
S-126	1	9,31	9,43	8,44	9,30	8,96	9,00	8,91	9,04
	2	9,24	8,60	8,38	9,29	8,94	11,64	8,79	9,46
	3	9,33	8,74	8,78	9,24	8,57	10,29	8,81	9,36
	4	9,23	8,89	8,34	9,66	9,28	10,07	8,96	9,33
	Mean	9,28	8,91	8,48	9,37	8,94	10,25	8,87	9,30
	1SD	0,05	0,36	0,20	0,19	0,29	1,08	0,08	0,18

Bibliography

- [1] KLUG H.P., & ALEXANDER L.E. *X-ray diffraction procedures for polycrystalline and amorphous materials*. Wiley, New York, Second Edition, 1974
- [2] BURKE V.E., JENKINS R., SMITH D.K. *A practical guide for preparation of specimens for X-ray fluorescence and X-ray diffraction analysis*. John Wiley and Sons, New York, 1998
- [3] International Centre for Diffraction Data, JCPDS-ICDD file no 46-1212, year 2003 version
- [4] AS 2879.3-2010, *Alumina — Determination of alpha alumina content by X-ray diffraction*
- [5] AS 2850, *Chemical analysis—Inter-laboratory test programs—For determining precision of analytical method(s)—Guide to the planning and conduct*
- [6] AS 4538.1, *Guide to the sampling of alumina — Sampling procedures*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™