

BS ISO 19960:2015



BSI Standards Publication

Cast steels and alloys with special physical properties

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 19960:2015. It supersedes BS ISO 19960:2005 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/111, Steel Castings and Forgings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 76506 3

ICS 77.140.80

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

BS ISO 19960:2015

ISO
19960

Second edition
2015-09-15

**Cast steels and alloys with special
physical properties**

Aciers et alliages moulés avec caractéristiques physiques particulières



Reference number
ISO 19960:2015(E)

© ISO 2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 General conditions for delivery	1
5 Chemical composition	1
6 Mechanical properties	1
7 Heat treatment	2
8 Welding	2
9 Verification of physical properties	2
10 Supplementary requirements	2
Annex A (informative) UNS cast grades similar to ISO cast grades	6
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 17, *Steel*, Subcommittee SC 11, *Steel castings*.

This second edition cancels and replaces the first edition (ISO 19960:2005), which has been technically revised with the following changes:

- [Tables 1, 2, 3, and 4](#), grade numbers added;
- Table 5, deleted;
- original [Annex A](#) deleted, new [Annex A](#) added.

Cast steels and alloys with special physical properties

1 Scope

This International Standard specifies cast steel and alloy grades with special physical properties. The cast steel and alloy grades covered by this International Standard are used in applications which require low linear thermal expansion, or low ferromagnetic responses, or low galling properties.

NOTE [Annex A](#) gives information on ISO grade designation and available UNS numbers which are similar to the ISO grade designations.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4990, *Steel castings — General technical delivery requirements*

ISO 11970, *Specification and approval of welding procedures for production welding of steel castings*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4990 and the following apply.

3.1

galling

damage or breaking of the surface by friction or abrasion

4 General conditions for delivery

Materials furnished according to this International Standard shall conform to the applicable requirements of ISO 4990 including the supplementary requirements that are indicated on the enquiry and purchase order.

5 Chemical composition

The cast steel and alloy grades shall conform to the requirements for chemical composition specified in [Table 1](#).

6 Mechanical properties

Cast steel and alloy grades shall conform to the mechanical property requirements given in [Table 2](#) up to the maximum ruling thickness. Verification of impact properties is not required except when indicated by the customer. Test blocks used to verify the mechanical properties shall not have a thickness exceeding 100 mm. For blocks taken from castings, the test bar location and the mechanical properties required shall be agreed between the manufacturer and purchaser.

For grades GX3NiCo32, GX3NiCo29-17, and G-NiCr13SnBiMo, no mechanical properties are specified.

7 Heat treatment

Castings shall be heat treated in accordance with the requirements of [Table 3](#).

8 Welding

Castings shall be welded in accordance with the procedures described in ISO 11970.

9 Verification of physical properties

When physical properties are specified, the method of measurement and acceptance requirements shall be the subject of an agreement between the manufacturer and purchaser. Typical values for some physical properties are given in [Table 4](#).

10 Supplementary requirements

A list of standardized supplementary requirements for use at the option of the purchaser is included in ISO 4990. The subclauses of ISO 4990 which are ordinarily considered suitable for use with this International Standard are given in [Annex A](#). Other supplementary requirements, whether or not in ISO 4990, may be used with this International Standard upon agreement by the manufacturer and purchaser.

Table 1 — Chemical composition, % (m/m)^d

Grade designation Name	Number	C	Si	Mn	P	S	Cr	Mo	Ni	N	Co	Others
GX12CrNi18-11 ^a	1.3955	0,15	1,00	2,0	0,045	0,030	16,5-18,5	0,75	10,0-12,0			
GX2CrNi18-13 ^a	1.3940	0,030	1,00	2,0	0,035	0,020	16,5-18,5	-	12,0-14,0	0,10-0,20		
GX2CrNiMoN18-14 ^a	1.3960	0,030	1,00	2,0	0,035	0,020	16,5-18,5	2,5-3,0	13,0-15,0	0,15-0,25		
GX2CrNi19-11 ^a	1.3939	0,030	1,5	2,0	0,035	0,020	18,0-20,0	1,0	10,0-12,0	0,10-0,20		
GX3CrNiMnSi17-9-8 ^a	1.3975	0,05	3,5-4,5	7,0-9,0	0,045	0,030	16,0-18,0	1,0	8,0-9,0	0,08-0,18		
GX4CrNiMnN22-12-5 ^a	1.3956	0,06	1,0	4,0-6,0	0,040	0,030	20,5-23,5	1,50-3,00	11,5-13,5	0,20-0,40		Nb: 0,10-0,30 V: 0,10-0,30
GX2CrNiMnMoNNb21-16-5-3 ^a	1.3967	0,030	1,0	4,0-6,0	0,025	0,010	20,0-21,5	3,0-3,5	15,0-17,0	0,20-0,35		Nb: 0,25
GX3NiCo32 ^b	1.3983	0,05	0,50	0,6	0,030	0,02	0,25	1,0	30,5-33,5		4,0-6,5	Al: 0,10
GX1NiCo29-17 ^b	1.3988	0,05	0,50	0,5	0,030	0,02	0,25	1,0	28,0-30,0		16,0-18,0	
GX3Ni36 ^b	1.3961	0,05	0,5	0,5	0,030	0,02	0,25	1,0	35,0-37,0			
GX5NiS36 ^b	1.3963	0,05	0,5	0,5	0,030	0,10-0,20	0,25	1,0	35,0-37,0			Fe: 2,0 Bi: 3,0-5,0 Sn: 3,0-5,0
G-NiCr13SnBiMoc	2.4712	0,05	0,5	1,5	0,030	0,030	11,0-14,0	2,0-3,5	balance			

^a Low ferromagnetic response grades with magnetic permeability, $\mu_r \leq 1,01$.

^b For low linear-expansion grades see [Table 4](#).

^c Low galling grade.

^d Single value indicates maximum.

Table 2 — Mechanical properties at room temperature

Grade designation		$R_{p0,2}$ min. MPa ^a	R_m N/mm ^{2a}	A min. %	KV min. J
Name	Number				
GX12CrNi18-11 ^b	1.3955	195	440 to 590	20	80
GX2CrNi18-13 ^b	1.3940	210	440 to 640	30	115
GX2CrNiMoN18-14 ^b	1.3960	240	490 to 690	30	80
GX2CrNi19-11 ^b	1.3939	180	≥440	30	
GX3CrNiMnSi17-9-8 ^b	1.3975	290	≥580	24	
GX4CrNiMnN22-12-5 ^b	1.3956	290	≥580	24	
GX2CrNiMnMoNNb21-16-5-3 ^b	1.3967	315	570 to 800	20	65
GX3Ni36 ^c	1.3961	275	≥395	28	
GX5NiS36 ^c	1.3963	275	≥395	25	

^a 1 MPa = 1 N/mm²
^b Low ferromagnetic response grades with magnetic permeability, $\mu_r \leq 1,01$.
^c For low linear-expansion grades, see [Table 4](#).

Table 3 — Heat treatment

Grade designation		Treatment
Name	Number	
GX12CrNi18-11 ^b	1.3955	Solution anneal 1 050 °C to 1 150 °C; quench
GX2CrNi18-13 ^b	1.3940	Solution anneal 1 050 °C to 1 150 °C; quench
GX2CrNiMoN18-14 ^b	1.3960	Solution anneal 1 050 °C to 1 150 °C; quench
GX2CrNi19-11 ^b	1.3939	Solution anneal 1 050 °C min; quench
GX3CrNiMnSi17-9-8 ^b	1.3975	Solution anneal 1 050 °C min; quench
GX4CrNiMnN22-12-5 ^b	1.3956	Solution anneal 1 065 °C min; quench
GX2CrNiMnMoNNb21-16-5-3 ^b	1.3967	Solution anneal 1 080 °C to 1180 °C; quench
GX3NiCo32 ^c	1.3983	820 °C to 850 °C/quench + 300 to 350 °C/air
GX1NiCo29-17 ^c	1.3988	820 °C to 850 °C/quench + 300 to 350 °C/air
GX3Ni36 ^c	1.3961	820 °C to 850 °C/quench + 300 to 350 °C/air
GX5NiS36 ^c	1.3963	820 °C to 850 °C/quench + 300 to 350 °C/air
G-NiCr13SnBiMo ^d	2.4712	As cast

^a Temperatures are for information only.
^b Low ferromagnetic response grades with magnetic permeability, $\mu_r \leq 1,01$.
^c For low linear-expansion grades see [Table 4](#).
^d Low galling grade.

Table 4 — Typical values for physical properties

Grade designation		Coefficient of expansion (mm/mm) (10 ⁻⁶ K ⁻¹)				
Name	Number	20 °C to 100 °C	20 °C to 200 °C	20 °C to 300 °C	20 °C to 500 °C	20 °C to 800 °C
GX3NiCo32	1.3983	0,63	—	—	—	—
GX1NiCo29-17	1.3988	5,9	5,2	5,1	6,1	10,3
GX3Ni36	1.3961	1,3	2,1	4,2	—	—
GX5Ni36S	1.3963	1,6	3,0	5,9	—	—

Annex A (informative)

UNS cast grades similar¹⁾ to ISO cast grades

Table A.1 — UNS cast grades similar to ISO cast grades

Grade designation		UNS Numbers
Name	Number	
GX12CrNi18-11	1.3955	-
GX2CrNi18-13	1.3940	J92500
GX2CrNiMoN18-14	1.3960	-
GX2CrNi19-11	1.3939	-
GX3CrNiMnSi17-9-8	1.3975	J92972
GX4CrNiMnN22-12-5	1.3956	J93790
GX2CrNiMnMoNb21-16-5-3	1.3967	-
GX3NiCo32	1.3983	-
GX1NiCo29-17	1.3988	-
GX3Ni36	1.3961	-
GX5NiS36	1.3963	-
G-NiCr13SnBiMo	2.4712	N26055
NOTE The grade designations including the names and the numbers follow the rules of EN 10027-1 and EN 10027-2.		

1) The similar UNS (Unified Numbering System) grades may not be equivalent to the grades in this International Standard.

Bibliography

- [1] EN 10027-1, *Designation system for steels — Part 1: Steel names*
- [2] EN 10027-2, *Designation system for steels — Part 2: Steel numbers*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™