

**Carbonaceous
materials used in the
production of
aluminium —
Determination of
density by gas
pyknometry
(volumetric) using
helium as the analysis
gas — Solid materials**

ICS 71.100.10

National foreword

This British Standard was published by BSI. It is the UK implementation of ISO 21687:2007.

The UK participation in its preparation was entrusted to Technical Committee CII/24, Raw materials for the aluminium industry.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

(c) BSI

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2007

© BSI 2007

ISBN 978 0 580 50730 4

Amendments issued since publication

Amd. No.	Date	Comments

INTERNATIONAL
STANDARD

ISO
21687

First edition
2007-03-01

**Carbonaceous materials used in the
production of aluminium —
Determination of density by gas
pycnometry (volumetric) using helium as
the analysis gas — Solid materials**

*Produits carbonés utilisés pour la production de l'aluminium —
Détermination de la masse volumique vraie par la méthode
pycnométrique gazeuse (volumétrique) utilisant de l'hélium comme gaz
analytique — Matériaux solides*



Reference number
ISO 21687:2007(E)

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus and materials	2
6 Sampling, sample preparation and drying	2
7 Procedure	3
8 Calculation	3
9 Precision	4
10 Test report	5
Bibliography	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21687 was prepared by Technical Committee ISO/TC 226, *Materials for the production of primary aluminium*.

Introduction

This International Standard is based on a DIN method: DIN 51913:2001, *Testing of carbon materials — Determination of density by gas pycnometer (volumetric) using helium as the measuring gas — Solid materials* prepared by Arbeitsausschuß NMP 281, *Test Methods for Carbon and Graphite*.

The density of calcined petrol coke permits an estimate of the degree of calcination of the analysed material.

Carbonaceous materials used in the production of aluminium — Determination of density by gas pycnometry (volumetric) using helium as the analysis gas — Solid materials

1 Scope

This International Standard specifies a method for the determination of the density of green and calcined petroleum coke and similar solid materials (e.g. electrodes). This standard is also suitable for hydrocarbons with a high-temperature boiling range and for other solid materials.

This method is not suitable for graphitized material.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3310-1:2000, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 6257:2002, *Carbonaceous materials used in the production of aluminium — Pitch for electrodes — Sampling*

ISO 6375:1980, *Carbonaceous materials for the production of aluminium — Coke for electrodes — Sampling*

ISO 8007-1:1999, *Carbonaceous materials used in the production of aluminium — Sampling plans and sampling from individual units — Part 1: Cathode blocks*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

density of a solid material

ρ
mass m per unit volume V

$$\rho = \frac{m}{V} \quad (1)$$

where

ρ is the density, expressed in grams per cubic centimetre;

m is the mass, in grams;

V is the volume of the solid, in cubic centimetres, excluding any pore volume.

BS ISO 21687:2007

NOTE Accessible and inaccessible pores contribute to the total pore volume of the solid. However, only accessible pores can be excluded from the volume of the solid.

4 Principle

A sample is ground and sieved to a size $\leq 0,063$ mm. The density ρ is determined volumetrically in a gas pycnometer with helium as the analysis gas. The mass of the dry test portion is determined and the test portion is loaded into the analysis chamber. Helium gas is introduced into the analysis chamber and pressurized to a set value. The helium gas is subsequently expanded into an expansion chamber. The instrument records the equilibration pressures for both steps. The density ρ of the sample is calculated from the mass m of the dry sample and its volume V determined by gas pycnometry.

5 Apparatus and materials

5.1 Crusher, e.g. jaw-type, faced with a hard material that will not be abraded to minimize sample contamination.

5.2 Grinder, capable of grinding the sample to a particle size of less than 0,063 mm, and with the parts that come into contact with the sample made of a hard material that will not be abraded to minimize sample contamination.

5.3 Porcelain bowl, 50 mm to 60 mm in diameter and 30 mm to 40 mm in depth.

5.4 Copper plate.

5.5 Sieve, with a mesh width of 0,063 mm in accordance with ISO 3310-1.

5.6 Drying oven, (preferably with vacuum option) capable of operating at temperatures ≥ 110 °C.

NOTE Use of a drying oven without a vacuum option may reduce the precision given in Clause 9.

5.7 Dessicator, containing silica gel.

5.8 Gas pycnometer.

5.9 Calibration balls, with known volume.

5.10 Sample cup, tared.

5.11 Helium, with a minimum purity of 99,996 % (by volume fraction).

5.12 Analytical balance, accurate to 0,1 mg.

6 Sampling, sample preparation and drying

6.1 Sampling and sample preparation

6.1.1 Pitch

Take a sample of the material in accordance with ISO 6257.

Coarsely crush the pitch sample, place about 50 g in the porcelain bowl (5.3), weigh and dry for about 2 h in the oven (5.6) at a temperature of about 50 °C above the softening point and at least 110 °C. During the process, stir the sample to avoid air bubbles. Repeat weighing and drying until the mass remains constant.

Pour the sample onto the copper plate (5.4), allow to cool then grind the sample to a particle size of $\leq 0,063$ mm using the grinder (5.2) and then sieve through the sieve (5.5).

Take a test portion of the sieved sample material $\leq 0,063$ mm by filling the tared sample cup.

6.1.2 Coke

Take a sample of the material in accordance with ISO 6375.

Crush, grind and sieve the sample to a particle size of $\leq 0,063$ mm using the grinder (5.2), and then sieve through the sieve (5.5). Store this sample in an airtight container until required for the determination.

NOTE In order to avoid the need to verify the particle size of each sample, it is advisable to determine the grinding conditions which will enable the required particle size to be obtained with each sample using the grinder available. This can be done with any apparatus capable of determining the size of such particles.

6.1.3 Cathode blocks and prebaked anodes

Take a sample of the material in accordance with ISO 8007-1.

Drill a cylinder or cut a piece out of the carbon block.

Crush, grind and sieve the sample to a particle size of $\leq 0,063$ mm using the grinder (5.2), and then sieve through the sieve (5.5). Store this sample in an airtight container until required for the determination.

NOTE In order to avoid the need to verify the particle size of each sample, it is advisable to determine the grinding conditions which will enable the required particle size to be obtained with each sample type (cathode blocks, prebaked anodes), using the grinder available. This can be done with any apparatus capable of determining the size of such particles.

6.2 Drying of coke, cathode blocks and prebaked anodes

Take a test portion of the sieved sample material $\leq 0,063$ mm by filling the tared sample cup. Place the test portion and sample cup in the drying oven at a temperature of 110 °C and a pressure of 1 kPa (10 mbar) for at least 30 min. Remove from the oven, allow to cool in the desiccator (5.7), weigh, reheat again to 110 °C, and introduce the sample cup immediately into the gas pyknometer.

7 Procedure

Calibrate the apparatus and perform the analysis according to the operator's manual supplied by the equipment manufacturer.

8 Calculation

Calculate the density ρ , in grams per cubic centimetre (g/cm^3), using the equation

$$\rho = \frac{m}{V} \quad (2)$$

where

ρ is the density of the sample, expressed in grams per cubic centimetre (g/cm^3);

m is the mass of the sample, in grams (g);

V is the measured volume of the sample, in cubic centimetres (cm^3).

BS ISO 21687:2007

The volume of the sample is usually calculated by the analysis instrument, but may also be calculated from the analysis data using the equation

$$V = V_{\text{cell}} - \frac{V_{\text{exp}}}{\frac{P_1}{P_2} - 1} \quad (3)$$

where

V_{cell} is the calibrated volume of the empty analysis chamber, in cubic centimetres (cm³);

V_{exp} is the calibrated volume of the expansion chamber, in cubic centimetres (cm³);

P_1 is the filling pressure of the analysis chamber before the expansion, in kPa;

P_2 is the pressure after the expansion, in kPa.

9 Precision

9.1 Determination

The precision of the method was determined in three Round Robins:

- a) green and calcined coke;
- b) pitch;
- c) baked anodes, cathode blocks and sidewall blocks;

and calculated by ASTM E 691:1999 under the following analysis conditions:

Gas pressure of helium	approximately 150 kPa
Purges	20
Purge/filling pressure	135 kPa
Equilibration rate	0,034 5 kPa/min

The precision is given for a 95 % confidence level.

9.2 Repeatability

The difference between two results, collected on the same sample by the same person with the same instrument under constant analysis conditions, should only in one out of 20 cases be larger than the mentioned value, if the method described is used under common and correct conditions.

Pitch: in the range 1,28 to 1,32 g/cm³, the following precision has been obtained:

Repeatability (r): 0,003 g/cm³

Coke: in the range 2,06 to 2,09 g/cm³, the following precision has been obtained:

Repeatability (r): 0,004 g/cm³

Anodes: in the range 2,06 to 2,12 g/cm³, the following precision has been obtained:

Repeatability (r): 0,002 g/cm³

9.3 Reproducibility

The difference between two single and independent results, collected on identical samples by different persons in different laboratories, should only in one out of 20 cases be larger than the mentioned value, if the method described is used under common and correct conditions.

Pitch: in the range 1,28 to 1,32 g/cm³, the following precision has been obtained:

Reproducibility (*R*): 0,015 g/cm³

Coke: in the range 2,06 to 2,09 g/cm³, the following precision has been obtained:

Reproducibility (*R*): 0,014 g/cm³

Anodes: in the range 2,06 to 2,12 g/cm³, the following precision has been obtained:

Reproducibility (*R*): 0,006 g/cm³

9.4 Examples of use

9.4.1 Repeatability

Given a pitch with real density in the range 1,28 to 1,32 g/cm³, if two test portions are measured by the same operator in the same laboratory, the measurements are acceptable if they differ by less than 0,003 g/cm³.

9.4.2 Reproducibility

Given a coke with real density in the range 2,06 to 2,09 g/cm³, if two test portions are measured at different laboratories, the measurements are acceptable if they differ by less than 0,014 g/cm³.

10 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) details necessary for the complete identification of the material tested;
- c) the type of pycnometer and its manufacturer;
- d) the density of the sample, in grams per cubic centimetre (g/cm³), rounded to 0,001 g/cm²;
- e) any agreed deviations from this International Standard;
- f) the date of the test.

Bibliography

- [1] ASTM E 691:1999, *Standard practice for conducting an interlaboratory study to determine the precision of a test method*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
 Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
 Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
 Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
 Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
 Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
 Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
 Email: copyright@bsi-global.com.

BSI
 389 Chiswick High Road
 London
 W4 4AL