

BS ISO 26842-2:2013



BSI Standards Publication

Adhesives — Test methods for the evaluation and selection of adhesives for indoor wood products

Part 2: Resistance to delamination in severe environments

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 26842-2:2013. It supersedes BS ISO 26842-2:2009 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/52, Adhesives.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 71906 6

ICS 83.180

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2013.

Amendments issued since publication

Date	Text affected
------	---------------

**Adhesives — Test methods for the
evaluation and selection of adhesives
for indoor wood products —**

**Part 2:
Resistance to delamination in severe
environments**

*Adhésifs — Méthodes d'essai pour l'évaluation et la sélection des
adhésifs destinés aux produits en bois pour l'usage intérieur —*

Partie 2: Résistance à la délamination dans des environnements sévères





COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	2
5 Specimens	2
5.1 Preparation and number	2
5.2 Conditioning	2
6 Delamination-resistance grades	3
7 Delamination-resistance tests	3
8 Procedure	3
9 Assessment of the delamination-resistance grade chosen	4
10 Test report	4
Annex A (informative) Report form	6
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

This second edition replaces the first edition (ISO 26842-2:2009), of which it constitutes a minor revision.

ISO 26842 consists of the following parts, under the general title *Adhesives — Test methods for the selection and evaluation of adhesives for indoor wood products*:

- *Part 1: Resistance to delamination in non-severe environments*
- *Part 2: Resistance to delamination in severe environments*

Adhesives — Test methods for the evaluation and selection of adhesives for indoor wood products —

Part 2:

Resistance to delamination in severe environments

SAFETY STATEMENT — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory conditions.

It is recognized that some of the materials permitted in this document might have a negative environmental impact. As technological advances lead to more acceptable alternatives for such materials, they will be eliminated to the greatest extent possible.

At the end of the test, care should be taken to dispose of all waste in an appropriate manner in accordance with local regulations.

1 Scope

This part of ISO 26842 gives guidelines to select, by means of delamination-resistance tests, adhesive/wood combinations for use in wood products placed in severe environments, in which the products are exposed to extreme change of temperature and humidity. A series of exposure cycles at various temperature and humidity values is provided to verify that the adhesive selected, or a product bonded with the adhesive, meets the necessary requirements for resistance to delamination.

This part of ISO 26842 is intended to help the user not only to select a suitable adhesive, but also to evaluate adhesives and adhesively bonded wood products.

NOTE When actual wood products are tested using this method, the test results might not be comparable because the test laboratory will not normally have had adequate control over the way the product was assembled.

This part of ISO 26842 is not intended for use in the qualification of structural components.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6238, *Adhesives — Wood-to-wood adhesive bonds — Determination of shear strength by compressive loading*

ISO 9424, *Wood-based panels — Determination of dimensions of test pieces*

ISO 16999, *Wood-based panels — Sampling and cutting of test pieces*

3 Principle

Test specimens or actual products that have been bonded with the test adhesive are placed in chambers at a specified temperature and humidity for a length of time and/or number of cycles depending on the grade of resistance to delamination under consideration. On completion of this exposure, the length of any delamination at the bond line is determined as a percentage of the overall length. If the length of

delamination does not exceed 10 %, the adhesive can be certified as complying, under the test conditions used, with the requirements of the grade of resistance to delamination under consideration.

4 Apparatus

NOTE Apparatus that includes the features of all the chambers specified in 4.1 to 4.4, might be available, in which case it will not be necessary to have one of each and also air is circulating at a velocity of $(2,25 \pm 0,25)$ m/s.

4.1 Conditioning chamber, capable of being maintained either at a temperature of (23 ± 2) °C and a relative humidity of (50 ± 5) % or at a temperature of (20 ± 2) °C and a relative humidity of (65 ± 5) %.

4.2 Dry-heat chamber, capable of being maintained at temperatures of (50 ± 2) °C and (80 ± 2) °C, with no provision for humidity control.

NOTE These temperatures can be experienced in the bottom of ships sailing in tropical seas or on heated floors.

4.3 Cold chamber, capable of being maintained at temperatures of (-20 ± 3) °C and (-30 ± 3) °C, with no provision for humidity control.

NOTE These temperatures can be experienced inside warehouses in cold latitudes.

4.4 Humidity chambers, capable of being maintained at relative humidity of 20 % and 90 %, and fitted with the following:

- a) equipment capable of maintaining the temperature at (50 ± 2) °C and measuring it to within ± 2 °C;
- b) equipment capable of measuring the relative humidity to within ± 3 %.

5 Specimens

5.1 Preparation and number

Test specimens shall be parallel two-ply laminates of dimensions 300 mm (width) × 300 mm (length) × 7,5 mm (thickness), prepared in accordance with ISO 6238 and measured in accordance with ISO 9424. The wood shall be cut to size in accordance with ISO 16999 and then adhesively bonded. Other test specimen dimensions may be agreed upon between the wood product manufacturer and the supplier of the adhesive, depending on the purpose of the test.

For each grade of resistance to delamination and specific set of test conditions within the grade, a minimum of 10 specimens is required.

NOTE If appropriate, actual adhesively bonded products can be tested using the test requirements and conditions specified in this part of ISO 26842.

These specimens shall be prepared in accordance with ISO 16999.

5.2 Conditioning

Prior to testing, condition all specimens in the conditioning chamber (4.1) at the standard atmospheric conditions of (23 ± 2) °C and (50 ± 5) % RH, unless agreed otherwise at a minimum of 88 h. If a longer conditioning period is deemed necessary, the wood product manufacturer and the manufacturer of the adhesive should agree on a longer time.

NOTE For actual bonded products, 88 h might not be sufficient.

Specimens should be conditioned to the equilibrium moisture content corresponding to the specified use conditions.

Conditioning shall be carried out after the adhesive has been cured in accordance with the material specification or as specified by the manufacturer of the adhesive.

6 Delamination-resistance grades

Two grades of resistance to delamination are specified, each representing a different type of use, i.e. the different conditions of temperature and humidity which different adhesively bonded wood products may experience in service:

- **grade 3 of resistance to delamination** applies to high-durability indoor use (e.g. chair legs, fixtures, musical instruments);
- **grade 4 of resistance to delamination** applies to semi-outdoor use (e.g. window frames and flooring exposed to the sunlight near windows);

7 Delamination-resistance tests

The following four tests, which take into consideration the meteorological conditions of service and transport, shall be used in this part of ISO 26842:

- **test A – cyclic hot/cold test**, intended for testing using temperature variation only;
- **test B – cyclic humid/dry test**, intended for testing at a fixed temperature using humidity variation only;
- **test C – hot and humid test**, intended to represent the conditions of service or transport in tropical regions;
- **test D – hot and dry test**, intended to represent the conditions of service or transport in desert regions.

Details of these tests are given in [Tables 1](#) and [2](#).

8 Procedure

Select a grade of resistance to delamination based on the conditions in which the wood product is expected to be used (see [Clause 6](#)) and then select a suitable grade of resistance to delamination based on the expected meteorological conditions of service and transport (see [Clause 7](#)).

Conduct the tests of resistance to delamination in accordance with [Table 1](#) and [Table 2](#), placing the test specimens at least 50 mm apart with the end-grain surfaces parallel to the air flow in the chamber appropriate to the particular test being sure to keep the grain direction of the wood oriented to the direction of the air flow in the chamber.

- For test A, place the specimens in a cold chamber ([4.3](#)) for the specified length of time, then immediately transfer them to a dry-heat chamber ([4.2](#)) or programme the fastest change of atmosphere in an automatic climate chamber for the specified length of time. Carry out the number of cycles specified in [Table 1](#).
- For test B, place the specimens in a humidity chamber ([4.4](#)) at the higher humidity for the specified length of time, then immediately transfer them to a humidity chamber ([4.4](#)) or programme the fastest change of atmosphere in an automatic climate chamber at the lower humidity for the specified length of time. Carry out the number of cycles specified in [Table 1](#).
- For tests C and D, place the specimens in a humidity chamber ([4.4](#)) for the specified length of time.

Except when transferring the specimens from one chamber to another, do not remove them from the chamber until the test has been completed.

At the end of the final test period, measure and record the total length of delamination of each specimen at the bond line.

Table 1 — Delamination-resistance grades

Delamination-resistance grade	Delamination-resistance test and test conditions			
	Test A	Test B	Test C	Test D
3	A2 10 cycles	B1 1 cycle	C1 7 days	D1 7 days
4	A1 10 cycles	B1 2 cycles	C1 14 days	D1 14 days

Table 2 — Delamination-resistance tests and test conditions

Test cycle	Conditions for 1 cycle
A1	-30 °C for 16 h/80 °C for 8 h
A2	-20 °C for 16 h/50 °C for 8 h
B1	50 °C, 90 % RH for 2 days/50 °C, 20 % RH for 5 days
C1	50 °C, 90 % RH
D1	50 °C, 20 % RH

9 Assessment of the delamination-resistance grade chosen

Within an hour (1 h) of the test period specified in [Table 1](#), visually examine each test specimen as it is removed from the test condition using a magnifying glass with a magnification of ca. 10x and with strong lighting recommended. Immediately measure and record, to the nearest 1 mm, and record the length of any delamination (bond line separation) in each of the four edges of each specimen. Calculate the total delamination length by adding together the individual delamination lengths recorded for the bond lines in the edges of all the specimens.

If the percentage delamination, i.e. the total delamination length divided by the total length of the bond lines in all four edges of all the specimens multiplied by 100, does not exceed 10 %, the adhesive tested can be certified as having, for the specific set of test conditions used, the grade of resistance to delamination initially selected.

Delamination caused by wood checking, knots or other wood issues should not be read as delamination and should be excluded from measurement.

10 Test report

The test report shall include the following particulars:

- a) a reference to this part of ISO 26842, i.e. ISO 26842-2;
- b) all details necessary for the identification of the adhesive tested;
- c) (if actual wood products were tested) all details necessary for the identification of the products tested;
- d) (if test specimens were prepared) the type of wood used to prepare the specimens;
- e) the method of application of the adhesive and the drying or curing conditions, as applicable, including the temperature and pressure;
- f) the number of specimens tested and the conditions under which the specimens were conditioned before testing;

- g) the delamination-resistance grade to which the specimens were tested and the specific delamination-resistance tests carried out (see [Table 1](#));
- h) the percentage delamination measured after the test and the result of the assessment of the delamination-resistance grade chosen;
- i) the date(s) of testing.

[Annex A](#) gives an example of a report form which may be used to record the results.

Bibliography

- [1] ISO 9142, *Adhesives — Guide to the selection of standard laboratory ageing conditions for testing bonded joints*
- [2] ISO 15605, *Adhesives — Sampling*
- [3] ISO 17087, *Specifications for adhesives used for finger joints in non-structural lumber products*
- [4] ASTM D1183, *Standard Practices for Resistance of Adhesives to Cyclic Laboratory Aging Conditions*
- [5] ASTM D4317, *Standard Specification for Polyvinyl Acetate-Based Emulsion Adhesives*
- [6] ASTM D5751, *Standard Specification for Adhesives Used for Laminate Joints in Nonstructural Lumber Products*
- [7] ASTM D5824, *Standard Test Method for Determining Resistance to Delamination of Adhesive Bonds in Overlay-Wood Core Laminates Exposed to Heat and Water*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™