

# Thermal insulating products for building applications — Determination of the apparent density

ICS 91.100.60

## National foreword

This British Standard is the UK implementation of ISO 29470:2008.

The UK participation in its preparation was entrusted to Technical Committee B/540/8, Mirror committee for ISO/TC 163.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2008

© BSI 2008

ISBN 978 0 580 58940 9

### Amendments/corrigenda issued since publication

Date	Comments

# INTERNATIONAL STANDARD

**ISO**  
**29470**

First edition  
2008-09-15

---

---

## **Thermal insulating products for building applications — Determination of the apparent density**

*Produits isolants thermiques destinés aux applications du bâtiment —  
Détermination de la masse volumique apparente*



Reference number  
ISO 29470:2008(E)

© ISO 2008

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 29470 was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 1, *Test and measurement methods*.

## Introduction

For this document, the conditions of approval within the Fast-Track procedure were not met, thus this document could not progress to the publication stage. ISO/TC 163/SC 1 decided per Resolution 205 in its Nanjing-meeting on 2008-04-15, that this document shall be forwarded modified to the FDIS-vote.

This International Standard includes the original EN 1602:1996 and EN 1602:1996/AC:1997 prepared by Technical Committee CEN/TC 88, *Thermal insulating materials and products*.

This International Standard is one of a series of documents specifying test methods, based on existing European Standards, that are being adopted by ISO. This “package” of standards includes the following group of interrelated documents.

ISO document	Respective EN standard
ISO 29465, <i>Thermal insulating products for building applications — Determination of length and width</i>	EN 822
ISO 29466, <i>Thermal insulating products for building applications — Determination of thickness</i>	EN 823
ISO 29467, <i>Thermal insulating products for building applications — Determination of squareness</i>	EN 824
ISO 29468, <i>Thermal insulating products for building applications — Determination of flatness</i>	EN 825
ISO 29469, <i>Thermal insulating products for building applications — Determination of compression behaviour</i>	EN 826
ISO 29470, <i>Thermal insulating products for building applications — Determination of the apparent density</i>	EN 1602
ISO 29471, <i>Thermal insulating products for building applications — Determination of dimensional stability under constant normal laboratory conditions (23 °C/50 % relative humidity)</i>	EN 1603
ISO 29472, <i>Thermal insulating products for building applications — Determination of dimensional stability under specified temperature and humidity conditions</i>	EN 1604
ISO 29764, <i>Thermal insulating products for building applications — Determination of deformation under specified compressive load and temperature conditions</i>	EN 1605
ISO 29765, <i>Thermal insulating products for building applications — Determination of tensile strength perpendicular to faces</i>	EN 1607
ISO 29766, <i>Thermal insulating products for building applications — Determination of tensile strength parallel to faces</i>	EN 1608
ISO 29767, <i>Thermal insulating products for building applications — Determination of short-term water absorption by partial immersion</i>	EN 1609
ISO 29768, <i>Thermal insulating products for building applications — Determination of linear dimensions of test specimens</i>	EN 12085

ISO 29769, <i>Thermal insulating products for building applications — Determination of behaviour under point load</i>	EN 12430
ISO 29770, <i>Thermal insulating products for building applications — Determination of thickness for floating-floor insulating products</i>	EN 12431
ISO 29771, <i>Thermal insulating materials for building applications — Determination of organic content</i>	EN 13820
ISO 29803, <i>Thermal insulation products for building applications — Determination of the resistance to impact of external thermal insulation composite systems (ETICS)</i>	EN 13497
ISO 29804, <i>Thermal insulation products for building applications — Determination of the tensile bond strength of the adhesive and of the base coat to the thermal insulation material</i>	EN 13494
ISO 29805, <i>Thermal insulation products for building applications — Determination of the mechanical properties of glass fibre meshes</i>	EN 13496





# Thermal insulating products for building applications — Determination of the apparent density

## 1 Scope

This International Standard specifies the equipment and procedures for determining the apparent overall density and the apparent core density under reference conditions. It is applicable to full-size thermal insulating products and test specimens. This International Standard can also be applied to the individual layers of multi-layered products.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 29465, *Thermal insulating products for building applications — Determination of length and width*

ISO 29466, *Thermal insulating products for building applications — Determination of thickness*

ISO 29768, *Thermal insulating products for building applications — Determination of linear dimensions of test specimens*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1 apparent overall density

$\rho_a$

mass per unit volume of a product, including all surface skins formed during production, but excluding any facings and/or coatings

### 3.2 apparent core density

$\rho_c$

mass per unit volume of the core of a product after all surface skins formed during production and all facings and/or coatings have been removed

## 4 Principle

The density is determined as the ratio of the mass and the volume of the specimen.

## 5 Apparatus

5.1 **Balance**, capable of determining the mass of a specimen to an accuracy of 0,5 %.

5.2 **Equipment**, for the determination of linear dimensions (see 7.2).

## 6 Test specimens

### 6.1 Dimensions of test specimens

The specimens shall be full-size products or parts thereof, or specimens used for other tests.

The shape of specimens shall be such that their volume can be easily calculated.

When the apparent overall density is being determined using specimens cut from a product with surface skins formed during production, the ratio of the area of the surface skin to the total volume shall be the same for the specimen as for the product.

The size of a specimen should preferably be as large as possible, commensurate with the apparatus available and with the shape of the original product. The size of the specimens may also be specified in other test methods.

### 6.2 Number of test specimens

The number of specimens for full-size products shall be as specified in the relevant product standard. If specimens from other tests are used, the number shall be as specified in the test method. If the number is not specified, then at least five test specimens shall be used.

In the absence of a product standard or any other international or European technical specification, the number of specimens may be agreed between parties.

### 6.3 Preparation of test specimens

The specimens shall be cut by methods that do not change the original structure of the product.

The location from which the specimens are taken shall be such that the density obtained is representative of the density of the product.

For a determination of the apparent overall density, any facings and/or coatings shall be removed from the product. For a determination of the apparent core density, any surface skins formed during production and any facings and/or coatings shall be removed from the product.

When it is not possible to remove the facings and/or coatings without influencing the apparent density of the product, the mass of the facings and/or coatings shall be deducted by calculation.

NOTE Special methods of preparation, when needed, are given in the relevant product standard.

### 6.4 Conditioning of test specimens

The specimens shall be conditioned at  $(23 \pm 2) ^\circ\text{C}$  and  $(50 \pm 5) \%$  relative humidity until a constant mass is achieved.

The time for conditioning and the required accuracy of the constant-mass measurements shall be given in the relevant product standard.

If it can be shown that temperature and humidity have negligible influence on the determination of the density, then the conditioning may be carried out at  $(23 \pm 5) ^\circ\text{C}$ .

The conditioning time can be shortened by pre-drying the specimen in a ventilated oven at a prescribed temperature. Appropriate procedures may be given in the relevant product standard.

In tropical countries, different conditioning and testing conditions can be relevant. In this case, the conditions shall be  $27 ^\circ\text{C}/65\% \text{ RH}$  and be stated clearly in the test report.

## 7 Procedure

### 7.1 Test conditions

The test shall be carried out at  $(23 \pm 2) ^\circ\text{C}$  and  $(50 \pm 5)\%$  relative humidity.

If it can be shown that temperature and humidity have negligible influence on the determination of the density, testing may be carried out at  $(23 \pm 5) ^\circ\text{C}$ .

In tropical countries, different conditioning and testing conditions can be relevant. In this case, the conditions shall be  $27 ^\circ\text{C}/65\% \text{ RH}$  and be stated clearly in the test report.

### 7.2 Test procedure

Measure the linear dimensions of full-size products in accordance with ISO 29465 and ISO 29466.

Measure the linear dimensions of specimens in accordance with ISO 29768.

For full-size products, the length, width and thickness shall be given to the nearest millimetre. For specimens, the measurements shall be made to an accuracy of 0,5 %.

Calculate the volumes of the specimens from these measurements.

Weigh each specimen to an accuracy of 0,5 % and record its mass expressed in kilograms.

If the facings and/or coatings are retained, the mass of the product shall be calculated by deducting the mass of the facings and/or coatings and adhesives, if any, from the overall mass.

If a greater accuracy for the dimensions of full size products is needed, this shall be specified in the relevant product standard.

## 8 Calculation and expression of results

Calculate the apparent overall density,  $\rho_a$ , or apparent core density,  $\rho_c$ , expressed in kilograms per cubic metre, using Equation (1):

$$\rho = \frac{m}{V} \quad (1)$$

where

$m$  is the mass of the specimen, expressed in kilograms;

$V$  is the volume of the specimen, expressed in cubic metres.

$\rho$  ( $\rho_a$  or  $\rho_c$ ) for the specimen shall be given to three significant figures.

## 9 Accuracy of the measurement

NOTE It has not been possible to include a statement on the accuracy of the measurement in this edition of the International Standard, but it is intended to include such a statement when the standard is next revised.

## 10 Test report

The test report shall include the following information:

- a) reference to this International Standard: ISO 29470:2008;
- b) product identification:
  - 1) product name, factory, manufacturer, or supplier,
  - 2) production code number,
  - 3) type of product,
  - 4) packaging,
  - 5) form in which the product arrived at the laboratory,
  - 6) other information as appropriate (e.g. nominal dimensions);
- c) test procedure:
  - 1) pre-test history and sampling (person taking the sample, place of sampling),
  - 2) conditioning,
  - 3) drying conditions,
  - 4) presence of facings, the mass of the facing and the method of removal, if necessary,
  - 5) presence of surface skins and the method of removal, if necessary,
  - 6) presence of densification, stratification or defects on the specimens,
  - 7) any deviations from Clauses 6 and 7,
  - 8) conditioning and testing conditions in tropical countries, if applicable,
  - 9) date of testing,
  - 10) general information relating to the test,
  - 11) events that can have affected the results;
- d) results: all individual values and the mean value.

NOTE It is expected that information about the apparatus and identity of the technician be available in the laboratory but it is not necessary to record them in the report.



---

---

**ICS 91.100.60**

Price based on 4 pages



---

## BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: [orders@bsigroup.com](mailto:orders@bsigroup.com) You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: [info@bsigroup.com](mailto:info@bsigroup.com)

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: [membership@bsigroup.com](mailto:membership@bsigroup.com)

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: [copyright@bsigroup.com](mailto:copyright@bsigroup.com)