

Methods of test for paints

Part B8: Determination of “soluble” barium content

[ISO title: Paints and varnishes — Determination of “soluble” metal content — Part 3: Determination of barium content — Flame atomic emission spectrometric method]

It is recommended that this Part be read in conjunction with the general information in the introduction to BS 3900, issued separately.

UDC 667.61:620.1

This British Standard, having been prepared under the direction of the Pigments, Paints and Varnishes Standards Committee, was published under the authority of the Board of BSI and comes into effect on 31 January 1986

© BSI 11-1999

The Committees responsible for this British Standard are shown in BS 3900: Introduction.

The following BSI references relate to the work on this standard:
Committee reference PVC/10
Draft for comment 78/51514 DC

ISBN 0 580 14947 1

Amendments issued since publication

Amd. No.	Date of issue	Comments

Contents

	Page
National foreword	ii
0 Introduction	1
1 Scope and field of application	1
2 References	1
3 Principle	1
4 Reagents and materials	1
5 Apparatus	1
6 Procedure	2
7 Expression of results	2
8 Test report	3
Publications referred to	Inside back cover

National foreword

This Part of BS 3900 has been prepared under the direction of the Pigments, Paints and Varnishes Standards Committee. It is identical with ISO 3856-3:1984 "*Paints and varnishes — Determination of "soluble" metal content — Part 3 "Determination of barium content — Flame atomic emission spectrometric method"*" published by the International Organization for Standardization (ISO).

It is assumed in the drafting of this standard that it will be used and applied by those who are appropriately qualified and experienced. The procedures described in this standard are intended to be carried out by suitably trained and/or supervised personnel. The substances and procedures described may be injurious to health if inadequate precautions are taken. This standard refers only to its technical suitability and does not absolve the user from statutory obligations relating to health and safety.

Terminology and conventions. The text of the International Standard has been approved as suitable for publication as a British Standard without deviation. Some terminology and certain conventions are not identical with those used in British Standards; attention is drawn especially to the following.

The comma has been used as a decimal marker. In British Standards, it is current practice to use a full point on the baseline as the decimal marker.

In British Standards it is current practice to use the symbol "L" for litre rather than "l".

Wherever the words "International Standard" and "part of ISO 3856" appear, referring to this standard, they should be read as "British Standard" and "Part of BS 3900" respectively, and wherever the identification "ISO 3856-3" appears, it should be read as "BS 3900:B8".

Cross-references

International Standards	Corresponding British Standards
ISO 1042:1983	BS 1792:1982 <i>Specification for one-mark volumetric flasks</i> (Identical)
ISO 6713:1984	BS 3900 <i>Methods of test for paints</i> Part B5:1986 <i>Preparation of acid extracts from liquid paints or coating powders</i> (Identical)

The Technical Committee has reviewed the provisions of ISO 385-1:1984, and ISO 648:1977 to which reference is made in the text, and has decided that they are acceptable for use in conjunction with this standard. ISO 385-1 is related to BS 846 "*Specification for burettes*" and ISO 648 is related to BS 1583 "*One-mark pipettes*".

The Technical Committee has reviewed the proposed provisions of ISO 3696 to which reference is made in clause 4 and has decided that they are acceptable for use in conjunction with this standard. ISO 3696 is related to BS 3978 "*Water for laboratory use*".

ISO 3856, to which reference is made in clause 0, is published in a number of Parts of BS 3900. At the time of publication of this standard, the relationship between other Parts of BS 3900 and Parts of ISO 3856 was as follows:

Part of ISO 3856	Corresponding Part of BS 3900
	BS 3900 <i>Methods of test for paints</i>
ISO 3856-1:1984	^a Part B6:1986 <i>Determination of "soluble" lead content</i> (Identical)
ISO 3856-2:1984	Part B7:1986 <i>Determination of "soluble" antimony content</i> (Identical)

Part of ISO 3856	Corresponding Part of BS 3900
ISO 3856-4:1984	Part B9:1986 <i>Determination of “soluble” cadmium content</i> (Identical)
ISO 3856-5:1984	Part B10:1986 <i>Determination of hexavalent chromium content of solid matter</i> (Identical)
ISO 3856-6:1984	Part B11:1986 <i>Determination of total chromium content of liquid matter</i> (Identical)
ISO 3856-7:1984	Part B12:1986 <i>Determination of “soluble” mercury content</i> (Identical)

^a Attention is drawn to a similar standard, BS 3900-B3 “*Determination of “soluble” lead in the solid matter in liquid paints: method for use in conjunction with The Control of Lead at Work Regulations, 1980 (S.I. 1980 No. 1248)*”.

Textual error. When adopting the text of the International Standard, the textual error given below was discovered. It has been marked in the text and has been reported to ISO in a proposal to amend the text of the International Standard.

In **6.3**, line 3, “absorbance” should be read as “emission”.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i to iv, pages 1 to 4, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

0 Introduction

This International Standard is a part of ISO 3856, *Paints and varnishes — Determination of “soluble” metal content*.

1 Scope and field of application

This part of ISO 3856 describes a flame atomic emission spectrometric (AES) method for the determination of the barium content of the test solutions prepared according to ISO 6713 or other suitable International Standards.

The method is applicable to paints having “soluble” barium contents in the range of about 0,05 to 5 %(*m/m*).

Other methods can be used by agreement between the interested parties but this method is the referee method in cases of dispute.

2 References

ISO 385-1, *Laboratory glassware — Burettes — Part 1: General requirements*¹⁾.

ISO 648, *Laboratory glassware — One-mark pipettes*.

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*.

ISO 3696, *Water for laboratory use — Specifications*²⁾.

ISO 6713, *Paints and varnishes — Preparation of acid extracts from paints in liquid or powder form*.

3 Principle

Aspiration of the test solution into a dinitrogen monoxide/acetylene flame. Measurement of the radiation emitted by barium at a wavelength of 553,5 nm. The ionization of barium atoms in the flame is suppressed by addition of potassium chloride.

4 Reagents and materials

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity according to ISO 3696.

4.1 Potassium chloride, 50 g/l solution.

4.2 Hydrochloric acid, $c(\text{HCl}) = 0,07 \text{ mol/l}$.

Use the hydrochloric acid, identical to that used for the preparation of the test solutions in accordance with ISO 6713. (See **6.2**.)

4.3 Dinitrogen monoxide, commercial grade, in a steel cylinder.

4.4 Acetylene, commercial grade, in a steel cylinder.

4.5 Barium, standard stock solution containing 1 g of Ba per litre.

Either

a) transfer the contents of an ampoule of standard barium solution containing exactly 1 g of Ba into a 1 000 ml one-mark volumetric flask, dilute to the mark with the hydrochloric acid (**4.2**) and mix well;

or

b) weigh, to the nearest 1 mg, 1,779 g of barium chloride dihydrate ($\text{BaCl}_2 \cdot 2\text{H}_2\text{O}$), dissolve in the hydrochloric acid (**4.2**) in a 1 000 ml one-mark volumetric flask, dilute to the mark with the same hydrochloric acid and mix well.

1 ml of this standard stock solution contains 1 mg of Ba.

4.6 Barium, standard solution containing 20 mg of Ba per litre.

Prepare this solution on the day of use.

Pipette 20 ml of the standard stock solution (**4.5**) into a 1 000 ml one-mark volumetric flask, dilute to the mark with the hydrochloric acid (**4.2**) and mix well.

1 ml of this standard solution contains 20 μg of Ba.

5 Apparatus

For this test, the laboratory glassware shall be barium-free.

Ordinary laboratory apparatus and

5.1 Flame atomic emission spectrometer, suitable for measurements at a wavelength of 553,5 nm and fitted with a burner fed with dinitrogen monoxide and acetylene.

5.2 Pipettes, of a suitable volume (see **6.2**), complying with the requirements of ISO 648.

5.3 Burettes, of capacity 10 and 50 ml, complying with the requirements of ISO 385-1.

5.4 One-mark volumetric flasks, of capacity 50 ml, complying with the requirements of ISO 1042.

If available:

5.5 Recording apparatus

A compensating recorder is recommended.

¹⁾ At present at the stage of draft. (Partial revision of ISO/R 385:1964.)

²⁾ At present at the stage of draft.

6 Procedure

6.1 Preparation of the calibration graph

6.1.1 Preparation of the standard matching solutions

Prepare these solutions on the day of use.

Into a series of six 50 ml one-mark volumetric flasks (5.4), introduce from the burette (5.3), respectively, the volumes of the standard barium solution (4.6) shown in the following table, add 5 ml of the potassium chloride solution (4.1), dilute each to the mark with the hydrochloric acid (4.2) and mix well.

Standard matching solution No.	Volume of the standard barium solution (4.6)	Corresponding concentration of Ba in the standard matching solution
	ml	µg/ml
0 ^a	0	0
1	2	0,8
2	5	2
3	10	4
4	20	8
5	40	16

^a Blank matching solution.

6.1.2 Spectrometric measurements

Measure the emission of the standard matching solutions in the spectrometer (5.1), using the operating conditions specified by the manufacturer of the instrument.

In order to determine and correct for the constant background emission due to the presence of calcium, carry out a measurement at a suitable point close to the barium line or record the emission over a wavelength range from 553,0 to 554,0 nm.

6.1.3 Calibration graph

Plot a graph having the masses, in micrograms, of Ba contained in 1 ml of the standard matching solutions as abscissae and the corresponding values of the emission, corrected for background emission, as ordinates.

6.2 Test solutions

6.2.1 Pigment portion of the liquid paint and paint in powder form

Pipette a suitable volume (volume V_3) of each of the solutions obtained by the procedure described in sub-clause 8.2.3 of ISO 6713 into 50 ml one-mark volumetric flasks (5.4) so that the barium concentration of each test solution will be within the calibration range. Add 5 ml of the potassium chloride solution (4.1), dilute to the mark with the hydrochloric acid (4.2) and mix well.

6.2.2 Liquid portion of the paint

Pipette a suitable volume (volume V_4) of each of the solutions obtained by the procedure described in sub-clause 9.3 of ISO 6713 into 50 ml one-mark volumetric flasks (5.4) so that the barium concentration of each test solution will be within the calibration range. Add 5 ml of the potassium chloride solution (4.1), dilute to the mark with the hydrochloric acid (4.2) and mix well.

6.2.3 Other test solutions

Pipette a suitable volume of each of the solutions obtained by the specified or agreed procedure into 50 ml one-mark volumetric flasks (5.4) so that the barium concentration of each test solution will be within the calibration range. Add 5 ml of the potassium chloride solution (4.1), dilute to the mark with the hydrochloric acid (4.2) and mix well.

6.3 Determination

Measure first the emission of the hydrochloric acid (4.2) in the spectrometer (5.1) after having adjusted it as described in 6.1.2. Then measure the absorbance of each test solution (6.2) three times and, afterwards, that of the hydrochloric acid again. Finally, re-determine the emission of the standard matching solution No. 4 (6.1.1) in order to verify that the response of the apparatus has not changed. If the emission of a test solution is higher than that of the standard matching solution with the highest barium concentration, dilute the test solution appropriately (dilution factor F) with a known volume of the hydrochloric acid (4.2).

7 Expression of results

7.1 Calculations

7.1.1 Pigment portion of the liquid paint

Calculate the mass of "soluble" barium in the hydrochloric acid extract, obtained by the method described in sub-clause 8.2.3 of ISO 6713, using the equation

$$m_0 = \frac{a_1 - a_0}{10^6} \times \frac{V_1}{V_3} \times 50 \times F_1$$

$$= (a_1 - a_0) \times \frac{V_1}{V_3} \times F_1 \times 5 \times 10^{-5}$$

where

a_0 is the barium concentration, in micrograms per millilitre, of the blank test solution prepared by the method described in sub-clause 8.4 of ISO 6713;

a_1 is the barium concentration, in micrograms per millilitre, of the test solution obtained from the calibration graph;

F_1 is the dilution factor referred to in 6.3;

m_0 is the mass, in grams, of “soluble” barium in the hydrochloric acid extract;

V_1 is the volume, in millilitres, of the hydrochloric acid plus ethanol used for the extraction described in sub-clause 8.2.3 of ISO 6713 (assumed to be 77 ml);

V_3 is the volume, in millilitres, of the aliquot portion of the hydrochloric acid plus ethanol extract taken for the test (6.2.1).

Calculate the “soluble” barium content of the pigment portion of the paint, using the equation

$$c_{\text{Ba}1} = m_0 \times \frac{10^2}{m_1} \times \frac{P}{10^2} = \frac{m_0 \times P}{m_1}$$

where

$C_{\text{Ba}1}$ is the “soluble” barium content, of the pigment portion of the paint, expressed as a percentage by mass of the paint;

m_1 is the mass, in grams, of the test portion taken to prepare the solution described in sub-clause 8.2.3 of ISO 6713;

P is the pigment content of the liquid paint, expressed as a percentage by mass, obtained by the appropriate method described in clause 6 of ISO 6713.

7.1.2 Liquid portion of the paint

Calculate the mass of barium in the solution (extract), obtained by the method described in sub-clause 9.3 of ISO 6713, using the equation

$$\begin{aligned} m_2 &= \frac{b_1 - b_0}{10^6} \times \frac{V_2}{V_4} \times 50 \times F_2 \\ &= (b_1 - b_0) \times \frac{V_2}{V_4} \times F_2 \times 5 \times 10^{-5} \end{aligned}$$

where

b_0 is the barium concentration, in micrograms per millilitre, of the blank test solution prepared by the method described in sub-clause 6.5 of ISO 6713;

b_1 is the barium concentration, in micrograms per millilitre, of the test solution obtained from the calibration graph;

F_2 is the dilution factor referred to in 6.3;

m_2 is the mass, in grams, of barium in the liquid portion of the paint;

V_2 is the volume, in millilitres, of the solution obtained by the method described in sub-clause 9.3 of ISO 6713 (= 100 ml);

V_4 is the volume, in millilitres, of the aliquot portion of the solution taken for the test.

Calculate the barium content of the liquid portion of the paint, using the equation

$$c_{\text{Ba}2} = \frac{m_2}{m_3} \times 10^2$$

where

$C_{\text{Ba}2}$ is the barium content, of the liquid portion of the paint, expressed as a percentage by mass of the paint;

m_3 is the total mass, in grams, of paint comprising a “set” as described in sub-clause 6.4 of ISO 6713.

7.1.3 Liquid paint

Calculate the total “soluble” barium content of the liquid paint as the sum of the results obtained according to 7.1.1 and 7.1.2, thus

$$C_{\text{Ba}3} = C_{\text{Ba}1} + C_{\text{Ba}2}$$

where $C_{\text{Ba}3}$ is the total “soluble” barium content of the paint, expressed as a percentage by mass.

7.1.4 Paint in powder form

The total “soluble” barium content of the paint in powder form is obtained by appropriate modification of the calculations given in 7.1.1.

7.1.5 Other test solutions

If the test solutions were prepared by methods other than those given in ISO 6713 (see 6.2.3), it will be necessary to modify the equations for the calculation of barium content given in 7.1.1 and 7.1.2.

7.2 Precision

No precision data are currently available.

8 Test report

The test report shall contain at least the following information:

- the type and identification of the product tested;
- a reference to this International Standard (ISO 3856-3);

- c) the method for the separation of the solid portion of the product under test according to ISO 6713, clause 6 (method A, B or C), where appropriate³⁾;
- d) the solvent or the solvent mixture used for the extraction, where appropriate³⁾;
- e) the results of the test, expressed as a percentage by mass of the product: either
 - the “soluble” barium content of the pigment portion of the paint, the barium content of the liquid portion of the paint and the total “soluble” barium content of the liquid paint, or
 - the total “soluble” barium content of the paint in powder form;
- f) any deviation, by agreement or otherwise, from the test procedure specified;
- g) the date of the test.

³⁾ Not required for paints in powder form (see clause 7 of ISO 6713).

Publications referred to

See national foreword.

BS 3900-B8:
1986
ISO 3856-3:
1984

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager.
Tel: 020 8996 7070.

BSI
389 Chiswick High Road
London
W4 4AL