

© British Standards Institution. No part of this publication may be photocopied or otherwise reproduced without the prior permission in writing of BSI

British Standard Specification for Vitrified hotelware

Vaisselle en céramique vitrifiée pour hôtels — Spécifications

Emailliertes Geschirr

Foreword

This revision of BS 4034 has been prepared under the direction of the Furniture and Household Equipment Standards Policy Committee. It supersedes BS 4034 : 1966 which is withdrawn.

There is a wide variety of terms used to describe different types of ceramic tableware, many of which are not well understood. An important class of product is that characterized by low water absorption and resistance to crazing generally known as vitrified hotelware and this standard specifies the two principal technical requirements that need to be fulfilled before a product can correctly be called vitrified hotelware viz. resistance to water absorption and crazing, determined by sampling from a consignment. It does not purport to have any relevance in the field of technical or industrial ceramics such as sanitary or electrical ceramics, nor does it cover any other aspects of fitness for purpose. It does not include any requirements for those characteristics which are matters of personal choice or which can be readily assessed by the purchaser at the point of sale.

Attention is drawn to Statutory Instrument 1988 No. 1647 The Ceramic Ware (Safety) Regulations 1988 which limits the amount of lead and cadmium which may be released from ceramic ware for contact with food.

Product certification. Users of this British Standard are advised to consider the desirability of third party certification of product conformity with this British Standard based on testing and continuing surveillance, which may be coupled with assessment of a supplier's quality systems against the appropriate Part of BS 5750.

Enquiries as to the availability of third party certification schemes will be forwarded by BSI to the Association of Certification Bodies. If a third party certification scheme does not already exist, users should consider approaching an appropriate body from the list of Association members.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Contents

	Page
Foreword	Inside front cover
Committees responsible	Back cover
Specification	
1 Scope	2
2 Definitions	2
3 Sampling	2
4 Performance	2
5 Marking	2
Appendices	
A Method of test for the determination of water absorption	3
B Method of test for the determination of crazing	4
Table	
1 Sample size for testing	2

Specification

1 Scope

This British Standard specifies requirements for resistance to water absorption and crazing for vitrified hotelware which determine that the description is applied correctly to the product. Compliance is determined by testing a representative sample taken from a consignment.

2 Definitions

For the purposes of this British Standard the following definitions apply.

2.1 types of tableware. Cups, saucers, plates, bowls, dishes, jugs, tea-pots and coffee-pots.

2.2 ceramic. Material generally made from a mixture of clays and other materials distinguished from glass and glass ceramic by the fact that it is first shaped and then rendered permanent by firing at a temperature generally well in excess of 1000 °C.

2.3 vitrified hotelware. Tableware composed of a vitrified ceramic body covered with glaze and resistant to water absorption and crazing.

2.4 biscuit. Unglazed body of ceramic ware.

2.5 consignment. Number of items supplied in response to a single order.

2.6 water absorption. Capacity of a ceramic body to absorb water.

2.7 crazing. Fine cracks which can be seen in the surface of glazed ceramic tableware but which do not penetrate the body.

3 Sampling

Samples for testing shall be taken at random from a consignment in accordance with table 1 and shall be representative of all of the types of tableware included in the consignment. Not more than 50 samples shall be taken from any one consignment.

4 Performance

4.1 Water absorption

When tested in accordance with appendix A, the average value for water absorption for all samples tested shall not exceed 0.2 %. Additionally, when tested in accordance with appendix A, the following shall apply for specific sample sizes.

Number of items in consignment	Minimum sample size
2 to 10	1
11 to 100	3
101 to 500	5
501 to 1000	10
1001 to 2500	15
2501 to 5000	20
5001 to 10 000	25
> 10 000	35

(a) For a sample size not exceeding 10 items, no item tested shall give an individual value for water absorption exceeding 0.4 %.

(b) For a sample size between 11 and 25 items, not more than one of the items tested shall give an individual value for water absorption exceeding 0.4 %.

(c) For a sample size between 26 and 35 items, not more than two of the items tested shall give an individual value for water absorption exceeding 0.4 %.

(d) For a sample size between 36 and 50 items, not more than three of the items tested shall give an individual value for water absorption exceeding 0.4 %.

If the criteria for compliance are not met at the minimum sampling level then it shall be permissible for further samples, to a maximum total of 50, to be tested and for compliance to be determined on the cumulative results of all tests performed.

4.2 Crazing

When tested in accordance with appendix B, no item tested shall exhibit crazing when examined as described in B.5.

5 Marking

Each item of vitrified hotelware complying with this standard shall be marked with the following.

(a) The name, trade mark or any other means of identifying the UK manufacturer or responsible supplier.

(b) The number of this British Standard, i.e. BS 4034*.

NOTE. The date of the standard, or the manufacturer's own marking of the date of manufacture (such that it is distinct from the date of the standard) may also be included.

(c) The word(s) 'Vitrified' or 'Vitrified hotelware'.

*Marking BS 4034 on or in relation to a product represents a manufacturer's declaration of conformity, i.e. a claim by or on behalf of the manufacturer that the product meets the requirements of the standard. The accuracy of the claim is therefore solely the responsibility of the person making the claim. Such a declaration is not to be confused with third party certification of conformity, which may also be desirable.

Appendices

Appendix A. Method of test for the determination of water absorption

A.1 Principle

The water absorption (see 2.6) of vitrified hotelware is assessed as the increase in mass which a prepared test piece undergoes as a result of controlled immersion in water, expressed as a percentage of the mass of the dry test piece.

A.2 Apparatus

A.2.1 *Air-circulating oven*, capable of maintaining a temperature of 110 ± 5 °C.

A.2.2 *Desiccator*.

A.2.3 *Balance*, capable of determining masses of between 5 g and 20 g to an accuracy of 0.001 g.

A.2.4 *Vessel*, from which air can safely be removed and in which boiling of the test pieces in water may take place.

A.2.5 *Source of heat*.

A.2.6 *De-gassed distilled or de-gassed de-ionized water*.

A.2.7 *Smooth cotton cloth*.

A.3 Test pieces

Immediately before commencement of the test procedure break the sample, by impact, and take two test pieces of between 5 g and 20 g in mass from areas of the broken sample as follows.

- (a) For flatware, take one test piece from the central area and the second test piece from the rim area of the sample.
- (b) For holloware, take one test piece from the top section and the second test piece from the base area of the sample.

A.4 Procedure

Dry the test pieces to constant mass in an air-circulating oven maintained at 110 ± 5 °C. Cool the test pieces in a desiccator (A.2.2) to ambient temperature. Weigh the test pieces and record their masses to the nearest 0.001 g.

Place the dry test pieces into a vessel (A.2.4), reduce the pressure therein to 2.5 ± 1.5 kPa and maintain at this pressure for 60 ± 5 min.

Without admitting air, admit de-gassed distilled or de-gassed de-ionized water (A.2.6) at ambient temperature to the vessel, until the test pieces are fully covered. Then admit air to the vessel, returning it to atmospheric pressure, and boil the water and test pieces for 60 ± 5 min ensuring that the test pieces remain fully submerged. Allow the test pieces to cool for not less than 24 h whilst remaining submerged in the boiled water.

Remove the test pieces from the water and wipe them with a moistened smooth cotton cloth (A.2.7) such that glazed surfaces are completely dry and broken surfaces retain a thin film of moisture appearing as a sheen. Weigh each test piece and record their masses to the nearest 0.001 g.

A.5 Calculation and expression of results

For each test piece calculate the water absorption as a percentage of the dry mass of the test piece from the following formula:

$$\frac{100 (W_2 - W_1)}{W_1}$$

where

W_1 is the mass of the test piece after drying to constant mass (in g).

W_2 is the mass of the test piece after immersion (in g).

Report the individual results and the arithmetic mean of the two results obtained for each sample.

Appendix B. Method of test for the determination of crazing

B.1 Principle

The crazing (see 2.7) of vitrified hotelware is assessed by subjecting a prepared sample to steam under pressure, then examining the glaze of the cooled sample for crazing with the assistance of a staining agent.

B.2 Apparatus

B.2.1 *Vessel*, which can be sealed and safely pressurized with steam.

B.2.2 *Staining agent*, consisting of a solution of 5 ± 1 g/L eosin and 5 ± 1 g/L domestic washing-up liquid.

B.2.3 *Soft cotton cloth*.

B.3 Sample preparation

Grind three separate circles of diameter 12.5 ± 2.5 mm into the surface of the complete sample, evenly distributed across the sample, such that the glaze is penetrated and the biscuit exposed over the entire area of these circles.

B.4 Procedure

Place the sample into a vessel (B.2.1) in a position where the sample is protected from direct contact with incoming steam and cannot contact any standing water which may result from steam condensation.

Seal the vessel and raise the pressure therein, by means of steam injection, to a maximum pressure of 340 ± 10 kPa and maintain at this pressure for 16 ± 1 h.

Reduce the pressure in the vessel to atmospheric pressure, by release of steam. Remove the sample and allow it to cool naturally to ambient temperature. Immerse the sample completely in the staining agent (B.2.2) for 5 ± 1 min and then dry it by wiping with a soft cotton cloth (B.2.3).

B.5 Assessment of samples

Examine the sample for crazing, exhibited as stained line markings within the glaze.

This British Standard, having been prepared under the direction of the Furniture and Household Equipment Standards Policy Committee, was published under the authority of the Board of BSI and comes into effect on 30 April 1990

© British Standards Institution, 1990

First published June 1966
Second edition April 1990

ISBN 0 580 18349 1

The following BSI references relate to the work on this standard:
Committee reference FHM/29 Draft for comment 89/39906 DC

British Standards Institution. Incorporated by Royal Charter, BSI is the independent national body for the preparation of British Standards. It is the UK member of the International Organization for Standardization and UK sponsor of the British National Committee of the International Electrotechnical Commission.

In addition to the preparation and promulgation of standards, BSI offers specialist services including the provision of information through the BSI Library and Standardline Database; Technical Help to Exporters; and other services. Advice can be obtained from the Enquiry Section, BSI, Milton Keynes MK14 6LE, telephone 0908 221166, telex 825777.

Copyright. Users of British Standards are reminded that copyright subsists in all BSI publications. No part of this publication may be reproduced in any form without the prior permission in writing of BSI. This does not preclude the free use, in the course of

implementing the standard, of necessary details such as symbols and size, type or grade designations. Enquiries should be addressed to the Publications Manager, BSI, Linford Wood, Milton Keynes MK14 6LE. The number for telephone enquiries is 0908 220022 and for telex 825777.

Contract requirements. A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Revision of British Standards. British Standards are revised, when necessary, by the issue either of amendments or of revised editions. It is important that users of British Standards should ascertain that they are in possession of the latest amendments or editions.

Automatic updating service. BSI provides an economic, individual and automatic standards updating service called PLUS. Details are available from BSI Enquiry Section at Milton Keynes, telephone 0908 221166, telex 825777.

Information on all BSI publications is in the BSI Catalogue, supplemented each month by *BSI News* which is available to subscribing members of BSI and gives details of new publications, revisions, amendments and withdrawn standards. Any person who, when making use of a British Standard, encounters an inaccuracy or ambiguity, is requested to notify BSI without delay in order that the matter may be investigated and appropriate action taken.

Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Furniture and Household Equipment Standards Policy Committee (FHM/-) to Technical Committee FHM/29, upon which the following bodies were represented:

Association of Metropolitan Authorities
Association of Public Analysts
British Ceramic Gift and Tableware Manufacturers' Association
British Ceramic Manufacturers Federation
British Ceramic Research Ltd.

British Glass Manufacturers Confederation
British Vitrified Hotelware Association
Consumer Policy Committee of BSI
Department of Health
Department of Trade and Industry (Consumer Safety Unit, CA Division)
Institute of Trading Standards Administration
Institute of Vitreous Enamellers
Stoneware Potters' Association
Vitreous Enamel Development Council

Amendments issued since publication

Amd. No.	Date of issue	Text affected

British Standards Institution · 2 Park Street London W1A 2BS · Telephone 01-629 9000 · Telex 266933