

Specification for

# Metal-Clad Base Materials for Printed Circuits —

**Part 6: Phenolic cellulose paper  
copper-clad laminated sheet of medium  
electrical quality, flame retardant  
grade: PF-CP-Cu-6**

UDC 621.39.049.75 – 217:678.066 – 419

## Co-operating organizations

The Telecommunication Industry Standards Committee, under whose supervision this British Standard was prepared, consists of representatives from the following Government departments and scientific and industrial organizations:

British Broadcasting Corporation	Electronic Valve and Semi-conductor Manufacturers' Association
British Electrical and Allied Manufacturers' Association	Home Office
British Radio Equipment Manufacturers' Association*	Institution of Electrical Engineers
British Radio Valve Manufacturers' Association	Institution of Electronic and Radio Engineers
British Railways Board	Institution of Production Engineers
Cable and Wireless Limited	Ministry of Defence
Crown Agents for Oversea Governments and Administrations	Ministry of Defence, Army Department
Department of Employment and Productivity (HM Factory Inspectorate)	Ministry of Defence, Navy Department*
Department of Trade and Industry	Ministry of Defence, Procurement Executive*
Electrical Contractors Association (Incorporated)	Post Office*
Electrical Research Association*	Radio and Electronic Component Manufacturers' Federation*
Electricity Council, the Central Electricity Generating Board and the Area Boards in England and Wales*	Relay Services Association of Great Britain
Electronic Engineering Association*	Science Research Council — Radio and Space Research Station
	Scientific Instrument Manufacturers' Association*
	Society of British Aerospace Companies*
	Telecommunication Engineering and Manufacturing Association*

The Government departments and scientific and industrial organizations marked with an asterisk in the above list, together with the following, were directly represented on the committee entrusted with the preparation of this British Standard:

British Plastics Federation	Society of Motor Manufacturers and Traders
Institute of Metal Finishing	

This British Standard, having been approved by the Telecommunication Industry Standards Committee, was published under the authority of the Executive Board on 28 July 1972

© BSI 10-1999

The following BSI references relate to the work on this standard:  
Committee references TLE/19 and TLE/19/1  
Draft for comment 70/9525  
Word Processing Centre reference ZZ702

### Amendments issued since publication

Amd. No.	Date of issue	Comments

ISBN 0 580 07423 4

# Contents

	Page
Co-operating organizations	Inside front cover
Foreword	ii
<hr/>	
1 Scope	1
2 Materials and construction	1
3 Marking	1
4 Electrical properties	1
5 Non-electrical properties of the copper-clad sheet	2
6 Non-electrical properties of the base material after complete removal of the copper foil	3
7 Packaging	3
<hr/>	
Table 1 — Mass per unit area and thickness of copper foil	1
Table 2 — Electrical properties	1
Table 3 — Nominal thickness and deviations of metal-clad sheet	2
Table 4 — $d$ Values for bow	2
Table 5 — $e$ Values for twist	2
Table 6 — Pull-off and peel strength requirements	3
Table 7 — Flexural strength and flammability requirements	3
<hr/>	
Publications referred to	Inside back cover
<hr/>	

## Foreword

This Part of the British Standard deals with material designated PF-CP-Cu-6. The letters PF denote phenolic resin, CP denotes cellulose paper, Cu denotes copper and 6 is a serial number.

At present, International Electrotechnical Commission (IEC) Publication 249-2, "*Metal-clad base materials for printed circuits*", Part 2: "*Specification*", does not contain a grade of base material equivalent to PF-CP-Cu-6.

The methods of test referred to by clause number in this specification are given in BS 4584:1970 "*Metal-clad base materials for printed circuits*", Part 1 "*Methods of test*".

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

### Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 to 4, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

## 1 Scope

This British Standard gives requirements for properties of phenolic cellulose paper copper-clad laminated sheet, of medium electrical quality, flame retardant grade.

The standard covers sheet of nominal thicknesses from 1.6 mm to 3.2 mm.

NOTE The title of the British Standard referred to in this standard is given on the inside back cover.

## 2 Materials and construction

The sheet consists of an insulating base with metal foil bonded to one or both sides.

**2.1 Insulating base.** Phenolic resin bonded cellulose paper laminate. It is flame retardant in terms of the requirements of Clause 6.2.

**2.2 Metal foil.** Copper, as specified in Table 1.

**Table 1 — Mass per unit area and thickness of copper foil**

Mass per unit area		Thickness	
Nominal	Limits	Nominal	Limits
g/m <sup>2</sup>	g/m <sup>2</sup>	μm	μm
305	275–335	35	30–45
610	545–675	70	62–88

Measurements to determine that the foil meets the above requirements before incorporation in the laminate shall be made in accordance with Clause 2.4 of BS 4584-1.

For information only;      minimum purity      99.5 %  
    minimum conductivity      95 % of the value equivalent to a resistivity  
    of  $1.7241 \times 10^{-8} \Omega \text{ m}$  at 20 °C.

## 3 Marking

It is preferred that each sheet should bear a manufacturer's identification mark that is:

- 1) red to indicate that the grade is flame retardant;
- 2) repeated at intervals so that no part of the sheet is further than 75 mm from the nearest mark;
- 3) printed so as to indicate the machine direction of the filler.

NOTE Attention is drawn to the certification facilities offered by BSI; see the inside back cover of this standard.

## 4 Electrical properties

When the sheet is tested by the methods shown in Table 2, it shall comply with the limits listed therein.

**Table 2 — Electrical properties**

Property	Test method of BS 4584-1, Clause	Requirement
Resistance of foil		
of 305 g/m <sup>2</sup>	<b>2.1.2</b>	3.5 mΩ max.
of 610 g/m <sup>2</sup>		1.75 mΩ max.
Surface resistance after damp heat and recovery	<b>2.1.3.3</b>	1 000 MΩ min.
Volume resistivity after damp heat and recovery	<b>2.1.3.3</b>	500 MΩ m min.
Surface resistance at 100 °C	<b>2.1.3.5</b>	15 MΩ min.
Volume resistivity at 100 °C	<b>2.1.3.5</b>	10 MΩ m min.
Permittivity after damp heat, steady state	<b>2.1.5</b>	7.0 max.
Loss tangent after damp heat, steady state	<b>2.1.5</b>	0.08 max.

## 5 Non-electrical properties of the copper-clad sheet

**5.1 Appearance of the copper-clad face.** The copper-clad face shall be substantially free from blisters, wrinkles, pinholes, deep scratches, pits and resin. Any discoloration or contamination shall be readily removable with a hydrochloric acid solution of density 1 020 kg/m<sup>3</sup> or with a suitable organic solvent.

**5.2 Thickness.** The thickness of a sheet, including the metal foil, shall not depart at any point from the nominal thickness by more than the appropriate value shown in Table 3.

**Table 3 — Nominal thickness and deviations of metal-clad sheet**

Nominal thickness mm		Deviation ± mm
Preferred	Non-preferred	
1.6	—	0.14
—	2.0	0.15
2.4	—	0.18
3.2	—	0.20

For any other value of nominal thickness, the deviation shall be that shown in Table 3 for the next greater thickness.

**5.3 Bow.** When the sheet is tested by the method given in Clause 2.2.1 of BS 4584-1, the bow shall not exceed the value given by the formula  $d (L/1\ 000)^2$  mm, where  $L$  is the length of the straight-edge in millimetres and  $d$  is as given in Table 4.

**Table 4 —  $d$  Values for bow**

Nominal thickness mm	Copper foil on one side		Copper foil on both sides
	305 g/m <sup>2</sup>	610 g/m <sup>2</sup>	305 or 610 g/m <sup>2</sup>
	$d$	$d$	$d$
1.6	61	76	30
over 1.6 to 1.8	50	63	30
over 1.8 to 3.2	46	53	15

The values shown in Table 4 apply only if length and width are each at least 460 mm.

When the sheet is tested by the method given in Clause 2.2.3 of BS 4584-1, the twist shall not exceed the value given by the formula  $e (M/1\ 000)^2$  mm, where  $M$  is the length in millimetres of the diagonal of the sheet and  $e$  is as given in Table 5.

**Table 5 —  $e$  Values for twist**

Nominal thickness mm	Copper foil on one side		Copper foil on both sides
	305 g/m <sup>2</sup>	610 g/m <sup>2</sup>	305 or 610 g/m <sup>2</sup>
	$e$	$e$	$e$
1.6	13	18	10
over 1.6 to 1.8	9	14	6
over 1.8 to 3.2	7	10	5

The values shown in Table 5 apply only if length and width are each at least 460 mm.

**5.4 Punching.** The sheet shall be capable of being punched in accordance with the recommendations of the manufacturer of the sheet.

**5.5 Solderability.** When the sheet is tested by the method given in Clause 2.2.9 of BS 4584-1, and in accordance with the times specified below, the soldered area of each specimen shall be covered with a smooth and bright solder coating with not more than traces (approximately 5 %) of scattered imperfections, e.g. small holes or unwetted or de-wetted areas.

- 1) Wetting test. *a.* Plate and matt finish material: the specimen shall wet within 2 s.
- 2) De-wetting test. *a.* Plate finish material: the specimen shall remain in contact with the molten solder for  $5^{+1}_0$  s.  
*b.* Matt finish material: no test available.

**5.6 Other properties of the copper-clad sheet.** When the sheet is tested by the methods shown in Table 6 it shall comply with the limits therein.

**Table 6 — Pull-off and peel strength requirements**

Property	Test method of BS 4584-1, Clause	Requirement
Pull-off strength	<b>2.2.5</b>	45 N min.
Peel strength after heat shock	<b>2.2.6.2</b> Solder temperature $245 \pm 2$ °C Time of contact 5 s	1.05 kN/m min. No delamination or blistering
Peel strength after dry heat at 100 °C	<b>2.2.6.3</b>	1.05 kN/m min. No delamination or blistering
Peel strength after exposure to solvent vapour (trichlorethylene)	<b>2.2.6.4</b>	1.05 kN/m min. No delamination or blistering
Peel strength after exposure to simulated plating conditions	<b>2.2.6.5</b>	0.6 kN/m min.

## 6 Non-electrical properties of the base material after complete removal of the copper foil

**6.1 Appearance of base material.** The base material shall be substantially free from pits, holes, scratches, surface porosity, foreign matter, conductive particles and resin inclusions and shall be substantially uniform in colour. A small amount of irregular variation of colour is permissible.

**6.2 Other properties of the base material after complete removal of the copper foil.** When the sheet is tested by the methods shown in Table 7 it shall comply with the limits listed therein.

**Table 7 — Flexural strength and flammability requirements**

Property	Test method of BS 4584-1, Clause	Requirement
Flexural strength	<b>2.3.1</b>	82 MN/m <sup>2</sup> min.
Flammability	<b>2.3.2</b>	1) average of four burning times not to exceed 15 s; 2) no individual burning time shall exceed 20 s; 3) no burning beyond the 25 mm line of any specimen shall occur; 4) the material shall not drip.

## 7 Packaging

The sheets shall be adequately packed and protected in cases or crates to avoid damage and contamination in transit and during storage.





## Publications referred to

This standard makes reference to the following British Standard:

BS 4584, *Metal-clad base materials for printed circuits.*

BS 4584-1, *Methods of test.*

---

### BSI Certification Trade Mark

#### The Kitemark

The British Standards Institution is the owner of a registered certification trade mark. It is usually associated with the words “approved to British Standard” as shown below, the number of the relevant British Standard being added. This mark may be used only by those licensed under the certification mark scheme operated by BSI. The presence of this mark on or in relation to a product is an assurance that the goods have been produced under a system of supervision, control and testing, operated during manufacture and including periodical inspection of the manufacturer’s works in accordance with the certification mark scheme of BSI designed to ensure compliance with a British Standard.

Further particulars, of the terms of licence may be obtained from the Quality Assurance Department, British Standards Institution, Maylands Avenue, Hemel Hempstead, Herts.

---

---

## **BSI — British Standards Institution**

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### **Revisions**

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### **Buying standards**

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### **Information on standards**

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

### **Copyright**

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.