

BSI

BS 4939 : 1987
ISO 3416-1986

UDC 645.13-037:677.017.224:620.173.27

ORIGINAL

Inchcape Testing Services
<< COPY >>

© British Standards Institution. No part of this publication may be photocopied or otherwise reproduced without the prior permission in writing of BSI.

CONTROL

ORIGINAL

British Standard Method for

Determination of thickness loss of textile floor coverings after prolonged heavy static loading

Méthode de détermination de la perte d'épaisseur des revêtements de sol textiles après application prolongée d'une charge statique élevée

Verfahren zur Bestimmung der Dickenminderung an textilen Bodenbelägen nach längerer statischer Belastung

POLYMER LABORATORY
Research Collection

ORIGINAL

Contents

	Page		Page
National foreword	Inside front cover	5. Atmosphere for conditioning and testing	1
Committees responsible	Back cover	6. Test specimens	1
Method		7. Preparation of test specimens	1
1. Scope and field of application	1	8. Procedure	2
2. References	1	9. Expression of results	2
3. Principle	1	10. Test report	2
4. Apparatus	1	Annex	

CONTROLLED

ORIGINAL

National foreword

This British Standard has been prepared under the direction of the Textiles and Clothing Standards Committee. It is identical with ISO 3416-1986 'Textile floor coverings - Determination of thickness loss after prolonged heavy static loading', published by the International Organization for Standardization (ISO). It is the second revision of BS 4939, first published in 1973 and it supersedes BS 4939 : 1980, which is withdrawn.

Terminology and conventions. The text of the international standard has been approved as suitable for publication as a British Standard without deviation. Some terminology and certain conventions are not identical with those used in British Standards; attention is drawn especially to the following.

The comma has been used as a decimal marker. In British Standards it is current practice to use a full point on the baseline as the decimal marker.

Wherever the words 'International Standard' appear, referring to this standard, they should be read as 'British Standard'.

Cross-references

International standard	Corresponding British Standard
ISO 139-1973	BS 1051 : 1981 Glossary of terms relating to the conditioning, testing and mass determination of textiles (Technically equivalent)
ISO 1765-1986	BS 4051 : 1987 Method for determination of thickness of textile floor coverings (Identical)
ISO 1957-1986	BS 4654 : 1985 Methods for sampling and cutting specimens of textile floor coverings for physical tests (Technically equivalent)

Compliance with a British Standard does not of itself confer immunity from legal obligations.

British Standard Method for

Determination of thickness loss of textile floor coverings after prolonged heavy static loading

ORIGINAL

CONTROLLED

ORIGINAL

1 Scope and field of application

This International Standard specifies a method for determination of thickness loss of textile floor coverings after prolonged, heavy static loading. It is applicable to all textile floor coverings of uniform thickness and construction. It does not apply to other textile floor coverings unless the areas of different thickness or construction can be separately tested.

NOTE — A method for determination of thickness loss of textile floor coverings after brief, moderate static loading is given separately in ISO 3415.

2 References

ISO 139, *Textiles — Standard atmospheres for conditioning and testing.*

ISO 1765, *Machine-made textile floor coverings — Determination of thickness.*

ISO 1957, *Machine-made textile floor coverings — Sampling and cutting specimens for physical tests.*

3 Principle

Subjection of a test specimen to a prolonged, heavy static loading treatment, the thickness being measured before loading and after various recovery periods.

4 Apparatus

4.1 Thickness tester, with circular presser foot of area between 300 and 1 000 mm² and capable of measuring thickness to an accuracy of 0,1 mm at the standard pressure of $2,00 \pm 0,2$ kPa* as defined in ISO 1765.

4.2 Five alloy specimen plates, each measuring 100 mm × 100 mm and approximately 6 mm thick.

4.3 Static loading machine, capable of applying a pressure of 700 kPa through a circular presser foot of radius at least

2 mm larger than the radius of the presser foot of the thickness tester, and which is constrained to move vertically. A suitable apparatus is described in the annex.

4.4 Double-sided adhesive tape.

4.5 Straightedge, for example a ruler, for brushing the surface of the specimen.

5 Atmosphere for conditioning and testing

The specimens shall be conditioned and all measurements made in the standard atmosphere for conditioning and testing textiles specified in ISO 139.

Preconditioning in a dry atmosphere before conditioning in the standard atmosphere for testing is not required.

6 Test specimens

Cut out at least five specimens, each measuring 100 mm × 100 mm, following the sampling procedure specified in ISO 1957.

7 Preparation of test specimens

7.1 Attach double-sided adhesive tape across the four corners of a specimen plate, pressing down firmly to ensure adhesion. Measure to the nearest 0,1 mm the thickness d_1 of the plate in the centre at the standard pressure.

7.2 Remove any backing paper and mount a test specimen, use-surface uppermost, on to the prepared specimen plate, pressing down at the corners sufficiently to ensure adhesion.

7.3 For specimens with a pile, lightly brush the use-surface firstly against, then with, the direction of pile length, using a straightedge. Allow the mounted test specimens to condition in the standard atmosphere for testing textiles, first, singly and use-surface uppermost, for at least 24 h.

Inchcape Testing Services
« COPY »

ORIGINAL

8 Procedure

8.1 General

Conduct the test in the standard atmosphere for testing textiles. Make all determinations of thickness to the nearest 0.1 mm.

8.2 Measurement of initial thickness

Measure the thickness of the conditioned and mounted specimen at the standard pressure (see 4.1) in the centre to obtain the total thickness d_2 of test specimen and plate.

8.3 Application of pressure

Place the measured specimen on the static loading machine so that the presser foot is central, and apply the specified pressure. Leave undisturbed for 24 h.

8.4 Measurement of thickness after recovery

Remove the mounted specimen from the static loading machine, place it on the thickness tester and re-measure the thickness of the assembly within the compressed area after recovery for 2 min.

Leave the specimen use-surface uppermost and without load during recovery periods and re-measure the thickness after total recovery times of 1 h and 24 h at the same place of the compressed area.

NOTE -- It is most convenient, if several static loading machines are used in conjunction with one thickness tester, to test several specimens at the same time.

9 Expression of results

9.1 Calculate the original thickness of each specimen by the difference $d_2 - d_1$ and express the result in millimetres, to the nearest 0.1 mm.

9.2 Calculate the thickness losses at each stage for each specimen, to the nearest 0.1 mm.

9.3 Calculate the arithmetic mean of the results (original thickness and thickness loss at each recovery stage).

ORIGINAL

CONTROLLED

10 Test report

The test report shall include the following particulars :

- a) that the procedure was conducted in accordance with this International Standard, and details of any operations not included, or optional;
- b) the original thickness of each specimen and the mean original thickness;
- c) the thickness loss at each recovery stage for each specimen and the arithmetic mean of the results for each recovery stage.

Annex

Static loading machine

(This annex forms an integral part of the Standard.)

ORIGINAL

Intertape Testing Services
 << COPY >>

A suitable static loading machine, meeting the requirements specified in 4.3, is based upon a lever system as shown in the figure below. In this, A is a fixed pivot point and the loading beam is extended backwards for counter-weight C to balance the weight of the beam. B is an oilite bearing constraining the circular presser foot P to move vertically and apply the load to the test specimen S.

The ratio y/x is chosen so that mass m applies a pressure of 700 kPa on the circular presser foot, of area A mm².

$$m = 7.4 \times \frac{y}{x} \times 10^{-2} \text{ kg}$$

ORIGINAL

CONTROLLED

