

Structural use of timber —

Part 7: Recommendations for the calculation basis for span tables —

Section 7.1 Domestic floor joists

UDC [624.011.1 + 674.038.5 + 691.1.11]:[692.526:694.5]:001.4

Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Civil Engineering and Building Structures Standards Committee (CSB/-) to Technical Committee CSB/32 upon which the following bodies were represented:

British Woodworking Federation
 Building Employers' Confederation
 Chartered Institute of Building
 Department of the Environment (Building Research Establishment, Princes Risborough Laboratory)
 Department of the Environment for Northern Ireland
 Department of the Environment (Housing and Construction Industries)
 Department of the Environment (Property Services Agency)
 Health and Safety Executive
 Incorporated Association of Architects and Surveyors
 Institute of Clerks of Works of Great Britain Inc.
 Institute of Wood Science
 Institution of Civil Engineers
 Institution of Structural Engineers
 International Truss Plate Association
 National House-building Council
 Royal Institute of British Architects
 Royal Institution of Chartered Surveyors
 Timber Research and Development Association
 Timber Trade Federation
 Coopted members

This British Standard, having been prepared under the direction of the Civil Engineering and Building Structures Standards Committee, was published under the authority of the Board of BSI and comes into effect on 30 June 1989

© BSI 03-1999

The following BSI references relate to the work on this standard:
 Committee reference CSB/32
 Draft for comment 84/11849 DC

ISBN 0 580 16586 8

Amendments issued since publication

Amd. No.	Date of issue	Comments

Contents

	Page
Committees responsible	Inside front cover
Foreword	ii
1 Scope	1
2 Definitions	1
3 Symbols	1
4 Design considerations	2
5 Permissible spans	3
6 Bearing length	6
7 Information to be given in span tables	6
Appendix A Sample calculation for a domestic floor joist	7
Appendix B Specimen span tables for domestic floor joists	9
Figure 1 — Bearing length, permissible effective and permissible clear span	5
Table 1 — Permissible clear spans for domestic floor joists: SC3: regularised sizes	9
Table 2 — Permissible clear spans for domestic floor joists: redwood/whitewood, SS grade, basic sizes	10
Table 3 — Permissible clear spans for domestic floor joists: spruce-pine-fir, joist and plank no. 2 grade, CLS sizes	11
Publications referred to	Inside back cover

Foreword

This Section of Part 7 of BS 5268 has been prepared under the direction of the Civil Engineering and Building Structures Standards Committee.

The general principles for the design of structural timber components are given in BS 5268-2 and using these principles it is possible for span tables to be prepared for a wide range of components.

Experience has shown that different interpretations of these principles has led to inconsistencies in span tables prepared by different compilers. It is the purpose of BS 5268-7 to eliminate these differences by recommending the design equations and the loading to be used in the preparation of span tables. Part 7 is intended to ensure that different organizations produce span tables on a consistent basis in the future, and is not necessarily intended for use by designers for individual designs carried out in their day-to-day work, where simplified equations may produce adequate designs. This Section deals with domestic floor joists. Other Sections of BS 5268-7, published or in preparation, are as follows.

- *Section 7.2: Joists for flat roofs;*
- *Section 7.3: Ceiling joists;*
- *Section 7.4: Ceiling binders;*
- *Section 7.5: Rafters;*
- *Section 7.6: Purlins supporting rafters;*
- *Section 7.7: Purlins supporting sheeting or decking.*

BS 5268-2 gives grade stresses for very many combinations of species and grade and it is considered impractical to publish in a British Standard span tables for all possible combinations of species, grades and sizes. BS 5268-7 is therefore restricted to the basis of the calculations.

The solution of the design equations for many combinations of geometry and material is most conveniently undertaken by computer. A program written by the Timber Research and Development Association (TRADA) was used to prepare Appendix A and Appendix B. For users wishing to prepare their own span tables or computer programs Appendix A gives a sample calculation. Appendix B gives span tables for three typical combinations of species and grade. Although the presentation of span tables is not covered in BS 5268-7, it is recommended that tables for predetermined domestic floor joist centres and loading follow this format.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 to 12, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

1 Scope

This Section of BS 5268 recommends a calculation basis for the permissible clear span for simply supported domestic floor joists of solid timber. The recommendations apply to joists at a maximum spacing of 610 mm centre-to-centre, this being the maximum spacing for which the "load-sharing" assumption may be adopted as described in BS 5268-2. The method of calculation makes no allowance for any contribution of the flooring to the load resistance of the joists where such action can be provided by adequate attachments between the elements as in a stressed skin panel floor. Only uniform loading is considered and concentrated or line loads applied by partitions, trimmers and other similar causes are excluded.

This Section of BS 5268 is applicable to the species and grades of timber given in BS 5268-2.

NOTE The titles of the publications referred to in this standard are listed on the inside back cover.

2 Definitions

For the purposes of this Section of BS 5268, the definitions given in BS 6100-4.1 to BS 6100-4.4, BS 6100-2.1 and BS 5268-2 apply, together with the following.

2.1

grade stress

stress that can safely be permanently sustained by material of a specific section size and of a particular strength class or species and grade

2.2

load-sharing system

assembly of pieces or members that are constrained to act together to support a common load

2.3

permissible stress

stress that can safely be sustained by a structural material under a particular condition

NOTE For the purpose of this Section of BS 5268 it is the product of the grade stress and the appropriate modification factors for section size, service and loading.

2.4

strength class

classification of timber based on particular values of grade stress

2.5

bearing length

length at each end of the joist in contact with the support

2.6

notional bearing length

bearing length required for the calculation of permissible clear spans

2.7

effective span

span from centre-to-centre of the minimum bearing lengths at each end

2.8

permissible effective span

lowest value of effective span found from the calculations for bending strength, shear strength and deflection

2.9

permissible clear span

permissible unsupported span of a joist, measured between the faces of the supports at its two ends

NOTE Permissible clear span is equal to permissible effective span less the notional bearing length.

3 Symbols

For the purposes of this Section of BS 5268, the following symbols apply.

NOTE The symbols used are generally in accordance with ISO 3898, published by the International Organization for Standardization, supplemented by the recommendations of CIB-W18-1 "Symbols for use in structural timber design", published by the International Council for Building Research Studies and Documentation, which takes particular account of timber properties.

The symbols used are:

a	Distance (notional bearing length)
b	Breadth of joist
E	Modulus of elasticity
F	Total load per metre length
F_d	Dead load per square metre applied by mass of ceiling and flooring materials (excluding joist self weight)
F_j	Self weight of joist per metre length
G	Shear modulus
h	Depth of joist
l	Second moment of area
K	Modification factor (always with a subscript)
L	Effective span
L_{adm}	Permissible effective span
L_{cl}	Permissible clear span
M	Bending moment
s	Spacing of joists, centre-to-centre
w	Deflection
Z	Section modulus
ρ	Density
σ	Stress
τ	Shear stress

The following subscripts are used:

a) **Type of force, stress etc.**

- c Compression
m Bending

b) **Significance**

- adm Permissible
cl Clear
g Grade
max Maximum

c) **Geometry**

- tra or \perp Perpendicular (to the grain)

It is recommended that where more than one subscript is used, the categories should be separated by commas.

Subscripts may be omitted when the context in which the symbols are used is unambiguous except in the case of modification factor K .

4 Design considerations

4.1 General

The design calculations recommended by this Section of BS 5268 are based on engineers' bending theory and are consistent with the recommendations of BS 5268-2. The design method ensures that the permissible bending and shear stresses as given in BS 5268-2, are not exceeded and that the deflection does not exceed the recommended limit of 0.003 times the span or 14 mm (see 14.7 of BS 5268-2:1988), whichever is smaller.

NOTE A sample calculation is given in Appendix A and Table 1 to Table 3 in Appendix B contain specimen span tables.

4.2 Qualifying assumptions

The calculations given in this Section apply to systems of at least four domestic floor joists, at a maximum spacing of 610 mm centre-to-centre and having adequate flooring to provide lateral load distribution. Because load sharing takes place the load sharing modification factor K_8 and the mean modulus of elasticity should be used.

Lateral support should be provided in accordance with 14.8 of BS 5268-2:1988.

The bearing length required at each end of the joist, calculated in accordance with 5.5, may not be sufficient for practical construction purposes.

4.3 Loading

The design calculations provide for domestic floor loads which consist of the following.¹⁾

a) *Imposed load*

1) for an effective span equal to or greater than 2 400 mm, the imposed load is 1.5 kN/m² uniformly distributed;

2) for an effective span less than 2 400 mm, the imposed load is 3.6 kN per metre width of floor (measured perpendicular to the span) uniformly distributed over the span.

NOTE This imposed load of 1.5 kN/m² entirely fulfils the recommendations of BS 6399-1. The maximum imposed load of 3.6 kN per metre width is a more onerous load applied to ensure that very small joist sizes do not result from the calculations for small spans.

The imposed load should be considered to be a long term load.

b) *Dead load*. Dead load per square metre F_d (in kN/m²) to provide for the mass of ceiling and flooring materials, pugging, etc. Weights of materials are given in BS 648.

c) *Self weight*. Self weight per metre length F_j (in kN/m) to provide for the mass of the joist. The timber densities (in kg/m³), given in Tables 9 and 92 of BS 5268-2:1988 should be used.

4.4 Design loads

The total load per metre length of span, F , is found in different ways depending on whether the span is less than or greater than 2 400 mm.

For spans equal to or greater than 2 400 mm F (in kN/m) is given by the equation

$$F = (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \quad (1)$$

For spans equal to or less than 2 400 mm F (in kN/m) is given by the equation

$$F = \left(\frac{3600}{L} + F_d \right) \left(\frac{s}{1000} \right) + F_j \quad (2)$$

where

- s is the joist spacing (in mm);
 L is the effective span (in mm);
 F_d is the dead load (in kN/m²);
 F_j is the self weight of joist (in kN/m).

NOTE At a span of 2 400 mm, equations (1) and (2) give the same value for F .

¹⁾ Concentrated or line loads applied by partitions, trimmers and other similar causes are excluded.

The value of F_j (in kN/m) may be found from the equation

$$F_j = 9.80665 \times 10^{-9} p b h \quad (3)$$

where

ρ is the timber density (in kg/m³);

b is the joist breadth (in mm);

h is the joist depth (in mm).

NOTE The value of F is regarded as being in N/mm in the equations given in clause 5, where all values are in newtons and millimetres because BS 5268-2 gives stresses in N/mm².

5 Permissible spans

5.1 General

The permissible effective span of a timber joist subjected to the applied loads given in 4.3 should be the shortest effective span resulting from calculations for bending strength, shear strength and deflection, as given in 5.2, 5.3 and 5.4.

The permissible clear span should be calculated as the permissible effective span less the notional bearing length, calculated in accordance with 5.5.

5.2 Limitation of bending stress

From BS 5268-2, the permissible bending stress $\sigma_{m,adm}$ (in N/mm²) is given by the equation

$$\sigma_{m,adm} = \sigma_{m,g} K_3 K_7 K_8 \quad (4)$$

where

$\sigma_{m,g}$ is the grade bending stress (in N/mm²) (see BS 5268-2);

K_3 is the load duration modification factor, 1.0 for long term (see Table 17 of BS 5268-2:1988);

K_7 is the section depth modification factor (see 14.6 of BS 5268-2:1988);

K_8 is the load sharing modification factor, 1.1 (see clause 13 item a) of BS 5268-2:1988).

Expanding the equation

$$\sigma_{m,adm} = \frac{M}{Z} \quad (5)$$

leads to the following equations.

Effective span, $L, \geq 2\ 400$ mm

$$\begin{aligned} \sigma_{m,g} \times 1.0 \times K_7 \times 1.1 \\ = \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} \frac{L^2}{8} \frac{6}{bh^2} \end{aligned} \quad (6)$$

Effective span, $L, \leq 2\ 400$ mm

$$\begin{aligned} \sigma_{m,g} \times 1.0 \times K_7 \times 1.1 \\ = \left\{ \left(\frac{3600}{L} + F_d \right) \left(\frac{s}{1000} \right) + F_j \right\} \frac{L^2}{8} \frac{6}{bh^2} \end{aligned} \quad (7)$$

NOTE These equations lead to the following polynomials in L .
 $L \geq 2\ 400$ mm

$$\begin{aligned} \frac{3}{4bh^2} \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} L^2 - \\ - \sigma_{m,g} \times 1.0 \times K_7 \times 1.1 = 0 \end{aligned} \quad (8)$$

$L \leq 2\ 400$ mm

$$\begin{aligned} \frac{3}{4bh^2} \left\{ F_d \left(\frac{s}{1000} \right) + F_j \right\} L^2 + \frac{2700}{bh^2} \left(\frac{s}{1000} \right) L - \\ - \sigma_{m,g} \times 1.0 \times K_7 \times 1.1 = 0 \end{aligned} \quad (9)$$

5.3 Limitation of shear stress

From BS 5268-2, the permissible shear stress τ_{adm} (in N/mm²) is given by the equation

$$\tau_{adm} = \tau_g K_3 K_8 \quad (10)$$

where

τ_g is the grade shear stress (in N/mm²) (see BS 5268-2);

K_3 is the load duration modification factor, 1.0 for long term (see Table 17 of BS 5268-2:1988);

K_8 is the load sharing modification factor, 1.1 (see clause 13 item a) of BS 5268-2:1988).

Expanding the equation

$$\tau_{adm} = \frac{3}{2} \frac{FL}{2bh} \quad (11)$$

leads to the following equations.

Effective span $L \geq 2\ 400$ mm

$$\begin{aligned} \tau_g \times 1.0 \times 1.1 \\ = \frac{3}{2} \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} \frac{L}{2bh} \end{aligned} \quad (12)$$

Effective span $L \leq 2\ 400$ mm

$$\begin{aligned} \tau_g \times 1.0 \times 1.1 \\ = \frac{3}{2} \left\{ \left(\frac{3600}{L} + F_d \right) \left(\frac{s}{1000} \right) + F_j \right\} \frac{L}{2bh} \end{aligned} \quad (13)$$

NOTE These equations lead to the following polynomials in L .

$L \geq 2\ 400\ \text{mm}$

$$\frac{3}{4bh} \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} L - \tau_g \times 1.0 \times 1.1 = 0 \quad (14)$$

$L \leq 2\ 400\ \text{mm}$

$$\frac{3}{4bh} \left\{ F_d \left(\frac{s}{1000} \right) + F_j \right\} L + \frac{2700}{bh} \left(\frac{s}{1000} \right) - \tau_g \times 1.0 \times 1.1 = 0 \quad (15)$$

5.4 Limitation of deflection

From BS 5268-2, the recommended deflection limitation W_{max} (in mm) is given by the equation

$$W_{\text{max}} = 0.003\ L \quad (16)$$

with an overriding limitation of 14 mm (see 14.7 of BS 5268-2:1988).

The design equation limiting deflection²⁾ is

$$w_{\text{max}} = \frac{5}{384} \frac{FL^4}{EI} + \frac{3}{20} \frac{FL^2}{Gb} \quad (17)$$

where E is the mean modulus of elasticity.

Taking G as $\frac{E}{16}$ (see clause 11 of BS 5268-2:1988), leads to the equation

$$w_{\text{max}} = \frac{5}{384} \frac{FL^4}{EI} + \frac{12}{5} \frac{FL^2}{Ebh} \quad (18)$$

or, inserting the expressions for equivalent uniformly distributed load, for an effective span $L \geq 2\ 400\ \text{mm}$

$$w_{\text{max}} = \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} \times \left(\frac{5}{384} \frac{L^4}{EI} + \frac{12}{5} \frac{L^2}{Ebh} \right) \quad (19)$$

and for an effective span $L \leq 2\ 400\ \text{mm}$

$$w_{\text{max}} = \left\{ \left(\frac{3600}{L} + F_d \right) \left(\frac{s}{1000} \right) + F_j \right\} \times \left(\frac{5}{384} \frac{L^4}{EI} + \frac{12}{5} \frac{L^2}{Ebh} \right) \quad (20)$$

With a deflection limitation of $0.003L$ for an effective span $L \geq 2\ 400\ \text{mm}$

$$0.003L = \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} \times \left(\frac{5}{384} \frac{L^4}{EI} + \frac{12}{5} \frac{L^2}{Ebh} \right) \quad (21)$$

and for an effective span $L \leq 2\ 400\ \text{mm}$

$$0.003L = \left\{ \left(\frac{3600}{L} + F_d \right) \left(\frac{s}{1000} \right) + F_j \right\} \times \left(\frac{5}{384} \frac{L^4}{EI} + \frac{12}{5} \frac{L^2}{Ebh} \right) \quad (22)$$

A further design equation is required for the 14mm limitation on deflection of spans greater than or equal to 2 400 mm: this is similar to equation (21) but with “0.003L” replaced by “14”. The deflection of spans less than 2 400 mm will be limited to less than 14 mm by equation (22).

NOTE The three design equations lead to the following polynomials in L .

Limitation 0.003L

$L \geq 2400\ \text{mm}$

$$\frac{5}{32Ebh^3} \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} L^3 + \frac{12}{5Ebh} \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} L - 0.003 = 0 \quad (23)$$

$L \leq 2400\ \text{mm}$

$$\frac{5}{32Ebh^3} \left\{ F_d \left(\frac{s}{1000} \right) + F_j \right\} L^3 + \frac{1125}{2Ebh^3} \left(\frac{s}{1000} \right) L^2 + \frac{12}{5Ebh} \left\{ F_d \left(\frac{s}{1000} \right) + F_j \right\} L + \frac{8640}{Ebh} \left(\frac{s}{1000} \right) - 0.003 = 0 \quad (24)$$

Limitation 14 mm

$L \geq 2400\ \text{mm}$

$$\frac{5}{32Ebh^3} \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} L^4 + \frac{12}{5Ebh} \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} L^2 - 14 = 0 \quad (25)$$

²⁾ In addition to the deflection due to bending the shear deflection may be significant and has been taken into account.

Licensed Copy: Puan Ms. Norhayati, Petroliaam Nasional Berhad, 07 November 2002, Uncontrolled Copy, (c) BSI

5.5 Permissible clear spans

The calculation of clear span requires the deduction of a notional bearing length from an effective span.

The calculation of the notional bearing length to be deducted from the permissible effective span to produce the clear span is made after finding L_{adm} , the smallest of the effective spans for a given cross section, as limited by:

- bending stress, $L \geq 2\ 400$ mm;
- bending stress, $L \leq 2\ 400$ mm;
- shear stress, $L \geq 2\ 400$ mm;
- shear stress, $L \leq 2\ 400$ mm;
- deflection, limitation $0.003L$, $L \geq 2\ 400$ mm;
- deflection, limitation $0.003L$, $L \leq 2\ 400$ mm;
- deflection, limitation 14 mm.

From BS 5268-2, the permissible compression perpendicular to the grain stress $\sigma_{c,\perp,adm}$ (in N/mm^2) is given by the equation

$$\sigma_{c,\perp,adm} = \sigma_{c,\perp,g} K_3 K_8 \quad (26)$$

where

- $\sigma_{c,\perp,g}$ is the grade compression perpendicular to the grain stress (in N/mm^2) (see BS 5268-2)^a;
- K_3 is the load duration modification factor, 1.0 for long term (see Table 17 of BS 5268-2:1989);
- K_8 is the load sharing modification factor, 1.1 (see clause 13 item a) of BS 5268-2:1989).

^a BS 5268-2 provides two values for the grade compression perpendicular to the grain stress. When the specification specifically prohibits wane at bearing areas, the higher value may be used, otherwise the lower level applies. (See footnotes to Tables 9, 10, 11, 12, and 13 in BS 5268-2:1988.) The span table should indicate whether wane is permitted.

The notional bearing length a (in mm) required at each end should be found from the equation

$$\sigma_{c,\perp,adm} b a = \frac{F L_{adm}}{2} \quad (27)$$

where

b is the breadth of the joist (in mm);

L_{adm} is the permissible effective span (in mm).

Inserting the expressions for F , equation (27) gives for an effective span $L \geq 2\ 400$ mm

$$\sigma_{c,\perp,g} \times 1.0 \times 1.1 b a = \left\{ (1.5 + F_d) \left(\frac{s}{1000} \right) + F_j \right\} \frac{L_{adm}}{2} \quad (28)$$

for $L \leq 2\ 400$ mm

$$\sigma_{c,\perp,g} \times 1.0 \times 1.1 b a = \left\{ \left(\frac{3600}{L_{adm}} + F_d \right) \left(\frac{s}{1000} \right) + F_j \right\} \frac{L_{adm}}{2} \quad (29)$$

The equation corresponding to the loading condition governing the permissible effective span should be solved for a , and half the value of a should be deducted from each end of the span (total deduction a , see Figure 1) to give the permissible clear span. L_{cl} (in mm) is given by the equation

$$L_{cl} = L_{adm} - a \quad (30)$$




Figure 1 — Bearing length, permissible effective and permissible clear span

6 Bearing length

Although correct for the calculation of clear span the procedure given in 5.5 for the calculation of notional bearing length may not ensure that the permissible compression perpendicular to the grain stress is not exceeded for all loading cases.

The design of some members may be governed by a loading case which does not represent the greatest total load of all loading cases. For example, the governing design case may include a concentrated load, but another less critical loading case may consist of a greater total load uniformly distributed along the span.

7 Information to be given in span tables

There are many possible formats for span tables. A typical format suitable for domestic floor joists at predetermined centres and for quoted loading is given in Appendix B.

This Section of BS 5268 does not recommend formats for different components but whatever format is used the following information should be given in the heading or in the main body or in the footnotes of the span tables, or in an introduction to the tables:

- a) the loading;
- b) details of the arrangement of the members;
- c) the member sizes and their maximum permissible deviations and/or the standards that define these quantities;
- d) the species, stress grade or strength class and/or the standards that define these properties;
- e) a statement specifying any requirements additional to those given in the stress grading rules, e.g. whether wane is prohibited at bearings;
- f) a statement that the spans have been calculated in accordance with the recommendations of BS 5268-2 and BS 5268-7.1;
- g) a statement specifying any structural requirements that may be necessary to comply with the qualifying assumptions made in 4.2, e.g. lateral support requirements, accommodation of lateral thrust at supports;
- h) the permissible clear spans.

Appendix A Sample calculation for a domestic floor joist

The object is to find the permissible clear span, given the following data as applicable to a particular design case.

Timber	Strength class SC3		(see Tables 3 to 6 of BS 5268-2:1988)
Dimensions	Joist breadth, b	= 50 mm	
	Joist depth, h	= 122 mm	
	Joist spacing, s	= 600 mm	
Loading	Dead load, F_d	= 0.25 kN/m ²	[see 4.3 b)]
	Imposed load	= 1.5 kN/m ² or = 3.6 kN/m width of floor	[$L \geq 2\ 400$ mm, see 4.3 a)] [$L \leq 2\ 400$ mm, see 4.3 a)]

The following data are given in BS 5268-2:1988.

Grade stresses and density		BS 5268-2:1988 reference
Grade bending stress, $\sigma_{m,g}$	= 5.3 N/mm ²	Table 9
Grade shear stress, τ_g	= 0.67 N/mm ²	Table 9
Grade mean modulus of elasticity, E	= 8 800 N/mm ²	Table 9
Grade compression perpendicular to the grain stress (with wane permitted), $\sigma_{c,\perp,g}$	= 1.7 N/mm ²	Table 9
Density, ρ	= 540 kg/m ³	Table 9
Modification factors		
Load duration, K_3	= 1.0 long term	Table 17
Depth, K_7	= $(300/h)^{0.11}$	14.6
Load sharing, K_8	= 1.1	clause 13
Permissible stresses and recommended deflection limitation		BS 5268-7.1 reference
Permissible bending stress, $\sigma_{m,adm}$ (in N/mm ²)	= $\sigma_{m,g} K_3 K_7 K_8$ = 6.437 N/mm ²	5.2
Permissible shear stress, τ_{adm} (in N/mm ²)	= $\tau_g K_3 K_8$ = 0.737 N/mm ²	5.3
Recommended deflection limitation, W_{max} (in mm)	= 0.003L or = 14 mm	5.4 5.4
Permissible compression perpendicular to the grain stress, $\sigma_{c,\perp,adm}$ (in N/mm ²)	= $\sigma_{c,\perp,g} K_3 K_8$ = 1.87 N/mm ²	5.5

Application of the design equations from 5.2 to 5.4 leads to the following solutions for effective span L :

- | | |
|---|--------------------------------------|
| a) limitation of bending stress | $L = 2\,429$ mm [equation (8)] |
| | or $L = 2\,450$ mm [equation (9)]; |
| b) limitation of shear stress | $L = 5\,538$ mm [equation (14)] |
| | or $L = 21\,032$ mm [equation (15)]; |
| c) limitation of deflection ($0.003 L$) | $L = 2\,389$ mm [equation (23)] |
| | or $L = 2\,384$ mm [equation (24)]; |
| d) limitation of deflection (14 mm) | $L = 2\,832$ mm [equation (25)]. |

NOTE Solutions to all seven design equations have been provided in a) to d) for illustrative purposes but in practice fewer solutions would be required for any individual permissible span calculation. Some solutions are invalid; for example the solution of equation (9) is invalid because it exceeds 2 400 mm.

The permissible effective span L_{adm} is therefore

$$L_{adm} = 2\,384 \text{ mm}$$

The appropriate equation is selected from 5.5 (i.e. in this case for $L < 2\,400$ mm) to calculate the notional bearing length, a , as 14 mm.

The permissible clear span L_{cl} for the joists is then

$$L_{cl} = L_{adm} - a$$

$$L_{cl} = 2\,370 \text{ mm}$$

Appendix B Specimen span tables for domestic floor joists

There are many possible formats for span tables and Table 1, Table 2 and Table 3 are typical examples. Whatever format is used, the information listed in clause 7 should be given.

Table 1 — Permissible clear spans for domestic floor joists: SC3^a: regularized sizes^b

Size of joist		Dead load (in kN/m ²) supported by joist, excluding the self weight of the joist								
		Not more than 0.25 (25.5 kg/m ²)			More than 0.25 but not more than 0.50 (51 kg/m ²)			More than 0.50 but not more than 1.25 (127.5 kg/m ²)		
		Centre-to-centre spacing of joists (in mm)								
		400	450	600	400	450	600	400	450	600
		Permissible clear span								
mm		m	m	m	m	m	m	m	m	m
38 ×	72	1.130	1.011	0.767	1.061	0.954	0.731	0.920	0.834	0.652
	97	1.828	1.692	1.303	1.717	1.556	1.214	1.423	1.301	1.037
	122	2.482	2.385	1.925	2.368	2.215	1.755	1.947	1.791	1.448
	147	2.983	2.868	2.510	2.853	2.707	2.331	2.453	2.290	1.872
	170	3.442	3.306	2.873	3.281	3.098	2.690	2.808	2.649	2.267
	195	3.939	3.752	3.263	3.724	3.518	3.056	3.189	3.010	2.609
	220	4.434	4.193	3.648	4.161	3.932	3.418	3.567	3.367	2.920
44 ×	72	1.281	1.160	0.884	1.207	1.088	0.839	1.035	0.941	0.740
	97	1.962	1.854	1.491	1.862	1.758	1.380	1.587	1.454	1.166
	122	2.606	2.506	2.186	2.493	2.396	1.979	2.156	1.987	1.616
	147	3.131	3.012	2.697	2.996	2.881	2.526	2.636	2.488	2.077
	170	3.612	3.475	3.087	3.457	3.325	2.891	3.018	2.848	2.470
	195	4.132	3.977	3.505	3.956	3.776	3.284	3.426	3.235	2.807
	220	4.648	4.476	3.917	4.453	4.219	3.672	3.830	3.617	3.140
47 ×	72	1.324	1.233	0.942	1.272	1.154	0.891	1.091	0.993	0.783
	97	2.024	1.914	1.583	1.920	1.818	1.460	1.665	1.527	1.228
	122	2.663	2.561	2.302	2.548	2.450	2.087	2.255	2.081	1.696
	147	3.200	3.078	2.786	3.062	2.945	2.609	2.723	2.570	2.174
	170	3.691	3.551	3.188	3.533	3.398	2.987	3.116	2.942	2.552
	195	4.221	4.063	3.619	4.042	3.889	3.391	3.538	3.341	2.900
	220	4.723	4.572	4.044	4.549	4.354	3.791	3.954	3.735	3.244
50 ×	72	1.365	1.287	0.999	1.311	1.218	0.943	1.145	1.043	0.825
	97	2.084	1.971	1.673	1.975	1.871	1.539	1.741	1.598	1.288
	122	2.718	2.615	2.370	2.601	2.501	2.192	2.327	2.171	1.774
	147	3.265	3.142	2.855	3.125	3.006	2.690	2.807	2.650	2.269
	170	3.765	3.624	3.285	3.605	3.469	3.078	3.212	3.032	2.632
	195	4.306	4.146	3.728	4.125	3.969	3.495	3.646	3.443	2.990
	220	4.793	4.660	4.166	4.641	4.467	3.907	4.074	3.849	3.345
63 ×	147	3.518	3.388	3.084	3.370	3.244	2.950	3.037	2.920	2.577
	170	4.055	3.905	3.558	3.886	3.741	3.404	3.504	3.370	2.950
	195	4.633	4.465	4.070	4.442	4.278	3.896	4.009	3.850	3.350
	220	5.061	4.923	4.580	4.905	4.770	4.365	4.512	4.301	3.745
75 ×	195	4.830	4.700	4.306	4.683	4.523	4.125	4.242	4.084	3.646
	220	5.268	5.128	4.793	5.109	4.971	4.641	4.740	4.595	4.074

NOTE 1 The tables are computed on the basis that the specification does not exclude wane at bearings.

NOTE 2 The spans have been calculated in accordance with the recommendations of BS 5268-2 and BS 5268-7.1. Lateral support should be provided in accordance with 14.8 of BS 5268-2:1988.

NOTE 3 The material should be stress graded in accordance with BS 4978.

NOTE 4 The sizes and their maximum permissible deviations should be in accordance with BS 4471.

^a For species/grade combinations in this strength class see Tables 3 to 7 of BS 5268-2:1988.

^b Regularized sizes are given in BS 4471.

Table 2 — Permissible clear spans for domestic floor joists: redwood/whitewood, SS grade, basic sizes^a

Size of joist	Dead load (in kN/m ²) supported by joist, excluding the self weight of the joist									
	Not more than 0.25 (25.5 kg/m ²)			More than 0.25 but not more than 0.50 (51 kg/m ²)			More than 0.50 but not more than 1.25 (127.5 kg/m ²)			
	Centre-to-centre spacing of joists (in mm)									
	400	450	600	400	450	600	400	450	600	
	Permissible clear span									
mm	m		m		m		m		m	
38 ×	75	1.381	1.302	1.123	1.326	1.252	1.079	1.204	1.139	0.932
	100	2.082	1.968	1.709	1.972	1.867	1.627	1.747	1.658	1.424
	125	2.702	2.598	2.346	2.585	2.484	2.208	2.306	2.194	1.935
	150	3.235	3.111	2.824	3.095	2.975	2.699	2.780	2.671	2.418
	175	3.765	3.622	3.290	3.603	3.465	3.144	3.239	3.111	2.812
	200	4.293	4.131	3.754	4.109	3.952	3.588	3.695	3.551	3.185
	225	4.774	4.637	4.216	4.614	4.438	4.031	4.151	3.989	3.555
44 ×	75	1.485	1.401	1.211	1.423	1.345	1.167	1.288	1.220	1.050
	100	2.231	2.111	1.838	2.108	1.998	1.746	1.862	1.769	1.556
	125	2.837	2.728	2.478	2.714	2.610	2.362	2.439	2.334	2.065
	150	3.395	3.266	2.968	3.249	3.125	2.837	2.922	2.808	2.544
	175	3.950	3.801	3.456	3.782	3.638	3.304	3.403	3.270	2.964
	200	4.502	4.334	3.942	4.312	4.149	3.770	3.882	3.732	3.384
	225	4.946	4.808	4.427	4.790	4.654	4.235	4.359	4.191	3.802
47 ×	75	1.534	1.448	1.253	1.469	1.388	1.206	1.327	1.258	1.099
	100	2.300	2.178	1.898	2.172	2.059	1.802	1.915	1.821	1.603
	125	2.899	2.789	2.533	2.774	2.668	2.422	2.494	2.397	2.124
	150	3.469	3.338	3.034	3.321	3.194	2.901	2.987	2.871	2.603
	175	4.035	3.884	3.533	3.864	3.718	3.379	3.478	3.344	3.032
	200	4.599	4.427	4.030	4.405	4.239	3.855	3.968	3.815	3.461
	225	5.025	4.885	4.524	4.867	4.730	4.329	4.456	4.285	3.889
50 ×	75	1.581	1.493	1.293	1.512	1.430	1.243	1.365	1.294	1.132
	100	2.367	2.242	1.956	2.233	2.118	1.855	1.966	1.870	1.648
	125	2.958	2.846	2.587	2.832	2.723	2.473	2.547	2.447	2.181
	150	3.539	3.406	3.097	3.389	3.260	2.962	3.050	2.932	2.659
	175	4.117	3.963	3.606	3.943	3.794	3.449	3.551	3.414	3.097
	200	4.681	4.517	4.113	4.494	4.326	3.935	4.050	3.895	3.535
	225	5.099	4.958	4.617	4.939	4.801	4.419	4.547	4.374	3.971
63 ×	150	3.812	3.671	3.344	3.653	3.516	3.200	3.293	3.167	2.876
	175	4.431	4.269	3.891	4.247	4.090	3.724	3.832	3.687	3.350
	200	4.943	4.808	4.435	4.790	4.658	4.247	4.369	4.204	3.822
	225	5.383	5.237	4.891	5.218	5.075	4.736	4.837	4.700	4.292
75 ×	200	5.146	5.009	4.681	4.990	4.855	4.494	4.621	4.450	4.050
	225	5.602	5.453	5.099	5.434	5.287	4.939	5.043	4.903	4.547

NOTE 1 The tables are computed on the basis that the specification does not exclude wane at bearings.
NOTE 2 The spans have been calculated in accordance with the recommendations of BS 5268-2 and BS 5268-7.1. Lateral support should be provided in accordance with 14.8 of BS 5268-2:1988.
NOTE 3 The material should be stress graded in accordance with BS 4978.
NOTE 4 The sizes and their maximum permissible deviations should be in accordance with BS 4471.

^a Basic sizes are given in BS 4471.

Table 3 — Permissible clear spans for domestic floor joists: spruce-pine-fir, joist and plank no. 2 grade, CLS sizes^a

Size of joist	Dead load (in kN/m ²) supported by joist, excluding the self weight of the joist								
	Not more than 0.25 (25.5 kg/m ²)			More than 0.25 but not more than 0.50 (51 kg/m ²)			More than 0.50 but not more than 1.25 (127.5 kg/m ²)		
	Centre-to-centre spacing of joists (in mm)								
	400	450	600	400	450	600	400	450	600
Permissible clear span									
mm	m	m	m	m	m	m	m	m	m
38 × 140	2.870	2.759	2.469	2.744	2.637	2.271	2.413	2.238	1.825
184	3.759	3.614	3.186	3.595	3.437	2.982	3.114	2.937	2.543
235	4.746	4.599	3.999	4.564	4.311	3.745	3.908	3.688	3.196
285	5.463	5.307	4.779	5.287	5.135	4.478	4.672	4.411	3.826

NOTE 1 The tables are computed on the basis that the specification does not exclude wane at bearings.
NOTE 2 The spans have been calculated in accordance with the recommendations of BS 5268-2 and BS 5268-7.1. Lateral support should be provided in accordance with 14.8 of BS 5268-2:1988.
NOTE 3 The material should be stress graded in accordance with NLGA rules.
NOTE 4 The sizes and their maximum permissible deviations should be in accordance with Appendix A of BS 4471:1987.

^a CLS sizes are given in Appendix A of BS 4471:1987.

Publications referred to

BS 648, *Schedule of weights of building materials.*

BS 4471, *Specification for sizes of sawn and processed softwood.*

BS 4978, *Specification for timber grades for structural use.*

BS 5268, *Structural use of timber.*

BS 5268-2, *Code of practice for permissible stress design, materials and workmanship.*

BS 5268-2-7.2, *Joists for flat roofs³⁾.*

BS 5268-2-7.3, *Ceiling joists³⁾.*

BS 5268-2-7.4, *Ceiling binders³⁾.*

BS 5268-2-7.5, *Rafters³⁾.*

BS 5268-2-7.6, *Purlins supporting rafters³⁾.*

BS 5268-2-7.7, *Purlins supporting sheeting or decking³⁾.*

BS 6100, *Glossary of building and civil engineering terms.*

BS 6100-2.1, *Structural design and elements.*

BS 6100-4.1, *Characteristics and properties of timber and wood based panel products.*

BS 6100-4.2, *Sizes and quantities of solid timber.*

BS 6100-4.3, *Wood based panel products.*

BS 6100-4.4, *Carpentry and joinery.*

BS 6399, *Loading for buildings.*

BS 6399-1, *Code of practice for dead and imposed loads.*

ISO 3898, *Bases for design of structures — Notations — General symbols.*

CIB-W18-1, *Symbols for use in structural timber design.* International Council for Building Research Studies and Documentation, Post Box 20704, 3001 JA Rotterdam, The Netherlands.

NLGA 1979, *The national grading rules for dimension lumber.* National Lumber Grades Authority, 1450-1055 West Hastings Street, Vancouver, British Columbia, Canada V6E 2G8.

³⁾ Referred to in the foreword only.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.