

Sampling and analysis of iron, steel and other ferrous metals —

Part 3: Methods of analysis —

Section 3.26 Determination of silicon —

Subsection 3.26.5 Ferrosilicon,
ferrosilicomanganese and
ferrosilichromium: gravimetric
method

UDC 669.1:543.21:546.28

National foreword

This Subsection of BS 6200 has been prepared under the direction of the Iron and Steel Standards Committee.

It is identical with ISO 4158:1978 *"Ferrosilicon, ferrosilicomanganese and ferrosilicochromium — Determination of silicon content — Gravimetric method"* published by the International Organization for Standardization (ISO).

Terminology and conventions. The text of the International Standard has been approved as suitable for publication as a British Standard without deviation. Some terminology and certain conventions are not identical with those used in British Standards; attention is drawn especially to the following. The comma has been used as a decimal marker. In British Standards it is current practice to use a full point on the baseline as the decimal marker. Wherever the words "International Standard" appear, referring to this standard, they should be read as "British Standard".

Cross-reference. At present, there is no corresponding British Standard for ISO 3713 which is still at draft stage. Appropriate procedures from ISO 3713 will be incorporated in BS 6200-2 *"Methods of sampling and sample preparation"*, which will be published in due course.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 and 2, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

This British Standard, having been prepared under the direction of the Iron and Steel Standards Committee, was published under the authority of the Board of BSI and comes into effect on 28 February 1985

©BSI 09-1999

The following BSI references relate to the work on this standard:
Committee reference ISM/18
Draft for comment 77/79236 DC

ISBN 0 580 14270 1

Amendments issued since publication

Amd. No.	Date of issue	Comments

Contents

	Page
National foreword	Inside front cover
1 Scope and field of application	1
2 Reference	1
3 Principle	1
4 Reagents	1
5 Apparatus	1
6 Sample	1
7 Procedure	1
8 Expression of results	2
9 Reproducibility	2
10 Test report	2
Publication referred to	Inside back cover

1 Scope and field of application

This International Standard specifies a gravimetric method for the determination of the silicon content of ferrosilicon, ferrosilicomanganese and ferrosilicochromium.

The method is applicable to alloys containing from 8 to 95 % (*mlm*) of silicon.

2 Reference

ISO 3713, *Ferroalloys — Sampling and preparation of samples — General rules*¹⁾.

3 Principle

Transformation of the silicon in a test portion into silicate by oxidizing fusion with sodium peroxide and taking up with acid.

Double dehydration of the silicate by evaporation in a perchloric acid medium, and weighing of the impure silica.

Double hydrofluoric-sulphuric volatilization of the silica, weighing of the residue, and determination, by difference, of the pure silica.

4 Reagents

During the analysis, use only reagents of recognized analytical grade, and only distilled water or water of equivalent purity.

- 4.1 *Sodium peroxide*
- 4.2 *Sodium carbonate* (anhydrous).
- 4.3 *Ammonia solution*, ρ 0,91 g/ml.
- 4.4 *Perchloric acid*²⁾, ρ 1,61 g/ml.
- 4.5 *Hydrofluoric acid*, ρ 1,14 g/ml.
- 4.6 *Hydrochloric acid*, ρ 1,19 g/ml.
- 4.7 *Sulphuric acid*, ρ 1,83 g/ml.
- 4.8 *Hydrochloric acid*, ρ 1,19 g/ml, diluted 1 + 9.
- 4.9 *Sulphuric acid*, ρ 1,83 g/ml, diluted 1 + 1.
- 4.10 *Silver nitrate*, 10 g/l solution.

5 Apparatus

Usual laboratory equipment, and in particular:

- 5.1 *Crucible*, capacity 40 ml, of silicon-free iron, vitreous carbon, nickel or zirconium.
- 5.2 *Beakers*, for melt dissolution, of polytetrafluoroethylene, stainless steel or high purity nickel.
- 5.3 *Platinum dish*, capacity 40 ml.
- 5.4 *Fluted glass funnel*, diameter 75 mm.

5.5 *Glass beaker*, capacity 600 ml or 800 ml.

5.6 *Muffle furnace*

5.7 *Desiccator*

6 Sample

Use powder which will pass through a sieve with a mesh size of 160 μm , prepared in accordance with ISO 3713.

7 Procedure

7.1 Test portion

For silicon contents less than or equal to 50 % (*mlm*), take a test portion of $0,50 \pm 0,000$ 2 g.

NOTE For silicon contents less than 25 % (m/m), it is possible to use a test portion of 1 g.

For silicon contents more than 50 % (*mlm*), take a test portion of $0,25 \pm 0,000$ 2 g.

7.2 Blank test

Carry out a blank test in parallel with the determination, following the same procedure and using the same quantities of all the reagents.

7.3 Determination

7.3.1 Transfer the test portion (**7.1**) to the crucible (**5.1**) containing 10 to 12 g of the sodium peroxide (**4.1**). Mix carefully and then, to prevent any loss of the test portion, cover with 3 g of the sodium peroxide (**4.1**) or 3 g of the sodium carbonate (**4.2**).

Heat the crucible containing the test portion and flux on an electric hot-plate at 350 to 400 °C until the melt blackens. Holding the crucible in tongs, swirl it over a flame, heating gently at first to avoid deflagration, and then more strongly until the attack is complete. Maintain the product of fusion at red heat for approximately 5 min. Allow the crucible to cool.

7.3.2 Dissolve the melt as specified in either **7.3.2.1** or **7.3.2.2**.

7.3.2.1 Alternative I

Place the crucible in a beaker (**5.2**), containing 200 ml of water. Cover with a watch glass. When effervescence has ceased, remove the crucible and wash it with hot water, collecting the washings in the same beaker. Transfer the alkaline solution to a glass beaker (**5.5**), containing 30 ml of the hydrochloric acid (**4.6**). Stir to mix the solution, wait for the salts to dissolve and add 100 ml of the perchloric acid (**4.4**).

Proceed as specified in **7.3.3**.

¹⁾ At present at the stage of draft.

²⁾ Attention is drawn to the hazards associated with perchloric acid when heated to fuming.

7.3.2.2 Alternative II

Cover the crucible and tap it on a hard surface to loosen the cake. Transfer the cake to a clean glass beaker (5.5), containing 100 ml of the perchloric acid (4.4). Fill the crucible with hot water and, after effervescence has ceased in the beaker, add the contents of the crucible to the beaker. Transfer any residue from the crucible to the beaker using a rubber-tipped stirring rod and a minimum of water. Add 30 ml of the hydrochloric acid (4.6).

Proceed as specified in 7.3.3.

7.3.3 Place the beaker on a strongly heated hot-plate until white perchloric fumes are evolved. Continue heating until the fuming residue begins to crystallize and acquires a pasty consistency. Remove from the hot-plate and allow to cool. Take up with 20 ml of the hydrochloric acid (4.6), added gently down the wall of the beaker, and a few millilitres of hot water. Stir and dilute with 250 ml of boiling water. Mix well and allow to settle.

Filter the silica on a 125 mm flat ashless filter paper placed on the fluted glass funnel (5.4). Retain the filtrate. Rinse the beaker with warm water, using a rubber-tipped stirrer. Wash the filter with warm hydrochloric acid (4.8) until the yellow colour due to iron salts disappears, then finally wash several times with hot water until chloride ions are no longer present [verify by means of a spot test with the silver nitrate solution (4.10)]. The filter shall be thoroughly washed, so as to remove any trace of perchloric acid, which would cause flaming up during incineration.

Transfer the filtrate and the washings to the beaker used for the initial dehydration. Evaporate to a volume of about 250 ml. Add 20 ml of the perchloric acid (4.4) and carry out a second dehydration as described in the first paragraph of 7.3.3. Take up, filter (using a fresh filter paper) and wash the precipitate as before, but carrying out the final washing with cold water instead of hot water.

7.3.4 Place the two filters containing the silica precipitates in the platinum dish (5.3). Add 4 drops of the ammonia solution (4.3) to the filters³⁾. Dry to remove excess moisture and incinerate in the muffle furnace (5.6), initially at 400 °C maximum. Allow to cool. Add 1 ml of the sulphuric acid (4.9). Evaporate to dryness until sulphuric fumes cease to be evolved and then calcine at 1 100 °C to constant mass. Allow to cool in a desiccator and weigh the dish containing the impure silica.

7.3.5 Moisten the impure silica with a few drops of water. Add about 10 ml of the hydrofluoric acid (4.5) and 2 or 3 drops of the sulphuric acid (4.7). Evaporate to dryness until sulphuric fumes cease to be evolved. Carry out a second volatilization under the same conditions, but decreasing the quantity of hydrofluoric acid to 2 ml. Calcine in the muffle furnace (5.6) at 1 100 °C to constant mass. Allow to cool in a desiccator and weigh the dish containing the impurities.

8 Expression of results

The silicon content, expressed as a percentage by mass of the sample, is given by the formula

$$\begin{aligned} & [(m_1 - m_2) - (m_3 - m_4)] \times 0,467\ 4 \times \frac{100}{m_0} \\ &= \frac{46,74 [(m_1 - m_2) - (m_3 - m_4)]}{m_0} \end{aligned}$$

where

- m_0 is the mass, in grams, of the test portion (7.1);
- m_1 is the mass, in grams, of the dish and impure silica obtained in the determination (7.3.4);
- m_2 is the mass, in grams, of the dish and impurities obtained in the determination (7.3.5);
- m_3 is the mass, in grams, of the dish and impure silica obtained in the blank test;
- m_4 is the mass, in grams, of the dish and impurities obtained in the blank test;
- 0,467 4 is the conversion factor from silica to silicon.

9 Reproducibility

Experience has shown that the 95 % confidence limits for an experienced operator are:

- ± 0,30 % for silicon contents exceeding 50 % (m/m);
- ± 0,20 % for silicon contents less than 50 % (m/m).

10 Test report

The test report shall include the following particulars:

- a) the reference of the method used;
- b) the results and the method of expression used;
- c) any unusual features noted during the determination;
- d) any operation not included in this International Standard or regarded as optional.

³⁾ This reduces the hazard of volatile perchlorates spitting some of the silica from the crucible.

Publication referred to

See national foreword.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means — electronic, photocopying, recording or otherwise — without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager.
Tel: 020 8996 7070.