

Analysis of aluminium ores —

Part 2: Chemical methods —

Section 2.3 Method for determination of loss of mass at 1075 °C: gravimetric method

[ISO title: Aluminium ores — Determination of loss of mass
at 1075 °C — Gravimetric method]

UDC 553.492:543

National foreword

This Section of BS 6870 has been prepared under the direction of the Non-ferrous Metals Standards Committee.

It is identical with ISO 6606:1986 “*Aluminium ores — Determination of loss of mass at 1 075 °C — Gravimetric method*”, published by the International Organization for Standardization (ISO).

Terminology and conventions. The text of the International Standard has been approved as suitable for publication as a British Standard without deviation. Some terminology and certain conventions are not identical with those used in British Standards; attention is drawn especially to the following.

The comma has been used as a decimal marker. In British Standards it is current practice to use a full point on the baseline as the decimal marker.

Wherever the words “International Standard” appear, referring to this standard, they should be read as “Section of BS 6870”.

Cross-reference

International Standard	Corresponding British Standard
ISO 8557:1985	BS 6870 <i>Analysis of aluminium ores</i> Section 2.2:1987 <i>Method for determination of hygroscopic moisture in analytical samples: gravimetric method</i> (Identical)

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 to 4, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

Amendments issued since publication

Amd. No.	Date of issue	Comments

This British Standard, having been prepared under the direction of the Non-ferrous Metals Standards Committee, was published under the authority of the Board of BSI and comes into effect on 28 August 1987

© BSI 12-1999

The following BSI references relate to the work on this standard:
Committee reference NFM/31
Draft for comment 84/42825 DC

ISBN 0 580 16055 6

Contents

	Page
National foreword	Inside front cover
0 Introduction	1
1 Scope and field of application	1
2 Reference	1
3 Principle	1
4 Apparatus	1
5 Sampling and samples	1
6 Procedure	1
7 Expression of results	2
8 Test report	3
Table — Precision data for loss of mass determinations	2
Publication referred to	Inside back cover

0 Introduction

Aluminium ores when heated undergo a loss of mass. At temperatures up to 110 °C the loss is due to hygroscopic moisture. At higher temperatures the loss of mass is due largely to the dissociation of hydroxides and oxyhydroxides of aluminium and iron and also, to a lesser degree, to the dissociation of minor constituents.

The total loss of mass is a function of the temperature and time of heating. There are no conditions at which the loss represents exclusively the water (hygroscopic and combined) in the sample.

The temperature chosen for the test, 1 075 °C, is a compromise between such factors as furnace suitability and the absorption of water by the sample during cooling.

The value obtained for loss on ignition is calculated on the basis of a dried sample.

The test portion is heated initially at 375 ± 25 °C and finally at $1\ 075 \pm 25$ °C and the loss of mass determined. The crucible is covered with a loose-fitting lid after the test portion is placed in the crucible and this is left in position throughout all the subsequent operations. The presence of the lid contributes to more reproducible results by preventing the random effects of small pieces of furnace lining falling into the crucible during heating and does not interfere with the maintenance of oxidizing conditions in the crucible.

1 Scope and field of application

This International Standard specifies a gravimetric method for the determination of the loss of mass of analytical samples of aluminium ores when heated to constant mass at 1 075 °C. The method is applicable to all aluminium ores having loss of mass values in the range of 10 to 30 %.

2 Reference

ISO 8557, *Aluminium ores — Determination of hygroscopic moisture of analytical samples — Gravimetric method*.

3 Principle

Heating of a test portion in a tared crucible in a furnace at 375 ± 25 °C for 10 min. Transfer of the covered crucible to a second furnace at $1\ 075 \pm 25$ °C and heating to constant mass. Correction of the resultant loss in mass for the original hygroscopic moisture.

4 Apparatus

Ordinary laboratory apparatus and

4.1 Dishes, of inert material of sufficient size to take the required quantity of sample at a layer density of 5 mg/mm².

4.2 Platinum crucible, approximately 30 mm top diameter, 20 mm bottom diameter and 35 mm deep, with matching platinum lid.

4.3 Electric furnaces, capable of being controlled at 375 ± 25 °C and at $1\ 075 \pm 25$ °C, and having provision for a flow of air through the heated cavity.

4.4 Balance, capable of being read to 0,000 1 g.

4.5 Desiccator, containing either fresh magnesium perchlorate or activated alumina as desiccant.

NOTE 1 Activated alumina should be activated by heating at 300 ± 10 °C overnight.

NOTE 2 When discarding magnesium perchlorate, flush down the sink using copious quantities of water.

5 Sampling and samples

5.1 Samples

Laboratory samples shall be taken and crushed to pass a 150 µm test sieve, in accordance with the methods specified in the relevant standards.¹⁾

5.2 Preparation of the test sample

Take approximately 10 g of the laboratory sample and place in a flat dish (4.1). Spread the sample evenly to give a layer density of approximately 5 mg/mm² and allow to equilibrate with the laboratory atmosphere for a minimum of 2 h.

6 Procedure

6.1 Number of determinations

Carry out the determination in duplicate on each ore sample.

NOTE The principle of carrying out a blank determination and a check test does not apply to this method.

6.2 Preparation of crucible and test portion

Heat the platinum crucible (4.2) and lid in the furnace (4.3) controlled at $1\ 075 \pm 25$ °C for 15 min. Remove the covered crucible from the furnace and place in the desiccator (4.5) to cool. Weigh the crucible and lid, to the nearest 0,000 2 g, as rapidly as possible after they have cooled to ambient temperature and within 1 h of placing them in the desiccator.

¹⁾ Where no International Standards exist, the relevant standards shall be the national standards. Two International Standards on this subject are currently in preparation: ISO 6137, *Aluminium ores — Method of sampling*, and ISO 6140, *Aluminium ores — Preparation of samples*.

Add approximately 1 g ($\pm 0,01$ g) of the test sample to the platinum crucible, distribute it evenly over the bottom of the crucible, replace the lid and weigh the crucible, lid and contents to the nearest 0,000 2 g. Record the mass of the test portion (m_1).

At the same time, weigh test portions for the determination of hygroscopic moisture by the procedure specified in ISO 8557.

6.3 Determination of loss on ignition

Place the covered crucible and contents, with the lid slightly displaced, in the furnace (4.3) controlled at 375 ± 25 °C and heat for 10 ± 1 min.

Transfer the partially covered crucible and contents to the furnace controlled at $1\ 075 \pm 25$ °C and heat for 60 ± 2 min.

Remove the covered crucible and contents from the furnace, ensuring that the lid is now fully in position, and place in the desiccator to cool. Weigh the covered crucible and contents, to the nearest 0,000 2 g, as rapidly as possible after they have cooled to ambient temperature and within 1 h after they have been placed in the desiccator.

NOTE Prior to each weighing, inspect the outside of the crucible lid and brush if necessary.

Return the covered crucible and contents to the furnace controlled at $1\ 075 \pm 25$ °C and heat for a further 30 ± 2 min. Allow to cool in the desiccator and re-weigh as soon as possible after the crucible and contents have cooled to ambient temperature and within 1 h of placing them in the desiccator.

If the difference between the weighings after the first and second heatings at $1\ 075$ °C exceeds 0,000 5 g, repeat the heating, cooling and weighing steps, until this requirement is met.

Use the minimum mass of the crucible, lid and contents to calculate the minimum mass of the heated sample (m_2).

7 Expression of results

7.1 Calculation of the loss on ignition

Calculate the loss on ignition (LOI), expressed as a percentage by mass, using the formula

$$\text{LOI} = \left[\frac{100 (m_1 - m_2)}{m_1} - H \right] \times \frac{100}{100 - H}$$

where

m_1 is the mass, in grams, of the test portion;

m_2 is the mass, in grams, of the test portion after heating;

H is the hygroscopic moisture content, as a percentage by mass, of the equilibrated sample.

7.2 General treatment of results

7.2.1 Precision

A planned trial of the method was carried out by nine countries with a total of sixteen laboratories participating. Two determinations were carried out by each analyst on each of four samples. From the results obtained, the repeatability, reproducibility and reproducibility index have been calculated and are presented in the following Table.

Table — Precision data for loss of mass determinations

Sample	Mean loss in mass at 1 075 °C % (m/m)	Components of standard deviation		Reproducibility index 2s
		s_w	s_b	
MT/12/12	14,47	0,064	0,215	0,45
MT/12/4	25,24	0,050	0,126	0,27
MT/12/1	26,43	0,090	0,101	0,27
MT/12/9	27,53	0,078	0,195	0,42

where

s_w is the within-laboratory standard deviation;

s_b is the between-laboratories standard deviation.

7.2.2 Acceptance of analytical values

The analytical value for the test sample shall be accepted when the difference between the two values for the test sample does not exceed $2,77 s_w$ as calculated from the appropriate value of S_w given in the Table.

When the range (absolute difference) of the two values for the test sample is greater than $2,77 s_w$, additional determinations shall be carried out on the test sample.

7.2.3 Calculation of final result

The final result is the arithmetical mean of the values for the test portions calculated to the fourth decimal place and rounded off to the second decimal place as follows:

1) When the figure in the third decimal place is less than 5, it is discarded and the figure in the second decimal place is kept unchanged.

2) When the figure in the third decimal place is 5 and there are figures other than 0 in the fourth decimal places, or when the figure in the third decimal place is greater than 5, the figure in the second decimal place is increased by one.

3) When the figure in the third decimal place is 5 and there are no figures other than 0 in the fourth decimal places, the 5 is discarded and the figure in the second decimal place is kept unchanged if it is 0, 2, 4, 6 or 8 and is increased by one if it is 1, 3, 5, 7 or 9.

8 Test report

The test report shall include the following information:

- a) details necessary for the identification of the sample;
- b) reference to this International Standard;
- c) the result of the analysis;
- d) reference number of the result;
- e) any characteristics noticed during the determination and any operations not specified in this International Standard which may have had an influence on the result.

Publication referred to

See national foreword.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager.
Tel: 020 8996 7070.