

# Analysis of nickel alloys by flame atomic absorption spectrometry

Part 2. Method for the determination  
of cobalt

## Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Non-ferrous Metals Standards Policy Committee (NFM/-) to Technical Committee NFM/10, upon which the following bodies were represented:

British Non-ferrous Metals Federation  
British Steel Industry  
Department of Trade and Industry (Laboratory of the Government Chemist)  
Engineering Equipment and Materials Users' Association  
Ministry of Defence  
Nickel Development Institute  
Non-ferrous Metal Stockists  
Process Plant Association  
Stainless Steel Fabricators' Association of Great Britain  
Coopted members

This British Standard, having been prepared under the direction of the Non-ferrous Metals Standards Policy Committee, was published under the authority of the Standards Board and comes into effect on 28 June 1991

© BSI 1991

The following BSI references relate to the work on this standard:  
Committee reference NFM/10  
Draft for comment 89/47725 DC

ISBN 0 580 19776 X

### Amendments issued since publication

Amd. No.	Date	Text affected

---

# Contents

	Page
Committees responsible	Inside front cover
National foreword	ii
<hr/>	
<b>Method</b>	
<b>1</b> Scope	1
<b>2</b> Normative references	1
<b>3</b> Principle	1
<b>4</b> Reagents	1
<b>5</b> Apparatus	2
<b>6</b> Sampling and sample preparation	2
<b>7</b> Procedure	2
<b>8</b> Expression of results	2
<b>9</b> Test report	3
<hr/>	
<b>Tables</b>	
<b>1</b> Nominal composition of test samples	3
<b>2</b> Results of statistical analysis	3

---

## National foreword

This Part of BS 7455 has been prepared under the direction of the Non-ferrous Metals Standards Policy Committee. It is identical with ISO 7530-2 'Nickel alloys — Flame atomic absorption spectrometric analysis — Part 2 : 1990 Determination of cobalt content', published by the International Organization for Standardization (ISO).

At present this British Standard consists of six Parts all concerned with methods for flame spectrometric analysis of nickel alloys. Further international standards are in preparation on the same subject and when available, these will be published as further Parts of this British Standard.

### Cross-references

<b>International standard</b>	<b>Corresponding British Standard</b>
ISO 5725 : 1986	BS 5497 Precision of test methods Part 1 : 1987 Guide for the determination of repeatability and reproducibility for a standard test method by inter-laboratory tests (Identical)
ISO 7530-1 : 1990	BS 7455 Analysis of nickel alloys by flame atomic absorption spectrometry Part 1 : 1991 General requirements and sample dissolution (Identical)

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

# Nickel alloys — Flame atomic absorption spectrometric analysis —

## Part 2:

## Determination of cobalt content

### 1 Scope

This part of ISO 7530 specifies a flame atomic absorption spectrometric method for the determination of cobalt in the range of 0,01 % (*m/m*) to 4 % (*m/m*) in nickel alloys. Typical compositions of some nickel alloys are given in ISO 7530-1, annex B.

The general requirements concerning the apparatus, sampling, dissolution of the test sample, atomic absorption measurements, calculations and test report are given in ISO 7530-1.

### 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 7530. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 7530 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 5725:1986, *Precision of test methods — Determination of repeatability and reproducibility for a standard test method by inter-laboratory tests*.

ISO 7530-1:—<sup>1)</sup>, *Nickel alloys — Flame atomic absorption spectrometric analysis — Part 1: General requirements and sample dissolution*.

1) To be published.

### 3 Principle

Dissolution of a test portion in acid and aspiration of the test solution into an air-acetylene flame of an atomic absorption spectrometer.

Measurement of the absorbance of the resonance line energy from the spectrum of cobalt and comparison with that of calibration solutions at a wavelength of 240,7 nm.

### 4 Reagents

In addition to the reagents listed in ISO 7530-1, the following special reagents are required.

#### 4.1 Strontium chloride, solution.

Transfer 113,5 g of strontium chloride hexahydrate ( $\text{SrCl}_2 \cdot 6\text{H}_2\text{O}$ ) to a 600 ml beaker, dissolve in 400 ml of hot water (50 °C to 60 °C), cool and transfer to a 1000 ml one-mark volumetric flask. Make up to the mark with water and mix. The strontium chloride should be free of heavy metals.

#### 4.2 Cobalt, standard reference solution (1,000 g/l).

Weigh, to the nearest 0,001 g, 1,000 g of cobalt metal of 99,9 % (*m/m*) minimum purity and transfer to a 400 ml beaker. Add 30 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml) diluted 1 + 1 and heat to complete dissolution. Cool, transfer to a 1000 ml one-mark volumetric flask and add 35 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water, mix and store in a polyethylene bottle.

### 4.3 Cobalt, standard solution (50 mg/l).

Pipette 50 ml of the cobalt standard reference solution (4.2) into a 1 000 ml one-mark volumetric flask and add 50 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water, mix and store in a polyethylene bottle.

## 5 Apparatus

The apparatus required is specified in clause 5 of ISO 7530-1.

## 6 Sampling and sample preparation

Refer to clause 6 of ISO 7530-1.

## 7 Procedure

### 7.1 Preparation of test solution

Proceed as directed in 7.1.1 to 7.1.4 of ISO 7530-1.

#### 7.1.1 Primary dilutions

##### 7.1.1.1 Initial dilution for 0,01 % (m/m) to 0,10 % (m/m) cobalt

Transfer the test solution (7.1) to a 100 ml one-mark volumetric flask. Add 4 ml of strontium chloride solution (4.1). Make up to the mark with water and mix. Remove any products of hydrolysis by settlement and dry filtration or by centrifuging.

##### 7.1.1.2 Initial dilution for 0,1 % (m/m) to 4,0 % (m/m) cobalt

Transfer the test solution (7.1) to a 500 ml one-mark volumetric flask. Add 20 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water and mix. Remove any products of hydrolysis by settlement and dry filtration or by centrifuging.

#### 7.1.2 Secondary dilutions

##### 7.1.2.1 Secondary dilution for 0,1 % (m/m) to 0,8 % (m/m) cobalt

Pipette 50 ml of the solution from 7.1.1.2 into a 100 ml one-mark volumetric flask. Add 4 ml of strontium chloride solution (4.1) and 3 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water and mix.

##### 7.1.2.2 Secondary dilution for 0,4 % (m/m) to 4 % (m/m) cobalt

Pipette 10 ml of the solution from 7.1.1.2 into a 100 ml one-mark volumetric flask. Add 4 ml of

strontium chloride solution (4.1) and 5 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water and mix.

### 7.2 Reagent blank solution

Carry out a blank test in parallel with the determination, following the same procedure and using the same quantities of all the reagents.

### 7.3 Cobalt calibration solutions

Using pipettes, transfer to each of five 100 ml one-mark volumetric flasks, 0 ml, 5 ml, 10 ml, 15 ml and 20 ml of cobalt standard solution (4.3). Add 4 ml of strontium chloride solution (4.1) and 5 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water and mix.

### 7.4 Calibration and determination

#### 7.4.1 Atomic absorption measurements

Proceed as directed in 7.4.1 of ISO 7530-1, using a wavelength of 240,7 nm and an air/acetylene flame.

#### 7.4.2 Preparation of calibration graphs

Proceed as directed in 7.4.2 of ISO 7530-1.

### 7.5 Number of determinations

Carry out the determination at least in duplicate.

## 8 Expression of results

### 8.1 Calculation

Proceed as directed in 8.1 of ISO 7530-1.

### 8.2 Precision

#### 8.2.1 Laboratory tests

Twelve laboratories in six countries participated in the testing of this procedure using five samples of nominal composition given in table 1.

#### 8.2.2 Statistical analysis

8.2.2.1 Results were treated according to ISO 5725 as described in 8.2.2 of ISO 7530-1. The results of this analysis are given in table 2.

8.2.2.2 Three laboratories were rejected as Cochran outliers; two for sample 825 and one for sample 3927.

## 9 Test report

Refer to clause 9 of ISO 7530-1.

**Table 1 — Nominal composition of test samples [% (m/m)]**

Sample	Al	Co	Cr	Cu	Fe	Mn	Ni	Si	Ti
825	0,2	0,07	21	1,6	30	0,7	Remainder	0,4	1,1
902	0,4	0,05	5	0,04	48	0,4	Remainder	0,35	2,5
3920	0,15	2	19	0,1	3	0,3	Remainder	0,6	2,3
3927	0,1	1	20	0,05	44	0,4	Remainder	0,8	0,6
7049	1	0,01	15	0,15	7	0,8	Remainder	0,3	2,3

**Table 2 — Results of statistical analysis**

Sample reference	Mean % (m/m)	Within-laboratory standard deviation	Between laboratory standard deviation	Repeatability	Reproducibility
825	0,067	0,000 6	0,002 1	0,001 6	0,006 0
902	0,046	0,001 2	0,001 7	0,003 5	0,006 0
3920	2,01	0,029	0,0	0,082	0,082
3927	1,03	0,016	0,022	0,045	0,077
7049	0,007 2	0,000 2	0,000 9	0,000 6	0,002 6

### Publication(s) referred to

See national foreword.

---

## **BSI — British Standards Institution**

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### **Contract requirements**

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

### **Revisions**

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

Any person who finds an inaccuracy or ambiguity while using this British Standard should notify BSI without delay so that the matter may be investigated swiftly.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### **Buying British Standards**

Orders for all British Standard publications should be addressed to the Sales Department at Milton Keynes.

### **Information on standards**

BSI provides a wide range of information on national, European and international standards through its Library, the Standardline Database, the BSI Information Technology Service (BITS) and its Technical Help to Exporters Service. Contact Customer Information at Milton Keynes: Tel: 0908 221166.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact the Manager, Membership Development at Milton Keynes: Tel: 0908 220022.

### **Copyright**

Copyright subsists in all BSI publications. No part of this publication may be reproduced in any form without the prior permission in writing of BSI. This does not preclude the free use, in the course of implementing the standard, of details such as symbols and size, type or grade designations. Enquiries about copyright should be made to the Copyright Manager, Marketing at Milton Keynes.

BSI  
2 Park Street  
London  
W1A 2BS

BSI  
Linford Wood  
Milton Keynes  
MK14 6LE